

dimensions et masses des tubes acier

ASME B 36.10 M-1996

dimensions and weights of steel pipe

ASME B 36.10 M-1996

Diamètre nominal Nominal size	Diamètre extérieur Outside diameter		Epaisseur Wall thickness		Masse Weight		Identification		
	Pouces Inches	mm	Pouces Inches	mm	lb/ft	kg/m	Specif. API	Epaisseur	Schedule
								W.T. STD XS XXS	
1/8	0.405	10,3	0.049	1,24	0.19	0,28	-	-	10
	0.405	10,3	0.057	1,45	0.21	0,32	-	-	30
	0.405	10,3	0.068	1,73	0.24	0,37	5L	STD	40
	0.405	10,3	0.095	2,41	0.31	0,47	5L	XS	80
1/4	0.540	13,7	0.065	1,65	0.33	0,49	-	-	10
	0.540	13,7	0.073	1,85	0.36	0,54	-	-	30
	0.540	13,7	0.088	2,24	0.42	0,63	5L	STD	40
	0.540	13,7	0.119	3,02	0.54	0,80	5L	XS	80
3/8	0.675	17,1	0.065	1,65	0.42	0,63	-	-	10
	0.675	17,1	0.073	1,85	0.47	0,70	-	-	30
	0.675	17,1	0.091	2,31	0.57	0,84	5L	STD	40
	0.675	17,1	0.126	3,20	0.74	1,10	5L	XS	80
1/2	0.840	21,3	0.065	1,65	0.54	0,80	-	-	5
	0.840	21,3	0.083	2,11	0.67	1,00	-	-	10
	0.840	21,3	0.095	2,41	0.76	1,12	-	-	30
	0.840	21,3	0.109	2,77	0.85	1,27	5L	STD	40
	0.840	21,3	0.147	3,73	1.09	1,62	5L	XS	80
	0.840	21,3	0.188	4,78	1.31	1,95	-	-	160
3/4	1.050	26,7	0.065	1,65	0.69	1,03	-	-	5
	1.050	26,7	0.083	2,11	0.86	1,28	-	-	10
	1.050	26,7	0.095	2,41	0.97	1,44	-	-	30
	1.050	26,7	0.113	2,87	1.13	1,69	5L	STD	40
	1.050	26,7	0.154	3,91	1.47	2,20	5L	XS	80
	1.050	26,7	0.219	5,56	1.94	2,90	-	-	160
1	1.315	33,4	0.065	1,65	0.87	1,30	-	-	5
	1.315	33,4	0.109	2,77	1.40	2,09	-	-	10
	1.315	33,4	0.114	2,90	1.46	2,18	-	-	30
	1.315	33,4	0.133	3,38	1.68	2,50	5L	STD	40
	1.315	33,4	0.179	4,55	2.17	3,24	5L	XS	80
	1.315	33,4	0.250	6,35	2.84	4,24	-	-	160
1 1/4	1.660	42,2	0.065	1,65	1.11	1,65	-	-	5
	1.660	42,2	0.109	2,77	1.81	2,70	-	-	10
	1.660	42,2	0.117	2,97	1.93	2,87	-	-	30
	1.660	42,2	0.140	3,56	2.27	3,39	5L	STD	40
	1.660	42,2	0.191	4,85	3.00	4,47	5L	XS	80

Diamètre nominal Nominal size	Diamètre extérieur Outside diameter		Epaisseur Wall thickness		Masse Weight		Identification		
	Pouces Inches	mm	Pouces Inches	mm	lb/ft	kg/m	Specif. API	Epaisseur	Schedule
								W.T. STD XS XXS	
1 1/4	1.660	42,2	0.250	6,35	3.76	5,61	-	-	160
	1.660	42,2	0.382	9,70	5.21	7,77	5L	XXS	-
	1.900	48,3	0.065	1,65	1.28	1,91	-	-	5
	1.900	48,3	0.109	2,77	2.09	3,11	-	-	10
1 1/2	1.900	48,3	0.125	3,18	2.37	3,53	-	-	30
	1.900	48,3	0.145	3,68	2.72	4,05	5L	STD	40
	1.900	48,3	0.200	5,08	3.63	5,41	5L	XS	80
	1.900	48,3	0.281	7,14	4.86	7,25	-	-	160
	1.900	48,3	0.400	10,15	6.41	9,56	5L	XXS	-
	2.375	60,3	0.065	1,65	1.61	2,40	-	-	5
2	2.375	60,3	0.083	2,11	2.03	3,03	5L	-	-
	2.375	60,3	0.109	2,77	2.64	3,93	5L	-	10
	2.375	60,3	0.125	3,18	3.00	4,48	5L	-	30
	2.375	60,3	0.141	3,58	3.36	5,01	5L	-	-
	2.375	60,3	0.154	3,91	3.65	5,44	5L	STD	40
	2.375	60,3	0.172	4,37	4.05	6,03	5L	-	-
	2.375	60,3	0.188	4,78	4.39	6,54	5L	-	-
	2.375	60,3	0.218	5,54	5.02	7,48	5L	XS	80
	2.375	60,3	0.250	6,35	5.67	8,45	5L	-	-
	2.375	60,3	0.281	7,14	6.28	9,36	5L	-	-
	2.375	60,3	0.344	8,74	7.46	11,11	-	-	160
	2.375	60,3	0.436	11,07	9.03	13,44	5L	XXS	-
2 1/2	2.875	73,0	0.083	2,11	2.47	3,69	5L	-	5
	2.875	73,0	0.109	2,77	3.22	4,80	5L	-	-
	2.875	73,0	0.120	3,05	3.53	5,26	-	-	10
	2.875	73,0	0.125	3,18	3.67	5,48	5L	-	-
	2.875	73,0	0.141	3,58	4.12	6,13	5L	-	-
	2.875	73,0	0.156	3,96	4.53	6,74	5L	-	-
	2.875	73,0	0.172	4,37	4.97	7,40	5L	-	-
	2.875	73,0	0.188	4,78	5.40	8,04	5L	-	30
	2.875	73,0	0.203	5,16	5.79	8,63	5L	STD	40
	2.875	73,0	0.216	5,49	6.13	9,14	5L	-	-
3	2.875	73,0	0.250	6,35	7.01	10,44	5L	-	-
	2.875	73,0	0.276	7,01	7.66	11,41	5L	XS	80
	2.875	73,0	0.375	9,53	10.01	14,92	-	-	160
	2.875	73,0	0.552	14,02	13.69	20,39	5L	XXS	-
	3.500	88,9	0.083	2,11	3.03	4,52	5L	-	5
	3.500	88,9	0.109	2,77	3.95	5,88	5L	-	-

dimensions et masses des tubes acier

ASME B 36.10 M-1996

dimensions and weights of steel pipe

ASME B 36.10 M-1996

Diamètre nominal Nominal size	Diamètre extérieur Outside diameter		Epaisseur Wall thickness		Masse Weight		Identification		
	Pouces Inches	mm	Pouces Inches	mm	lb/ft	kg/m	Specif. API	Epaisseur	Schedule
								W.T. STD XS XXS	
3	3.500	88,9	0.120	3,05	4.33	6,45	-		10
	3.500	88,9	0.125	3,18	4.51	6,72	5L		
	3.500	88,9	0.141	3,58	5.06	7,53	5L		
	3.500	88,9	0.156	3,96	5.57	8,29	5L		
	3.500	88,9	0.172	4,37	6.11	9,11	5L		
	3.500	88,9	0.188	4,78	6.65	9,92	5L		30
	3.500	88,9	0.216	5,49	7.58	11,29	5L	STD	40
	3.500	88,9	0.250	6,35	8.68	12,93	5L		
	3.500	88,9	0.281	7,14	9.66	14,40	5L		
	3.500	88,9	0.300	7,62	10.25	15,27	5L	XS	80
	3.500	88,9	0.438	11,13	14.32	21,35	-		160
	3.500	88,9	0.600	15,24	18.58	27,68	5L	XXS	
3 1/2	4.000	101,6	0.083	2,11	3.47	5,18	5L		5
	4.000	101,6	0.109	2,77	4.53	6,75	5L		
	4.000	101,6	0.120	3,05	4.97	7,40	-		10
	4.000	101,6	0.125	3,18	5.17	7,72	5L		
	4.000	101,6	0.141	3,58	5.81	8,65	5L		
	4.000	101,6	0.156	3,96	6.40	9,53	5L		
	4.000	101,6	0.172	4,37	7.03	10,48	5L		
	4.000	101,6	0.188	4,78	7.65	11,41	5L		30
	4.000	101,6	0.226	5,74	9.11	13,57	5L	STD	40
	4.000	101,6	0.250	6,35	10.01	14,92	5L		
	4.000	101,6	0.281	7,14	11.16	16,63	5L		
	4.000	101,6	0.318	8,08	12.50	18,63	5L	XS	80
4	4.500	114,3	0.083	2,11	3.92	5,84	5L		5
	4.500	114,3	0.109	2,77	5.11	7,62	-		10
	4.500	114,3	0.120	3,05	5.61	8,36	-		
	4.500	114,3	0.125	3,18	5.84	8,71	5L		
	4.500	114,3	0.141	3,58	6.56	9,77	5L		
	4.500	114,3	0.156	3,96	7.24	10,78	5L		
	4.500	114,3	0.172	4,37	7.95	11,85	5L		
	4.500	114,3	0.188	4,78	8.66	12,91	5L		30
	4.500	114,3	0.203	5,16	9.32	13,89	5L		
	4.500	114,3	0.219	5,56	10.01	14,91	5L		
	4.500	114,3	0.237	6,02	10.79	16,07	5L	STD	40
	4.500	114,3	0.250	6,35	11.35	16,90	5L		
4.500	114,3	0.281	7,14	12.66	18,87	5L			
4.500	114,3	0.312	7,92	13.96	20,78	5L			

Diamètre nominal Nominal size	Diamètre extérieur Outside diameter		Epaisseur Wall thickness		Masse Weight		Identification		
	Pouces Inches	mm	Pouces Inches	mm	lb/ft	kg/m	Specif. API	Epaisseur	Schedule
								W.T. STD XS XXS	
4	4.500	114,3	0.337	8,56	14.98	22,32	5L	XS	80
	4.500	114,3	0.438	11,13	19.00	28,32	5L		120
	4.500	114,3	0.531	13,49	22.51	33,54	5L		160
	4.500	114,3	0.674	17,12	27.54	41,03	5L	XXS	
	5.563	141,3	0.083	2,11	4.86	7,24	5L		
	5.563	141,3	0.109	2,77	6.36	9,47	-		5
	5.563	141,3	0.125	3,18	7.26	10,83	5L		
	5.563	141,3	0.134	3,40	7.77	11,57	-		10
	5.563	141,3	0.156	3,96	9.01	13,41	5L		
	5.563	141,3	0.188	4,78	10.79	16,09	5L		
	5.563	141,3	0.219	5,56	12.50	18,61	5L		
	5.563	141,3	0.258	6,55	14.62	21,77	5L	STD	40
5	5.563	141,3	0.281	7,14	15.85	23,62	5L		
	5.563	141,3	0.312	7,92	17.50	26,05	5L		
	5.563	141,3	0.344	8,74	19.17	28,57	5L		
	5.563	141,3	0.375	9,53	20.78	30,97	5L	XS	80
	5.563	141,3	0.500	12,70	27.04	40,28	5L		120
	5.563	141,3	0.625	15,88	32.96	49,11	5L		160
	5.563	141,3	0.750	19,05	38.55	57,43	5L	XXS	
	6.625	168,3	0.083	2,11	5.80	8,65	5L		
	6.625	168,3	0.109	2,77	7.59	11,31	5L		5
	6.625	168,3	0.125	3,18	8.68	12,95	5L		
	6.625	168,3	0.134	3,40	9.29	13,84	-		10
	6.625	168,3	0.141	3,58	9.76	14,54	5L		
6.625	168,3	0.156	3,96	10.78	16,05	5L			
6.625	168,3	0.172	4,37	11.85	17,67	5L			
6.625	168,3	0.188	4,78	12.92	19,27	5L			
6.625	168,3	0.203	5,16	13.92	20,76	5L			
6.625	168,3	0.219	5,56	14.98	22,31	5L			
6.625	168,3	0.250	6,35	17.02	25,36	5L			
6.625	168,3	0.280	7,14	18.97	28,26	5L	STD	40	
6.625	168,3	0.312	7,92	21.04	31,32	5L			
6.625	168,3	0.344	8,74	23.08	34,39	5L			
6.625	168,3	0.375	9,53	25.03	37,31	5L			
6.625	168,3	0.432	10,97	28.57	42,56	5L	XS	80	
6.625	168,3	0.500	12,70	32.71	48,73	5L			
6.625	168,3	0.562	14,27	36.39	54,20	5L		120	
6.625	168,3	0.625	15,88	40.05	59,69	5L			

dimensions et masses des tubes acier

ASME B 36.10 M-1996

dimensions and weights of steel pipe

ASME B 36.10 M-1996

Diamètre nominal Nominal size	Diamètre extérieur Outside diameter		Epaisseur Wall thickness		Masse Weight		Identification			
	Pouces Inches	mm	Pouces Inches	mm	lb/ft	kg/m	Specif. API	Epaisseur	Schedule	
								W.T. STD XS XXS		
6	6.625	168,3	0.719	18,26	45.35	67,56	5L		160	
	6.625	168,3	0.750	19,05	47.06	70,11	5L			
	6.625	168,3	0.864	21,95	53.16	79,22	5L	XXS		
	6.625	168,3	0.875	22,23	53.73	80,07	5L			
	8.625	219,1	0.109	2,77	9.93	14,79	-		5	
	8.625	219,1	0.125	3,18	11.35	16,93	5L			
	8.625	219,1	0.148	3,76	13.40	19,96	-		10	
	8.625	219,1	0.156	3,96	14.11	21,01	5L			
	8.625	219,1	0.188	4,78	16.94	25,26	5L			
	8.625	219,1	0.203	5,16	18.26	27,22	5L			
	8.625	219,1	0.219	5,56	19.66	29,28	5L			
	8.625	219,1	0.250	6,35	22.36	33,31	5L		20	
	8.625	219,1	0.277	7,04	24.70	36,81	5L		30	
	8.625	219,1	0.312	7,92	27.70	41,24	5L			
	8.625	219,1	0.322	8,18	28.55	42,55	5L	STD	40	
	8	8.625	219,1	0.344	8,74	30.42	45,34	5L		
8.625		219,1	0.375	9,53	33.04	49,25	5L			
8.625		219,1	0.406	10,31	35.64	53,08	-		60	
8.625		219,1	0.438	11,13	38.30	57,08	5L			
8.625		219,1	0.500	12,70	43.39	64,64	5L	XS	80	
8.625		219,1	0.562	14,27	48.40	72,08	5L			
8.625		219,1	0.594	15,09	50.95	75,92	-		100	
8.625		219,1	0.625	15,88	53.40	79,58	5L			
8.625		219,1	0.719	18,26	60.71	90,44	5L		120	
8.625		219,1	0.750	19,05	63.08	93,98	5L			
8.625		219,1	0.812	20,62	67.76	100,92	5L		140	
8.625		219,1	0.875	22,23	72.42	107,92	5L	XXS		
8.625		219,1	0.906	23,01	74.69	111,27	-		160	
8.625		219,1	1.000	25,40	81.44	121,33	5L			
10		10.750	273,0	0.134	3,40	15.19	22,63	-		5
		10.750	273,0	0.156	3,96	17.65	26,28	5L		
	10.750	273,0	0.165	4,19	18.65	27,78	-		10	
	10.750	273,0	0.188	4,78	21.21	31,63	5L			
	10.750	273,0	0.203	5,16	22.87	34,09	5L			
	10.750	273,0	0.219	5,56	24.63	36,68	5L			
	10.750	273,0	0.250	6,35	28.04	41,77	5L		20	
	10.750	273,0	0.279	7,09	31.20	46,51	5L			
	10.750	273,0	0.307	7,80	34.24	51,03	5L		30	

Diamètre nominal Nominal size	Diamètre extérieur Outside diameter		Epaisseur Wall thickness		Masse Weight		Identification		
	Pouces Inches	mm	Pouces Inches	mm	lb/ft	kg/m	Specif. API	Epaisseur	Schedule
								W.T. STD XS XXS	
10	10.750	273,0	0.344	8,74	38.23	56,98	5L		
	10.750	273,0	0.365	9,27	40.48	60,31	5L	STD	40
	10.750	273,0	0.438	11,13	48.24	71,90	5L		
	10.750	273,0	0.500	12,70	54.74	81,55	5L	XS	60
	10.750	273,0	0.562	14,27	61.15	91,08	5L		
	10.750	273,0	0.594	15,09	64.43	96,01	-		80
	10.750	273,0	0.625	15,88	67.58	100,73	5L		
	10.750	273,0	0.719	18,26	77.03	114,75	5L		100
	10.750	273,0	0.812	20,62	86.18	128,38	5L		
	10.750	273,0	0.844	21,44	89.29	133,06	-		120
	10.750	273,0	0.875	22,23	92.28	137,52	5L		
	10.750	273,0	0.938	23,83	98.30	146,48	5L		
	10.750	273,0	1.000	25,40	104.13	155,15	5L	XXS	140
	10.750	273,0	1.125	28,58	115.64	172,33	-		160
	10.750	273,0	1.250	31,75	126.83	188,97	5L		
	12	12.750	323,8	0.156	3,96	20.98	31,25	-	
12.750		323,8	0.172	4,37	23.11	34,43	5L		
12.750		323,8	0.180	4,57	24.17	36,00	-		10
12.750		323,8	0.188	4,78	25.22	37,62	5L		
12.750		323,8	0.203	5,16	27.20	40,56	5L		
12.750		323,8	0.219	5,56	29.31	43,65	5L		
12.750		323,8	0.250	6,35	33.38	49,73	5L		20
12.750		323,8	0.281	7,14	37.42	55,77	5L		
12.750		323,8	0.312	7,92	41.45	61,71	5L		
12.750		323,8	0.330	8,38	43.77	65,20	5L		30
12.750		323,8	0.344	8,74	45.58	67,93	5L		
12.750		323,8	0.375	9,53	49.56	73,88	5L	STD	
12.750		323,8	0.406	10,31	53.52	79,73	5L		40
12.750		323,8	0.438	11,13	57.59	85,84	5L		
12.750		323,8	0.500	12,70	65.42	97,46	5L	XS	
12.750		323,8	0.562	14,27	73.15	108,96	5L		60
12.750	323,8	0.625	15,88	80.93	120,62	5L			
12.750	323,8	0.688	17,48	88.63	132,08	5L		80	
12.750	323,8	0.750	19,05	96.12	143,21	5L			
12.750	323,8	0.812	20,62	103.53	154,21	5L			
12.750	323,8	0.844	21,44	107.32	159,91	-		100	
12.750	323,8	0.875	22,23	110.97	165,37	5L			
12.750	323,8	0.938	23,83	118.33	176,33	5L			

dimensions et masses des tubes acier

ASME B 36.10 M-1996

dimensions and weights of steel pipe

ASME B 36.10 M-1996

Diamètre nominal Nominal size	Diamètre extérieur Outside diameter		Epaisseur Wall thickness		Masse Weight		Identification		
	Pouces Inches	mm	Pouces Inches	mm	lb/ft	kg/m	Specif. API	Epaisseur	Schedule
								W.T. STD XS XXS	
12	12.750	323,8	1.000	25,40	125.49	186,97	5L	XXS	120
	12.750	323,8	1.062	26,97	132.57	197,48	5L		
	12.750	323,8	1.125	28,58	139.67	208,14	5L		140
	12.750	323,8	1.250	31,75	153.53	228,74	5L		
	12.750	323,8	1.312	33,32	160.27	238,76	-		160
	14.000	355,6	0.156	3,96	23.07	34,36	-		5
	14.000	355,6	0.188	4,78	27.73	41,35	5L		
	14.000	355,6	0.203	5,16	29.91	44,59	5L		
	14.000	355,6	0.210	5,33	30.93	46,04	5L		
	14.000	355,6	0.219	5,56	32.23	47,99	5L		
14	14.000	355,6	0.250	6,35	36.71	54,69	5L		10
	14.000	355,6	0.281	7,14	41.17	61,35	5L		
	14.000	355,6	0.312	7,92	45.61	67,90	5L		20
	14.000	355,6	0.344	8,74	50.17	74,76	5L		
	14.000	355,6	0.375	9,53	54.57	81,33	5L	STD	30
	14.000	355,6	0.406	10,31	58.94	87,79	5L		
	14.000	355,6	0.438	11,13	63.44	94,55	5L		40
	14.000	355,6	0.469	11,91	67.78	100,94	5L		
	14.000	355,6	0.500	12,70	72.09	107,39	5L	XS	
	14.000	355,6	0.562	14,27	80.66	120,11	5L		
	14.000	355,6	0.594	15,09	85.05	126,71	-		60
	14.000	355,6	0.625	15,88	89.28	133,03	5L		
	14.000	355,6	0.688	17,48	97.81	145,75	5L		
	14.000	355,6	0.750	19,05	106.13	158,10	5L		80
	14.000	355,6	0.812	20,62	114.37	170,33	5L		
	14.000	355,6	0.875	22,23	122.65	182,75	5L		
	14.000	355,6	0.938	23,83	130.85	194,96	5L		100
	14.000	355,6	1.000	25,40	138.84	206,83	5L		
	14.000	355,6	1.062	26,97	146.74	218,57	5L		
	14.000	355,6	1.094	27,79	150.79	224,65	-		120
	14.000	355,6	1.125	28,58	154.69	230,48	5L		
	14.000	355,6	1.250	31,75	170.21	253,56	5L		140
	14.000	355,6	1.406	35,71	189.11	281,70	-		160
	14.000	355,6	2.000	50,80	256.32	381,83	-		
	14.000	355,6	2.125	53,98	269.50	401,50	-		
	14.000	355,6	2.200	55,88	277.25	413,01	-		
	14.000	355,6	2.500	63,50	307.05	457,40	-		

Diamètre nominal Nominal size	Diamètre extérieur Outside diameter		Epaisseur Wall thickness		Masse Weight		Identification			
	Pouces Inches	mm	Pouces Inches	mm	lb/ft	kg/m	Specif. API	Epaisseur	Schedule	
								W.T. STD XS XXS		
16	16.000	406,4	0.165	4,19	27.90	41,56	-		5	
	16.000	406,4	0.188	4,78	31.75	47,34	5L			
	16.000	406,4	0.203	5,16	34.25	51,06	5L			
	16.000	406,4	0.219	5,56	36.91	54,96	5L			
	16.000	406,4	0.250	6,35	42.05	62,64	5L		10	
	16.000	406,4	0.281	7,14	47.17	70,30	5L			
	16.000	406,4	0.312	7,92	52.27	77,83	5L		20	
	16.000	406,4	0.344	8,74	57.52	85,71	5L			
	16.000	406,4	0.375	9,53	62.58	93,27	5L	STD	30	
	16.000	406,4	0.406	10,31	67.62	100,70	5L			
	16.000	406,4	0.438	11,13	72.80	108,49	5L			
	16.000	406,4	0.469	11,91	77.79	115,86	5L			
	16.000	406,4	0.500	12,70	82.77	123,30	5L	XS	40	
	16.000	406,4	0.562	14,27	92.66	137,99	5L			
	16.000	406,4	0.625	15,88	102.63	152,93	5L			
	16.000	406,4	0.656	16,66	107.50	160,12	-		60	
	16.000	406,4	0.688	17,48	112.51	167,65	5L			
	16.000	406,4	0.750	19,05	122.15	181,97	5L			
	16.000	406,4	0.812	20,62	131.71	196,16	5L			
	16.000	406,4	0.844	21,44	136.61	203,53	-		80	
	16.000	406,4	0.875	22,23	141.34	210,60	5L			
	16.000	406,4	0.938	23,83	150.89	224,82	5L			
	16.000	406,4	1.000	25,40	160.20	238,64	5L			
	16.000	406,4	1.031	26,19	164.82	245,56	-		100	
	16.000	406,4	1.062	26,97	169.43	252,35	5L			
	16.000	406,4	1.125	28,58	178.72	266,28	5L			
	16.000	406,4	1.188	30,18	187.93	280,00	5L			
	16.000	406,4	1.219	30,96	192.43	286,64	-		120	
	16.000	406,4	1.250	31,75	196.91	293,33	5L			
	16.000	406,4	1.438	36,53	223.64	333,19	-		140	
	16.000	406,4	1.594	40,49	245.25	365,35	-		160	
	18	18.000	457,0	0.165	4,19	31.43	46,81	-		5
		18.000	457,0	0.188	4,78	35.76	53,31	5L		
		18.000	457,0	0.219	5,56	41.59	61,90	5L		
		18.000	457,0	0.250	6,35	47.39	70,57	5L		10
		18.000	457,0	0.281	7,14	53.18	79,21	5L		
		18.000	457,0	0.312	7,92	58.94	87,71	5L		20
		18.000	457,0	0.344	8,74	64.87	96,61	5L		

dimensions et masses des tubes acier

ASME B 36.10 M-1996

dimensions and weights of steel pipe

ASME B 36.10 M-1996

Diamètre nominal Nominal size	Diamètre extérieur Outside diameter		Epaisseur Wall thickness		Masse Weight		Identification			
	Pouces Inches	mm	Pouces Inches	mm	lb/ft	kg/m	Specif. API	Epaisseur W.T.		Schedule
								STD	XS XXS	
18	18.000	457	0.375	9,53	70.59	105,16	5L	STD		
	18.000	457	0.406	10,31	76.29	113,57	5L			
	18.000	457	0.438	11,13	82.15	122,38	5L		30	
	18.000	457	0.469	11,91	87.81	130,72	5L			
	18.000	457	0.500	12,70	93.45	139,15	5L	XS		
	18.000	457	0.562	14,27	104.67	155,80	5L		40	
	18.000	457	0.625	15,88	115.98	172,74	5L			
	18.000	457	0.688	17,48	127.21	189,46	5L			
	18.000	457	0.750	19,05	138.17	205,74	5L		60	
	18.000	457	0.812	20,62	149.06	221,89	5L			
	18.000	457	0.875	22,23	160.03	238,34	5L			
	18.000	457	0.938	23,83	170.92	254,55	5L		80	
	18.000	457	1.000	25,40	181.56	270,34	5L			
	18.000	457	1.062	26,97	192.11	286,00	5L			
	18.000	457	1.125	28,58	202.75	301,94	5L			
	18.000	457	1.156	29,36	207.96	309,62	-		100	
	18.000	457	1.188	30,18	213.31	317,66	5L			
	18.000	457	1.250	31,75	223.61	332,95	5L			
	18.000	457	1.375	34,93	244.14	363,56	-		120	
	18.000	457	1.562	39,67	274.22	408,26	-		140	
18.000	457	1.781	45,24	308.50	459,37	-		160		
20	20.000	508	0.188	4,78	39.78	59,25	-		5	
	20.000	508	0.219	5,56	46.27	68,89	5L			
	20.000	508	0.250	6,35	52.73	78,55	5L		10	
	20.000	508	0.281	7,14	59.18	88,19	5L			
	20.000	508	0.312	7,92	65.60	97,67	5L			
	20.000	508	0.344	8,74	72.21	107,60	5L			
	20.000	508	0.375	9,53	78.60	117,15	5L	STD	20	
	20.000	508	0.406	10,31	84.96	126,53	5L			
	20.000	508	0.438	11,13	91.51	136,37	5L			
	20.000	508	0.469	11,91	97.83	145,70	5L			
	20.000	508	0.500	12,70	104.13	155,12	5L	XS	30	
	20.000	508	0.562	14,27	116.67	173,74	5L			
	20.000	508	0.594	15,09	123.11	183,42	-		40	
	20.000	508	0.625	15,88	129.33	192,71	5L			
	20.000	508	0.688	17,48	141.90	211,44	5L			
	20.000	508	0.750	19,05	154.19	229,70	5L			
	20.000	508	0.812	20,62	166.40	247,83	5L		60	

Diamètre nominal Nominal size	Diamètre extérieur Outside diameter		Epaisseur Wall thickness		Masse Weight		Identification			
	Pouces Inches	mm	Pouces Inches	mm	lb/ft	kg/m	Specif. API	Epaisseur W.T.		Schedule
								STD	XS XXS	
20	20.000	508	0.875	22,23	178.72	266,29	5L			
	20.000	508	0.938	23,83	190.96	284,52	5L			
	20.000	508	1.000	25,40	202.92	302,28	5L			
	20.000	508	1.031	26,19	208.87	311,17	-		80	
	20.000	508	1.062	26,97	214.80	319,92	5L			
	20.000	508	1.125	28,58	226.78	337,89	5L			
	20.000	508	1.188	30,18	238.68	355,61	5L			
	20.000	508	1.250	31,75	250.31	372,88	5L			
	20.000	508	1.281	32,54	256.10	381,53	-		100	
	20.000	508	1.312	33,32	261.86	390,03	5L			
	20.000	508	1.375	34,93	273.51	407,49	5L			
	20.000	508	1.500	38,10	296.37	441,49	-		120	
	20.000	508	1.750	44,45	341.09	508,11	-		140	
	20.000	508	1.969	50,01	379.17	564,81	-		160	
	22	22.000	559	0.188	4,78	43.80	65,24	-		5
		22.000	559	0.219	5,56	50.94	75,88	5L		
		22.000	559	0.250	6,35	58.07	86,54	5L		10
		22.000	559	0.281	7,14	65.18	97,17	5L		
		22.000	559	0.312	7,92	72.27	107,63	5L		
		22.000	559	0.344	8,74	79.56	118,60	5L		
22.000		559	0.375	9,53	86.61	129,13	5L	STD	20	
22.000		559	0.406	10,31	93.63	139,50	5L			
22.000		559	0.438	11,13	100.86	150,37	5L			
22.000		559	0.469	11,91	107.85	160,68	5L			
22.000		559	0.500	12,70	114.81	171,09	5L	XS	30	
22.000		559	0.562	14,27	128.67	191,69	5L			
22.000		559	0.625	15,88	142.68	212,69	5L			
22.000		559	0.688	17,48	156.60	233,43	5L			
22.000		559	0.750	19,05	170.21	253,65	5L			
22.000		559	0.812	20,62	183.75	273,76	5L			
22.000		559	0.875	22,23	197.41	294,25	5L		60	
22.000		559	0.938	23,83	211.00	314,49	5L			
22.000		559	1.000	25,40	224.28	334,23	5L			
22.000		559	1.062	26,97	237.48	353,84	5L			
22.000	559	1.125	28,58	250.81	373,83	5L		80		
22.000	559	1.188	30,18	264.06	393,57	5L				
22.000	559	1.250	31,75	277.01	412,81	5L				
22.000	559	1.312	33,32	289.88	431,94	5L				

dimensions et masses des tubes acier

ASME B 36.10 M-1996

dimensions and weights of steel pipe

ASME B 36.10 M-1996

Diamètre nominal Nominal size	Diamètre extérieur Outside diameter		Epaisseur Wall thickness		Masse Weight		Identification		
							Specif. API	Epaisseur W.T. STD XS XXS	Schedule
	Pouces Inches	mm	Pouces Inches	mm	lb/ft	kg/m			
22	22.000	559	1.375	34,93	302.88	451,42	5L		100
	22.000	559	1.438	36,53	315.79	470,66	5L		
	22.000	559	1.500	38,10	328.41	489,41	5L		
	22.000	559	1.625	41,28	353.61	527,02	-		120
	22.000	559	1.875	47,63	403.00	600,63	-		140
	22.000	559	2.125	53,98	451.06	672,26	-		160
	24.000	610	0.218	5,54	55.37	82,47	-		5
	24.000	610	0.250	6,35	63.41	94,53	5L		10
	24.000	610	0.281	7,14	71.18	106,15	5L		
	24.000	610	0.312	7,92	78.93	117,59	5L		
24	24.000	610	0.344	8,74	86.91	129,59	5L		
	24.000	610	0.375	9,53	94.62	141,12	5L	STD	20
	24.000	610	0.406	10,31	102.31	152,47	5L		
	24.000	610	0.438	11,13	110.22	164,37	5L		
	24.000	610	0.469	11,91	117.86	175,66	5L		
	24.000	610	0.500	12,70	125.49	187,06	5L	XS	
	24.000	610	0.562	14,27	140.68	209,64	5L		30
	24.000	610	0.625	15,88	156.03	232,66	5L		
	24.000	610	0.688	17,48	171.29	255,41	5L		40
	24.000	610	0.750	19,05	186.23	277,61	5L		
	24.000	610	0.812	20,62	201.09	299,69	5L		
	24.000	610	0.875	22,23	216.10	322,21	5L		
	24.000	610	0.938	23,83	231.03	344,46	5L		
	24.000	610	0.969	24,61	238.35	355,26	-		60
	24.000	610	1.000	25,40	245.64	366,17	5L		
	24.000	610	1.062	26,97	260.17	387,76	5L		
	24.000	610	1.125	28,58	274.84	409,77	5L		
	24.000	610	1.188	30,18	289.44	431,52	5L		
	24.000	610	1.219	30,96	296.58	442,08	-		80
	24.000	610	1.250	31,75	303.71	452,74	5L		
	24.000	610	1.312	33,32	317.91	473,84	5L		
	24.000	610	1.375	34,93	332.25	495,35	5L		
	24.000	610	1.438	36,53	346.50	516,80	5L		
	24.000	610	1.500	38,10	360.45	537,33	5L		
	24.000	610	1.531	38,89	367.39	547,71	-		100
	24.000	610	1.562	39,67	374.31	557,43	5L		
	24.000	610	1.812	46,02	429.39	640,03	-		120
	24.000	610	2.062	52,37	483.12	720,15	-		140
	24.000	610	2.344	59,54	542.13	808,22	-		160

Diamètre nominal Nominal size	Diamètre extérieur Outside diameter		Epaisseur Wall thickness		Masse Weight		Identification			
							Specif. API	Epaisseur W.T. STD XS XXS	Schedule	
	Pouces Inches	mm	Pouces Inches	mm	lb/ft	kg/m				
26	26.000	660	0.250	6,35	68.75	102,36	5L			
	26.000	660	0.281	7,14	77.18	114,95	5L			
	26.000	660	0.312	7,92	85.60	127,36	5L		10	
	26.000	660	0.344	8,74	94.26	140,37	5L			
	26.000	660	0.375	9,53	102.63	152,87	5L	STD		
	26.000	660	0.406	10,31	110.98	165,18	5L			
	26.000	660	0.438	11,13	119.57	178,09	5L			
	26.000	660	0.469	11,91	127.88	190,34	5L			
	26.000	660	0.500	12,70	136.17	202,72	5L	XS	20	
	26.000	660	0.562	14,27	152.68	227,23	5L			
	26.000	660	0.625	15,88	169.38	252,24	5L			
	26.000	660	0.688	17,48	185.99	276,96	5L			
	26.000	660	0.750	19,05	202.25	301,10	5L			
	26.000	660	0.812	20,62	218.43	325,12	5L			
	26.000	660	0.875	22,23	234.79	349,62	5L			
	26.000	660	0.938	23,83	251.07	373,84	5L			
	26.000	660	1.000	25,40	267.00	397,49	5L			
	28	28.000	711	0.250	6,35	74.09	110,34	5L		
		28.000	711	0.281	7,14	83.19	123,93	5L		
		28.000	711	0.312	7,92	92.26	137,32	5L		10
28.000		711	0.344	8,74	101.61	151,36	5L			
28.000		711	0.375	9,53	110.64	164,85	5L	STD		
28.000		711	0.406	10,31	119.65	178,15	5L			
28.000		711	0.438	11,13	128.93	192,09	5L			
28.000		711	0.469	11,91	137.90	205,32	5L			
28.000		711	0.500	12,70	146.85	218,69	5L	XS	20	
28.000		711	0.562	14,27	164.69	245,18	5L			
30	28.000	711	0.625	15,88	182.73	271,21	5L		30	
	28.000	711	0.688	17,48	200.68	298,95	5L			
	28.000	711	0.750	19,05	218.27	325,06	5L			
	28.000	711	0.812	20,62	235.78	351,05	5L			
	28.000	711	0.875	22,23	253.48	377,58	5L			
	28.000	711	0.938	23,83	271.10	403,81	5L			
	28.000	711	1.000	25,40	288.36	429,44	5L			
	30.000	762	0.250	6,35	79.43	118,33	5L			
	30.000	762	0.281	7,14	89.19	132,91	5L			
	30.000	762	0.312	7,92	98.93	147,28	5L		10	
30.000	762	0.344	8,74	108.95	162,35	5L				

dimensions et masses des tubes acier

ASME B 36.10 M-1996

dimensions and weights of steel pipe

ASME B 36.10 M-1996

Diamètre nominal Nominal size	Diamètre extérieur Outside diameter		Epaisseur Wall thickness		Masse Weight		Identification			
	Pouces Inches	mm	Pouces Inches	mm	lb/ft	kg/m	Specif. API	Epaisseur W.T.		Schedule
								STD	XS XXS	
30	30.000	762	0.375	9,53	118.65	176,84	5L	STD		
	30.000	762	0.406	10,31	128.32	191,11	5L			
	30.000	762	0.438	11,13	138.29	206,09	5L			
	30.000	762	0.469	11,91	147.92	220,30	5L			
	30.000	762	0.500	12,70	157.53	234,67	5L	XS	20	
	30.000	762	0.562	14,27	176.69	263,12	5L			
	30.000	762	0.625	15,88	196.08	292,18	5L			30
	30.000	762	0.688	17,48	215.38	320,93	5L			
	30.000	762	0.750	19,05	234.29	349,02	5L			
	30.000	762	0.812	20,62	253.12	376,98	5L			
	30.000	762	0.875	22,23	272.17	405,54	5L			
	30.000	762	0.938	23,83	291.14	433,78	5L			
	30.000	762	1.000	25,40	309.72	461,38	5L			
	30.000	762	1.062	26,97	328.22	488,85	5L			
	30.000	762	1.125	28,58	346.93	516,90	5L			
	30.000	762	1.188	30,18	365.56	544,65	5L			
	30.000	762	1.250	31,75	383.81	571,75	5L			
	32	32.000	813	0.250	6,35	84.77	126,31	5L		
32.000		813	0.281	7,14	95.19	141,89	5L			
32.000		813	0.312	7,92	105.59	157,24	5L			10
32.000		813	0.344	8,74	116.30	173,34	5L			
32.000		813	0.375	9,53	126.66	188,82	5L	STD		
32.000		813	0.406	10,31	136.99	204,08	5L			
32.000		813	0.438	11,13	147.64	220,08	5L			
32.000		813	0.469	11,91	157.94	235,28	5L			
32.000		813	0.500	12,70	168.21	250,64	5L	XS	20	
32.000		813	0.562	14,27	188.70	281,07	5L			
32.000		813	0.625	15,88	209.43	312,15	5L			30
32.000		813	0.688	17,48	230.08	342,91	5L			40
32.000		813	0.750	19,05	250.31	372,98	5L			
32.000		813	0.812	20,62	270.47	402,92	5L			
32.000		813	0.875	22,23	290.86	433,49	5L			
32.000		813	0.938	23,83	311.17	463,75	5L			
32.000		813	1.000	25,40	331.08	493,32	5L			
32.000		813	1.062	26,97	350.90	522,77	5L			
32.000		813	1.125	28,58	370.96	552,85	5L			
32.000		813	1.188	30,18	390.94	582,61	5L			
32.000		813	1.250	31,75	410.51	611,68	5L			

Diamètre nominal Nominal size	Diamètre extérieur Outside diameter		Epaisseur Wall thickness		Masse Weight		Identification				
	Pouces Inches	mm	Pouces Inches	mm	lb/ft	kg/m	Specif. API	Epaisseur W.T.		Schedule	
								STD	XS XXS		
34	34.000	864	0.250	6,35	90.11	134,30	5L				
	34.000	864	0.281	7,14	101.19	150,87	5L				
	34.000	864	0.312	7,92	112.25	167,20	5L			10	
	34.000	864	0.344	8,74	123.65	184,33	5L				
	34.000	864	0.375	9,53	134.67	200,31	5L	STD			
	34.000	864	0.406	10,31	145.67	217,05	5L				
	34.000	864	0.438	11,13	157.00	234,08	5L				
	34.000	864	0.469	11,91	167.95	250,26	5L				
	34.000	864	0.500	12,70	178.89	266,61	5L	XS	20		
	34.000	864	0.562	14,27	200.70	299,02	5L				
	34.000	864	0.625	15,88	222.78	332,12	5L			30	
	34.000	864	0.688	17,48	244.77	364,90	5L			40	
	34.000	864	0.750	19,05	266.33	396,93	5L				
	34.000	864	0.812	20,62	287.81	428,85	5L				
	34.000	864	0.875	22,23	309.55	461,45	5L				
	34.000	864	0.938	23,83	331.21	493,72	5L				
	34.000	864	1.000	25,40	352.44	525,27	5L				
	34.000	864	1.062	26,97	373.59	556,69	5L				
	34.000	864	1.125	28,58	394.99	588,79	5L				
	34.000	864	1.188	30,18	416.31	620,56	5L				
	34.000	864	1.250	31,75	437.21	651,61	5L				
	36	36.000	914	0.250	6,35	95.45	142,13	5L			
		36.000	914	0.281	7,14	107.20	159,67	5L			
		36.000	914	0.312	7,92	118.92	176,96	5L			10
36.000		914	0.344	8,74	131.00	195,11	5L				
36.000		914	0.375	9,53	142.68	212,56	5L	STD			
36.000		914	0.406	10,31	154.34	229,76	5L				
36.000		914	0.438	11,13	166.35	247,31	5L				
36.000		914	0.469	11,91	177.97	264,94	5L				
36.000		914	0.500	12,70	189.57	282,27	5L	XS	20		
36.000		914	0.562	14,27	212.70	316,11	5L				
36.000		914	0.625	15,88	236.13	351,70	5L			30	
36.000		914	0.688	17,48	259.47	386,45	5L				
36.000		914	0.750	19,05	282.35	420,42	5L			40	
36.000		914	0.812	20,62	305.16	454,27	5L				
36.000		914	0.875	22,23	328.24	488,86	5L				
36.000		914	0.938	23,83	351.25	523,11	5L				
36.000	914	1.000	25,40	373.80	556,59	5L					

dimensions et masses des tubes acier

ASME B 36.10 M-1996

dimensions and weights of steel pipe

ASME B 36.10 M-1996

Diamètre nominal Nominal size	Diamètre extérieur Outside diameter		Epaisseur Wall thickness		Masse Weight		Identification			
	Pouces Inches	mm	Pouces Inches	mm	lb/ft	kg/m	Specif. API	Epaisseur W.T.		Schedule
								STD	XS XXS	
36	36.000	914	1.062	26,97	396,27	589,95	5L			
	36.000	914	1.125	28,58	419,02	624,03	5L			
	36.000	914	1.188	30,18	441,69	657,77	5L			
	36.000	914	1.250	31,75	463,91	690,76	5L			
	38.000	965	0.312	7,92	125,58	186,92	5L			
	38.000	965	0.344	8,74	138,35	206,10	5L			
	38.000	965	0.375	9,53	150,69	224,54	5L	STD		
	38.000	965	0.406	10,31	163,01	242,72	5L			
	38.000	965	0.438	11,13	175,71	261,80	5L			
	38.000	965	0.469	11,91	187,99	279,92	5L			
	38.000	965	0.500	12,70	200,25	298,24	5L	XS		
	38.000	965	0.562	14,27	224,71	334,56	5L			
38	38.000	965	0.625	15,88	249,48	371,68	5L			
	38.000	965	0.688	17,48	274,16	408,43	5L			
	38.000	965	0.750	19,05	298,37	444,38	5L			
	38.000	965	0.812	20,62	322,50	480,21	5L			
	38.000	965	0.875	22,23	346,93	516,82	5L			
	38.000	965	0.938	23,83	371,28	553,08	5L			
	38.000	965	1.000	25,40	395,16	588,53	5L			
	38.000	965	1.062	26,97	418,96	623,87	5L			
	38.000	965	1.125	28,58	443,05	659,97	5L			
	38.000	965	1.188	30,18	467,06	695,73	5L			
	38.000	965	1.250	31,75	490,61	730,69	5L			
	40	40.000	1016	0.312	7,92	132,25	196,89	5L		
40.000		1016	0.344	8,74	145,69	217,09	5L			
40.000		1016	0.375	9,53	158,70	236,53	5L	STD		
40.000		1016	0.406	10,31	171,68	255,69	5L			
40.000		1016	0.438	11,13	185,06	275,80	5L			
40.000		1016	0.469	11,91	198,01	294,90	5L			
40.000		1016	0.500	12,70	210,93	314,22	5L	XS		
40.000		1016	0.562	14,27	236,71	352,51	5L			
40.000		1016	0.625	15,88	262,83	391,65	5L			
40.000		1016	0.688	17,48	288,86	430,42	5L			
40.000		1016	0.750	19,05	314,39	468,34	5L			
40.000		1016	0.812	20,62	339,84	506,14	5L			
40.000	1016	0.875	22,23	365,62	544,78	5L				
40.000	1016	0.938	23,83	391,32	583,05	5L				
40.000	1016	1.000	25,40	416,52	620,48	5L				
40.000	1016	1.062	26,97	441,64	657,78	5L				

Diamètre nominal Nominal size	Diamètre extérieur Outside diameter		Epaisseur Wall thickness		Masse Weight		Identification			
	Pouces Inches	mm	Pouces Inches	mm	lb/ft	kg/m	Specif. API	Epaisseur W.T.		Schedule
								STD	XS XXS	
40	40.000	1016	1.125	28,58	467,08	695,92	5L			
	40.000	1016	1.188	30,18	492,44	733,68	5L			
	40.000	1016	1.250	31,75	517,31	770,62	5L			
	42.000	1067	0.344	8,74	153,04	228,09	5L			
	42.000	1067	0.375	9,53	166,71	248,52	5L	STD		
	42.000	1067	0.406	10,31	180,35	268,66	5L			
	42.000	1067	0.438	11,13	194,42	289,80	5L			
	42.000	1067	0.469	11,91	208,03	309,88	5L			
	42.000	1067	0.500	12,70	221,61	330,19	5L	XS		
	42.000	1067	0.562	14,27	248,72	370,45	5L			
	42.000	1067	0.625	15,88	276,18	411,62	5L			
	42.000	1067	0.688	17,48	303,55	452,40	5L			
42	42.000	1067	0.750	19,05	330,41	492,30	5L			
	42.000	1067	0.812	20,62	357,19	532,07	5L			
	42.000	1067	0.875	22,23	384,31	572,73	5L			
	42.000	1067	0.938	23,83	411,35	613,02	5L			
	42.000	1067	1.000	25,40	437,88	652,42	5L			
	42.000	1067	1.062	26,97	464,32	691,70	5L			
	42.000	1067	1.125	28,58	491,11	731,86	5L			
	42.000	1067	1.188	30,18	517,82	771,64	5L			
	42.000	1067	1.250	31,75	544,01	810,55	5L			
	44.000	1118	0.344	8,74	160,39	239,08	5L			
	44.000	1118	0.375	9,53	174,72	260,50	5L	STD		
	44.000	1118	0.406	10,31	189,03	281,62	5L			
44.000	1118	0.438	11,13	203,78	303,80	5L				
44.000	1118	0.469	11,91	218,04	324,80	5L				
44.000	1118	0.500	12,70	232,29	346,16	5L	XS			
44.000	1118	0.562	14,27	260,72	388,40	5L				
44.000	1118	0.625	15,88	289,53	431,59	5L				
44.000	1118	0.688	17,48	318,25	474,37	5L				
44	44.000	1118	0.750	19,05	346,43	516,26	5L			
	44.000	1118	0.812	20,62	374,53	558,00	5L			
	44.000	1118	0.875	22,23	403,00	600,69	5L			
	44.000	1118	0.938	23,83	431,39	642,99	5L			
	44.000	1118	1.000	25,40	459,24	684,37	5L			
	44.000	1118	1.062	26,97	487,01	725,62	5L			
	44.000	1118	1.125	28,58	515,14	767,80	5L			
	44.000	1118	1.188	30,18	543,19	809,60	5L			
	44.000	1118	1.250	31,75	570,71	850,48	5L			

dimensions et masses des tubes acier

ASME B 36.10 M-1996

dimensions and weights of steel pipe

ASME B 36.10 M-1996

Diamètre nominal Nominal size	Diamètre extérieur Outside diameter		Epaisseur Wall thickness		Masse Weight		Identification			
	Pouces Inches	mm	Pouces Inches	mm	lb/ft	kg/m	Specif. API	Epaisseur W.T.		Schedule
								STD	XS XXS	
46	46.000	1168	0.344	8,74	167.74	249,85	5L			
	46.000	1168	0.375	9,53	182.73	272,25	5L	STD		
	46.000	1168	0.406	10,31	197.70	294,34	5L			
	46.000	1168	0.438	11,13	213.13	317,52	5L			
	46.000	1168	0.469	11,91	228.06	339,54	5L			
	46.000	1168	0.500	12,70	242.97	351,82	5L	XS		
	46.000	1168	0.562	14,27	272.73	406,00	5L			
	46.000	1168	0.625	15,88	302.88	451,17	5L			
	46.000	1168	0.688	17,48	332.95	495,94	5L			
	46.000	1168	0.750	19,05	362.45	539,76	5L			
	46.000	1168	0.812	20,62	391.88	583,43	5L			
	46.000	1168	0.875	22,23	421.69	628,10	5L			
	46.000	1168	0.938	23,83	451.42	672,37	5L			
	46.000	1168	1.000	25,40	480.60	715,68	5L			
	46.000	1168	1.062	26,97	509.69	758,88	5L			
	46.000	1168	1.125	28,58	539.17	803,04	5L			
	46.000	1168	1.188	30,18	568.57	846,81	5L			
	46.000	1168	1.250	31,75	597.41	889,63	5L			
48	48.000	1219	0.344	8,74	175.08	260,85	5L			
	48.000	1219	0.375	9,53	190.74	284,24	5L	STD		
	48.000	1219	0.406	10,31	206.37	307,30	5L			
	48.000	1219	0.438	11,13	222.49	331,52	5L			
	48.000	1219	0.469	11,91	238.08	354,52	5L			
	48.000	1219	0.500	12,70	253.65	377,79	5L	XS		
	48.000	1219	0.562	14,27	284.73	423,94	5L			
	48.000	1219	0.625	15,88	316.23	471,14	5L			
	48.000	1219	0.688	17,48	347.64	517,92	5L			
	48.000	1219	0.750	19,05	378.47	563,70	5L			
	48.000	1219	0.812	20,62	409.22	609,36	5L			
	48.000	1219	0.875	22,23	440.38	656,06	5L			
	48.000	1219	0.938	23,83	471.46	702,34	5L			
	48.000	1219	1.000	25,40	501.96	747,63	5L			
	48.000	1219	1.062	26,97	532.38	792,80	5L			
	48.000	1219	1.125	28,58	563.20	838,99	5L			
	48.000	1219	1.188	30,18	593.94	884,77	5L			
	48.000	1219	1.250	31,75	624.11	929,56	5L			
52	52.000	1321	0.375	9,53	206.76	308,21	5L	STD		
	52.000	1321	0.406	10,31	223.72	333,24	5L			
	52.000	1321	0.438	11,13	241.20	359,51	5L			

Diamètre nominal Nominal size	Diamètre extérieur Outside diameter		Epaisseur Wall thickness		Masse Weight		Identification				
	Pouces Inches	mm	Pouces Inches	mm	lb/ft	kg/m	Specif. API	Epaisseur W.T.		Schedule	
								STD	XS XXS		
52	52.000	1321	0.469	11,91	258.11	384,48	5L				
	52.000	1321	0.500	12,70	275.01	409,64	5L	XS			
	52.000	1321	0.562	14,27	308.74	459,84	5L				
	52.000	1321	0.625	15,88	342.93	511,09	5L				
	52.000	1321	0.688	17,48	377.03	561,89	5L				
	52.000	1321	0.750	19,05	410.51	611,62	5L				
	52.000	1321	0.812	20,62	443.91	661,23	5L				
	52.000	1321	0.875	22,23	477.76	711,98	5L				
	52.000	1321	0.938	23,83	511.53	762,28	5L				
	52.000	1321	1.000	25,40	544.68	811,52	5L				
	52.000	1321	1.062	26,97	577.75	860,63	5L				
	52.000	1321	1.125	28,58	611.26	910,88	5L				
	52.000	1321	1.188	30,18	644.69	960,68	5L				
	52.000	1321	1.250	31,75	677.51	1009,42	5L				
	56	56.000	1422	0.375	9,53	222.78	331,94	5L			
		56.000	1422	0.406	10,31	241.06	358,91	5L			
		56.000	1422	0.438	11,13	259.91	387,24	5L			
		56.000	1422	0.469	11,91	278.15	414,14	5L			
56.000		1422	0.500	12,70	296.37	441,37	5L				
56.000		1422	0.562	14,27	332.75	495,38	5L				
56.000		1422	0.625	15,88	369.63	550,54	5L				
56.000		1422	0.688	17,48	406.42	605,43	5L				
56.000		1422	0.750	19,05	442.55	659,07	5L				
56.000		1422	0.812	20,62	478.60	712,59	5L				
56.000		1422	0.875	22,23	515.14	767,34	5L				
56.000		1422	0.938	23,83	551.60	821,63	5L				
56.000		1422	1.000	25,40	587.40	875,78	5L				
56.000		1422	1.062	26,97	623.12	927,81	5L				
56.000		1422	1.125	28,58	659.32	982,06	5L				
56.000		1422	1.188	30,18	695.45	1035,85	5L				
56.000		1422	1.250	31,75	730.91	1088,50	5L				
60		60.000	1524	0.375	9,53	238.80	355,92	5L			
	60.000	1524	0.406	10,31	258.40	384,85	5L				
	60.000	1524	0.438	11,13	278.62	415,23	5L				
	60.000	1524	0.469	11,91	298.19	444,10	5L				
	60.000	1524	0.500	12,70	317.73	473,31	5L				
	60.000	1524	0.562	14,27	356.76	531,27	5L				
	60.000	1524	0.625	15,88	396.33	590,58	5L				
	60.000	1524	0.688	17,48	435.81	649,40	5L				

dimensions et masses des tubes acier

ASME B 36.10 M-1996

dimensions and weights of steel pipe

ASME B 36.10 M-1996

Diamètre nominal Nominal size	Diamètre extérieur Outside diameter		Epaisseur Wall thickness		Masse Weight		Identification				
	Pouces Inches	mm	Pouces Inches	mm	lb/ft	kg/m	Specif. API	Epaisseur W.T.		Schedule	
								STD	XS XXS		
60	60.000	1524	0.750	19,05	474.59	706,98	5L				
	60.000	1524	0.812	20,62	513.29	764,45	5L				
	60.000	1524	0.875	22,23	552.52	823,26	5L				
	60.000	1524	0.938	23,83	591.67	881,57	5L				
	60.000	1524	1.000	25,40	630.12	938,67	5L				
	60.000	1524	1.062	26,97	668.48	995,64	5L				
	60.000	1524	1.125	28,58	707.38	1053,95	5L				
	60.000	1524	1.188	30,18	746.20	1111,76	5L				
	60.000	1524	1.250	31,75	784.31	1168,36	5L				
	64.000	1626	0.375	9,53	254.82	379,89	5L				
	64.000	1626	0.406	10,31	275.75	410,78	5L				
	64.000	1626	0.438	11,13	297.33	443,23	5L				
64	64.000	1626	0.469	11,91	318.22	474,06	5L				
	64.000	1626	0.500	12,70	339.09	505,26	5L				
	64.000	1626	0.562	14,27	380.76	567,16	5L				
	64.000	1626	0.625	15,88	423.03	630,52	5L				
	64.000	1626	0.688	17,48	465.21	693,36	5L				
	64.000	1626	0.750	19,05	506.63	754,90	5L				
	64.000	1626	0.812	20,62	547.98	816,32	5L				
	64.000	1626	0.875	22,23	589.90	879,17	5L				
	64.000	1626	0.938	23,83	631.74	941,51	5L				
	64.000	1626	1.000	25,40	672.84	1002,56	5L				
	64.000	1626	1.062	26,97	713.85	1063,48	5L				
	64.000	1626	1.125	28,58	755.44	1125,83	5L				
	64.000	1626	1.188	30,18	796.95	1187,67	5L				
	64.000	1626	1.250	31,75	837.71	1248,23	5L				
	68	68.000	1727	0.469	11,91	338.26	503,72	5L			
		68.000	1727	0.500	12,70	360.45	536,89	5L			
		68.000	1727	0.562	14,27	404.77	602,71	5L			
		68.000	1727	0.625	15,88	449.73	670,08	5L			
68.000		1727	0.688	17,48	494.60	736,90	5L				
68.000		1727	0.750	19,05	538.67	802,35	5L				
68.000		1727	0.812	20,62	582.66	867,68	5L				
68.000		1727	0.875	22,23	627.28	934,54	5L				
68.000		1727	0.938	23,83	671.82	1000,86	5L				
68.000		1727	1.000	25,40	715.56	1065,82	5L				
68.000		1727	1.062	26,97	759.22	1130,66	5L				
68.000		1727	1.125	28,58	803.50	1197,02	5L				
68.000		1727	1.188	30,18	847.70	1262,84	5L				
68.000		1727	1.250	31,75	891.11	1327,30	5L				

Diamètre nominal Nominal size	Diamètre extérieur Outside diameter		Epaisseur Wall thickness		Masse Weight		Identification				
	Pouces Inches	mm	Pouces Inches	mm	lb/ft	kg/m	Specif. API	Epaisseur W.T.		Schedule	
								STD	XS XXS		
72	72.000	1829	0.500	12,70	381.81	568,83	5L				
	72.000	1829	0.562	14,27	428.78	638,60	5L				
	72.000	1829	0.625	15,88	476.43	710,02	5L				
	72.000	1829	0.688	17,48	523.99	780,87	5L				
	72.000	1829	0.750	19,05	570.71	850,29	5L				
	72.000	1829	0.812	20,62	617.35	919,54	5L				
	72.000	1829	0.875	22,23	664.66	990,46	5L				
	72.000	1829	0.938	23,83	711.89	1060,80	5L				
	72.000	1829	1.000	25,40	758.28	1129,71	5L				
	72.000	1829	1.062	26,97	804.59	1198,49	5L				
	72.000	1829	1.125	28,58	851.56	1268,91	5L				
	72.000	1829	1.188	30,18	898.45	1338,75	5L				
	72.000	1829	1.250	31,75	944.51	1407,17	5L				
	76	76.000	1930	0.500	12,70	403.17	600,46	5L			
		76.000	1930	0.562	14,27	452.79	674,14	5L			
		76.000	1930	0.625	15,88	503.13	749,57	5L			
		76.000	1930	0.688	17,48	553.38	824,40	5L			
		76.000	1930	0.750	19,05	602.75	897,71	5L			
76.000		1930	0.812	20,62	652.04	970,90	5L				
76.000		1930	0.875	22,23	702.04	1045,82	5L				
76.000		1930	0.938	23,83	751.96	1120,16	5L				
76.000		1930	1.000	25,40	801.00	1192,97	5L				
76.000		1930	1.062	26,97	849.96	1265,67	5L				
76.000		1930	1.125	28,58	899.62	1340,09	5L				
76.000		1930	1.188	30,18	949.20	1413,92	5L				
80	80.000	2032	0.562	14,27	476.80	710,04	5L				
	80.000	2032	0.625	15,88	529.83	789,51	5L				
	80.000	2032	0.688	17,48	582.77	868,37	5L				
	80.000	2032	0.750	19,05	634.79	945,63	5L				
	80.000	2032	0.812	20,62	686.73	1022,76	5L				
	80.000	2032	0.875	22,23	739.42	1101,74	5L				
	80.000	2032	0.938	23,83	792.03	1180,10	5L				
	80.000	2032	1.000	25,40	843.72	1256,86	5L				
	80.000	2032	1.062	26,97	895.33	1333,50	5L				
	80.000	2032	1.125	28,58	947.68	1411,97	5L				
	80.000	2032	1.188	30,18	999.95	1489,83	5L				
	80.000	2032	1.250	31,75	1051.31	1566,11	5L				