



Standard Test Method for Resistivity of Electrical Conductor Materials¹

This standard is issued under the fixed designation B193; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This test method covers the determination of the electrical resistivity of metallic electrical conductor material. It provides for an accuracy of $\pm 0.30\%$ on test specimens having a resistance of $0.00001\ \Omega$ ($10\ \mu\Omega$) or more. Weight resistivity accuracy may be adversely affected by possible inaccuracies in the assumed density of the conductor.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

A111 Specification for Zinc-Coated (Galvanized) “Iron” Telephone and Telegraph Line Wire

A326 Specification for Zinc-Coated (Galvanized) High Tensile Steel Telephone and Telegraph Line Wire (Withdrawn 1990)³

B9 Specification for Bronze Trolley Wire

B105 Specification for Hard-Drawn Copper Alloy Wires for Electric Conductors

B298 Specification for Silver-Coated Soft or Annealed Copper Wire

B355 Specification for Nickel-Coated Soft or Annealed Copper Wire

B415 Specification for Hard-Drawn Aluminum-Clad Steel Wire

B566 Specification for Copper-Clad Aluminum Wire

B800 Specification for 8000 Series Aluminum Alloy Wire

¹ This test method is under the jurisdiction of ASTM Committee B01 on Electrical Conductors and is the direct responsibility of Subcommittee B01.02 on Methods of Test and Sampling Procedure.

Current edition approved April 1, 2014. Published April 2014. Originally approved in 1944. Last previous edition approved in 2008 as B193 – 02 (2008). DOI: 10.1520/B0193-02R14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

for Electrical Purposes—Annealed and Intermediate Temper

2.2 NIST Document:

NBS Handbook 100—Copper Wire Tables⁴

3. Resistivity

3.1 *Resistivity* (Explanatory Note 1) is the electrical resistance of a body of unit length, and unit cross-sectional area or unit weight.

3.2 *Volume Resistivity* is commonly expressed in ohms for a theoretical conductor of unit length and cross-sectional area; in inch-pound units in $\Omega\cdot\text{cmil/ft}$ and in acceptable metric units in $\Omega\cdot\text{mm}^2/\text{m}$. It may be calculated by the following equation:

$$\rho_v = (A/L)R$$

where:

ρ_v = volume resistivity, $\Omega\cdot\text{cmil/ft}$ or $\Omega\cdot\text{mm}^2/\text{m}$,

A = cross-sectional area, cmil or mm^2 ,

L = gage length, used to determine R , ft or m, and

R = measured resistance, Ω .

3.3 *Weight Resistivity* is commonly expressed in ohms for a theoretical conductor of unit length and weight. The method for calculating weight resistivity, based on resistance, length, and weight measurements, of a test specimen is given in Explanatory Note 2.

4. Apparatus

4.1 Resistance shall be measured with a circuit configuration and instrumentation that has a resistance measurement capability of $\pm 0.15\%$ accuracy.

5. Test Specimen

5.1 The test specimen may be in the form of a wire, strip, rod, bar, tube, or shape. It shall be of uniform cross section throughout its length within $\pm 0.75\%$ of the cross-sectional area. Wherever possible it shall be the full cross section of the material it represents, if the full cross section is such that the uniformity of the cross-sectional area can be accurately determined.

⁴ Available from National Institute of Standards and Technology (NIST), 100 Bureau Dr., Stop 1070, Gaithersburg, MD 20899-1070, <http://www.nist.gov>.

5.2 The test specimen shall have the following characteristics:

5.2.1 A resistance of at least 0.00001 Ω (10 $\mu\Omega$) in the test length between potential contacts,

5.2.2 A test length of at least 1 ft or 300 mm,

5.2.3 A diameter, thickness, width, or other dimension suitable to the limitations of the resistance measuring instrument,

5.2.4 No surface cracks or defects visible to the unaided normal eye, and substantially free from surface oxide, dirt, and grease, and

5.2.5 No joints or splices.

6. Procedure

6.1 Make all determinations of the dimensions and weight of the test specimen using instruments accurate to $\pm 0.05\%$. In order to assure this accuracy in measuring the length between potential contacts, the surface in contact with the test specimen shall be a substantially sharp knife-edge when using a Kelvin-type bridge or a potentiometer.

6.2 The cross-sectional dimensions of the specimen may be determined by micrometer measurements, and a sufficient number of measurements shall be made to obtain the mean cross section to within $\pm 0.10\%$. In case any dimension of the specimen is less than 0.100 in. and cannot be measured to the required accuracy, determine the cross-section from the weight, density, and length of the specimen.

6.3 When the density is unknown, determine the density by weighing a specimen first in air and then in a liquid of known density at the test temperature, which shall be room temperature to avoid errors due to convection currents. Exercise care in removing all air bubbles from the specimen when weighing it in the liquid. Calculate the density from the following equation:

$$\delta = (W_a \times d) / (W_a - W_l)$$

where:

δ = density of the specimen, g/cm³;

W_a = weight of the specimen in air, g;

W_l = weight of the specimen in the liquid, g; and

d = density of the liquid at the test temperature, g/cm³.

6.4 When potential leads are used, make sure the distance between each potential contact and the corresponding current contact is at least equal to 1½ times the cross-sectional perimeter of the specimen. Make sure the yoke resistance (between reference standard and test specimen) is appreciably smaller than that of either the reference standard or the test specimen unless a suitable lead compensation method is used, or it is known that the coil and lead ratios are sufficiently balanced so that variation in yoke resistance will not decrease the bridge accuracy below stated requirements.

6.5 Make resistance measurements to an accuracy of $\pm 0.15\%$. To ensure a correct reading, allow the reference standard and the test specimen to come to the same temperature as the surrounding medium. (If the reference standard is made of manganin it is possible to obtain correct readings with the test specimen at reference temperatures other than room temperature). In all resistance measurements, the measuring current raises the temperature of the medium. Therefore, take care to keep the magnitude of the current low, and the time of its use short enough so that the change in resistance cannot be detected with the galvanometer. To eliminate errors due to contact potential, take two readings, one direct and one with current reversed, in direct succession. Check tests are recommended whereby the specimen is turned end for end, and the test repeated. Surface cleaning of the specimen at current and potential contact points may be necessary to obtain good electrical contact.

TABLE 1 Resistivity and Conductivity Conversion

NOTE 1—These factors are applicable only to resistivity and conductivity values corrected to 20°C (68°F). They are applicable for any temperature when used to convert between volume units only or between weight units only. Values of density, δ , for the common electrical conductor materials, are listed in Table 2.

Given $N \rightarrow$ Perform indicated operation to obtain $\downarrow$	Volume Resistivity at 20°C				Weight Resistivity at 20°C		Conductivity at 20°C	
	$\Omega \cdot \text{cmil/ft}$	$\Omega \cdot \text{mm}^2/\text{m}$	$\mu\Omega \cdot \text{in.}$	$\mu\Omega \cdot \text{cm}$	$\Omega \cdot \text{lb/mile}^2$	$\Omega \cdot \text{g/m}^2$	% IACS (Volume Basis)	% IACS (Weight Basis)
Volume Resistivity at 20°C								
$\Omega \cdot \text{cmil/ft}$	...	$N \times 601.52$	$N \times 15.279$	$N \times 6.0153$	$N \times 0.10535 \times (1/\delta)$	$N \times 601.53 \times (1/\delta)$	$(1/N) \times 1037.1$	$(1/N) \times 9220.0 \times (1/\delta)$
$\Omega \cdot \text{mm}^2/\text{m}$	$N \times 0.0016624$	...	$N \times 0.025400$	$N \times 0.010000$	$N \times 0.00017513 \times (1/\delta)$	$N \times (1/\delta)$	$(1/N) \times 1.7241$	$(1/N) \times 15.328 \times (1/\delta)$
$\mu\Omega \cdot \text{in.}$	$N \times 0.065450$	$N \times 39.370$	...	$N \times 0.39370$	$N \times 0.0068950 \times (1/\delta)$	$N \times 39.370 \times (1/\delta)$	$(1/N) \times 67.879$	$(1/N) \times 603.45 \times (1/\delta)$
$\mu\Omega \cdot \text{cm}$	$N \times 0.16624$	$N \times 100.00$	$N \times 2.5400$	...	$N \times 0.017513 \times (1/\delta)$	$N \times 100.00 \times (1/\delta)$	$(1/N) \times 172.41$	$(1/N) \times 1532.8 \times (1/\delta)$
Weight Resistivity at 20°C								
$\Omega \cdot \text{lb/mile}^2$	$N \times 9.4924 \times \delta$	$N \times 5710.0 \times \delta$	$N \times 145.03 \times \delta$	$N \times 57.100 \times \delta$	...	$N \times 5710.0$	$(1/N) \times 9844.8 \times \delta$	$(1/N) \times 87520$
$\Omega \cdot \text{g/m}^2$	$N \times 0.0016624 \times \delta$	$N \times \delta$	$N \times 0.025400 \times \delta$	$N \times 0.010000 \times \delta$	$N \times 0.00017513$	...	$(1/N) \times 1.7241 \times \delta$	$(1/N) \times 15.328$
Conductivity at 20°C								
% IACS (volume basis)	$(1/N) \times 1037.1$	$(1/N) \times 1.7241$	$(1/N) \times 67.879$	$(1/N) \times 172.41$	$(1/N) \times 9844.8 \times \delta$	$(1/N) \times 1.7241 \times \delta$	...	$N \times 0.11249 \times \delta$
% IACS (weight basis)	$(1/N) \times 9220.0 \times (1/\delta)$	$(1/N) \times 15.328 \times (1/\delta)$	$(1/N) \times 603.45 \times (1/\delta)$	$(1/N) \times 1532.8 \times (1/\delta)$	$(1/N) \times 87520$	$(1/N) \times 15.328$	$N \times 8.89 \times (1/\delta)$	...



TABLE 2 Density and Temperature Coefficient of Resistance for Electrical Conductor Materials

Material	Approximate Density, δ , at 20°C, g/cm ³	Temperature Coefficient of Resistance, α , at 20°C	Material	Approximate Density, δ , at 20°C, g/cm ³	Temperature Coefficient of Resistance, α , at 20°C
Copper, % IACS:			Aluminum Alloy 8000, Specification B800, % IACS:		
101	8.89	0.00397	61.8	2.71	0.00408
100	8.89	0.00393	61.5	2.71	0.00406
98.40	8.89	0.00387	61.4	2.71	0.00406
98.16	8.89	0.00386	61.3	2.71	0.00405
97.80	8.89	0.00384	61.2	2.71	0.00404
97.66	8.89	0.00384	61.0	2.71	0.00403
97.40	8.89	0.00383	60.9	2.71	0.00402
97.16	8.89	0.00382	60.8	2.71	0.00402
96.66	8.89	0.00380	60.7	2.71	0.00401
96.16	8.89	0.00378	60.6	2.71	0.00400
94.16	8.89	0.00370			
93.15	8.89	0.00366	Aluminum Alloy 6101, % IACS:		
Silver Coated Copper, Specification B298:			59.5	2.70	0.00393
Class A	8.91	0.00393	59.0	2.70	0.00390
Class B	8.93	0.00393	57.0	2.70	0.00377
Class C	8.95	0.00394	56.5	2.70	0.00373
Class D	8.99	0.00394	56.0	2.70	0.00370
Class E	9.05	0.00395	55.0	2.70	0.00363
Nickel Coated Copper, Specification B355:			54.0	2.70	0.00357
Class 2	8.89	0.00395	53.0	2.70	0.00350
Class 4	8.89	0.00397	Aluminum Alloy, % IACS:		
Class 7	8.89	0.00400	5005-H19 53.5	2.70	0.00353
Class 10	8.89	0.00404	6201-T81 52.5	2.69	0.00347
Class 27	8.89	0.00422	Aluminum Clad Steel, % IACS:		
Bronze, Specification B9:			20.3	6.59	0.0036
Alloy 40	8.89	0.00157	27	5.91	0.0036
Alloy 55	8.89	0.00224	30	5.61	0.0038
Alloy 80	8.89	0.00322	40	4.64	0.0040
Copper Alloy, Specification B105:			Copper Clad Steel:		
Grade 8.5	8.78	0.00042	Grade 30 A, HS, EHS	8.15	0.00378
Grade 13	8.78	0.00063	Grade 40 A, HS, EHS	8.25	0.00378
Grade 15	8.54	0.00072	Galvanized Steel (Telephone and Telegraph), Specification A111:		
Grade 20	8.89	0.00079	Class A Coating:		
Grade 30	8.89	0.00118	Grade EBB (Non cu-brg)	7.83	0.0056
Grade 40	8.89	0.00157	Grade BB (Cu-brg)	7.83	0.0046
Grade 55	8.89	0.00224	Grade BB (Non cu-brg)	7.83	0.0042
Grade 74	8.89	0.00299	Class B Coating:		
Grade 80	8.89	0.00322	Grade EBB (Non cu-brg)	7.80	0.0056
Grade 85	8.89	0.00342	Grade BB (Cu-brg)	7.80	0.0046
Aluminum 1350, % IACS:			Grade BB (Non cu-brg)	7.80	0.0042
61.8	2.705	0.00408	Class C Coating:		
61.5	2.705	0.00406	Grade EBB (Non cu-brg)	7.77	0.0056
61.4	2.705	0.00406	Grade BB (cu-brg)	7.77	0.0046
61.3	2.705	0.00405	Grade BB (Non cu-brg)	7.77	0.0042
61.2	2.705	0.00404	Copper Clad Aluminum, Specification B566:		
61.0	2.705	0.00403	Class 10A and 10H	3.32	0.00405
			Class 15A and 15H	3.63	0.00404
			Galvanized Steel, Specification A326:		
			Class A Coating:		
			Grade 85	7.83	0.0046
			Grade 135 and 195	7.83	0.0042
			Class B Coating:		
			Grade 85	7.80	0.0046
			Grade 135 and 195	7.80	0.0042
			Class C Coating:		
			Grade 85	7.77	0.0046
			Grade 135 and 195	7.77	0.0042



7. Temperature Correction

7.1 When the measurement is made at any other than a reference temperature, the resistance may be corrected for moderate temperature differences to what it would be at the reference temperature, as follows:

$$R_T = \frac{R_t}{1 + \alpha_T(t - T)}$$

where:

R_T = resistance at reference temperature T ,

R_t = resistance as measured at temperature t ,

α_T = known or given temperature coefficient of resistance of the specimen being measured at reference temperature T ,

T = reference temperature, and

t = temperature at which measurement is made.

NOTE 1—The parameter α_T , in the above equation, varies with conductivity and temperature. For copper of 100 % conductivity and a reference temperature of 20°C, its value is 0.00393. Values at other conductivities and temperatures will be found in *NBS Handbook 100*.⁴ Table 1 lists temperature coefficients for the common electrical conductor materials.

8. Report

8.1 For referee tests, report the following information:

8.1.1 Identification of test specimen,

8.1.2 Kind of material,

8.1.3 Test temperature,

8.1.4 Test length of specimen,

8.1.5 Method of obtaining cross-sectional area:

8.1.5.1 *If by micrometer*, the average values of micrometer readings, or

8.1.5.2 *If by weighing*, a record of length, weight, any density determinations that may be made, and calculated cross-sectional areas.

8.1.6 Weight, if used,

8.1.7 Method of measuring resistance,

8.1.8 Value of resistance,

8.1.9 Reference temperature,

8.1.10 Calculated value of resistivity at the reference temperature, and

8.1.11 Previous mechanical and thermal treatments. (Since the resistivity of a material usually depends upon them, these shall be stated whenever the information is available.)

8.2 For routine tests, only such of the items in 8.1 as apply to the particular case, or are significant, shall be reported.

9. Precision and Bias

9.1 *Precision*—This test method has been in use for many years. No statement of precision has been made and no work has been planned to develop such a statement.

9.2 *Bias*—This test method has no bias because the value for resistivity is determined solely in terms of this test method.

10. Keywords

10.1 conductivity; electrical conductor materials; resistivity; resistivity of electrical conductor; volume resistivity; weight resistivity

EXPLANATORY NOTES

NOTE 1—*Volume resistivity* is used in place of “weight resistivity” and “percent conductivity.”

Resistivity units are based on the International Annealed Copper Standard (IACS) adopted by IEC in 1913, which is 1/58 $\Omega\text{-mm}^2/\text{m}$ at 20°C (68°F) for 100 % conductivity. The value of 0.017241 $\Omega\text{-mm}^2/\text{m}$ and the value of 0.15328 $\Omega\text{-g}/\text{m}^2$ at 20°C (68°F) are respectively the international equivalent of volume and weight resistivity of annealed copper equal (to five significant figures) to 100 % conductivity. The latter term means that a copper wire 1 m in length and weighing 1 g would have a resistance of 0.15328 Ω . This is equivalent to a resistivity value of 875.20 $\Omega\text{-lb}/\text{mile}^2$, which signifies the resistance of a copper wire 1 mile in length weighing 1 lb. It is also equivalent, for example, to 1.7241 $\mu\Omega/\text{cm}$ of length of a copper bar 1 cm^2 in cross section. A complete discussion of this subject is

contained in *NBS Handbook 100*.⁴ The use of five significant figures in expressing resistivity does not imply the need for greater accuracy of measurement than that specified in Test Method B193. The use of five significant figures is required for reasonably accurate reversible conversion from one set of resistivity units to another. The equivalent resistivity values in Table 3 were derived from the fundamental IEC value (1/58 $\Omega\text{-mm}^2/\text{m}$) computed to seven significant figures and then rounded to five significant figures.

NOTE 2—*Weight resistivity* is expressed in U.S. customary units in $\Omega\text{-lb}/\text{mile}^2$ and in metric units in $\Omega\text{-g}/\text{m}^2$. It may be calculated as follows:

$$\rho_w = (W/L_1 L_2)R$$

TABLE 3 Equivalent Resistivity Values for Copper^A

Conductivity at 20°C (68°F) percent IACS	100.0
Volume Resistivity	
$\Omega\text{-cmil}/\text{ft}$	10.371
$\Omega\text{-mm}^2/\text{m}$	0.017241
$\mu\Omega\text{-in.}$	0.67879
$\mu\Omega\text{-cm}$	1.7241
Weight Resistivity	
$\Omega\text{-lb}/\text{mile}^2$	875.20
$\Omega\text{-g}/\text{m}^2$	0.15328

^A The equivalent resistivity values for 100 % IACS (soft copper) were each computed from the fundamental IEC value (1/58 $\Omega\text{-mm}^2/\text{m}$) using conversion factors each accurate to at least seven significant figures. Corresponding values for other conductivities (aluminum, etc.) may be derived from these by multiplying by the reciprocal of the conductivity ratios and where applicable also by the density ratios, both accurate to at least seven significant figures.

where:

ρ_w = weight resistivity, $\Omega\text{-lb/mile}^2$ or $\Omega\text{-g/m}^2$,
 W = weight of the test specimen, lb or g,
 L_2 = length of the test specimen, miles or m,
 L_1 = gage length, used to determine R , miles or m, and
 R = measured resistance, Ω .

NOTE 3—*Resistivity and Conductivity Conversion*—Conversion of the various units of volume resistivity, weight resistivity, and conductivity, may be facilitated by employing the formulas and factors shown in **Table**

1. The factors given therein are applicable to all metallic electrical conductor material. **Table 2** lists values of density, δ , for the common electrical conductor materials.

NOTE 4—*Density*—For the purpose of resistivity and conductivity conversion, the density of the various conductor materials may be taken as shown in **Table 2**, based on a temperature of 20°C (68°F).

However, if the conversion is for specification acceptance purposes, the density used shall be that specified in the product specification involved.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>