



Standard Specification for Aluminum and Aluminum-Alloy Drawn Seamless Tubes¹

This standard is issued under the fixed designation B 210; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification² covers aluminum and aluminum-alloy drawn seamless tubes in straight lengths and coils for general purpose and pressure applications in alloys (Note 2), tempers, and thicknesses shown in Table 2. Coiled tubes are generally available only as round tubes with a wall thickness not exceeding 0.083 in. and only in nonheat-treatable alloys.

1.2 Alloy and temper designations are in accordance with ANSI H35.1. The equivalent Unified Numbering System alloy designations are those of Table 1 preceded by A9, for example, A91100 for aluminum designation 1100 in accordance with Practice E 527.

NOTE 1—See Specification B 483 for aluminum-alloy drawn tubes for general purpose applications; Specification B 234 for aluminum-alloy drawn seamless tubes for condensers and heat exchangers; and Specification B 241/B 241M for aluminum-alloy seamless pipe and seamless extruded tube.

NOTE 2—Throughout this specification, use of the term *alloy* in the general sense includes aluminum as well as aluminum alloy.

1.3 A complete metric companion to Specification B 210 has been developed—Specification B 210M; therefore, no metric equivalents are presented in this specification.

1.4 For acceptance criteria for inclusion of new aluminum and aluminum alloys in this specification, see Annex A2.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

¹ This specification is under the jurisdiction of ASTM Committee B07 on Light Metals and Alloys and is the direct responsibility of Subcommittee B07.03 on Aluminum Alloy Wrought Products.

Current edition approved Dec. 1, 2004. Published December 2004. Originally approved in 1946. Last previous edition approved in 2002 as B 210 – 02.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SB-210 in Section II of that Code.

2.2 ASTM Standards:³

B 234 Specification for Aluminum and Aluminum-Alloy Drawn Seamless Tubes for Condensers and Heat Exchangers

B 241/B 241M Specification for Aluminum and Aluminum-Alloy Seamless Pipe and Seamless Extruded Tube

B 483 Specification for Aluminum and Aluminum-Alloy Drawn Tubes for General Purpose Applications

B 557 Test Methods of Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products

B 660 Practices for Packaging/Packing of Aluminum and Magnesium Products

B 666/B 666M Practice for Identification Marking of Aluminum and Magnesium Products

B 881 Terminology Relating to Aluminum- and Magnesium-Alloy Products

B 918 Practice for Heat Treatment of Wrought Aluminum Alloys

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E 34 Test Methods for Chemical Analysis of Aluminum and Aluminum-Base Alloys

E 55 Practice for Sampling Wrought Nonferrous Metals and Alloys for Determination of Chemical Composition

E 215 Practice for Standardizing Equipment for Electromagnetic Examination of Seamless Aluminum-Alloy Tube

E 527 Practice for Numbering Metals and Alloys (UNS)

E 607 Test Method for Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique, Nitrogen Atmosphere

E 716 Practices for Sampling Aluminum and Aluminum Alloys for Spectrochemical Analysis

E 1004 Practice for Determining Electrical Conductivity Using the Electromagnetic (Eddy-Current) Method

E 1251 Test Method for Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Argon

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Chemical Composition Limits^{A,B,C}

Alloy	Silicon	Iron	Copper	Manganese	Magnesium	Chromium	Zinc	Titanium	Other Elements ^D		Aluminum, min
									Each	Total ^E	
1060	0.25	0.35	0.05	0.03	0.03	...	0.05	0.03	0.03 ^F	...	99.60 min ^G
1100	0.95 Si + Fe		0.05–0.20	0.05	...	...	0.10	...	0.05	0.15	99.00 min ^G
2011	0.40	0.7	5.0–6.0	...	...	...	0.30	...	0.05 ^H	0.15	remainder
2014	0.50–1.2	0.7	3.9–5.0	0.40–1.2	0.20–0.8	0.10	0.25	0.15	0.05	0.15	remainder
2024	0.50	0.50	3.8–4.9	0.30–0.9	1.2–1.8	0.10	0.25	0.15	0.05	0.15	remainder
3003	0.6	0.7	0.05–0.20	1.0–1.5	...	...	0.10	...	0.05	0.15	remainder
Alclad 3003 ^I											
3102	0.40	0.7	0.10	0.05–0.40	...	...	0.30	0.10	0.05	0.15	remainder
Alclad 3102 ^I											
5005	0.30	0.7	0.20	0.20	0.50–1.1	0.10	0.25	...	0.05	0.15	remainder
5050	0.40	0.7	0.20	0.10	1.1–1.8	0.10	0.25	...	0.05	0.15	remainder
5052	0.25	0.40	0.10	0.10	2.2–2.8	0.15–0.35	0.10	...	0.05	0.15	remainder
5083	0.40	0.40	0.10	0.40–1.0	4.0–4.9	0.05–0.25	0.25	0.15	0.05	0.15	remainder
5086	0.40	0.50	0.10	0.20–0.7	3.5–4.5	0.05–0.25	0.25	0.15	0.05	0.15	remainder
5154	0.25	0.40	0.10	0.10	3.1–3.9	0.15–0.35	0.20	0.20	0.05	0.15	remainder
5456	0.25	0.40	0.10	0.50–1.0	4.7–5.5	0.05–0.20	0.25	0.20	0.05	0.15	remainder
6061	0.40–0.8	0.7	0.15–0.40	0.15	0.8–1.2	0.04–0.35	0.25	0.15	0.05	0.15	remainder
6063	0.20–0.6	0.35	0.10	0.10	0.45–0.9	0.10	0.10	0.10	0.05	0.15	remainder
6262	0.40–0.8	0.7	0.15–0.40	0.15	0.8–1.2	0.04–0.14	0.25	0.15	0.05 ^J	0.15	remainder
7072 cladding ^K	0.7 Si + Fe		0.10	0.10	0.10	...	0.8–1.3	...	0.05	0.15	remainder
7075	0.40	0.50	1.2–2.0	0.30	2.1–2.9	0.18–0.28	5.1–6.1	0.20	0.05	0.15	remainder

^A Limits are in weight percent maximum unless shown as a range or otherwise stated.

^B Analysis shall be made for the elements for which limits are shown in this table.

^C For purposes of determining conformance to these limits, an observed value or a calculated value obtained from analysis shall be rounded to the nearest unit in the last right-hand place of figures used in expressing the specified limit, in accordance with the rounding-off method of Practice E 29.

^D *Others* includes listed elements for which no specific limit is shown as well as unlisted metallic elements. The producer may analyze samples for trace elements not specified in the specification. However, such analysis is not required and may not cover all metallic *Others* elements. Should any analysis by the producer or the purchaser establish that an *Others* element exceeds the limit of *Each* or that the aggregate of several *Others* elements exceeds the limit of *Total*, the material shall be considered non-conforming.

^E *Other elements*—Total shall be the sum of unspecified metallic elements 0.010 % or more, rounded to the second decimal before determining the sum.

^F Vanadium 0.05 % max.

^G The aluminum content shall be calculated by subtracting from 100.00 % the sum of all metallic elements present in amounts of 0.010 % or more each, rounded to the second decimal before determining the sum.

^H Bismuth and lead each 0.20–0.6 %.

^I Alloy clad with Alloy 7072.

^J Bismuth and lead each 0.40–0.7 %.

^K Composition of cladding alloy as applied during the course of manufacture. The samples from finished tube shall not be required to conform to these limits.

Atmosphere, Point-to-Plane, Unipolar Self-Initiating Capacitor Discharge

2.3 *ANSI Standards*:⁴

H35.1 Alloy and Temper Designation Systems for Aluminum

H35.2 Dimensional Tolerances for Aluminum Mill Products

2.4 *Military Standard*:⁵

MIL-STD-129 Marking for Shipment and Storage

2.5 *AMS Specification*:⁶

AMS 2772 Heat Treatment of Aluminum Alloy Raw Materials

2.6 *Federal Standard*:⁵

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)

3. Terminology

3.1 *Definitions*: Refer to Terminology B 881 for definitions of product terms used in this specification.

3.2 *Definitions of Terms Specific to This Standard*:

3.2.1 *capable of*—The term *capable of* as used in this specification means that the test need not be performed by the producer of the material. However, should subsequent testing by the purchaser establish that the material does not meet these requirements, the material shall be subject to rejection.

TABLE 2 Tensile Property Limits^{A,B}

Temper	Specified Wall Thickness, ^C in.	Tensile Strength, ksi		Yield Strength ^D (0.2 % offset), min, ksi	Elongation in 2 in. or 4 × Diameter, ^E min, %	
		min	max		Full-Section Specimen	Cut-Out Specimen
Aluminum 1060 ^F						
O	0.014–0.500	8.5	13.5	2.5	...	...
H12		10.0	...	4.0	...	...
H14		12.0	...	10.0	...	...
H18		16.0	...	13.0	...	...

TABLE 2 *Continued*

Temper	Specified Wall Thickness, ^C in.	Tensile Strength, ksi		Yield Strength ^D (0.2 % offset), min, ksi	Elongation in 2 in. or 4 × Diameter, ^E min, %	
		min	max		Full-Section Specimen	Cut-Out Specimen
H113 ^G		8.5	...	2.5	...	...
Aluminum 1100 ^F						
O	0.010–0.500	11.0	15.5	3.5	...	...
H12		14.0	...	11.0	...	...
H14		16.0	...	14.0	...	...
H16		19.0	...	17.0	...	...
H18		22.0	...	20.0	...	...
H113 ^G		11.0	...	3.5	...	...
Alloy 2011						
T3	0.018–0.049	47.0	...	40.0	...	...
	0.050–0.500	47.0	...	40.0	10	8
T4511	0.018–0.049	44.0	...	25.0	...	...
					...	...
	0.050–0.259	44.0	...	25.0	20	18
	0.260–0.500	44.0	...	25.0	20	20
T8	0.018–0.500	58.0	...	46.0	10	8
Alloy 2014						
O	0.018–0.500	...	32.0	16.0 max	...	...
T4, T42 ^H	0.018–0.024	54.0	...	30.0	10	...
	0.025–0.049	54.0	...	30.0	12	10
	0.050–0.259	54.0	...	30.0	14	10
	0.260–0.500	54.0	...	30.0	16	12
T6, T62 ^H	0.018–0.024	65.0	...	55.0	7	...
	0.025–0.049	65.0	...	55.0	7	6
	0.050–0.259	65.0	...	55.0	8	7
	0.260–0.500	65.0	...	55.0	9	8
Alloy 2024						
O	0.018–0.500	...	32.0	15.0 max	...	...
T3 ^H	0.018–0.024	64.0	...	42.0	10	...
	0.025–0.049	64.0	...	42.0	12	10
	0.050–0.259	64.0	...	42.0	14	10
	0.260–0.500	64.0	...	42.0	16	12
T42 ^H	0.018–0.024	64.0	...	40.0	10	...
	0.025–0.049	64.0	...	40.0	12	10
	0.050–0.259	64.0	...	40.0	14	10
	0.260–0.500	64.0	...	40.0	16	12
Alloy 3003 ^F						
O	0.010–0.024	14.0	19.0	5.0	...	...
	0.025–0.049	14.0	19.0	5.0	30	20
	0.050–0.259	14.0	19.0	5.0	35	25
	0.260–0.500	14.0	19.0	5.0	...	30
H12	0.010–0.500	17.0	...	12.0	...	...
H14	0.010–0.024	20.0	...	17.0	3	...
	0.025–0.049	20.0	...	17.0	5	3
	0.050–0.259	20.0	...	17.0	8	4
	0.260–0.500	20.0	...	17.0	...	...
H16	0.010–0.024	24.0	...	21.0	...	...
	0.025–0.049	24.0	...	21.0	3	2
	0.050–0.259	24.0	...	21.0	5	4
	0.260–0.500	24.0	...	21.0	...	...
H18	0.010–0.024	27.0	...	24.0	2	...
	0.025–0.049	27.0	...	24.0	3	2
	0.050–0.259	27.0	...	24.0	5	3
	0.260–0.500	27.0	...	24.0	...	...
H113 ^G	0.010–0.500	14.0	...	5.0	...	...
Alloy Alclad 3003						
O	0.010–0.024	13.0	19.0	4.5	...	...
	0.025–0.049	13.0	19.0	4.5	30	20
	0.050–0.259	13.0	19.0	4.5	35	25
	0.260–0.500	13.0	19.0	4.5	...	30
H14	0.010–0.024	19.0	...	16.0	...	...
	0.025–0.049	19.0	...	16.0	5	...
	0.050–0.259	19.0	...	16.0	8	4
	0.260–0.500	19.0	...	16.0	...	...
H18	0.010–0.500	26.0	...	23.0	...	...

TABLE 2 *Continued*

Temper	Specified Wall Thickness, ^C in.	Tensile Strength, ksi		Yield Strength ^D (0.2 % offset), min, ksi	Elongation in 2 in. or 4 × Diameter, ^E min, %	
		min	max		Full-Section Specimen	Cut-Out Specimen
H113 ^G	0.010–0.500	13.0	...	4.5	...	...
Alloy 3102 ^F						
O	0.018–0.049	12.0	17.0	4.0	30 ^I	20 ^I
	0.050–0.065	12.0	17.0	4.0	35	25
Alloy Alclad 3102 ^F						
O	0.018–0.049	10.0	17.0	3.5	30 ^I	20 ^I
	0.050–0.065	10.0	17.0	3.5	35	25
Alloy 5005 ^F						
O ^F	0.018–0.500	15.0	21.0	5.0	...	...
Alloy 5050 ^F						
O ^F	0.010–0.500	18.0	24.0	6.0	...	...
H32		22.0	...	16.0	...	...
H34		25.0	...	20.0	...	...
H36		27.0	...	22.0	...	...
H38		29.0	...	24.0	...	...
Alloy 5052 ^F						
O ^F	0.010–0.450	25.0	35.0	10.0	...	...
H32		31.0	...	23.0	...	...
H34		34.0	...	26.0	...	...
H36		37.0	...	29.0	...	...
H38		39.0	...	24.0	...	...
Alloy 5083 ^F						
O ^F	0.018–0.450	39.0	51.0	16.0	...	14
Alloy 5086 ^F						
O ^F	0.010–0.450	35.0	46.0	14.0	...	...
H32		40.0	...	28.0	...	...
H34		44.0	...	34.0	...	...
H36		47.0	...	38.0	...	...
Alloy 5154 ^F						
O	0.010–0.500	30.0	41.0	11.0	10	10
H34		39.0	...	29.0	5	5
H38	0.010–0.250	45.0	...	34.0	...	...
Alloy 5456 ^F						
O	0.018–0.450	41.0	53.0	19.0	...	14
Alloy 6061						
O	0.018–0.500	...	22.0	14.0 max	15	15
T4	0.025–0.049	30.0	...	16.0	16	14
	0.050–0.259					
	0.260–0.500	30.0	...	16.0	18	16
		30.0	...	16.0	20	18
T42 ^H	0.025–0.049	30.0	...	14.0	16	14
	0.050–0.259	30.0	...	14.0	18	16
	0.260–0.500	30.0	...	14.0	20	18
T6, T62 ^H	0.025–0.049	42.0	...	35.0	10	8
	0.050–0.259	42.0	...	35.0	12	10
	0.260–0.500	42.0	...	35.0	14	12
Alloy 6063						
O	0.018–0.500	...	19.0	...	...	...
T4, T42 ^H	0.025–0.049	22.0	...	10.0	16	14
	0.050–0.259	22.0	...	10.0	18	16
	0.260–0.500	22.0	...	10.0	20	18
T6, T62 ^H	0.025–0.049	33.0	...	28.0	12	8
	0.050–0.259	33.0	...	28.0	14	10
	0.260–0.500	33.0	...	28.0	16	12
T83	0.025–0.259	33.0	...	30.0	5	...

TABLE 2 *Continued*

Temper	Specified Wall Thickness, ^C in.	Tensile Strength, ksi		Yield Strength ^D (0.2 % offset), min, ksi	Elongation in 2 in. or 4 × Diameter, ^E min, %	
		min	max		Full-Section Specimen	Cut-Out Specimen
T831	0.025–0.259	28.0	...	25.0	5	...
T832	0.025–0.049	41.0	...	36.0	8	5
	0.050–0.259	40.0	...	35.0	8	5
Alloy 6262						
T6, T62 ^H	0.025–0.049	42.0	...	35.0	10	8
	0.050–0.259	42.0	...	35.0	12	10
	0.260–0.500	42.0	...	35.0	14	12
T9	0.025–0.375	48.0	...	44.0	5	4
Alloy 7075						
O	0.025–0.049	...	40.0	21.0 max	10	8
	0.050–0.500	...	40.0	21.0 max	12	10
T6, T62 ^H	0.025–0.259	77.0	...	66.0	8	7
	0.260–0.500	77.0	...	66.0	9	8
T73 ^J	0.025–0.259	66.0	...	56.0	10	8
	0.260–0.500	66.0	...	56.0	12	10

^A See Annex A1.

^B To determine conformance to this specification, each value for tensile strength and for yield strength shall be rounded to the nearest 0.1 ksi and each value for elongation to the nearest 0.5 % both in accordance with the rounding-off method of Practice E 29.

^C Coiled tube is generally available with a maximum wall thickness of 0.083 in. and only in nonheat-treatable alloys.

^D Yield strength to be determined only on straight tube.

^E Elongation of full-section and cut-out sheet-type specimens is measured in 2 in. of cut-out round specimens, in 4× specimen diameter.

^F In this alloy tube other than round is produced only in the F (as drawn) and O tempers. Properties for F temper are not specified or guaranteed.

^G Beginning with the 1982 issue the requirements for the H112 tempers were replaced by the H113 temper, applicable to other than round tube, which is fabricated by cold-forming annealed round tube and acquires some temper in this forming operation.

^H Material in the T42 or T62 tempers is not available from the material producers.

^I For specified wall thickness under 0.025 in., elongation is not required.

^J Material in this temper exhibits improved resistance to stress corrosion compared to that of the T6 temper. The stress-corrosion resistance capability of individual lots is determined by testing the previously selected tension-test samples in accordance with the applicable electrical conductivity acceptance criteria of Table 3.

4. Ordering Information

4.1 Orders for material to this specification shall include the following information:

4.1.1 This specification designation (which includes the number, the year, and the revision letter, if applicable),

4.1.2 Quantity in pieces or pounds,

4.1.3 Alloy (Section 7),

4.1.4 Temper (Section 8),

4.1.5 Cross-sectional dimensions (outside diameter and wall thickness, or inside diameter and wall thickness for round tube;

for tube other than round, square, rectangular, hexagonal, or octagonal with sharp corners, a drawing is required),

4.1.6 Length (straight or coiled),

4.1.7 Nominal inside diameter of coils and weight or maximum outside diameter, if applicable,

4.1.8 For alloy Alclad 3003 or Alclad 3102 state clad inside or outside (17.1).

4.2 Additionally, orders for material to this specification shall include the following information when required by the purchaser:

TABLE 3 Lot Acceptance Criteria for Resistance to Stress-Corrosion

Alloy and Temper	Lot Acceptance Criteria		Lot Acceptance Status
	Electrical Conductivity, ^{A,B} % IACS	Level of Mechanical Properties	
7075–T73	40.0 or greater	per specified requirements	acceptable
	38.0 through 39.9	per specified requirements and yield strength does not exceed minimum by more than 11.9 ksi	acceptable
	38.0 through 39.9	per specified requirements but yield strength exceeds minimum by 12.0 ksi or more	unacceptable ^C
	less than 38.0	any level	unacceptable ^C

^A The electrical conductivity shall be determined in accordance with Practice E 1004 in the following locations:

Wall Thickness, in.

Up through 0.100

0.101 and over

Location

surface of tensile sample

subsurface after removal of approximately 10 % of thickness.

^B For curved surfaces, the conductivity shall be measured on a machined flat spot; however, for small size tubes, a cut-out piece may be flattened and the conductivity determined.

^C When material is found to be unacceptable, it shall be reprocessed (additional precipitation heat treatment or resolution heat treatment and precipitation heat treatment).

4.2.1 Whether heat treatment in accordance with Practice B 918 is required (11.2),

4.2.2 Whether flattening tests are required (Section 9 and Table 4),

4.2.3 Whether flare testing is required (Section 10),

4.2.4 Whether 7075-O material is required to develop requirements for T73 temper (12.3),

4.2.5 Whether testing for leaks is required and, when leaks are allowed, the number of leaks allowed and the manner of marking leaks (15.1.3.2),

4.2.6 Whether inside cleanliness test is required on coiled tubes (16.2) and frequency of testing required,

4.2.7 Whether inspection or witness of inspection and tests by the purchaser's representative is required prior to material shipment (Section 20),

4.2.8 Whether certification is required (Section 22),

4.2.9 Whether marking for identification is required (Section 23), and

4.2.10 Whether Practices B 660 applies, and if so, the levels of preservation, packaging, and packing required (Section 24).

5. Materials and Manufacture

5.1 The tube shall be produced by drawing an extruded tube made from hollow extrusion ingot (cast in hollow form or pierced) and extruded by the use of the die and mandrel method.

5.2 The ends of coiled tube shall be crimped or otherwise sealed to avoid contamination during shipment.

TABLE 4 Minimum Outside Diameter Flattening Factor

Alloy	Temper	Wall Thickness, in.	Minimum Diameter Flattening Factor, F
1100	O	0.014–0.500	2
	H12	0.014–0.500	3
	H14	0.014–0.500	6
	H16	0.014–0.500	8
3003	O	0.025–0.500	2
	H12	0.025–0.500	3
	H14	0.025–0.500	6
	H16	0.025–0.500	8
2024	O	0.018–0.049	3
		0.050–0.500	4
	T3	0.018–0.500	8
5052	O	0.010–0.450	3
	H32	0.010–0.450	6
	H34	0.010–0.450	8
5086	O	0.010–0.450	3
	H32	0.010–0.450	8
6061	O	0.018–0.120	3
		0.121–0.238	4
		0.239–0.500	6
		0.025–0.500	6
	T4	0.025–0.500	6
	T6	0.025–0.500	8
7075	O	0.025–0.049	4
		0.050–0.259	5
	T6	0.025–0.259	10

6. Responsibility for Quality Assurance

6.1 *Responsibility for Inspection and Tests*—Unless otherwise specified in the contract or purchase order, the producer is responsible for the performance of all inspection and test requirements specified herein. The producer may use his own or any other suitable facilities for the performance of the inspection and test requirements specified herein, unless disapproved by the purchaser in the order or at the time of signing the contract. The purchaser shall have the right to perform any of the inspections and tests set forth in this specification where such inspections are deemed necessary to ensure that material conforms to prescribed requirements.

6.2 *Lot Definition*—An inspection lot shall be defined as follows:

6.2.1 For heat-treated tempers an inspection lot shall consist of an identifiable quantity of material of the same mill form, alloy, temper, and nominal dimensions traceable to a heat-treat lot or lots, and subjected to inspection at one time.

6.2.2 For nonheat-treated tempers, an inspection lot shall consist of an identifiable quantity of material of the same mill form, alloy, temper, and nominal dimensions subjected to inspection at one time.

7. Chemical Composition

7.1 *Limits*—The tubes shall conform to the chemical composition limits prescribed in Table 1. Conformance shall be determined by the producer by analyzing samples taken at the time the ingots are poured, or samples taken from the finished or semi-finished product. If the producer has determined the chemical composition of the material during the course of manufacture, he shall not be required to sample and analyze the finished product.

NOTE 3—It is standard practice in the United States aluminum industry to determine conformance to the chemical composition limits prior to further processing of ingots into wrought products. Due to the continuous nature of the process, it is not practical to keep a specific ingot analysis identified with a specific quantity of finished material.

7.2 *Number of Samples*—The number of samples taken for determination of chemical composition shall be as follows:

7.2.1 When samples are taken at the time the ingots are poured, at least one sample shall be taken for each group of ingots poured simultaneously from the same source of molten metal.

7.2.2 When samples are taken from the finished or semi-finished product, a sample shall be taken to represent each 4000 lb or fraction thereof of material in the shipment, except that no more than one sample shall be required per piece.

7.3 *Methods of Sampling*—Samples for determination of chemical composition shall be taken in accordance with one of the following methods:

7.3.1 Samples for chemical analysis shall be taken from the material by drilling, sawing, milling, turning, or clipping a representative piece or pieces to obtain a prepared sample not less than 75 g. Sampling shall be in accordance with Practice E 55.

7.3.2 Sampling for spectrochemical analysis shall be in accordance with Practices E 716. Samples for other methods of

analysis shall be suitable for the form of material being analyzed and the type of analytical method used.

NOTE 4—It is difficult to obtain a reliable analysis of each of the components of clad materials using material in its finished state. A reasonably accurate determination of the core composition can be made if the cladding is substantially removed prior to analysis. The cladding composition is more difficult to determine because of the relatively thin layer and because of diffusion of core elements to the cladding. The correctness of cladding alloy used can usually be verified by a combination of metallographic examination and spectrochemical analysis of the surface at several widely separated points.

7.4 Methods of Analysis—The determination of chemical composition shall be made in accordance with suitable chemical (Test Methods E 34), or spectrochemical (Test Methods E 607 and E 1251), methods. Other methods may be used only when no published ASTM method is available. In case of dispute, the methods of analysis shall be agreed upon between the producer and the purchaser.

8. Tensile Properties of Material as Supplied

8.1 Limits—Tube shall conform to the tensile property requirements specified in Table 2.

8.2 Number of Specimens:

8.2.1 For tubes having a nominal weight of less than 1 lb/linear ft, one tension test specimen shall be taken for each 1000 lb, or fraction thereof, in a lot.

8.2.2 For tubes having a nominal weight of 1 lb or more/linear ft, one tension test specimen shall be taken for each 1000 ft, or fraction thereof, in a lot.

8.2.3 If the shipment contains tubes of more than one alloy, temper, or size, only those tubes of the same alloy, temper, and size shall be grouped for the purpose of selecting tension test specimens. Other procedures for selecting samples may be employed if agreed upon by the producer and the purchaser.

8.3 Test Specimens—Geometry of test specimens and the location in the product from which they are taken shall be as specified in Test Methods B 557.

8.4 Test Methods—The tension tests shall be made in accordance with Test Methods B 557.

9. Flattening Properties

9.1 Limits—When specified by the purchaser at the time of placing the order, round tube in alloys and tempers listed in Table 4 shall be tested in full section and withstand, without cracking, the minimum outside diameter flattening factor specified in Table 4.

9.2 Number of Specimens:

9.2.1 For tubes having a nominal weight of less than 1 lb/linear ft, one flattening test specimen shall be taken for each 1000 lb or fraction thereof in a lot.

9.2.2 For tubes having a nominal weight of 1 lb or more/linear ft, one flattening test specimen shall be taken for each 1000 ft, or fraction thereof, in a lot.

9.3 Methods of Test—Flattening test specimens shall be flattened sidewise under a gradually applied load so as to give a uniform radius of bend until the minimum outside diameter under load is not more than F times the wall thickness of the tube as specified in Table 4.

9.4 Alternative Bend Test—In case the tube does not flatten so as to give a uniform radius of bend, suitable jigs may be used to bring about this result, or a section of tube of not less than $\frac{1}{2}$ in. in length, with the subtended arc not greater than one half nor less than one third of the circumference of the original tube, shall be removed from the material in question and without further treatment shall be bent around a mandrel having a diameter N times the wall thickness of the tube as specified in Table 5. The bend shall be made with the pin placed on the inside surface of the specimen, with the longitudinal axis of the pin and the specimen parallel. The bend shall be continued until the specimen encloses at least 180° of the pin.

9.4.1 After the flattening test, the outer surface of the tube shall be examined visually for cracks. Any evidence of cracking shall be cause for rejection.

10. Flaring Properties

10.1 Limits—When specified by the purchaser at the time of placing the order, round tube in straight lengths in alloys and tempers 1100-H14, 3003-H14, 5052-O, and 6061-O with a nominal outside diameter of 0.375 in. or less, shall be capable of being double-flared to the configuration of Fig. 1, and with a nominal outside diameter over 0.375 in. shall be capable of being single-flared to the configuration of Fig. 2, without formation of cracks or other defects clearly visible to the unaided eye.

10.2 Number of Specimens—When flare testing is specified in the order, for tube sizes having a nominal weight of less than 1 lb/linear ft, one flaring test specimen shall be taken for each 1000 lb or fraction thereof in the lot. For tubes having a nominal weight of 1 lb or more/linear ft, one flaring test specimen shall be taken for each 1000 ft, or fraction thereof, in the lot.

10.3 Preparation of Specimens—Specimens for flaring may be cut from any portion of the tube, or an entire tube may be used as a specimen. The end of the specimen to be flared shall be cut square, with the cut end smooth and free from burrs, but not rounded, except for sizes 0.375 in. and under.

TABLE 5 Minimum Bend Factor

Alloy	Temper	Wall Thickness, in.	Minimum Bend Factor, N
2024	T3	0.018–0.128	6
5052	O	0.010–0.249	1
	H32	0.010–0.249	4
	H34	0.010–0.249	6
5086	O	0.010–0.249	1
	H32	0.010–0.249	6
6061	O	0.018–0.120	1
		0.121–0.238	2
		0.239–0.500	4
		0.025–0.500	4
	T6	0.025–0.500	6
7075	O	0.025–0.125	4
		0.126–0.259	6
		0.025–0.062	8
		0.063–0.125	10
	T6	0.126–0.259	12




FIG. 1 Double Flare




FIG. 2 Single Flare

10.4 *Test Methods*—The specimen shall be forced axially with steady pressure over a hardened and polished tapered steel pine having a 74° included angle, to produce a flare having the permanent expanded outside diameter specified in Table 6.

11. Heat Treatment

11.1 Unless specified in 11.2, producer or supplier heat treatment for the applicable tempers in Table 2 shall be in accordance with AMS 2772.

11.2 When specified, heat treatment of applicable tempers in Table 2 shall be in accordance with Practice B 918.

12. Producer's Confirmation of Heat-Treat Response

12.1 In addition to the requirements of Section 8, material in Alloys 2014, 2024, 6061, and 6063 produced in the O or F temper (within the size limits specified in Table 2) shall, after proper solution heat treatment and natural aging for not less than 4 days at room temperature, conform to the properties specified in Table 2 for T42 temper material. The heat-treated

samples may be tested prior to 4 days natural aging, but if they fail to conform to the T42 temper properties, the tests may be repeated after completion of 4 days natural aging without prejudice.

12.2 Alloy 7075 material produced in the O or F temper (within the size limits specified in Table 2) shall, after proper solution heat treatment and precipitation heat treatment, conform to the properties specified in Table 2 for T62 temper material.

12.3 When specified, 7075-O material (within the size limits specified in Table 2) shall, after proper solution and precipitation heat treatment, conform to the properties specified for T73 temper in Table 2 and Section 14.

12.4 *Number of Specimens*—The number of specimens from each lot of O temper material and F temper material to verify conformance with Section 12 shall be as specified in 8.2.

13. Heat Treatment and Reheat Treatment Capability

13.1 As-received material in the O or F temper and in Alloys 2014, 2024, 6061, and 6063 (within the size limitations specified in Table 2 and without the imposition of cold work) shall, after proper solution heat treatment and natural aging for not less than 4 days at room temperature, conform to the properties specified in Table 2 for T42 temper material.

13.2 As-received Alloy 7075 material in the O or F temper (within the size limitations specified in Table 2 and without the imposition of cold work) shall, after proper solution and precipitation heat treatment, conform to the properties specified in Table 2 for the T62 temper.

13.3 Material in Alloys and Tempers 2014-T4, T6; 2024-T8; and 6063-T4, T6 shall, after proper resolution heat treatment and natural aging for not less than 4 days at room temperature, conform to the properties specified in Table 2 for the T42 temper.

NOTE 5—Beginning with the 1975 revision of B 210, 6061-T4 and T6 were deleted from this paragraph because experience has shown the reheat-treated material may develop large recrystallized grains and may fail to develop the tensile properties shown in Table 2.

13.4 Alloy 7075 material in T6 and T73 tempers shall, after proper resolution heat treatment and precipitation heat treatment, conform to the properties specified in Table 2 for the T62 temper.

13.5 Material in T4 and T42 tempers shall, after proper precipitation heat treatment, conform to the properties specified in Table 2 for the T6 and T62 tempers, respectively.

14. Stress-Corrosion Resistance

14.1 For lot acceptance purposes, resistance to stress-corrosion cracking for each lot of 7075-T73 material shall be established by testing the previously selected tension-test samples to the criteria shown in Table 3.

14.2 The producer shall maintain records of all lots so tested and make them available for examination at the producer's facility.

15. Test for Leaks

15.1 When specified by the purchaser at the time of placing the order, tube shall be tested for leaks by one of the following methods at the option of the producer.

TABLE 6 Flare^A Dimensions, in.

Nominal OD	Expanded OD, min	Nominal OD	Expanded OD, min
0.125	0.224	0.750	0.937
0.188	0.302	1.000	1.187
0.250	0.359	1.250	1.500
0.312	0.421	1.500	1.721
0.375	0.484	1.750	2.106
0.500	0.656	2.000	2.356
0.625	0.781		

^A Tube with intermediate nominal diameters shall meet the same requirements as those for the next largest diameter. Tube with nominal diameters larger than 2.000 or less than 0.125 in. shall meet requirements as agreed by the purchaser and producer.



15.1.1 *Method 1*—Tubes 1½ in. or less in diameter shall be tested pneumatically at not less than 60 psi air pressure while immersed in water or other suitable liquid. Any evidence of leakage shall be cause for rejection.

15.1.2 *Method 2*—Tubes 1½ in. or less in diameter shall be tested pneumatically at not less than 90 psi air pressure with a gage that will indicate loss of pressure. There shall not be any loss of pressure during a test period of at least 15-s duration.

15.1.3 *Method 3*—Tubes shall be subjected to an eddy-current test in accordance with the procedures described in Practice E 215. Reference standards or secondary standards having equivalent eddy-current response shall serve to define acceptance-rejection limits. These reference standards are acceptable for testing any strain-hardened temper of the nonheat-treatable alloys and the F temper of heat-treatable alloys of Table 2 in tubes 1½ in. or less in diameter having a maximum wall thickness of 0.083 in.

15.1.3.1 For *straight lengths* of tube reference standards described in Appendixes X1 and X2 of Practice E 215 shall be used to standardize the equipment. Tubes 1½ in. or less in diameter and maximum wall thickness of 0.083 in. that produce eddy-current indications less than those from the 2A holes of the applicable reference standard or an equivalent secondary standard shall be acceptable. Any tube having a discontinuity that produces an eddy-current indication equal to or greater than those from the 2A holes of the applicable reference standard or an equivalent secondary standard shall be rejected.

15.1.3.2 For *coiled tube* secondary standards having an equivalent eddy-current response to a No. 70 (0.028 in.) and No. 60 (0.040 in.) drill holes shall be used to standardize the equipment. Tubes ¾ to 1 in., incl, in diameter and maximum wall thickness of 0.083 in. that produce eddy-current indications less than those from the No. 60 hole of the secondary standard shall be acceptable. Any tube that produces an indication equal to or greater than those from the No. 60 hole of the secondary standard shall be rejected. Setup procedures shall include a check to ensure that tubes containing defects giving responses equal to or greater than that from a No. 60 hole are rejected at the speed of inspection. Tube in long coils may contain up to a specified number of defects per coil when agreed upon between the producer and purchaser. In cases where a specified number of defects per coil is allowed, the need for marking such defects in a coil shall be handled as agreed upon between the producer and purchaser.

16. Special Requirements for Coiled Tubes Special Requirements for Coiled Tubes

16.1 *Expansion Test*—Coiled tube in the annealed temper only shall be capable of being expanded on a hardened ground tapered steel pin having an included angle of 60°, to the following amounts, without signs of cracks, ruptures, or other defects clearly visible to the unaided eye:

Nominal Outside Diameter, in.	Expansion of Outside Diameter, %
Up through 0.750	40
0.751 and over	30

NOTE 6—Other expansion capabilities may be required in special cases

but shall be the subject of negotiation between the producer and the purchaser.

16.2 *Inside Cleanliness Requirements and Test*—When specified by the purchaser at the time of placing the order, the inside of coiled tube in the annealed temper only shall be sufficiently clean so that, when a test sample of 50 ft or a minimum of 375 in.² internal surface is washed with 1,1,1-trichloroethane or trichloroethylene or equivalent, the residue remaining upon evaporation of the solvent shall not exceed 0.002 g/ft² of interior surface.

16.2.1 To perform the test a measured quantity of the solvent shall be pulled through the tube into a flask which is, in turn, attached to an aspirator or vacuum pump. The solvent shall then be transferred to a weighed container (crucible, evaporating dish, or beaker). The solvent in the container shall be evaporated to dryness on a low-temperature hot plate or steam bath. Overheating of the container shall be avoided to prevent charring of the residue. The container shall then be dried in an oven at 100 to 110°C for 10 min, cooled in a desiccator, and weighed. A blank determination shall be run on the measured quantity of solvent, and the gain in weight for the blank shall be subtracted from the weighings of the residue sample. The corrected weight shall then be calculated in grams of residue per internal area of tube.

16.2.2 The quantity of the solvent used may vary with the size of tube being examined. A minimum quantity of 100 mL should be used for diameters up to ½ in. and should be increased proportionately for the larger sizes. The quantity of solvent used for the blank run shall be the same as that used for the actual examination of the tube sample.

16.2.3 In performing the test, care must be exercised to clean the outside surface of the end of the sample to be immersed in the solvent. The sample must be prepared in such a manner as to prevent the inclusion in the residue of aluminum chips or dust resulting from the cutting of the sample.

17. Cladding

17.1 The aluminum-alloy cladding of Alloy Alclad 3003 and Alloy Alclad 3102 tubes shall comprise either the inside surface (only) or the outside surface (only) of the tube as specified. The purchaser shall specify whether “clad inside” or “clad outside” tubes are required.

17.2 The Alloy Alclad 3003 and Alloy Alclad 3102 tubes shall be fabricated in such a manner that the cladding thickness will be approximately 10 % of the specified composite wall thickness for “clad inside” and 7 % for “clad outside.”

17.3 When the thickness of the cladding is to be determined on finished tubes, transverse cross sections of at least three tubes from the lot shall be polished for examination with a metallurgical microscope. Using a magnification of 100×, the cladding thickness at four points, 90° apart, in each sample shall be measured and the average of the twelve measurements shall be taken as the thickness. In the case of tubes having a diameter larger than can properly be mounted for polishing and examination, the portions of the cross section polished for examination may consist of an arc about ½ in. in length.

18. Dimensional Tolerances

18.1 Variations from the specified or nominal dimensions shall not exceed the permissible variations prescribed in tables of ANSI H35.2 in accordance with Table 7.

18.2 *Sampling for Inspection*—Examinations for dimensions shall be made to ensure conformance to the tolerances specified.

19. General Quality

19.1 Unless otherwise specified, the material shall be supplied in the mill finish and shall be uniform as defined by the requirements of this specification and shall be commercially sound. Any requirement not so covered is subject to negotiation between producer and purchaser.

19.2 Each tube shall be examined to determine conformance to this specification with respect to general quality and identification marking. On approval of the purchaser, however, the producer may use a system of statistical quality control for such examinations.

20. Source Inspection

20.1 If the purchaser desires that his representative inspect or witness the inspection and testing of the material prior to shipment, such agreement shall be made by the purchaser and the producer as part of the purchase contract.

20.2 When such inspection or witness of inspection and testing is agreed upon, the producer or supplier shall afford the purchaser's representative all reasonable facilities to satisfy him that the material meets the requirements of this specification. Inspection and tests shall be conducted so there is no unnecessary interference with the producer's operations.

21. Retest and Rejection

21.1 If any material fails to conform to all the applicable requirements of this specification, it shall be cause for rejection of the inspection lot.

21.2 When there is evidence that a failed specimen was not representative of the inspection lot and when no other sampling plan is provided or approved by the purchaser through the

contract or purchase order, at least two additional specimens shall be selected to replace each test specimen that failed. All specimens so selected for retest shall meet the requirements of the specification or the lot shall be subject to rejection.

21.3 Material in which defects are discovered subsequent to inspection may be rejected.

21.4 If material is rejected by the purchaser, the producer or supplier is responsible only for replacement of the material to the purchaser. As much as possible of the rejected material shall be returned to the producer or supplier.

22. Certification

22.1 The producer or supplier shall, on request, furnish to the purchaser a certificate stating that the material has been sampled, tested, and inspected in accordance with this specification, and has met the requirements.

23. Identification Marking of Product

23.1 When specified in the contract or purchase order all tubes in straight lengths shall be marked in accordance with Practice B 666/B 666M and the marking legend shall include the word "seamless."

23.2 Alloys in the 2000 and 7000 series furnished in the T6 and T73 tempers shall also be marked with the lot number in at least one location on each piece.

23.3 The foregoing requirements are minimum; marking systems that involve added information, larger characters, and greater frequencies are acceptable under this specification.

24. Packaging and Package Marking

24.1 The material shall be packaged to provide adequate protection during normal handling and transportation and each package shall contain only one size, alloy, and temper of material unless otherwise agreed. The type of packing and gross weight of containers shall, unless otherwise agreed upon, be at the producer's or supplier's discretion, provided that they are such as to ensure acceptance by common or other carriers for safe transportation at the lowest rate to the delivery point.

24.2 Each shipping container shall be marked with the purchase order number, material size, specification number, alloy and temper, gross and net weights, and the producer's name or trademark.

24.3 When specified in the contract or purchase order, material shall be preserved, packaged, and packed in accordance with the requirements of Practices B 660. The applicable levels shall be as specified in the contract or order. Marking for shipment of such material shall be in accordance with Fed. Std. No. 123 for civil agencies and MIL-STD-129 for military agencies.

25. Keywords

25.1 aluminum alloy; aluminum-alloy drawn seamless tubes

TABLE 7 Index to Tables of Permissible Variations of ANSI H35.2

Table No.	Title
12.20	Diameter Drawn, Round Tube
12.21	Width and Depth, Drawn Square, Rectangular, Hexagonal and Octagonal Tube
12.22	Diameter-Drawn, Oval, Elliptical, and Streamline Tube
12.23	Corner Radii-Drawn Tube
12.24	Wall Thickness-Drawn Round and Other-than-Round Tube
12.25	Straightness-Drawn Tube
12.26	Twist-Drawn Tube
12.27	Length-Drawn Tube
12.28	Flatness, (Flat Surfaces) Other-than-Round Drawn Tube
12.29	Squareness of Cut Ends-Drawn Tube
12.30	Angularity-Drawn Tube
12.31	Surface Roughness-Drawn Tube
12.32	Dents-Drawn Tube



ANNEXES

(Mandatory Information)

A1. BASIS FOR INCLUSION OF PROPERTY LIMITS

A1.1 Limits are established at a level at which a statistical evaluation of the data indicates that 99 % of the population obtained from all standard material meets the limit with 95 % confidence. For the products described, mechanical property limits for the respective size ranges are based on the analysis of at least 100 data from standard production material with no

more than ten data from a given lot. All tests are performed in accordance with the appropriate ASTM test methods. For informational purposes, refer to “Statistical Aspects of Mechanical Property Assurance” in the Related Material section of the *Annual Book of ASTM Standards*, Vol 02.02.

A2. ACCEPTANCE CRITERIA FOR INCLUSION OF NEW ALUMINUM AND ALUMINUM ALLOYS IN THIS SPECIFICATION

A2.1 Prior to acceptance for inclusion in this specification, the composition of wrought or cast aluminum or aluminum alloy shall be registered in accordance with ANSI H35.1. The Aluminum Association⁷ holds the Secretariat of ANSI H35 Committee and administers the criteria and procedures for registration.

A2.2 If it is documented that the Aluminum Association could not or would not register a given composition, an alternative procedure and the criteria for acceptance shall be as follows:

A2.2.1 The designation submitted for inclusion does not utilize the same designation system as described in ANSI H35.1. A designation not in conflict with other designation systems or a trade name is acceptable.

A2.2.2 The aluminum or aluminum alloy has been offered for sale in commercial quantities within the prior twelve months to at least three identifiable users.

A2.2.3 The complete chemical composition limits are submitted.

A2.2.4 The composition is, in the judgment of the responsible subcommittee, significantly different from that of any other aluminum or aluminum alloy already in the specification.

A2.2.5 For codification purposes, an alloying element is any element intentionally added for any purpose other than grain refinement and for which minimum and maximum limits are specified. Unalloyed aluminum contains a minimum of 99.00 % aluminum.

A2.2.6 Standard limits for alloying elements and impurities are expressed to the following decimal places:

Less than 0.001 %	0.000X
0.001 to but less than 0.01 %	0.00X
0.01 to but less than 0.10 %	
Unalloyed aluminum made by a refining process	0.0XX
Alloys and unalloyed aluminum not made by a refining process	0.0X
0.10 through 0.55 %	0.XX
(It is customary to express limits of 0.30 through 0.55 % as 0.X0 or 0.X5)	
Over 0.55 %	0.X, X.X, and so forth.

(except that combined Si + Fe limits for 99.00 % minimum aluminum must be expressed as 0.XX or 1.XX)

A2.2.7 Standard limits for alloying elements and impurities are expressed in the following sequence: Silicon; Iron; Copper; Manganese; Magnesium; Chromium; Nickel; Zinc (**Note A2.1**); Titanium; Other Elements, Each; Other Elements, Total; Aluminum (**Note A2.2**).

NOTE A2.1—Additional specified elements having limits are inserted in alphabetical order of their chemical symbols between zinc and titanium, or are specified in footnotes.

NOTE A2.2—Aluminum is specified as *minimum* for unalloyed aluminum and as a *remainder* for aluminum alloys.

⁷ The Aluminum Association, 900 19th Street, NW, Washington, DC 20006.

**SUMMARY OF CHANGES**

This section identifies the principal changes to this standard that have been incorporated since the last issue.

- | | |
|--|--|
| <p>(1) Deleted Specification E 227 in Sections 2.2 and 7.4.</p> <p>(2) Deleted Sections 3.1.1 through 3.1.5 and referred the reader to Terminology B 881 for these definitions.</p> <p>(3) Table 2 was made Table 1 and vice versa to allow the chemical compositions to move to the beginning of the document.</p> <p>(4)<usb> Deleted 3303 alloy and Alclad 3303 from the new Table 1.</p> <p>(5) Changed in the new Table 2 wall thickness ranges on Alloys</p> | <p>1060–O, Alclad 3003–H113, 5050–O, 5052–O, 5086–O, 5154–O, 5154–H38, and 5456–O to be consistent with AS&D.</p> <p>(6) Added to the new Table 2 were updated 2011–T8 and 3102–O properties.</p> <p>(7) Removed from the new Table 2 were the tempers 3303 and Alclad 3303</p> <p>(8)<usb> Removed the Alloy Alclad 3303 from the text in Section 17.</p> <p>(9) Revised Table 7 to be consistent with ANSI H35.2–2001.</p> |
|--|--|

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).