



Standard Specification for Standard Nominal Diameters and Cross-Sectional Areas of AWG Sizes of Solid Round Wires Used as Electrical Conductors¹

This standard is issued under the fixed designation B 258; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification prescribes standard nominal diameters and cross-sectional areas of American Wire Gage (AWG) sizes of solid round wires, used as electrical conductors, and gives equations and rules for the calculation of standard nominal mass and lengths, resistances, and breaking strengths of such wires (Explanatory **Note 1**).

1.2 The values stated in inch-pound or SI units are to be regarded separately as standard. Each system shall be used independently of the other. Combining values of the two systems may result in nonconformance with the specification. For conductor sizes designated by AWG or kcmil sizes, the requirements in SI units have been numerically converted from the corresponding values stated or derived, in inch-pound units. For conductor sizes designated by SI units only, the requirements are stated or derived in SI units.

1.2.1 For density, resistivity and temperature, the values stated in SI units are to be regarded as standard.

2. Referenced Documents

2.1 ASTM Standards:²

- A 111** Specification for Zinc-Coated (Galvanized) “Iron” Telephone and Telegraph Line Wire
- A 326** Specification for Zinc-Coated (Galvanized) High Tensile Steel Telephone and Telegraph Line Wire³
- B 1** Specification for Hard-Drawn Copper Wire
- B 2** Specification for Medium-Hard-Drawn Copper Wire
- B 3** Specification for Soft or Annealed Copper Wire

¹ This specification is under the jurisdiction of ASTM Committee B01 on Electrical Conductors and is the direct responsibility of Subcommittee B01.02 on Methods of Test and Sampling Procedure.

Current edition approved Sept. 1, 2008. Published September 2008. Originally approved in 1951. Last previous edition approved in 2002 as B 258 – 02.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

³ Withdrawn

- B 9** Specification for Bronze Trolley Wire
- B 33** Specification for Tinned Soft or Annealed Copper Wire for Electrical Purposes
- B 47** Specification for Copper Trolley Wire
- B 105** Specification for Hard-Drawn Copper Alloy Wires for Electric Conductors
- B 189** Specification for Lead-Coated and Lead-Alloy-Coated Soft Copper Wire for Electrical Purposes
- B 193** Test Method for Resistivity of Electrical Conductor Materials
- B 227** Specification for Hard-Drawn Copper-Clad Steel Wire
- B 230/B 230M** Specification for Aluminum 1350–H19 Wire for Electrical Purposes
- B 314** Specification for Aluminum 1350 Wire for Communication Cable³
- B 396** Specification for Aluminum-Alloy 5005-H19 Wire for Electrical Purposes³
- B 398/B 398M** Specification for Aluminum-Alloy 6201-T81 Wire for Electrical Purposes
- B 415** Specification for Hard-Drawn Aluminum-Clad Steel Wire
- B 609/B 609M** Specification for Aluminum 1350 Round Wire, Annealed and Intermediate Tempers, for Electrical Purposes
- B 800** Specification for 8000 Series Aluminum Alloy Wire for Electrical Purposes—Annealed and Intermediate Tempers
- E 29** Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- F 205** Test Method for Measuring Diameter of Fine Wire by Weighing

3. Standard Reference Temperature

3.1 For the purpose of this specification, all wire dimensions and properties shall be considered as occurring at the internationally standardized reference temperature of 20°C (68°F).



4. Standard Rules for Rounding

4.1 All calculations for the standard nominal dimensions and properties of solid round wires shall be rounded in the *final* value only, in accordance with rounding method of Practice E 29.

5. Standard Nominal Diameters

5.1 Standard nominal diameters of AWG sizes of solid round wires shall be calculated in accordance with the conventional mathematical law of the American Wire Gage (see Explanatory Note 1) and in accordance with Section 4.

5.2 For wire sizes 4/0 to 44 AWG, inclusive, nominal diameters shall be expressed in no more than four significant figures but in no case closer than the nearest 0.1 mil (0.0001 in.).

5.3 For wire sizes 45 to 56 AWG, inclusive, nominal diameters shall be expressed to the nearest 0.01 mil (0.00001 in.).

5.4 The standard nominal diameters expressed in mils have been calculated in accordance with these rules and are given in Table 1 for convenient reference (Explanatory Note 2).

6. Standard Nominal Cross-Sectional Areas

6.1 Standard nominal cross-sectional areas in circular mils and square millimetres shall be calculated in accordance with the following equations and shall be rounded in accordance with Section 4 to the same number of significant figures as used in expressing the standard diameters, but in no case to less than three significant figures:

$$\text{Area, cmil} = d^2$$

$$\text{Area, mm}^2 = d^2 \times 5.067 \times 10^{-4}$$

where:

d = diameter of the wire in mils as given in Table 1.

Standard nominal cross-sectional areas in circular mils and square millimetres have been calculated in accordance with the foregoing rules and are given in Table 1 for convenient reference.

7. Rules for Calculations Involving Mass and Length

7.1 Standard nominal mass and lengths shall be calculated from the standard wire diameters specified in Table 1, in accordance with the following equations. They shall be rounded in the *final* value only, in accordance with Section 4, to the same number of significant figures as used in expressing the standard diameters, but in no case to less than three significant figures:

$$W = d^2 \times \delta \times 0.34049 \times 10^{-3}$$

$$L = (1/d^2) \times (1/\delta) \times 2.9369 \times 10^6$$

where:

W = mass, lb/1000 ft,

d = diameter of the wire in mils as given in Table 1,

δ = density of the wire material at 20°C in g/cm³ as given in Table 2, and

L = length, ft/lb.

TABLE 1 Standard Nominal Diameters and Cross-Sectional Areas of AWG Sizes of Solid Round Wires at 20°C

Size		Diameter		Cross-Sectional Area		Size		Diameter		Cross-Sectional Area	
AWG		mils	mm	cmils	mm ²	AWG		mils	mm	cmils	mm ²
4/0		460.0	11.684	211 600	107.2	29		11.3	0.287	128	0.0647
3/0		409.6	10.404	167 800	85.0	30		10.0	0.254	100	0.0507
2/0		364.8	9.26	133 100	67.4	31		8.9	0.226	79.2	0.0401
1/0		324.9	8.25	105 600	53.5	32		8.0	0.203	64.0	0.0324
1		289.3	7.35	83 690	42.4	33		7.1	0.180	50.4	0.0255
2		257.6	6.54	66 360	33.6	34		6.3	0.160	39.7	0.0201
3		229.4	5.82	52 620	26.7	35		5.6	0.142	31.4	0.0159
4		204.3	5.19	41 740	21.1	36		5.0	0.127	25.0	0.0127
5		181.9	4.62	33 090	16.8	37		4.5	0.114	20.2	0.0103
6		162.0	4.11	26 240	13.3	38		4.0	0.102	16.0	0.00811
7		144.3	3.67	20 820	10.6	39		3.5	0.0890	12.2	0.00621
8		128.5	3.26	16 510	8.37	40		3.1	0.0787	9.61	0.00487
9		114.4	2.91	13 090	6.63	41		2.8	0.0711	7.84	0.00397
10		101.9	2.59	10 380	5.26	42		2.5	0.0635	6.25	0.00317
11		90.7	2.30	8 230	4.17	43		2.2	0.0559	4.84	0.00245
12		80.8	2.05	6 530	3.31	44		2.0	0.0508	4.00	0.00203
13		72.0	1.83	5 180	2.63	45		1.76	0.0447	3.10	0.00157
14		64.1	1.63	4 110	2.08	46		1.57	0.0399	2.46	0.00125
15		57.1	1.45	3 260	1.65	47		1.40	0.0356	1.96	0.000993
16		50.8	1.29	2 580	1.31	48		1.24	0.0315	1.54	0.000779
17		45.3	1.15	2 050	1.04	49		1.11	0.0282	1.23	0.000624
18		40.3	1.02	1 620	0.823	50		0.99	0.0252	0.980	0.000497
19		35.9	0.904	1 290	0.653	51		0.88	0.0224	0.774	0.000392
20		32.0	0.813	1 020	0.519	52		0.78	0.0198	0.608	0.000308
21		28.5	0.724	812	0.412	53		0.70	0.0178	0.490	0.000248
22		25.3	0.643	640	0.324	54		0.62	0.0158	0.384	0.000195
23		22.6	0.574	511	0.259	55		0.55	0.0140	0.302	0.000153
24		20.1	0.511	404	0.205	56		0.49	0.0125	0.240	0.000122
25		17.9	0.455	320	0.162						
26		15.9	0.404	253	0.128						
27		14.2	0.361	202	0.102						
28		12.6	0.320	159	0.0804						



TABLE 2 Density and Resistivity of Electrical Conductor Materials

Material	Density, δ , at 20°C, g/cm ³	Resistivity ^A , ρ , at 20°C, $\Omega \cdot \text{lb}/\text{mile}^2$	Material	Density, δ , at 20°C, g/cm ³	Resistivity, ρ , at 20°C $\Omega \cdot \text{lb}/\text{mile}^2$
Copper (Specifications B 1, B 2, B 3, B 33, B 47 and B 189), Volume Conductivity, % IACS:			Aluminum-Clad Steel (Specification B 415)	6.59	3191
100	8.89	875.20	Copper-Clad Steel (Specification B 227):		
97.66	8.89	896.15	Grade 30 HS	8.15	2728
97.16	8.89	900.77	Grade 30 EHS	8.15	2728
96.66	8.89	905.44	Grade 40	8.15	2045
96.16	8.89	910.15	Grade 40 EHS	8.15	2045
94.16	8.89	929.52	Galvanized Steel (Telephone and Telegraph) (Specification A 111):		
93.15	8.89	939.51	Class A Coating:		
Bronze (Specification B 9):			Grade EBB (Non-Copper Bearing)	7.78	5000
Class A	8.89	2188	Grade BB (Copper Bearing)	7.78	5800
Class B	8.89	1346	Grade BB (Non-Copper Bearing)	7.78	5600
Class C	8.89	1094	Class B Coating:		
Copper Alloys (Specification B 105 ^B):			Grade EBB (Non-Copper Bearing)	7.78	4900
Grade 8.5	8.78	10 169	Grade BB (Copper Bearing)	7.78	5600
Grade 13	8.78	6649	Grade BB (Non-Copper Bearing)	7.78	5450
Grade 15	8.54	5605	Class C Coating:		
Grade 20	8.89	4376	Grade EBB (Non-Copper Bearing)	7.78	4800
Grade 30	8.89	2917	Grade BB (Copper Bearing)	7.78	5400
Grade 40	8.89	2188	Grade BB (Non-Copper Bearing)	7.78	5300
Grade 55	8.89	1591	Galvanized Steel (Telephone and Telegraph) (Specification A 326):		
Grade 65	8.89	1346	Class A Coating:		
Grade 74	8.89	1183	Grade 85	7.83	5800
Grade 80	8.89	1094	Class B Coating:		
Grade 85	8.89	1030	Grade 135	7.83	6500
Aluminum, 1350 (Specifications B 230/B 230M, B 314, and B 609/B 609M), Volume Conductivity, % IACS:			Grade 85	7.80	5600
61.8	2.705	430.91	Grade 135	7.80	6300
61.2	2.705	435.13	Class C Coating:		
61.0	2.705	436.56	Grade 85	7.77	5400
Aluminum Alloys (Specifications B 396 and B 398/B 398M)			Grade 135	7.77	6100
Alloy 5005–H19	2.70	496.84			
Alloy 6201–T81	2.69	504.43			
Aluminum Alloy 8000 Series (Specification B 800) Volume Conductivity, % IACS:					
61.0	2.71	437.36			

^A To convert from $\Omega \cdot \text{lb}/\text{mile}^2$ to $\Omega \cdot \text{g}/\text{m}^2$ multiply by 5710.0. See Table 1 in Test Method B 193.

^B Various compositions are permitted for some of the grades in Specification B 105 and the density value may not apply to all materials supplied to this specification. In case of doubt, the density value should be determined or obtained from the manufacturer.

8. Rules for Calculations Involving Resistivity

8.1 Standard nominal resistances and other values derived from the resistivity units shall be calculated from the standard wire diameters specified in Table 1 in accordance with the following equations. All values so derived shall be rounded in the *final* value only, in accordance with Section 4, to the same number of significant figures as used in expressing the standard diameters, but in no case to less than three significant figures:

$$D-c \text{ resistance at } 20^\circ\text{C}, \Omega/1000 \text{ ft} = [\rho/(d^2 \times \delta)] \times 105.35$$

$$D-c \text{ resistance at } 20^\circ\text{C}, \Omega/\text{lb} = [\rho/(\delta^2 \times d^4)] \times 0.30940 \times 10^{-6}$$

$$\text{Length at } 20^\circ\text{C}, \text{ft}/\Omega = [(d^2 \times \delta)/\rho] \times 9.4924$$

$$\text{Mass at } 20^\circ\text{C}, \text{lb}/\Omega = [(\delta^2 \times d^4)/\rho] \times 3.2321 \times 10^{-6}$$

where:

d = diameter of the wire in mils as given in Table 1,

ρ = resistivity of the wire material at 20°C in $\Omega \cdot \text{lb}/\text{mile}^2$ as given in Table 2 (Explanatory Note 3), and
 δ = density of the wire material at 20°C in g/cm³ as given in Table 2.

9. Rules for Calculating Rated Strength

9.1 Standard rated strengths shall be calculated from the standard wire diameters specified in Table 1 in accordance with the following equation and shall be rounded in the *final* value only, in accordance with Section 4, to the same number of significant figures as used in expressing the standard diameters, but in no case to less than three significant figures:

$$\text{Rated strength, lb} = d^2 \times T \times 0.7854 \times 10^{-6}$$

where:

d = diameter of the wire in mils as given in Table 1, and



T = tensile strength, psi, applicable to the wire material, temper, and size, for which reference should be made to the specifications which cover the material.

10. Tolerances

10.1 The standard dimensions given in Table 1 and the calculated values for mass, resistances, and rated strengths obtained by the use of the formulas included in this specifica-

tion are all *nominal* values. This specification is not concerned with quantitative values of tolerances per se, but it is contemplated that the standard nominal wire dimensions specified in Table 1, and the properties derived therefrom, shall be made subject to tolerances as indicated in either the individual specifications applicable to the wires of various materials and tempers or as may be mutually agreed by the manufacturer and the purchaser.

EXPLANATORY NOTES

NOTE 1—Except for certain classes of wire products, the American Wire Gage (formerly known as the Brown & Sharpe Gage) has been almost universally employed in the United States for many years for the designation of wire sizes. This gage is based upon fixed diameters for two wire sizes (4/0 and 36 AWG, respectively), and the simple mathematical law that the thirty-eight intermediate gage designations vary in size in geometric progress. The extent of the American Wire Gage is not, however, limited to the forty gage numbers from 4/0 to 36 AWG, inclusive, both larger and smaller sizes being determined by extrapolation in accordance with the geometric progression mentioned. Like many other wire gages, the American Wire Gage is an inverse gage, that is, a higher size number denotes a wire of smaller size.

The specified diameters for sizes 4/0 AWG and 36 AWG are 460 mils and 5 mils, respectively (1 mil is equal to 0.001 in.). Designating the ratio between ascending adjacent wire sizes by r , and the ratio between descending adjacent wire sizes by $1/r$, the law of the American Wire Gage is indicated explicitly by an ascending and descending series, expressed in tabular form as shown in Table 3.

It is implicit in these series that the diameters of the various AWG wire sizes may be calculated either by ascending from $d = 5$ for size 36 AWG, or descending from $d = 460$ for 4/0 AWG, for intermediate sizes, as well as descending from $d = 5$ for size 36 AWG, for sizes 37 AWG and smaller. It is further implicit in these series that the diameter of any AWG size of wire may be derived directly from any other AWG size whose diameter is known by multiplying the known diameter by r^n or $1/r^n$, as the case may be, where n is the number of steps between the two gage numbers. For example, size 18 AWG is eighteen gage numbers apart from 36 AWG, and twenty-one gage numbers apart from size 4/0 AWG. The diameter of size 18 AWG is, then,

$$d_{18} = d_{36} \times r^{18} = 5 \times 1.1229322^{18} = 5 \times 8.060653 = 40.30 \text{ mils}$$

or:

$$d_{18} = d_{4/0} / r^{21} = 460 \times 0.89052571^{21} \\ = 460 \times 0.0876144 = 40.30 \text{ mils}$$

Similarly, size 45 AWG is nine gage numbers removed from size 36 AWG, from which the diameter of size 45 AWG is:

$$d_{45} = d_{36} / r^9 = 5 \times 0.89052571^9 = 5 \times 0.352223 = 1.761 \text{ mils}$$

Since areas and mass vary directly as the square of wire diameter, it can be shown similarly that the mathematical law of the American Wire Gage holds rigorously for these quantities when the ratio of r^2 (1.2609767) or $1/r^2$ (0.79303605), as the case may be (depending upon the quantity involved and whether the calculation is an ascending or descending one), is assigned to the properties of adjacent gage sizes. Thus, for size 18 AWG, the circular-mil area is given by the expression:

$$A_{18} = A_{36} r^{36} = 25 \times 1.2609767^{18} = 25 \times 64.9721 = 1624 \text{ cmils}$$

or:

$$A_{18} = A_{4/0} / r^{42} \\ = 211,600 \times 0.79303605^{21} \\ = 211,600 \times 0.00767629 \\ = 1624 \text{ cmils}$$

Similar calculations can be made for mass where these quantities are known for size 36 AWG or size 4/0 AWG.

NOTE 2—AWG numbers appearing in Columns 1 and 5 of Table 1 are given only to facilitate conversion from AWG numbers to the wire size in mils. It is emphasized that this is not intended to be an endorsement of the use of AWG numbers to designate wire sizes. Wire diameters should be specified in mils as shown in Table 1, Columns 2 and 6.

Micrometer calipers calibrated to measure 0.1 mil (0.0001 in.) should be considered satisfactory for measuring the diameters of 4/0 to 44 AWG (0.4600 to 0.0020 in.) inclusive.

For greater accuracy in obtaining the mean diameter of ultrafine wire size 45 to 56 AWG (0.00176 to 0.00049 in.) inclusive, Test Method F 205 should be considered satisfactory. The density values in Table 2 shall be used in determining constants C and K .

NOTE 3—The value of 875.20 Ω -lb/mile² at 20°C (68°F) is the mass resistivity equivalent to the International Annealed Copper Standard (IACS) for 100 % conductivity. This term means that a wire one mile in length, with a mass of 1 lb, would have a resistance of 875.20 Ω . This is equivalent to a resistivity value of 0.15328 Ω -g/m² which signifies the resistance of a wire 1 m in length with a mass of 1 g. It is also equivalent for example to a volume resistivity of 1.7241 $\mu\Omega$ /cm of length of a bar 1

TABLE 3 American Wire Gage Series

<i>Ascending Wire Sizes:</i>										
Step No.	1	2	3	4	5	...	37	38	39	40
AWG No.	36	35	34	33	32	...	1/0	2/0	3/0	4/0
Wire diameter, mils	5	5r	5r ²	5r ³	5r ⁴	...	5r ³⁶	5r ³⁷	5r ³⁸	5r ³⁹ = 460
<i>Descending Wire Sizes:</i>										
Step No.	1	2	3	4	5	...	37	38	39	40
AWG No.	4/0	3/0	2/0	1/0	1	...	33	34	35	36
Wire diameter, mils	460	460/r	460/r ²	460/r ³	460/r ⁴	...	460/r ³⁶	460/r ³⁷	460/r ³⁸	460/r ³⁹ = 5

Since the last wire diameter term of both the ascending and descending series indicates that $r^{39} = 460/5 = 92$, the value for r is $92^{1/39} = 1.1229322$, and the value of $1/r$ is 0.89052571.



cm² in cross section. A complete discussion of this subject is contained in *NBS Handbook 100* of the National Institute of Standards and Technology.⁴ Conversion of the various units of mass resistivity, volume resistiv-

ity, and conductivity may be facilitated by employing the formulas and factors shown in Table 1 of Test Method **B 193**. The factors given therein are applicable to all metallic electrical conductor material. **Table 2** lists values of δ for the common electrical conductor materials.

⁴ *NBS Handbook 100*, Nat. Institute of Standards and Technology, is sold by the National Technical Information Service, 5285 Port Royal Road, Springfield, VA 22161.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).