



Standard Specification for Ni-Fe-Cr-Mo-Cu-N Low-Carbon Alloys (UNS N08925, UNS N08031, UNS N08354, and UNS N08926), and Cr-Ni-Fe-N Low-Carbon Alloy (UNS R20033) Bar and Wire, and Ni-Cr-Fe-Mo-N Alloy (UNS N08936) Wire¹

This standard is issued under the fixed designation B 649; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers nickel-iron-chromium-molybdenum-copper-nitrogen alloys (UNS N08925, UNS N08031, UNS N08354, and UNS N08926), and chromium-nickel-iron-nitrogen low-carbon alloy (UNS R20033) bar and wire, and nickel-chromium-iron-molybdenum-nitrogen alloy (UNS N08936) wire.

1.2 ASTM International has adopted definitions whereby some grades, such as UNS N08904, previously in this specification were recognized as stainless steels, because those grades have iron as the largest element by mass percent. Such grades are under the oversight of ASTM Committee A01 and its subcommittees. The products of N08904 previously covered in this specification are now covered by Specifications **A 479/A 479M** and **A 484/A 484M**.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved June 1, 2006. Published June 2006. Originally approved in 1981. Last previous edition approved in 2005 as B 649 - 05.

* New designation established in accordance with Practice **E 527** and SAE J1086, Practice for Numbering Metals and Alloys (UNS).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

A 479/A 479M Specification for Stainless Steel Bars and Shapes for Use in Boilers and Other Pressure Vessels

A 484/A 484M Specification for General Requirements for Stainless Steel Bars, Billets, and Forgings

B 880 Specification for General Requirements for Chemical Check Analysis Limits for Nickel, Nickel Alloys and Cobalt Alloys

E 8 Test Methods for Tension Testing of Metallic Materials

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E 55 Practice for Sampling Wrought Nonferrous Metals and Alloys for Determination of Chemical Composition

E 527 Practice for Numbering Metals and Alloys (UNS)

E 1473 Test Methods for Chemical Analysis of Nickel, Cobalt, and High-Temperature Alloys

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *bars, n*—hot-finished rounds, squares, octagons, and hexagons: ¼ in. (6.35 mm) and over in diameter or size. Hot-finished flats: ¼ in. to 10 in. (254 mm) inclusive in width, ⅛ in. (3.18 mm) and over in thickness. Cold-finished rounds, squares, octagons, hexagons, and shapes: over ½ in. (12.70 mm) in diameter or size. Cold-finished flats: ⅜ in. (9.52 mm) and over in width (see 3.1.1.1) and ⅛ in. and over in thickness (see 3.1.1.2).

3.1.1.1 *Discussion*—Widths less than ⅜ in. (9.52 mm) and thicknesses less than ⅜ in. (4.76 mm) are described generally as flat wire.

3.1.1.2 *Discussion*—Thickness ⅛ in. to under ⅜ in. (3.18 mm to under 4.76 mm) can be cold-rolled strip as well as bar.

3.1.2 *wire, n*—cold-finished only: round, square, octagon, hexagon, and shape wire, ½ in. (12.70 mm) and under in diameter or size. Cold-finished only: flat wire, ⅜ in. to under ⅜ in. (4.76 mm to under 9.52 mm) in width, 0.010 to under ⅜ in. (0.25 to under 4.76 mm) in thickness.

*A Summary of Changes section appears at the end of this standard.

4. Ordering Information

4.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered to this specification. Examples of such requirements include, but are not limited to, the following:

- 4.1.1 Quantity (weight or number of pieces),
- 4.1.2 Alloy name or UNS number,
- 4.1.3 Form (bar or wire),
- 4.1.4 Dimensions,
- 4.1.5 Finish (Section 9),
- 4.1.6 ASTM designation and year of issue,
- 4.1.7 Exceptions to the specification or special requirements, and
- 4.1.8 Certification (Section 16). State if certification is required.

5. Materials and Manufacture

5.1 *Heat Treatment*—With the exception of UNS N08936, the material shall be supplied in the solution-treated condition except as noted in 5.2. UNS N08936 shall be supplied in the cold drawn condition.

NOTE 1—The recommended heat treatment shall consist of heating to a temperature of 2010 to 2100°F (1100 to 1150°C) followed by water quenching for UNS N08925, UNS N08031, 1975 to 2150°F (1080 to 1180°C) followed by water quenching or fast air cool for UNS N08354, and UNS N08926, or 2010 to 2150°F (1100 to 1180°C) followed by water quenching or fast air cool for UNS R20033.

5.2 The heat treatment shall be waived for forging quality material.

6. Chemical Composition

6.1 The material sampled in accordance with 10.2 shall conform to the requirements as to chemical composition prescribed in Table 1.

6.2 *Product Analysis*—Product analysis may be made by the purchaser to verify the identity of the finished material representing each heat or lot. Such analysis may be made by any of the commonly accepted methods that will positively identify the material.

6.2.1 If a product analysis is made, the material shall conform to the product check analysis variation per Specification B 880.

7. Mechanical and Other Requirements

7.1 *Tensile Requirements*—The material shall conform to the requirements as to the mechanical property prescribed in Table 2.

8. Dimensions, Weights, and Permissible Variations

8.1 *Bar*—The material referred to as bar shall conform to the variations in dimensions prescribed in Tables 3-11 inclusive, as applicable.

8.2 *Wire*—The material referred to as wire shall conform to the permissible variations in dimensions prescribed in Tables 12-16 inclusive, as applicable.

9. Workmanship, Finish, and Appearance

9.1 The material shall be uniform in quality and condition, smooth, commercially straight or flat, and free of injurious defects.

9.2 Bars in the hot-finished condition may be furnished with one of the following finishes:

- 9.2.1 Scale not removed,
- 9.2.2 Pickled or descaled, or
- 9.2.3 Turned (rounds only).

9.3 Bars in the cold-finished condition may be furnished with one of the following finishes:

- 9.3.1 Cold-drawn,
- 9.3.2 Centerless ground (rounds only), or
- 9.3.3 Polished (rounds only).

9.4 Wire in the cold-finished condition may be furnished with one of the following finishes:

- 9.4.1 Cold-drawn,
- 9.4.2 Centerless ground (rounds only),
- 9.4.3 Polished (rounds only), or
- 9.4.4 Pickled.

10. Sampling

10.1 *Lots for Chemical Analysis and Mechanical Testing*:

- 10.1.1 A lot for chemical analysis shall consist of one heat.
- 10.1.2 A lot for testing and inspection purposes shall consist of material from one heat of the same condition (temper), finish, and cross section, and in no case more than 30 000 lb (13 600 kg) in mass.

NOTE 2—Where material cannot be identified by heat, a lot shall consist of not more than 500 lb (227 kg) of material in the same thickness and

TABLE 1 Chemical Requirements

Element	UNS N08936	UNS N08925	UNS N08031	UNS N08354	UNS N08926	UNS R20033
Carbon, max	0.020	0.020	0.015	0.030	0.020	0.015
Manganese, max	4.00–6.00	1.00	2.0	1.00	2.00	2.0
Phosphorus, max	0.025	0.045	0.020	0.030	0.03	0.02
Sulfur, max	0.010	0.030	0.010	0.010	0.01	0.01
Silicon, max	0.50	0.50	0.3	1.00	0.5	0.50
Nickel	33.00–35.00	24.00–26.00	30.0–32.0	34.0–36.0	24.00–26.00	30.0–33.0
Chromium	26.00–28.00	19.00–21.00	26.0–28.0	22.0–24.0	19.00–21.00	31.0–35.0
Molybdenum	5.00–6.00	6.0–7.0	6.0–7.0	7.0–8.0	6.0–7.0	0.50–2.0
Copper	0.50	0.8–1.5	1.0–1.4	...	0.5–1.5	0.30–1.20
Nitrogen	0.30–0.50	0.1–0.2	0.15–0.25	0.17–0.24	0.15–0.25	0.35–0.60
Iron	balance	balance	balance	balance	balance	balance

**TABLE 2 Mechanical Property Requirements^A**

Alloy	Cold Finished and Hot Finished Annealed, ^B All Sizes Except Where Noted			Forging Quality, All Sizes
	Tensile Strength, min, psi (MPa) ^C	Yield Strength min, psi (MPa) ^C	Elongation in 2 in. (50.8 mm), min, %	
UNS N08925	87 000 (600)	43 000 (300)	40	A
UNS N08031	94 000 (650)	40 000 (270)	40	A
UNS N08926	94 000 (650)	43 000 (295)	35	A
UNS N08354	93 000 (640)	43 000 (295)	40	A
UNS R20033	109 000 (750)	55 000 (380)	40	A
UNS N08936				
Up to 0.063 in. (1.60 mm) dia., incl.	280 000 (1931)	240 000 (1655)	...	...
Over 0.063 in. (1.60 mm) dia.	250 000 (1724)	220 000 (1517)	...	...

^A No tensile properties are required on forging quality.^B UNS N08936 shall be supplied in the cold drawn condition only.^C For cold finished and annealed wire only, tensile strength 90 000 to 120 000 psi (620 to 830 MPa).

condition, except that for pieces weighing over 500 lb, only one specimen shall be taken.

10.2 Sampling for Chemical Analysis:

10.2.1 A representative sample shall be taken from each heat during pouring or subsequent processing.

10.2.2 If the manufacturer determines that the material meets the chemical requirements during pouring or subsequent processing, he shall not be required to sample and analyze the finished product.

10.2.3 Product analysis, if performed, shall be wholly the responsibility of the purchaser.

10.3 Sampling for Mechanical Tests:

10.3.1 A sample of the material to provide test specimens for mechanical tests shall be taken from such a location in each lot as to be representative of that lot.

10.3.2 When samples are to be taken after delivery, the purchaser of material ordered to cut lengths may request on the purchase order additional material of adequate size to provide sample coupons for inspection purposes.

11. Number of Tests

11.1 One chemical analysis shall be made on each lot in accordance with 10.1.1.

11.2 One tension test shall be made on each lot in accordance with 10.1.2.

11.2.1 If any specimens selected to represent any heat fail to meet any of the test requirements, the material represented by such specimens may be reheat-treated and resubmitted for test.

12. Specimen Preparation

12.1 Tension test specimens shall be taken from material after final heat treatment and shall be selected in the longitudinal direction. The tension test specimens shall conform to the appropriate sections of Test Methods E 8.

13. Test Methods

13.1 The chemical composition and mechanical properties of the material as enumerated in this specification shall, in case of disagreement, be determined in accordance with the following methods:

Test	ASTM Designations
Chemical analysis	E 1473 ^A
Tension	E 8
Rounding procedure	E 29
Method of sampling	E 55

^A Iron shall be determined arithmetically by difference.

13.2 For purposes of determining compliance with the limits in this specification, an observed value or a calculated value shall be rounded as indicated in accordance with the rounding method of Practice E 29.

Requirements	Rounded Unit for Observed or Calculated Value
Chemical composition (when expressed in decimals)	nearest unit in the last right-hand place of figures of the specified limit
Tensile strength and yield strength	nearest 1000 psi (7 MPa)
Elongation	nearest 1 %

14. Inspection

14.1 Inspection of the material by the purchaser shall be made as agreed upon between the purchaser and the seller as part of and set forth in the purchase contract.

15. Rejection and Rehearing

15.1 Material that fails to conform to the requirements of this specification may be rejected. Rejection should be reported to the producer or supplier promptly and in writing. In case of dissatisfaction with the results of the test, the producer or supplier may make claim for a rehearing.

16. Certification

16.1 If required by the purchaser in the contract or purchase order, a manufacturer's certification that the material was manufactured and tested in accordance with this specification shall be furnished at the time of shipment.

16.2 If required by the purchaser in the contract or purchase order, a copy of the test results shall be furnished at the time of shipment.

17. Packaging and Package Marking

17.1 *Marking*—Each bundle or box shall be tagged properly with metal tags showing heat number, grade, condition, specification number, and size to assure proper identification.

17.1.1 Large diameter bars may be line marked showing heat number, grade, condition, specification number, and size at the manufacturer's discretion.

17.2 *Packaging*—Bars or wire shall be bundled or boxed in such a manner as to assure safe delivery to their destination when properly transported by any common carrier.

18. Keywords

18.1 UNS N08031; UNS N08925; UNS N08926; UNS N08354; UNS N08936; UNS R20033; bar; wire



TABLE 3 Permissible Variations in Size of Hot-Finished Round and Square Bars

	Permissible Variations from Specified Size, in. (mm)		Out-of-Round ^A or Out-of-Square, ^B in. (mm)
	Over	Under	
$\frac{1}{4}$ (6.35) to $\frac{5}{16}$ (7.94), incl. ^{C,D}	<i>E</i>	<i>E</i>	<i>E</i>
Over $\frac{5}{16}$ (7.94) to $\frac{7}{16}$ (11.11), incl. ^{C,D}	0.006 (0.15)	0.006 (0.15)	0.009 (0.23)
Over $\frac{7}{16}$ (11.11) to $\frac{5}{8}$ (15.88), incl. ^{C,D}	0.007 (0.18)	0.007 (0.18)	0.010 (0.25)
Over $\frac{5}{8}$ (15.88) to $\frac{7}{8}$ (22.22), incl	0.008 (0.20)	0.008 (0.20)	0.012 (0.30)
Over $\frac{7}{8}$ (22.22) to 1 (25.40), incl	0.009 (0.23)	0.009 (0.23)	0.013 (0.33)
Over 1 (25.40) to $1\frac{1}{8}$ (28.58), incl.	0.010 (0.25)	0.010 (0.25)	0.015 (0.38)
Over $1\frac{1}{8}$ (28.58) to $1\frac{1}{4}$ (31.75), incl	0.011 (0.28)	0.011 (0.28)	0.016 (0.41)
Over $1\frac{1}{4}$ (31.75) to $1\frac{3}{8}$ (34.92), incl	0.012 (0.30)	0.012 (0.30)	0.018 (0.46)
Over $1\frac{3}{8}$ (34.92) to $1\frac{1}{2}$ (38.10), incl	0.014 (0.36)	0.014 (0.36)	0.021 (0.53)
Over $1\frac{1}{2}$ (38.10) to 2 (50.80), incl	$\frac{1}{64}$ (0.40)	$\frac{1}{64}$ (0.40)	0.023 (0.58)
Over 2 (50.80) to $2\frac{1}{2}$ (63.50), incl	$\frac{1}{32}$ (0.79)	0	0.023 (0.58)
Over $2\frac{1}{2}$ (63.50) to $3\frac{1}{2}$ (88.90), incl	$\frac{3}{64}$ (1.19)	0	0.035 (0.89)
Over $3\frac{1}{2}$ (88.90) to $4\frac{1}{2}$ (114.30), incl	$\frac{1}{16}$ (1.59)	0	0.046 (1.17)
Over $4\frac{1}{2}$ (114.30) to $5\frac{1}{2}$ (139.70), incl	$\frac{5}{64}$ (1.98)	0	0.058 (1.47)
Over $5\frac{1}{2}$ (139.70) to $6\frac{1}{2}$ (165.10), incl	$\frac{1}{8}$ (3.18)	0	0.070 (1.78)
Over $6\frac{1}{2}$ (165.10) to 8 (203.20), incl	$\frac{5}{32}$ (3.97)	0	0.085 (2.18)

^A Out-of-round is the difference between the maximum and minimum diameters of the bar, measured at the same cross section.

^B Out-of-square section is the difference in the two dimensions at the same cross section of a square bar, each dimension being the distance between opposite faces.

^C Size tolerances have not been evolved for rounds in the size range from $\frac{1}{4}$ to $\frac{5}{16}$ in. (6.35 to 7.94 mm), incl. Size tolerances have not been evolved for round sections in the size range from $\frac{1}{4}$ (6.35 mm) to approximately $\frac{5}{8}$ in. (15.88 mm) in diameter which are produced on rod mills in coils.

^D Squares in this size are not produced as hot-rolled products.

^E Variations in size of coiled product made on rod mills are greater than size tolerances for product made on bar mills.

TABLE 4 Permissible Variations in Size of Hot-Finished Hexagonal and Octagonal Bars

Specified Sizes Measured Between Opposite Sides, in. (mm)	Permissible Variations from Specified Size, in. (mm)		Maximum Difference in 3 Measurements for Hexagons only, in. (mm)
	Over	Under	
$\frac{1}{4}$ (6.35) to $\frac{1}{2}$ (12.70), incl	0.007 (0.18)	0.007 (0.18)	0.011 (0.28)
Over $\frac{1}{2}$ (12.70) to 1 (25.40), incl	0.010 (0.25)	0.010 (0.25)	0.015 (0.38)
Over 1 (25.40) to $1\frac{1}{2}$ (38.10), incl	0.021 (0.53)	0.021 (0.53)	0.025 (0.64)
Over $1\frac{1}{2}$ (38.10) to 2 (50.80), incl	$\frac{1}{32}$ (0.79)	$\frac{1}{32}$ (0.79)	$\frac{1}{32}$ (0.79)
Over 2 (50.80) to $2\frac{1}{2}$ (63.50), incl.	$\frac{3}{64}$ (1.19)	$\frac{3}{64}$ (1.19)	$\frac{3}{64}$ (1.19)
Over $2\frac{1}{2}$ (63.50) to $3\frac{1}{2}$ (88.90), incl	$\frac{1}{16}$ (1.59)	$\frac{1}{16}$ (1.59)	$\frac{1}{16}$ (1.59)



TABLE 5 Permissible Variations in Thickness and Width for Hot-Finished Flat Bars

Specified Width, in. (mm)	Permissible Variations in Thickness for Thicknesses Given, in. (mm)					
	$\frac{1}{8}$ (3.18) to $\frac{1}{2}$ (12.70), incl		Over $\frac{1}{2}$ (12.70) to 1 (25.40), incl		Over 1 (25.40) to 2 (50.80), incl	
	Over	Under	Over	Under	Over	Under
To 1 (25.40), incl	0.008 (0.20)	0.008 (0.20)	0.010 (0.25)	0.010 (0.25)	...	...
Over 1 (25.40) to 2 (50.80), incl	0.012 (0.30)	0.012 (0.30)	0.015 (0.38)	0.015 (0.38)	0.031 (0.79)	0.031 (0.79)
Over 2 (50.80) to 4 (101.60), incl	0.015 (0.38)	0.015 (0.38)	0.020 (0.51)	0.020 (0.51)	0.031 (0.79)	0.031 (0.79)
Over 4 (101.60) to 6 (152.40), incl	0.015 (0.38)	0.015 (0.38)	0.020 (0.51)	0.020 (0.51)	0.031 (0.79)	0.031 (0.79)
Over 6 (152.40) to 8 (203.20), incl	0.016 (0.41)	0.016 (0.41)	0.025 (0.64)	0.025 (0.64)	0.031 (0.79)	0.031 (0.79)
Over 8 (203.20) to 10 (254.00), incl	0.021 (0.53)	0.021 (0.53)	0.031 (0.79)	0.031 (0.79)	0.031 (0.79)	0.031 (0.79)
Specified Width, in. (mm)	Over 2 (50.80) to 4 (101.60), incl		Over 4 (101.60) to 6 (152.40), incl		Over 6 (152.40) to 8 (203.20), incl	
	Over	Under	Over	Under	Over	Under
	Over	Under	Over	Under	Over	Under
To 1 (25.40), incl	...	...	...	...	...	...
Over 1 (25.40) to 2 (50.80), incl	...	...	...	...	...	...
Over 2 (50.80) to 4 (101.60), incl	0.062 (1.57)	0.031 (0.79)	...	...	...	...
Over 4 (101.60) to 6 (152.40), incl	0.062 (1.57)	0.031 (0.79)	0.093 (2.36)	0.062 (1.57)	...	...
Over 6 (152.40) to 8 (203.20), incl	0.062 (1.57)	0.031 (0.79)	0.093 (2.36)	0.062 (1.57)	0.125 (3.18)	0.156 (3.96)
Over 8 (203.20) to 10 (254.00), incl	0.062 (1.57)	0.031 (0.79)	0.093 (2.36)	0.062 (1.57)	0.125 (3.18)	0.156 (3.96)
Specified Width, in. (mm)	Permissible Variations in Width, in. (mm)					
	Over			Under		
	Over			Under		
To 1 (25.40), incl	0.015 (0.38)			0.015 (0.38)		
Over 1 (25.40) to 2 (50.80), incl	0.031 (0.79)			0.031 (0.79)		
Over 2 (50.80) to 4 (101.60), incl	0.062 (1.57)			0.031 (0.79)		
Over 4 (101.60) to 6 (152.40), incl	0.093 (2.36)			0.062 (1.57)		
Over 6 (152.40) to 8 (203.20), incl	0.125 (3.18)			0.156 (3.96)		
Over 8 (203.20) to 10 (254.00), incl	0.156 (3.96)			0.187 (4.75)		

TABLE 6 Permissible Variations in Size of Cold-Finished Round Bars

Specified Size, in. (mm)	Permissible Variations from Specified Size, in. (mm) ^{A,B}	
	Over	Under
Over $\frac{1}{2}$ (12.70) to 1 (25.40), excl	0.002 (0.05)	0.002 (0.05)
1 (25.40) to $1\frac{1}{2}$ (38.10), excl	0.0025 (0.06)	0.0025 (0.06)
$1\frac{1}{2}$ (38.10) to 4 (101.60), incl ^C	0.003 (0.08)	0.003 (0.08)

^A Unless otherwise specified, size tolerances are over and under as shown in the above table. When required, however, they may be specified all over and nothing under, or all under and nothing over, or any combination of over and under, if the total spread in size tolerance for a specified size is not less than the total spread shown in the table.

^B When it is necessary to heat treat or heat treat and pickle after cold finishing, size tolerances are double those shown in the table.

^C Cold-finished bars over 4 in. (101.60 mm) in diameter are produced; size tolerances for such bars have not been evolved.

TABLE 7 Permissible Variations in Size of Cold-Finished Hexagonal, Octagonal, and Square Bars

Specified Size, in. (mm)	Permissible Variations from Specified Size, in. (mm) ^A	
	Over	Under
Over $\frac{1}{2}$ (12.70) to 1 (25.40), incl	0	0.004 (0.10)
Over 1 (25.40) to 2 (50.80), incl	0	0.006 (0.15)
Over 2 (50.80) to 3 (76.20), incl	0	0.008 (0.20)
Over 3 (76.20)	0	0.010 (0.25)

^A When it is necessary to heat treat or heat treat and pickle after cold finishing, size tolerances are double those shown in the table.

TABLE 8 Permissible Variations in Width and Thickness of Cold-Finished Flat Bars

Width, in. (mm)	Permissible Variations in Width, over and under, in. (mm) ^A	
	For Thicknesses $\frac{1}{4}$ (6.35) and Under	For Thicknesses Over $\frac{1}{4}$ (6.35)
$\frac{3}{8}$ (9.52) to 1 (25.40), incl	0.004 (0.10)	0.002 (0.05)
Over 1 (25.40) to 2 (50.80), incl	0.006 (0.15)	0.003 (0.08)
Over 2 (50.80) to 3 (76.20), incl	0.008 (0.20)	0.004 (0.10)
Over 3 (76.20) to $4\frac{1}{2}$ (114.30), incl	0.010 (0.25)	0.005 (0.13)
Thickness, in. (mm)	Permissible Variations in Thickness, over and under, in. (mm) ^A	
	Permissible Variations in Thickness, over and under, in. (mm) ^A	
$\frac{1}{8}$ (3.18) to 1 (25.40), incl	0.002 (0.05)	
Over 1 (25.40) to 2 (50.80), incl	0.003 (0.08)	
Over 2 (50.80) to 3 (76.20), incl	0.004 (0.10)	
Over 3 (76.20) to $4\frac{1}{2}$ (114.30), incl ^B	0.005 (0.13)	

^A When it is necessary to heat treat and pickle after cold finishing, size tolerances are double those shown in the table.

^B Cold-finished flat bars over $4\frac{1}{2}$ in. (114.30 mm) wide or thick are produced; width and thickness tolerances for such bars have not been evolved.

**TABLE 9 Permissible Variations in Length of Hot-Finished or Cold-Finished Bars**

NOTE 1—The order should specify random lengths or specific lengths. When random lengths are ordered, the length tolerance is not less than 24 in. (609.60 mm). When specific lengths are ordered, Table 9 or Table 10 shall apply.

Specified Size of Rounds, Squares, Hexagons, and Octagons, and Widths of Flats, ^A in. (mm)	Permissible Variations in Length, in. (mm)			
	For Lengths Up to 12 ft (3658 mm), incl		For Lengths Over 12 ft (3658 mm) to 25 ft (7620 mm), incl	
	Over	Under	Over	Under
To 2 (50.80), incl	½ (12.70)	0	¾ (19.05)	0
Over 2 (50.80) to 4 (101.60), incl	¾ (19.05)	0	1 (25.40)	0
Over 4 (101.60) to 6 (152.40), incl	1 (25.40)	0	1¼ (31.75)	0
Over 6 (152.40) to 9 (228.60), incl	1¼ (31.75)	0	1½ (38.10)	0
Over 9 (228.60) to 12 (304.80), incl	1½ (38.10)	0	2 (50.80)	0

^A The maximum width of bar flats is 10 in. (254.00 mm).

TABLE 10 Permissible Variations in Length of Hot-Finished or Cold-Finished Bars Machine Cut After Machine Straightening

NOTE 1—The order should specify random lengths or specific lengths. When random lengths are ordered, the length tolerance is not less than 24 in. (609.60 mm). When specific lengths are ordered, Table 9 or Table 10 shall apply.

Specified Size of Rounds, Squares, Hexagons, and Octagons, and Widths of Flats, ^A in. (mm)	For Lengths Up to 12 ft (3658 mm), incl		For Lengths Over 12 ft (3658 mm) to 25 ft (7620 mm), incl	
	Over	Under	Over	Under
	Over	Under	Over	Under
To 3 (76.20), incl	⅛ (3.18)	0	⅜ (9.53)	0
Over 3 (76.20) to 6 (152.40), incl	⅜ (9.53)	0	¼ (6.35)	0
Over 6 (152.40) to 9 (228.60), incl	¼ (6.35)	0	⅝ (7.94)	0
Over 9 (228.60) to 12 (304.80), incl	½ (12.70)	0	½ (12.70)	0

^A The maximum width of bar flats is 10 in. (254.00 mm).

TABLE 11 Permissible Variations in Straightness of Machine Straightened Hot-Finished or Cold-Finished Bars

Measurement is taken on the concave side of the bar with a straightedge. Unless otherwise specified, hot-finished or cold-finished bars for machining purposes are furnished machine straightened to the following tolerances:

Hot finished:
 ⅛ in. (3.18 mm) in any 5 ft (1524 mm), but may not exceed ⅛ in. (3.18 mm) × (length in feet (mm))/(5 ft (1524 mm))

Cold finished:
 ⅛ in. (1.59 mm) in any 5 ft (1524 mm), but may not exceed ⅛ in. (1.59 mm) × (length in feet (mm))/(5 ft (1524 mm))

TABLE 12 Diameter and Out-of-Round Tolerances for Round Wire (Drawn, Polished, Centerless Ground, Centerless Ground and Polished)^{A,B,C}

Specified Diameter, in. (mm)	Diameter Tolerance, in. (mm)	
	Over	Under
0.5000 (12.70)	0.002 (0.05)	0.002 (0.05)
Under 0.5000 (12.70) to 0.3125 (7.94), incl	0.0015 (0.04)	0.0015 (0.04)
Under 0.3125 (7.94) to 0.0440 (1.12), incl	0.001 (0.03)	0.001 (0.03)
Under 0.0440 (1.12) to 0.0330 (0.84), incl	0.0008 (0.02)	0.0008 (0.02)
Under 0.0330 (0.84) to 0.0240 (0.61), incl	0.0005 (0.013)	0.0005 (0.013)
Under 0.0240 (0.61) to 0.0120 (0.30), incl	0.0004 (0.010)	0.0004 (0.010)
Under 0.0120 (0.30) to 0.0080 (0.20), incl	0.0003 (0.008)	0.0003 (0.008)
Under 0.0080 (0.20) to 0.0048 (0.12), incl	0.0002 (0.005)	0.0002 (0.005)
Under 0.0048 (0.12) to 0.0030 (0.08), incl	0.0001 (0.003)	0.0001 (0.003)

^A Diameter tolerances are over and under as given in this table. Also, round wire can be produced to tolerances all over and nothing under, or all under and nothing over, or any combination over and under, if the total spread in diameter tolerances for a specified diameter is not less than the total spread given in this table.

^B The maximum out-of-round tolerance for round wire is one half of the total size tolerance given in this table.

^C When it is necessary to heat treat after cold finishing because of special mechanical property requirements, tolerances are commonly double those shown.

TABLE 13 Size Tolerances for Drawn Wire in Hexagons, Octagons, and Squares

Specified Size, ^A in. (mm)	Size Tolerance, in. (mm)	
	Over	Under
½ (12.70)		0.004 (0.10)
Under ½ (12.70) to ⅝ (7.94), incl	0	0.003 (0.08)
	0	
Under ⅝ (7.94) to ⅜ (3.18), incl	0	0.002 (0.05)

^A Distance across flats.

TABLE 14 Length Tolerances for Round and Shape, Straightened and Cut Wire, Exact Length Resheared Wire

Diameter, in. (mm)	Length, ft (mm)	Tolerance, in. (mm)	
		Over	Under
0.125 (3.18) and under	Up to 12 (3658), incl	⅛ (1.59)	0
0.125 (3.18) and under	Over 12 (3658)	⅛ (3.18)	0
Over 0.125 (3.18) to 0.500 (12.70), incl	Under 3 (914)	⅜ (9.53)	0
Over 0.125 (3.18) to 0.500 (12.70), incl	3 (914) to 12 (3658), incl	⅛ (1.59)	0
Over 0.125 (3.18) to 0.500 (12.70), incl	Over 12 (3658)	⅛ (3.18)	0

TABLE 15 Size Tolerances for Wire for Which the Final Operation is a Surface Treatment for the Purpose of Removing Scale or Drawing Lubricant

Specified Size, in. (mm)	Tolerance, in. (mm)	
	Over	Under
½ (12.70)	0.004 (0.10)	0.004 (0.10)
Under ½ (12.70) to ⅝ (7.94), incl	0.003 (0.08)	0.003 (0.08)
Under ⅝ (7.94) to 0.044 (1.12), incl	0.002 (0.05)	0.002 (0.05)
Under 0.044 (1.12) to 0.033 (0.84), incl	0.0013 (0.03)	0.0013 (0.03)
Under 0.033 (0.84) to 0.024 (0.61), incl	0.0008 (0.02)	0.0008 (0.02)

**TABLE 16 Thickness and Width Tolerances for Cold-Finished Flat Wire**

Specified Width, in. (mm)	Thickness Tolerance, in. (mm), over or under, for Given Thicknesses, in. (mm)			Width Tolerance, in. (mm)	
	Under 0.029 (0.74)	0.029 (0.74) to 0.035 (0.89), excl	0.035 (0.89) to $\frac{3}{16}$ (4.76), excl	Over	Under
Under $\frac{3}{8}$ (9.52) to $\frac{1}{16}$ (1.59), incl	0.001 (0.03)	0.0015 (0.04)	0.002 (0.05)	0.005 (0.13)	0.005 (0.13)

SUMMARY OF CHANGES

Committee B02 has identified the location of selected changes to this standard since the last issue (B 649 - 05) that may impact the use of this standard. (Approved June 1, 2006.)

- (1) Added new wire grade UNS N08936 to Scope, Section 5, Table 1, and Table 2.
- (2) Modified footnotes in Table 2.
- (3) Modified 1.1 for consistency.
- (4) Modified 6.1 to correct reference for chemical composition sampling.
- (5) Removed check analysis reference from 6.2.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).