



Standard Specification for Aluminum Alloy Castings, High-Strength¹

This standard is issued under the fixed designation B 686/B 686M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification covers aluminum-alloy high-strength castings designated as shown in **Table 1**.

1.2 Castings covered by this specification are intended for use in airframe, missile, and other critical applications where high strength, ductility, and sound castings are required.

1.3 Alloy and temper designations are in accordance with ANSI **H35.1/H35.1 (M)**. The equivalent Unified Numbering System alloy designations are in accordance with Practice **E 527**.

1.4 Unless the order specifies the “M” specification designation, the material shall be furnished to the inch-pound units.

1.5 For acceptance criteria for inclusion of new aluminum and aluminum alloys and their properties in this specification, see **Annex A1** and **Annex A2**.

1.6 **Units**—The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regular limitations prior to use.*

2. Referenced Documents

2.1 The following documents of the issue in effect on the date of purchase form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards*:²

B 179 Specification for Aluminum Alloys in Ingot and

Molten Forms for Castings from All Casting Processes

B 275 Practice for Codification of Certain Nonferrous Metals and Alloys, Cast and Wrought

B 557 Test Methods for Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products

B 557M Test Methods for Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products (Metric)

B 660 Practices for Packaging/Packing of Aluminum and Magnesium Products

B 881 Terminology Relating to Aluminum- and Magnesium-Alloy Products

B 917/B 917M Practice for Heat Treatment of Aluminum-Alloy Castings from All Processes

D 3951 Practice for Commercial Packaging

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E 34 Test Methods for Chemical Analysis of Aluminum and Aluminum-Base Alloys

E 94 Guide for Radiographic Examination

E 155 Reference Radiographs for Inspection of Aluminum and Magnesium Castings

E 165 Test Method for Liquid Penetrant Examination

E 527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

E 607 Test Method for Atomic Emission Spectrometric Analysis Aluminum Alloys by the Point to Plane Technique Nitrogen Atmosphere

E 716 Practices for Sampling Aluminum and Aluminum Alloys for Spectrochemical Analysis

E 1251 Test Method for Analysis of Aluminum and Aluminum Alloys by Atomic Emission Spectrometry

IEEE/ASTM SI 10 Standard for Use of the International System of Units (SI): The Modern Metric System

2.3 *AMS Standard*:³

AMS 2771 Heat Treatment of Aluminum Alloy Castings

2.4 *ANSI Standards*:⁴

H35.1 / H35.1 (M) – 2006 Alloy and Temper Designation

¹ This specification is under the jurisdiction of ASTM Committee B07 on Light Metals and Alloys and is the direct responsibility of Subcommittee B07.01 on Aluminum Alloy Ingots and Castings.

Current edition approved May 1, 2008. Published June 2008. Originally approved in 1981. Last previous edition approved in 2007 as B 686/B 686M – 07.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://www.sae.org>.

⁴ Available from Aluminum Association, Inc., 1525 Wilson Blvd., Suite 600, Arlington, VA 22209, <http://www.aluminum.org>.

*A Summary of Changes section appears at the end of this standard.



TABLE 1 Chemical Composition Limits

NOTE 1—When single units are shown, they indicate the maximum amounts permitted.

NOTE 2—Analysis shall be made for the elements for which limits are shown in this table.

NOTE 3—The following applies to all specified limits in this table: For purposes of determining conformance to these limits, an observed value or a calculated value obtained from analysis shall be rounded to the nearest unit in the last right-hand place of figures used in expressing the specified limit in accordance with the rounding-off method of Practice E 29.

Composition, %												
ANSI H35.1	ASTM E 527	Former	Silicon	Iron	Copper	Man- ganese	Magne- sium	Zinc	Titanium		Others Each ^A	Aluminum Total ^B
A201.0	A12010		0.05	0.10	4.0–5.0	0.20–0.40	0.15–0.35		0.15–0.35	^C	0.03	0.10 remainder
354.0	A03540	SC92A	8.6–9.4	0.20	1.6–2.0	0.10	0.40–0.6	0.10	0.20		0.05	0.15 remainder
C355.0	A33550	SC51B	4.5–5.5	0.20	1.0–1.5	0.10	0.40–0.6	0.10	0.20		0.05	0.15 remainder
A356.0	A13560	SG70B	6.5–7.5	0.20	0.20	0.10	0.25–0.45	0.10	0.20		0.05	0.15 remainder
A357.0	A13570		6.5–7.5	0.20	0.20	0.10	0.40–0.7	0.10	0.04–0.20	^D	0.05	0.15 remainder

^A “Others” includes listed elements for which no specific limit is shown as well as unlisted metallic elements. The producer may analyze samples for trace elements not specified in the specification. However, such analysis is not required and may not cover all metallic “Others” elements. Should any analysis by the producer or the purchaser establish that an “Others” element exceeds the limit of “Each” or that the aggregate of several “Others” elements exceeds the limit of “Total”, the material shall be considered nonconforming.

^B Other Elements—Total shall be the sum of unspecified metallic elements 0.010 % or more, rounded to the second decimal before determining the sum.

^C Silver 0.40 to 1.0 %.

^D Beryllium 0.04–0.07.

Systems for Aluminum

Z1.4 Sampling Procedures and Tables for Inspection by Attributes

2.5 Military Standard:⁵

MIL-STD-129 Marking for Shipment and Storage

2.6 Federal Standard:⁵

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)

2.7 Other Standards:⁶

CEN EN 14242 Aluminum and aluminum alloys . Chemical analysis. Inductively coupled plasma optical emission spectral analysis

3. Terminology

3.1 *Definitions*: Refer to Terminology B 881 for definitions of product terms used in this specification.

4. Classification

4.1 Castings shall be classified by inspection classes.

4.1.1 Classes (Inspection):

4.1.1.1 *Class 1*—A class of casting, the single failure of which would result in the loss of a missile, aircraft, or other vehicle.

4.1.1.2 *Class 2*—Class 1 castings not included in Class 1, the single failure of which would cause significant danger to operating personnel or would result in a significant operational penalty. In the case of missiles, aircraft, and other vehicles, this includes loss of major components, loss of control, unintentional release of inability to release armament stores, or failure of weapon installation components.

4.1.1.3 *Class 3*—Castings having a margin of safety of 200 % or less.

4.1.1.4 *Class 4*—Castings having a margin of safety of greater than 200 %, or for which no stress analysis is required. All target drone castings and aerospace ground support equipment fall in this category, except for such critical parts, the failure of which would make the equipment unsatisfactory and cause the vehicles which they are intended to support to be inoperable.

4.1.2 Grades (Radiographic Quality):

NOTE 1—Caution should be exercised in specifying the grade of maximum permissible radiographic discontinuity level to be met in the casting. Radiographic quality has only a qualitative relationship to mechanical properties. In general, the highest property levels of an alloy will require the higher grades of radiographic quality. However, section size and shape parameters may be able to tolerate certain discontinuities without significant reduction in functional integrity. Too severe soundness requirements may cause the part producibility to be impractical or uneconomical.

4.1.2.1 *Grade A*—A grade in which there is no discernible discontinuity visible on the radiograph of the specified area of the casting.

4.1.2.2 *Grade B*—A premium grade of casting for critical applications or specified area of a casting with low margins of safety.

4.1.2.3 *Grade C*—A high-quality grade of casting or area of a casting for general applications.

4.1.2.4 *Grade D*—A grade included for less important areas of a casting.

5. Ordering Information

5.1 Orders for material under this specification shall include the following information:

5.1.1 This specification designation (which includes the number, the year, and the revision letter, if applicable).

NOTE 2—For inch-pound application, specify Specification B 686 and for metric application specify Specification B 686M. Do not mix units.

⁵ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://dodssp.daps.dla.mil>.

⁶ Available from European Committee for Standardization (CEN), 36 rue de Stassart, B-1050, Brussels, Belgium, <http://www.cenorm.be>.

5.1.2 Alloy number (Section 7.1, Table 1) radiographic grade (4.1.2, Table 2) inspection class of castings (4.1.1, Table 3 or [Table 4]) and class of mechanical properties (Table 5 or [Table 6]),

5.1.3 Tensile property requirements on the drawing or purchase order (9.1.5, 15.4, 15.5, Table 3 and Table 5 or [Table 4] and [Table 6]),

5.1.4 Identification of product information (Section 11),

5.1.5 Applicable drawings or part number,

5.1.6 The quantity in either pieces or [kilograms],

5.2 Additionally, orders for material to this specification shall include the following information when required by the purchaser:

5.2.1 Whether heat treatment is to be performed in accordance with AMS 2771 (10.2),

5.2.2 Where the preproduction samples shall be sent, and activity responsible for testing, and instructions concerning submittal of the test reports (14.2.1 and 14.2.2),

5.2.3 Penetrant inspection standards (15.2).

5.2.4 Whether the material shall be packed or marked, or both, in accordance with MIL-STD-129, Practices B 660, or Fed. Std. No. 123 (16.3),

5.2.5 Whether certification is required (17).

6. Materials and Manufacture

6.1 The responsibility of furnishing castings that can be laid out and machined to the finished dimensions within the permissible variations specified, as shown on the blueprints or

drawings, shall rest with the producer, except where pattern equipment is furnished by the purchaser and any dimensional discrepancies can be clearly attributed to the pattern equipment as furnished.

6.1.1 Unless otherwise specified, only aluminum alloy conforming to the requirements of Specification B 179 or producer's foundry scrap (identified as being made from alloy conforming to Specification B 179) shall be used in the remelting furnace from which molten metal is taken for pouring directly into castings. Additions of small amounts of modifiers and grain refining elements or alloys are permitted.

6.1.2 Pure materials, recycled materials, and master alloys may be used to make alloys conforming to this specification, provided chemical analysis can be taken and adjusted to conform to Table 1 prior to pouring any castings.

7. Chemical Composition and Sampling

7.1 The product shall conform to the chemical composition limits prescribed in Table 1. Conformance shall be determined by the producer by taking samples at the time castings are poured in accordance with E 716 and analyzed in accordance with E 607, E 1251, E 34 or CEN EN 14242. If the producer has determined the composition of the material during casting, they shall not be required to sample and analyze the finished product.

7.2 If it becomes necessary to analyze castings for conformance to chemical composition limits, the method used to sample castings for the determination of chemical composition

TABLE 2 Discontinuity-Level Requirements for High-Strength Aluminum Castings—Maximum Permissible in Accordance with (Reference Radiographs E 155)

NOTE 1—When two or more types of discontinuities are present within a 2 by 2-in. [50 mm by 50 mm] area to an extent equal to or not significantly better than the acceptance standards for respective discontinuities, the castings shall be rejected.

NOTE 2—When two or more types of discontinuities are present within a 2 by 2-in. [50 mm by 50 mm] area and the predominating discontinuity is not significantly better than the acceptance standard, the casting shall be considered borderline.

NOTE 3—Borderline castings shall be reviewed for acceptance or rejection by competent engineering personnel from the manufacturer and purchaser.

NOTE 4—Gas holes, sand spots, and inclusions allowed by this table shall be cause for rejection when closer than twice their maximum dimension to an edge or extremity of a casting.

NOTE 5—Castings with the following characteristics apply to Alloy A201.1 only:

1. Banding or striated segregation shall be acceptable to the extent that the mechanical properties in the affected section meet the requirements of Table 3.
2. Healed hot tears or discrete segregation cracks, evidenced by linear irregular white lines, shall be rejected.
3. Spheroidal segregation, evidenced by white spheroids, shall be evaluated for size and concentration by using the standards for gas holes.

Discontinuity	Radiograph	Grade A		Grade B		Grade C		Grade D	
		Section Thickness, in.							
		1/4 [6 mm]	3/4 [19 mm]	1/4 [6 mm]	3/4 [19 mm]	1/4 [6 mm]	3/4 [19 mm]	1/4 [6 mm]	3/4 [19 mm]
Gas holes	1.1	none		1	1	2	2	5	5
Gas porosity (round)	1.21	none		1	1	3	3	7	7
Gas porosity (elongated)	1.22	none		1	1	3	4	5	5
Shrinkage cavity	2.1	none		1	^A	2	^A	3	^A
Shrinkage porosity or sponge	2.2	none		1	1	2	2	4	3
Foreign material (less dense material)	3.11	none		1	1	2	2	4	4
Foreign material (more dense material)	3.12	none		1	1	2	1	4	3
Segregation		none		none		none		none	
Cracks		none		none		none		none	
Cold shuts		none		none		none		none	
Laps		none		none		none		none	
Surface irregularity				not to exceed drawing tolerance					
Core shift				not to exceed drawing tolerance					

^A Not available. Use 1/4 in. [6 mm] for all section thicknesses.

TABLE 3 Mechanical Properties of Specimens^A Cut from Designated Areas of Casting^B (Inch-Pound Units).

Alloy Number			Class Number	Tensile Strength, min, ksi	Yield Strength, 0.2 % Offset, min, ksi	Elongation in 2 in. or 4D, min, %
ANSI H35.1	ASTM E 527 (UNS)	Former				
A201.0 ^C	A12010		1	60.0	50.0	3
			2 ^D	60.0	50.0	5
354.0	A03540	SC92A	1	47.0	36.0	3
			2 ^D	50.0	42.0	2
C355.0	A33550	SC51	1	41.0	31.0	3
			2	44.0	33.0	3
			3 ^D	50.0	40.0	2
A356.0	A13560	SC70B	1	38.0	28.0	5
			2	40.0	30.0	3
			3 ^D	45.0	34.0	3
A357.0	A13570		1	45.0	35.0	3
			2 ^D	50.0	40.0	5

^A For purposes of determining conformance with this specification, each value for tensile strength and yield strength shall be rounded to the nearest 0.1 ksi, and each value for elongation shall be rounded to the nearest 0.5 %, both in accordance with the rounding method of Practice E 29.

^B For any casting process utilized, special mold, or sand mold permanent mold with chills may be used. Properties in other areas may vary with mold process and foundry techniques used but will be inspected under foundry control (0.1.2). Special negotiated properties may be called for by the drawing note.

^C Alloy A201.0 is intended for use in the –T7 temper, which provides a high level of resistance to stress-corrosion cracking when properly heat treated. In other tempers, alloy A201.0 may exhibit susceptibility to stress-corrosion cracking. Additionally, its tendency for hot shortness may make alloy A201.0 unsuitable in some casting designs.

^D This class is obtainable in favorable casting configurations and must be negotiated with the foundry for particular configuration desired. See Note 1 and 8.3.

TABLE 4 Mechanical Properties of Specimens^A Cut from Designated Areas of Casting^B (SI Units) - [Metric].^C

Alloy Number			Class Number	Tensile Strength, min, MPa	Yield Strength, 0.2 % Offset, min, MPa	Elongation in 5D, min, %
ANSI H35.1	ASTM E 527 (UNS)	Former				
A201.0 ^D	A12010		1	415	345	3
			2 ^E	415	345	5
354.0	A03540	SC92A	1	325	250	3
			2 ^E	345	290	2
C355.0	A33550	SC51	1	285	215	3
			2	305	230	3
			3 ^E	345	275	2
A356.0	A13560	SC70B	1	260	195	5
			2	275	205	3
			3 ^E	310	235	3
A357.0	A13570		1	310	240	3
			2 ^E	345	275	5

^A For purposes of determining conformance with this specification, each value for tensile strength and yield strength shall be rounded to the nearest 1 MPa, and each value for elongation shall be rounded to the nearest 0.5 %, both in accordance with the rounding method of Practice E 29.

^B For any casting process utilized, special mold or sand mold, or permanent mold, with chills may be used. Properties in other areas may vary with mold process and foundry techniques used but will be inspected under foundry control (8.3). Special negotiated properties may be called for by the drawing note.

^C Guidelines for metric conversion from the *Tempers for Aluminum and Aluminum Alloys, Metric Edition (Tan Sheets)* were used to convert the tensile and yield values to SI units. Section 15.4 and 15.5.3 state that the “coupons must meet the tensile property requirements specified,” therefore there has been no reduction in elongation values during metric conversion.⁷

^D Alloy A201.0 is intended for use in the –T7 temper, which provides a high level of resistance to stress-corrosion cracking when properly heat treated. In other tempers, alloy A201.0 may exhibit susceptibility to stress-corrosion cracking. Additionally, its tendency for hot shortness may make alloy A201.0 unsuitable in some casting designs.

^E This class is obtainable in favorable casting configurations and must be negotiated with the foundry for particular configuration desired. See Note 1 and 8.3.

shall be by agreement between the producer and the purchaser. Analysis shall be performed in accordance with E 716, E 607, E 1251, E 34 or CEN EN 14242 (ICP method).

7.3 Other methods of analysis or in the case of dispute may be by agreement between the producer and the purchaser.

7.4 A sample for determining of chemical composition shall be taken to represent the following:

7.4.1 Not more than 2000 lb [1000 kg] of clean castings (gates and risers removed) or a single casting poured from one furnace.

7.4.2 Castings poured continuously from one furnace for not more than 8 consecutive hours.

8. Preproduction Sample

8.1 In advance of production, unless otherwise specified in the contract or order, two castings heat treated and straightened

to drawing requirements shall be submitted as directed by the purchaser for examination and written approval. One casting shall be completely laid out by the foundry and identified as the “dimensional sample” for dimensional approval. The other casting shall be identified as the “foundry control sample” and shall be for all other inspections and requirements as necessary for approval.

8.2 The submitted castings shall be fully representative of the foundry practice that will be used in production. If temporary gating was used to develop suitable foundry practice, the submitted casting shall be made after the gating has been installed. If chills are required, their size and location shall also be permanently identified and recorded. Pouring temperature of the submitted casting shall be recorded. All details of manufacture and processing shall be recorded and

TABLE 5 Mechanical Properties of Specimens^A Cut from Any Area of Casting^B (Inch-Pound Units)

Alloy Number			Class of Mechanical Property (see 5.1.2) ^C	Tensile Strength, min, ksi	Yield Strength, 0.2 % Offset, min, ksi ^C	Elongation in 2 in. or 4, min, %
ANSI H35.1	ASTM E 527 (UNS)	Former				
A201.0 ^D	A12010		10	60.0	50.0	3
			11	56.0	48.0	1.5
354.0	A03540	SC92A	10	47.0	36.0	3
			11	43.0	33.0	2
C355.0	A33550	SC51	10	41.0	31.0	3
			11	37.0	30.0	1
			12	35.0	28.0	1
A356.0	A13560	SG70B	10	38.0	28.0	5
			11	33.0	27.0	3
			12	32.0	22.0	2
A357.0	A13570		10	38.0	28.0	5
			11	41.0	31.0	3

^A For any casting process utilized, special mold or sand mold, or permanent mold, with chills may be used. Properties in other areas may vary with mold process and foundry techniques used but will be inspected under foundry control (8.3). Special negotiated properties may be called for by the drawing note.

^B For purposes of determining conformance with this specification, each value for tensile strength and yield strength shall be rounded to the nearest 0.1 ksi, and each value for elongation shall be rounded to the nearest 0.5 %, both in accordance with the rounding method of Practice E 29.

^C For any alloy, yield strength will be reasonably consistent throughout the casting. This should be considered when selecting combinations of classes from Table 3 and Table 5. See Note 1 and 8.3.

^D Alloy A201.0 is intended for use in the –T7 temper, which provides a high level of resistance to stress-corrosion cracking when properly heat treated. In other tempers, alloy A201.0 may exhibit susceptibility to stress-corrosion cracking. Additionally, its tendency for hot shortness may make alloy A201.0 unsuitable in some casting designs.

TABLE 6 Mechanical Properties of Specimens^A Cut from Any Area of Casting^B (SI Units) - [Metric]^C

Alloy Number			Class of Mechanical Property (see 5.1.2) ^C	Tensile Strength, min, MPa ^C	Yield Strength, 0.2 % Offset, min, MPa ^D	Elongation in 5D, min, %
ANSI H35.1	ASTM E 527 (UNS)	Former				
A201.0 ^E	A12010		10	415	345	3
			11	385	330	1.5
354.0	A03540	SC92A	10	325	250	3
			11	295	230	2
C355.0	A33550	SC51	10	285	215	3
			11	255	205	1
			12	240	195	1
A356.0	A13560	SG70B	10	260	195	4
			11	230	185	3
			12	220	150	2
A357.0	A13570		10	260	195	4
			11	285	215	3

^A For purposes of determining conformance with this specification, each value for tensile strength and yield strength shall be rounded to the nearest 1 MPa, and each value for elongation shall be rounded to the nearest 0.5 %, both in accordance with the rounding method of Practice E 29.

^B For any casting process utilized, special mold, sand mold, or permanent mold chills may be used. Properties in other areas may vary with mold process and foundry techniques used, but will be inspected under foundry control (8.3). Special negotiated properties may be called for by the drawing note.

^C Guidelines for metric conversion from the *Tempers for Aluminum and Aluminum Alloys, Metric Edition (Tan Sheets)* were used to convert the tensile and yield values to SI units. Section 15.4 and 15.5.3 state that the “coupons must meet the tensile property requirements specified,” therefore there has been no reduction in elongation values during metric conversion.⁷

^D For any alloy, yield strength will be reasonably consistent throughout the casting. This should be considered when selecting combinations of classes from Table 5 and Table 6. See Note 1 and 8.3.

^E Alloy A201.0 is intended for use in the –T7 temper, which provides a high level of resistance to stress-corrosion cracking when properly heat treated. In other tempers, alloy A201.0 may exhibit susceptibility to stress-corrosion cracking. Additionally, its tendency for hot shortness may make alloy A201.0 unsuitable in some casting designs.

documented by photographs, sketches, specifications, and manufacturing procedures.

8.3 The user of this specification is specifically cautioned to verify the capability of the foundry to competently produce parts to the specification. On-site survey should be performed to verify the producers’ technical, manufacturing, and quality control capabilities. Verification of properties of sample test parts is suggested. The ability to produce guaranteed property castings requires technical knowledge, foundry technique, and vigorous controls uncommon to conventional foundries.

9. Radiographic Soundness and Mechanical Property Control

9.1 Prior to production, radiographic and mechanical property control shall be established. Castings shall be examined by radiographic methods for internal discontinuities. Sectioning

and etching may be performed to determine the presence of internal discontinuities. Full-size casting or tension specimens machined from castings shall be tested for conformance to the required mechanical properties. This control shall be continued until the gating and other foundry practices have been established to produce castings conforming to this specification.

9.1.1 *Radiographic Requirements*—After the foundry control methods have been established as specified in 8.1, 8.2, and 8.3, castings shall be radiographically inspected as specified in 15.1. Unless otherwise specified in the contract or order, acceptance shall be by comparison with a standard set of radiographs contained in Reference Radiograph E 155. Unless otherwise specified, radiographic indications shall be identified in terms of the discontinuities listed in Table 2. Unless otherwise specified, acceptance shall be made in accordance with one of four grades specified on the engineering drawing

(4.1.2). When no grade is specified, Grade C shall apply. When a drawing specifies “critical” area and indicates no grade, Grade B shall apply to that area and Grade C to the remainder of the casting.

9.1.1.1 Acceptability is indicated in Table 2 by the indexed number of the E 155 radiograph which is acceptable for the applicable grade. To be acceptable to the applicable grade, a casting must be acceptable for all discontinuities listed in Table 2. Nonconformance with the applicable standard for any single discontinuity shall make a casting nonacceptable.

9.1.2 *Acceptance Procedure*—The radiographs shall be reviewed to determine conformance to Table 2. Unless otherwise noted, mechanical property test coupons shall be located in relation to the radiographs and high- and low-stress areas of the casting. Mechanical properties tests shall be made to assure conformance to this specification. Mechanical property test coupons sectioned through areas of discrete allowable radiographic soundness discontinuities should be tested for information only and shall not be cause for rejection of the casting or lot except when the test coupon includes a significant portion of the total cast section.

9.1.3 *Foundry Control Approval*—Production of a given casting shall not begin until the foundry control is approved, unless such approval is waived in writing by the purchaser.

9.1.4 *Manufacturing Changes*—The manufacturer shall use the same foundry practices and the same heat-treating procedures for production castings as for approved sample castings. If necessary to make any change, the foundry shall notify the purchaser prior to the first shipment of castings incorporating such a change, and shall submit sample castings produced by the changed procedure for approval in accordance with Section 9. A sample casting may be required by the purchaser to assure that any of the following change(s) do not adversely affect the quality of the casting:

- 9.1.4.1 When a new pattern or permanent mold is used,
- 9.1.4.2 For each new pattern or cavity in multiple tooling,
- 9.1.4.3 When a duplicate pattern or mold is to be used,
- 9.1.4.4 When any change is made in gates, risers, or chills,
- 9.1.4.5 When any change in the “as-cast” shape is made,
- 9.1.4.6 When strength requirements are raised,
- 9.1.4.7 When an old pattern is transferred to a new vendor,
- 9.1.4.8 When another alloy is used, or
- 9.1.4.9 When melting or processing techniques are changed.

9.1.5 *Tensile Properties*—The mechanical properties of test specimens, taken as specified in 9.1.2, shall conform to the requirements of Table 3 and Table 5 or [Table 4 and Table 6]. The strength requirement of the casting tested in full size shall be as agreed upon between the foundry and the purchaser.

10. Heat Treatment

10.1 Heat treatment shall be performed in accordance with Practice B 917/917M.

10.2 When specified, heat treatment shall be in accordance with AMS 2771.

11. Identification of Product

11.1 Where practicable, or unless otherwise specified in the contract or order, each casting shall be identified with the part number and the serial number by the use of raised numbers in

a location indicated on the drawing. When no location is shown on the drawing, the numbers shall be so located as not to be machined off in finishing to the required dimensions.

11.1.1 Castings on which it is impractical to provide raised numerals shall be marked in accordance with the purchaser’s requirements.

12. Dimensions

12.1 The dimensions of the castings shall be within the dimensions and tolerances specified on the applicable drawing.

13. Workmanship, Finish, and Appearance

13.1 Requirements such as surface finish, parting line projections, snagging projections where gates and risers were removed, etc., may be checked visually. It is advisable to have agreed upon observational standards representing both acceptable and unacceptable material.

13.1.1 Castings may be repaired only by processes approved and agreed upon between the producer and purchaser; that is, welding, impregnation, chemical treatment or coating to prevent leaking, peening, blending, soldering, etc. Limitations on the extent and frequency of such repairs, and methods of inspection of repaired areas should also be agreed upon.

13.1.2 Castings shall not be mechanically straightened after precipitation heat treatment without written permission from the purchaser.

14. Responsibility for Quality Assurance

14.1 *Responsibility for Inspection and Tests*—Unless otherwise specified in the contract or purchase order, the producer shall be responsible for the performance of all inspection and test requirements specified herein. Except as otherwise specified in the contract or order, the producer may use his own or any other suitable facilities for the performance of the inspection and test requirements specified herein unless disapproved by the purchaser. The purchaser shall have the right to perform any of the inspection and tests set forth in this specification where such inspections are deemed necessary to confirm that material conforms to prescribed requirements.

14.2 *Classification of Tests*—The inspection and testing of castings shall be classified as (1) preproduction tests and (2) quality-conformance tests.

14.2.1 *Preproduction Tests*—The first two castings submitted under each contract or order shall be the preproduction test samples. The manufacturer shall supply a certified statement of composition and prior tests that shows that the castings comply with the requirements of this specification.

14.2.2 *Preproduction Testing*—Preproduction testing of the castings shall consist of all tests described in Section 15.

14.3 *Quality-Conformance Tests*—Quality-conformance tests shall consist of all tests required under Section 15.

14.3.1 *Lot*—A lot shall consist of not more than 4000 lb [2000 kg] of castings of the same part number produced in a pouring period not exceeding eight hours with metal from a single melt that are heat-treated in one furnace load. A melt is defined as metal withdrawn from a single furnace to which all alloying, grain refining, degassing, and processing has been completed.

14.3.2 *Traceability*—Castings produced to this specification shall be serialized sequentially as they are produced. The serial number shall be used to provide traceability to all production and inspection operations. The drawing or contract shall denote the method of serialization, that is, cast-on, vibro-etched, etc.

14.3.3 *Sampling Instructions*—Sampling plans and procedures in the determination of the acceptability of products submitted by a supplier shall be in accordance with the provisions set forth in ANSI Z1.4 or as specified in this specification; however, more stringent sampling requirements may be specified on the drawing or in purchase documents.

15. Test Methods

15.1 Radiographic Inspection:

15.1.1 Radiographic inspection shall be in accordance with Guide E 94 and Reference Radiograph E 155.

15.1.2 Radiographic acceptance shall be in accordance with requirements selected from Table 2. Any modifications of this table and the frequency per unit area and location shall also be agreed upon.

15.1.3 Castings shall be radiographically inspected as indicated below:

15.1.3.1 *Class 1* (see Section 4) *Castings*—Each shall be completely examined.

15.1.3.2 *Class 2 Castings*—Casting shall be selected in accordance with Table 7 and completely examined.

15.1.3.3 *Class 3 Castings*—Castings shall be selected in accordance with Table 8 and completely examined.

15.1.3.4 *Class 4 Castings*—Radiographic examination is not required unless otherwise specified.

15.2 Liquid Penetrant Inspection:

15.2.1 When specified, liquid penetrant inspection shall be in accordance with Test Method E 165, and Type I penetrant shall be used unless otherwise specified.

15.2.2 Acceptance standards for discontinuities shall be agreed upon, including size and frequency per unit area and location.

15.2.3 Each casting shall be subjected to penetrant inspection.

15.3 *Tensile Properties*—The tensile properties shall be determined in accordance with Test Methods B 557 or [B 557M]. When the size or shape of the casting restricts the use of test specimens, or when otherwise determined, the full-size casting may be tested. When a complete casting test is required, the strength requirement and the direction or method of loading of the full-size casting shall be specified on the drawing for the part concerned.

TABLE 7 Sample Size (Radiographic Class 2 Castings)

NOTE 1—Acceptance number is 0.

Lot Size	Sample Size	Lot Size	Sample Size
2–5	all	27–36	10
6–8	5	37–51	11
9–11	6	52–82	12
12–15	7	83–162	13
16–20	8	163–971	14
21–26	9	972 and over	15

TABLE 8 Sample Size (Radiographic Class 3 Castings)

NOTE 1—Acceptance number is 0.

Lot Size	Sample Size	Lot Size	Sample Size
2–4	all	18–27	7
5–6	4	28–48	8
7–11	5	49 and over	9
12–17	6		

15.4 *Tensile Properties—Small Castings*—Castings shall be selected at random from each lot, after heat treatment and nondestructive testing operations have been completed, in accordance with ANSI Z1.4, Inspection Level S-2, acceptance number zero, for the test of 9.1.5. Tension test coupons shall be cut from locations specified on the engineering drawing. If no location is shown, three specimens shall be taken from a thick, medium, and thin section of each casting selected at random. Tests of these coupons must meet the tensile property requirements specified for the zone of the casting from which they were taken. In the event of a failure of any test the lot of castings that the sample represents shall be rejected pending material review board action by the purchaser.

15.5 Tensile Properties—Larger Castings:

15.5.1 Each casting shall be cast with one or more cast-on coupons for tensile property testing. These coupons shall remain on the casting until after the completion of all heat-treat operations and shall then be tested to ensure that the casting has been heat-treated to achieve the required tensile properties. Regardless of where they are attached, the coupons shall meet the highest strength requirements for the casting. If cast-on coupons must be removed prior to heat treatment or if the casting must be reheat treated after they have been removed, the cast-on coupons shall accompany the part through the heat treat operation.

15.5.2 One casting shall be selected at random from each 25 castings or major fraction thereof. The casting selected for testing must be one of 25 castings remaining to be submitted from a sequence of pouring. All castings, sequentially serialized as they are poured, must be accounted for, either as scrapped out or submitted in the batch of 25 castings. Tension test specimens shall be taken from each tensile property strength zone in the casting from locations designated on the engineering drawings. In addition, the attached coupon or coupons shall be tested and reported as part of the survey.

15.5.3 All tests must meet the minimum requirements for the zone of the casting from which they are taken. In the event of a test failure, the group of 25 castings which the test casting represents shall be rejected pending material review board action by the purchaser.

15.6 *Visual and Dimensional Examination*—A random sample shall be selected from each lot in accordance with ANSI Z1.4, Inspection Level 11, Acceptance Quality Level 2.5 % Defective, for the examinations of Sections 12 and 13.

15.7 Source Inspection:

15.7.1 If the purchaser desires to make an inspection of the casting at the producers works, it shall be so stated in the contract or order.

15.7.2 If the purchaser elects to have inspection made at the producer's works, the producer shall afford the inspector all reasonable facilities to satisfy him that the material is being furnished in accordance with this specification. All tests and inspection shall be so conducted as not to interfere unnecessarily with the operation of the works.

16. Packaging, Marking, and Shipping

16.1 The material shall be packaged to provide adequate protection during normal handling and transportation, and each package shall contain only castings of the same configuration unless otherwise agreed upon. The type of packaging and gross weight of containers shall, unless otherwise agreed upon, be at the producer's discretion, provided they are such to ensure acceptance by common or other carriers for safe transportation at the lowest rate to the delivery point.

16.2 Each package or container shall be marked with the purchase order number, drawing number, quantity, specifica-

tion number, alloy and temper, gross and net weights, and the name of the producer.

16.3 When specified in the contract or purchase order, castings shall be preserved, packaged, and packed in accordance with the requirements of Practices **B 660**. The applicable levels shall be specified in the contract or order. Marking for shipment of such material shall be in accordance with **Fed. Std. No. 123** or Practice **D 3951** for civil agencies and **MIL-STD-129** for military agencies.

17. Certification

17.1 The producer shall, on request, furnish to the purchaser a certificate stating that each lot has been sampled, tested, and inspected in accordance with this specification, and has met the requirements.

18. Keywords

18.1 aluminum; high strength; sand casting

ANNEXES

(Mandatory Information)

A1. BASIS FOR INCLUSION OF PROPERTY LIMITS

A1.1 Limits are established at a level at which a statistical evaluation of the data indicates that 99 % of the population obtained from all standard material meets the limit with 95 % confidence. For the products described, mechanical property limits for the respective size ranges are based on the analyses of at least 100 data from standard production material with no

more than ten data from a given lot. All tests are performed in accordance with the appropriate ASTM test methods. For informational purposes, refer to "Statistical Aspects of Mechanical Property Assurance" in the Related Material section of the *Annual Book of ASTM Standards*, Vol 02.02.

A2. ACCEPTANCE CRITERIA FOR INCLUSION OF NEW ALUMINUM AND ALUMINUM ALLOYS IN THIS SPECIFICATION

A2.1 Prior to acceptance for inclusion in this specification, the composition of wrought or cast aluminum or aluminum alloy shall be registered in accordance with ANSI **H35.1 / H35.1 (M)**. The Aluminum Association⁷ holds the Secretariat of ANSI H35 Committee and administers the criteria and procedures for registration.

A2.2 If it is documented that the Aluminum Association could not or would not register a given composition, an alternative procedure and the criteria for acceptance shall be as follows:

A2.2.1 The designation submitted for inclusion does not utilize the same designation system as described in ANSI **H35.1 / H35.1 (M)**. A designation not in conflict with other designation systems or a trade name is acceptable.

A2.2.2 The aluminum or aluminum alloy has been offered for sale in commercial quantities within the prior twelve months to at least three identifiable users.

A2.2.3 The complete chemical composition limits are submitted.

A2.2.4 The composition is, in the judgement of the responsible subcommittee, significantly different from that of any other aluminum or aluminum alloy already in this specification.

A2.2.5 For codification purposes, an alloying element is any element intentionally added for any purpose other than grain refinement and for which minimum and maximum limits are specified. Unalloyed aluminum contains a minimum of 99.00 % aluminum.

A2.2.6 Standard limits for alloying elements and impurities are expressed to the following decimal places:

Less than 0.001 %	0.000X
0.001 to but less than 0.01 %	0.00X
0.01 to but less than 0.10 %	
Unalloyed aluminum made by a refining process	0.0XX
Alloys and unalloyed aluminum not made by a refining process	0.0X
0.10 through 0.55 %	0.XX
(It is customary to express limits of 0.30 through 0.55 % as 0.X0 or 0.X5)	
Over 0.55 %	0.X, X.X, etc.

⁷ Available from Aluminum Association, Inc., 1525 Wilson Blvd., Suite 600, Arlington, VA 22209, <http://www.aluminum.org>.

(Except that combined Si + Fe limits for 99.00 % minimum aluminum must be expressed as 0.XX or 1.XX)

A2.2.7 Standard limits for alloying elements and impurities are expressed in the following sequence: Silicon; Iron; Copper; Manganese; Magnesium; Chromium; Nickel; Zinc; Titanium (**Note A2.1**); Other Elements, Each; Other Elements, Total; Aluminum (**Note A2.2**).

NOTE A2.1—Additional specified elements having limits are inserted in alphabetical order of their chemical symbols between Titanium and Other Elements, Each or are specified in footnotes.

NOTE A2.2—Aluminum is specified as *minimum* for unalloyed aluminum and as a *remainder* for aluminum alloys.

APPENDIXES

(Nonmandatory Information)

X1. ALLOY PROPERTIES AND CHARACTERISTICS

X1.1 The data in **Table X1.1** are approximate and are supplied for general information only.

TABLE X1.1 Properties and Characteristics (Inch-Pound Units) and (SI Units) - [Metric]

NOTE 1—1 indicates best of group, 5 indicates poorest of group.

Alloy ^A		Pattern Shrinkage Allowance, in. ft ^B [mm/m]	Approximate Melting Range, ° F ^C [°C]	Resistance to Hot Cracking ^D	Pressure Tightness	Fluidity ^E	Solidification Shrinkage Tendency ^F	Normally Heat Treated	Resistance to Corrosion ^G	Machining ^H	Polishing ^I	Electroplating ^J	Anodizing (Appearance) ^K	Chemical Oxide Coating (Protection) ^L	Strength at Elevated Temperature ^M	Suitability for Welding ^N	Suitability for Brazing ^O
ANSI	UNS																
201.0	A02010	5/32 [13]	1060–1200 [565–649]	4	3	3	4	yes	4	1	1	1	2	2	1	4	no
354.0	A03540	5/32 [13]	1015–1150 [546–621]	1	1	1	1	yes	3	3	3	1	4	2	2	2	no
C355.0	A33550	5/32 [13]	1015–1150 [546–621]	1	1	1	1	yes	3	3	3	1	4	2	2	2	no
A356.0	A13560	5/32 [13]	1035–1135 [557–613]	1	1	1	1	yes	2	4	5	2	4	2	3	2	no
A357.0	A13570	5/32 [13]	1035–1135 [557–613]	1	1	1	1	yes	2	4	5	2	4	2	3	2	no

^A ASTM alloy designations are in Practice **B 275**.

^B Allowances for average castings. Shrinkage requirements will vary with intricacy of design and dimensions.

^C Temperatures of solidus and liquidus are indicated; pouring temperatures will be higher.

^D Ability of alloy to withstand contraction stresses while cooling through hot-short or brittle-temperature range.

^E Ability of liquid alloy to flow readily in mold and fill thin sections.

^F Decrease in volume accompanying freezing of alloy and measure of amount of compensating feed metal required in form of risers.

^G Based on alloy resistance in standard-type salt-spray test.

^H Composite rating based on ease of cutting, chip characteristics, quality of finish, and tool life. Ratings in the case of heat-treatable alloys, based on – T6 Temper. Other tempers, particularly the annealed temper, may have lower rating.

^I Composite rating based on ease and speed of polishing and quality of finish provided by typical polishing procedure.

^J Ability of casting to take and hold an electroplate applied by present standard methods.

^K Rated on lightness of color, brightness, and uniformity of clear anodized coating applied in sulfuric acid electrolyte.

^L Rated on combined resistance of coating and base alloy to corrosion.

^M Rating based on tensile and yield strengths at temperatures up to 500°F (260°C), after prolonged heating at testing temperature.

^N Based on ability of material to be fusion welded with filler rod of same alloy.

^O Refers to suitability of alloy to withstand brazing temperatures without excessive distortion or melting.

X2. METRIC EQUIVALENTS

X2.1 The SI unit for strength properties now shown is in accordance with the International Systems of Units (SI) (**IEEE/ASTM SI 10**). The derived SI unit for force is the newton (N), which is defined as that force which when applied to a body having a mass of 1 kg gives it an acceleration of 1 m/s² (N = kg·m/s²). The derived SI unit for pressure or stress is the

newton per square metre (N/m²), which has been named the pascal (Pa) by the General Conference on Weights and Measures. Since 1 ksi = 6 894 757 Pa, the metric equivalents are expressed as megapascal (MPa), which is the same as MN/m² and N/mm².

SUMMARY OF CHANGES

Committee B07 has identified the location of selected changes to this standard since the last issue (B 608/B 608M – 07) that may impact the use of this standard. (Approved May 1, 2008.)

- | | |
|---|---|
| <ul style="list-style-type: none"> (1) Addition of Reference CEN EN 14242. (2) Deletion of E 88. (3) Revision of Section 7, Chemical Composition and Sampling, including complete rewrite of section 7.1. | <ul style="list-style-type: none"> (4) Deleted previously labeled section 7.3. (5) Deleted section 15.1, Chemical Composition and renumbered subsections. |
|---|---|

Committee B07 has identified the location of selected changes to this standard since the last issue (B 686 – 03) that may impact the use of this standard. (Approved October 1, 2007.)

- | | |
|---|--|
| <ul style="list-style-type: none"> (1) Add new section 1.3 and renumber following sections as shown. (2) Revise section 1.5 to define scope of standard as dual (Inch- Pounds & SI Units). (3) In section 2.2, ASTM Standards, add references to B275, B557 and B881 and appropriate reference footnotes. (4) Add new section 2.3 AMS standards and reference to AMS2771 with appropriate source footnote and renumber the following sections as shown. (5) Section 2.4, add reference to standard H35.1 (M) with source footnote. Renumber sections as appropriate. (6) Add new section 3. Terminology and 3.1 Definitions. Renumber following section as appropriate. (7) In 5.1.1 add Note 1- defining which standard to use for inch-pound or metric. (8) Sections 5.1.2 and 5.1.3 add references to Table 5 and Table 6. (9) In 5.1.6 add “[kilograms]”. (10) Add 5.2.1 to define heat treatment practice- B917 or AMS 2771. Renumber following sections as shown. (11) Add section 5.2.5 for certification requirements. (12) Revise 7.1 and add new sections 7.2, 7.2.1, 7.2.2, 7.3, 7.3.1, and 7.3.2 to define sampling practices for analysis. (13) Revise 9.1.1 to correct references to other sections. (14) Revise 9.1.5 to reference new metric mechanical properties Tables 5 & 6. (15) Revise section 10.1 and add section 10.2 to define which heat treat practice is to be used. (16) Add metric units to lot size in section 14.3.1 (17) Correct Table references in 15.2.3.2 & 15.2.3.3 that define radiographic lot size. (18) In 15.4 add reference to B557 M. (19) Add new section 17. which defines when certification shall be required. | <ul style="list-style-type: none"> (20) In Table 1: a) Move 201.0 to top of table b) Beryllium Column – remove title c) Remove Beryllium limits for A357.0 from Beryllium column add footnote ‘D’ in untitled column for A357.0 and add footnote ‘D’ which defines beryllium limits for A357.0 d) Move 201.0 footnote letter ‘C’ to untitled column (Makes Table 1 consistent with ‘Pink Sheets’ format) (21) In Table 2 added SI units to note 1 & 2. (22) Table 3: a) Added (Inch-Pound Units) to title b) Added UNS to column ASTM E527 c) Added word ‘utilized’ to footnote B d) Deleted footnote C which indicated SI units for information only and revise letter designations for the following footnotes (23) Table 4: a) Added (Inch-Pound Units) to title b) Added UNS to column ASTM E527 c) Added word ‘utilized’ to footnote A d) Corrected reference to “see 4.1.2” in footnote C e) Deleted footnote D which indicated SI units for information only and renumbered following footnotes as shown. Table 4: a) Added (Inch-Pound Units) to title b) Added UNS to column ASTM E527 c) Added word ‘utilized’ to footnote A d) Corrected reference to “see 4.1.2” in footnote C e) Deleted footnote D which indicated SI units for information only and renumbered following footnotes as shown (24) Add new table, Table 5, which is the metric version of Table 3. (25) Add new table, Table 6, which is the metric version of Table 4 and renumber following tables as appropriate. (26) Added reference to H35.1 (M) to sections A2.1 and A2.2.1 (27) Corrected address and added website for Aluminum Association in footnotes 4, 6 & 7. (28) Added new table, Table X1.1. (29) Revise Summary of Changes section. |
|---|--|



ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).