



Standard Specification for Copper Alloy Sand Castings for Valve Applications¹

This standard is issued under the fixed designation B 763; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification establishes requirements for copper alloy sand castings for valve applications. Nominal compositions of the alloys defined by this specification are shown in **Table 1**.²

NOTE 1—This specification does not cover Copper Alloy UNS Nos. C83600, C92200, C96200, and C96400. These alloys are also used in valve applications. They are covered by the following specifications:

C83600: **B 62**
C92200: **B 61**
C96200: **B 369**
C96400: **B 369**

1.2 The castings produced under this specification are used in products which may be manufactured in advance and supplied for sale from stock by the manufacturer.

1.3 *Units*—The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

2. Referenced Documents

2.1 ASTM Standards:³

- B 61** Specification for Steam or Valve Bronze Castings
- B 62** Specification for Composition Bronze or Ounce Metal Castings
- B 208** Practice for Preparing Tension Test Specimens for Copper Alloy Sand, Permanent Mold, Centrifugal, and

Continuous Castings

- B 369** Specification for Copper-Nickel Alloy Castings
- B 824** Specification for General Requirements for Copper Alloy Castings
- E 10** Test Method for Brinell Hardness of Metallic Materials
- E 527** Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

3. General Requirements

3.1 The following sections of Specification **B 824** form a part of this specification.

- 3.1.1 Terminology,
- 3.1.2 Other Requirements,
- 3.1.3 Dimensions, Mass, and Permissible Variations,
- 3.1.4 Workmanship, Finish, and Appearance,
- 3.1.5 Sampling,
- 3.1.6 Number of Tests and Retests,
- 3.1.7 Specimen Preparation,
- 3.1.8 Test Methods,
- 3.1.9 Significance of Numerical Limits,
- 3.1.10 Inspection,
- 3.1.11 Rejection and Rehearing,
- 3.1.12 Certification,
- 3.1.13 Test Report,
- 3.1.14 Product Marking,
- 3.1.15 Packaging and Package Marking, and
- 3.1.16 Supplementary Requirements.

4. Ordering Information

4.1 Include the following information when placing orders for product under this specification, as applicable:

- 4.1.1 Specification title, number, and year of approval,
- 4.1.2 Quantity of castings,
- 4.1.3 Copper Alloy UNS Number and temper (as-cast, heat-treated, etc.),
- 4.1.4 Pattern or drawing number and condition (as-cast, machined, etc.),
- 4.1.5 When castings are purchased for agencies of the U.S. Government, the Supplementary Requirements of Specification **B 824** may be specified.

4.2 The following requirements are optional and should be specified in the purchase order when required.

¹ This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.05 on Castings and Ingots for Remelting.

Current edition approved Oct. 1, 2008. Published November 2008. Originally approved in 1986. Last previous edition approved in 2008 as B 763 – 08.

² The UNS system for copper and copper alloys (see Practice **E 527**) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “C” and a suffix “00”. The suffix can be used to accommodate composition variations of the base alloy.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Nominal Compositions

Classification	Copper Alloy UNS No.	Commercial Designation	Copper	Tin	Lead	Zinc	Nickel	Iron	Alumi- num	Man- ganese	Sili- con	Bismuth	Selenium
Leaded red brass	C83450		88	2½	2	6½	1	...	...	...	...	...	...
	C83800	83-4-6-7 or commercial red brass	83	4	6	7	...	...	...	...	...	...	...
Leaded semi-red brass	C84400	81-3-7-9 or valve composition	81	3	7	9	...	...	...	...	...	...	...
	C84800	76-2½-6½-15, or semi-red brass	76	2½	6½	15	...	...	...	...	...	...	...
Leaded yellow brass	C85200	high-copper yellow brass	72	1	3	24	...	...	...	...	...	...	...
	C85400	commercial No. 1 yellow brass	67	1	3	29	...	...	...	...	...	...	...
	C85700	leaded naval brass	61	1	1	37	...	...	...	...	...	...	...
High-strength yellow brass	C86200	high-strength manganese bronze	63	...	...	27	...	3	4	3	...	...	...
	C86300	high-strength manganese bronze	61	...	...	27	...	3	6	3	...	...	...
	C86400	leaded manganese bronze	58	1	1	38	...	1	½	½	...	...	...
	C86500	No. 1 manganese bronze	58	...	...	39	...	1	1	1	...	...	...
	C86700	leaded manganese bronze	58	1	1	34	...	2	2	2	...	...	...
Silicon bronze and silicon brass	C87300	silicon bronze	95	...	...	...	...	...	...	1	4	...	...
	C87400	silicon brass	82	...	½	14	...	...	...	...	3½	...	...
	C87500	silicon brass	82	...	...	14	...	...	...	...	4	...	...
	C87600	silicon bronze	89	...	...	6	...	...	...	...	5	...	...
	C87610	silicon bronze	92	...	...	4	...	...	...	...	4	...	...
	C89530	Bismuth-Selenium	86.5	4.7	...	8.0	...	...	...	...	...	1.5	.20
	C89535	Bismuth	86.5	3.0	...	7.0	.65	...	...	...	...	1.4	...
Bismuth semi-red brass	C89844	bismuth brass	84½	4	...	8	...	...	...	...	...	3	...
Tin bronze and leaded tin bronze	C90300	88-8-0-4, or modified "G" bronze	88	8	...	4	...	...	...	...	...	...	...
	C90500	88-10-0-2, on "G" bronze	88	10	...	2	...	...	...	...	...	...	...
	C92300	87-8-1-4, or Navy PC	87	8	1	4	...	...	...	...	...	...	...
High-lead tin bronze	C92600	87-10-1-2	87	10	1	2	...	...	...	...	...	...	...
	C93200	83-7-7-3	83	7	7	3	...	...	...	...	...	...	...
	C93500	85-5-9-1	85	5	9	1	...	...	...	...	...	...	...
	C93700	80-10-10	80	10	10	...	...	...	...	...	...	...	...
	C93800	78-7-15	78	7	15	...	...	...	...	...	...	...	...
	C94300	71-5-24	71	5	24	...	...	...	...	...	...	...	...
	C94700	nickel-tin bronze grade "A"	88	5	...	2	5	...	...	...	...	...	...
Nickel-tin bronze and leaded nickel-tin bronze	C94800	leaded nickel-tin bronze grade "B"	87	5	1	2	5	...	...	...	...	...	...
	C94900	leaded nickel-tin bronze grade "C"	80	5	5	5	5	...	...	...	...	...	...
	C95200	Grade A	88	...	...	...	...	3	9	...	...	...	...
Aluminum bronze	C95300	Grade B	89	...	...	...	...	1	10	...	...	...	...
	C95400	Grade C	85	...	...	...	...	4	11	...	...	...	...
	C95410	...	84	...	...	...	...	2	4	10	...	...	...
Silicon aluminum bronze	C95600	Grade E	91	...	...	...	...	...	7	...	2	...	...
Nickel aluminum bronze	C95500	Grade D	81	...	...	...	4	4	11	...	...	...	...
	C95800	...	81.3	...	...	...	4.5	4	9	1.2	...	...	...
	C97300	12 % leaded nickel silver	57	2	9	20	12	...	...	...	...	...	...
Leaded nickel bronze	C97600	20 % leaded nickel silver	64	4	4	8	20	...	...	...	...	...	...
	C97800	25 % leaded nickel silver	66	5	2	2	25	...	...	...	...	...	...
	C99400	...	87	...	...	4.4	3.0	3.0	1.6	...	1.0	...	...
Special alloys	C99500	...	87	...	...	1.5	4.5	4.0	1.7	...	1.3	...	...

- 4.2.1 Chemical analysis of residual elements (6.3),
- 4.2.2 Pressure test or soundness requirements (Specification B 824),
- 4.2.3 Approval of weld repair and records of repair (Section 10),
- 4.2.4 Certification (Specification B 824),
- 4.2.5 Foundry test report (Specification B 824),
- 4.2.6 Witness inspection (Specification B 824),
- 4.2.7 Product marking (Specification B 824),
- 4.2.8 Castings for seawater service (5.1).

5. Materials and Manufacture

5.1 For better corrosion resistance in sea water applications, castings in Copper Alloy UNS No. C95800 shall be given a temper anneal heat treatment at 1250 ± 50°F (675 ± 10°C) for 6-h minimum. Cooling shall be by the fastest means possible that will not cause excessive distortion or cracking.

5.2 Copper Alloy UNS Nos. C94700, C95300, C95400, C95410, and C95500 may be supplied in the heat-treated condition to obtain the higher mechanical properties shown in

Table 4. Suggested heat treatments for these alloys and copper alloy UNS No. C95520 are given in **Table 5**. Actual practice may vary by manufacturer.

5.3 Separately cast test bar coupons representing castings made in Copper Alloy UNS Nos. C94700HT, C95300HT, C95400HT, C95410HT, and C95500HT shall be heat treated with the castings.

6. Chemical Composition

6.1 The castings shall conform to the requirements for major elements shown in **Table 2**.

6.2 These specification limits do not preclude the presence of other elements. Limits may be established and analysis required for unnamed elements agreed upon between the manufacturer or supplier and the purchaser. Copper or zinc may be given as remainder and may be taken as the difference between the sum of all elements analyzed and 100 %. When all named elements in **Table 2** are analyzed, their sum shall be as specified in **Table 3**.

TABLE 2 Chemical Requirements

Composition, % max, except as indicated

Copper Alloy UNS No.	Major Elements											Residual Elements								
	Copper	Tin	Lead	Zinc	Iron	Nickel incl Cobalt	Aluminum	Manganese	Silicon	Bismuth	Selenium	Iron	Antimony	Nickel incl Cobalt	Sulfur	Phosphorus	Aluminum	Manganese	Silicon	Lead
C83450	87.0–89.0	2.0–3.5	1.5–3.0	5.5–7.5	...	0.8–2.0	...	...	...	...	...	0.30	0.25	...	0.08	0.03	0.005	...	0.005	...
C83800	82.0–83.8	3.3–4.2	5.0–7.0	5.0–8.0	...	1.0 ^A	...	...	...	...	...	0.30	0.25	...	0.08	0.03	0.005	...	0.005	...
C84400	78.0–82.0	2.3–3.5	6.0–8.0	7.0–10.0	...	1.0 ^A	...	...	...	...	...	0.40	0.25	...	0.08	0.02	0.005	...	0.005	...
C84800	75.0–77.0	2.0–3.0	5.5–7.0	13.0–17.0	...	1.0 ^A	...	...	...	...	...	0.40	0.25	...	0.08	0.02	0.005	...	0.005	...
C85200	70.0–74.0	0.7–2.0	1.5–3.8	20.0–27.0	...	...	...	...	...	...	...	0.6	0.20	1.0	0.05	0.02	0.005	...	0.05	...
C85400	65.0–70.0	0.50–1.5	1.5–3.8	24.0–32.0	...	...	...	...	...	...	...	0.7	...	1.0	...	...	0.35	...	0.05	...
C85700	58.0–64.0	0.50–1.5	0.8–1.5	32.0–40.0	...	...	...	...	...	...	...	0.7	...	1.0	...	...	0.8	...	0.05	...
C86200	60.0–66.0	0.20	0.20	22.0–28.0	2.0–4.0	...	3.0–4.9	2.5–5.0	...	...	...	...	...	1.0	...	...	...	...	...	...
C86300	60.0–66.0	0.20	0.20	22.0–28.0	2.0–4.0	...	5.0–7.5	2.5–5.0	...	...	...	...	...	1.0	...	...	...	...	...	...
C86400	56.0–62.0	0.50–1.5	0.50–1.5	34.0–42.0	0.40–2.0	...	0.50–1.5	0.10–1.5	...	...	...	...	...	1.0	...	...	...	...	...	...
C86500	55.0–60.0	1.0	0.40	36.0–42.0	0.40–2.0	...	0.50–1.5	0.10–1.5	...	...	...	...	...	1.0	...	...	...	...	...	...
C86700	55.0–60.0	1.5	0.50–1.5	30.0–38.0	1.0–3.0	...	1.0–3.0	1.0–3.5	...	...	...	...	...	1.0	...	...	...	...	...	...
C87300	94.0 min	...	0.09	0.25	...	...	...	0.8–1.5	3.5–5.0	...	...	0.20	...	...	...	...	...	...	...	...
C87400	79.0 min	...	1.0	12.0–16.0	...	...	...	...	2.5–4.0	...	...	...	...	...	...	...	0.8	...	...	...
C87500	79.0 min	...	0.09	12.0–16.0	...	...	...	...	3.0–5.0	...	...	...	...	...	...	...	0.50	...	...	...
C87600	88.0 min	...	0.09	4.0–7.0	0.20	...	...	...	3.5–5.5	...	...	...	...	...	...	...	...	0.25	...	...
C87610	90.0 min	...	0.09	3.0–5.0	0.20	...	...	...	3.0–5.0	...	...	...	...	...	...	...	...	0.25	...	...
C89530	84.0–89.0	3.5–6.0	.20	7.0–9.0	...	1.0	...	...	...	1.0–2.0	.10–.30	.30	.20	...	...	.05	.01	...	.01	...
C89535	84.0–89.0	2.5–5.5	.25	5.0–9.0	...	.30–1.0	...	...	...	.8–2.0	.50	.30	.20	...	...	.10–.40	.01	...	.01	...
C89844	83.0–86.0	3.0–5.0	...	7.0–10.0	...	1.0 ^A	...	...	...	2.0–4.0	...	0.30	0.25	...	0.08	0.05	0.005	...	0.005	0.20
C90300	86.0–89.0	7.5–9.0	0.30	3.0–5.0	...	1.0 ^A	...	...	...	...	...	0.20	0.20	...	0.05	0.05	0.005	...	0.005	...
C90500	86.0–89.0	9.0–11.0	0.30	1.0–3.0	...	1.0 ^A	...	...	...	...	...	0.20	0.20	...	0.05	0.05	0.005	...	0.005	...
C92300	85.0–89.0	7.5–9.0	0.30–1.0	2.5–5.0	...	1.0 ^A	...	...	...	...	...	0.25	0.25	...	0.05	0.05	0.005	...	0.005	...
C92600	86.0–88.5	9.3–10.5	0.8–1.5	1.3–2.5	...	0.7 ^A	...	...	...	...	...	0.20	0.25	...	0.05	0.03	0.005	...	0.005	...
C93200	81.0–85.0	6.3–7.5	6.0–8.0	1.0–4.0	...	1.0 ^A	...	...	...	...	...	0.20	0.35	...	0.08	0.15	0.005	...	0.005	...
C93500	83.0–86.0	4.3–6.0	8.0–10.0	2.0	...	1.0 ^A	...	...	...	...	...	0.20	0.30	...	0.08	0.05	0.005	...	0.005	...
C93700	78.0–82.0	9.0–11.0	8.0–11.0	0.8	...	0.50 ^A	...	...	...	...	...	0.7	0.50	...	0.08	0.10	0.005	...	0.005	...
C93800	75.0–79.0	6.3–7.5	13.0–16.0	0.8	...	1.0 ^A	...	...	...	...	...	0.15	0.8	...	0.08	0.05	0.005	...	0.005	...
C94300	67.0–72.0	4.5–6.0	23.0–27.0	0.8	...	1.0 ^A	...	...	...	...	...	0.15	0.8	...	0.08	0.08	0.005	...	0.005	...
C94700	85.0–90.0	4.5–6.0	0.09 ^B	1.0–2.5	...	4.5–6.0	...	...	...	...	...	0.25	0.15	...	0.05	0.05	0.005	0.20	0.005	...
C94800	84.0–89.0	4.5–6.0	0.30–1.0	1.0–2.5	...	4.5–6.0	...	...	...	...	...	0.25	0.15	...	0.05	0.05	0.005	0.20	0.005	...
C94900	79.0–81.0	4.0–6.0	4.0–6.0	4.0–6.0	...	4.0–6.0	...	...	...	...	...	0.30	0.25	...	0.08	0.05	0.005	0.10	0.005	...
C95200	86.0 min	...	...	...	2.5–4.0	...	8.5–9.5	...	...	...	...	...	...	...	...	...	...	...	...	...
C95300	86.0 min	...	...	...	0.8–1.5	...	9.0–11.0	...	...	...	...	...	...	...	...	...	...	...	...	...
C95400	83.0 min	...	...	...	3.0–5.0	1.5	10.0–11.5	0.50	...	...	...	...	...	...	...	...	...	...	...	...
C95410	83.0 min	...	...	...	3.0–5.0	1.5–2.5	10.0–11.5	0.50	...	...	...	...	...	...	...	...	...	...	...	...
C95500	78.0 min	...	...	...	3.0–5.0	3.0–5.5	10.0–11.5	3.5	...	...	...	...	...	...	...	...	...	...	...	...
C95600	88.0 min	...	...	...	...	0.25	6.0–8.0	...	1.8–3.2	...	...	...	...	...	...	...	...	...	...	...
C95800	79.0 min	...	0.03	...	3.5–4.5 ^C	4.0–5.0 ^C	8.5–9.5	0.8–1.5	...	...	...	...	...	...	...	...	...	...	0.10	...
C97300	53.0–58.0	1.5–3.0	8.0–11.0	17.0–25.0	1.5	11.0–14.0	...	...	...	...	...	...	0.35	...	0.08	0.05	0.005	0.50	0.15	...
C97600	63.0–67.0	3.5–4.5	3.0–5.0	3.0–9.0	1.5	19.0–21.5	...	...	...	...	...	...	0.25	...	0.08	0.05	0.005	1.0	0.15	...
C97800	64.0–67.0	4.0–5.5	1.0–2.5	1.0–4.0	1.5	24.0–27.0	...	...	...	...	...	...	0.20	...	0.08	0.05	0.005	1.0	0.15	...
C99400	remainder	...	0.09	0.5–5.0	1.0–3.0	1.0–3.5	0.5–2.0	0.50	0.5–2.0	...	...	...	...	...	...	...	...	...	...	...
C99500	remainder	...	0.09	0.5–2.0	3.0–5.0	3.5–5.5	0.5–2.0	0.50	0.5–2.0	...	...	...	...	...	...	...	...	...	...	...

^A In determining copper minimum copper may be calculated as copper plus nickel.^B It is possible that the mechanical requirements of Copper Alloy UNS No. C94700 (heat treated) will not be obtained if the lead content exceeds 0.01 %.^C Iron content shall not exceed the nickel content.

TABLE 3 Sum of All Named Elements Analyzed

Copper Alloy UNS No.	Copper Plus Sum on Named Elements, % Min
C83450	99.3
C83800	99.3
C84400	99.3
C84800	99.3
C85200	99.1
C85400	98.9
C85700	98.7
C86200	99.0
C86300	99.0
C86400	99.0
C86500	99.0
C86700	99.0
C87300	99.5
C87400	99.2
C87500	99.5
C87600	99.5
C87610	99.5
C89530	99.5
C89535	99.5
C89844	99.3
C90300	99.4
C90500	99.7
C92300	99.3
C92600	99.3
C93200	99.0
C93500	99.0
C93700	99.0
C93800	99.0
C94300	99.0
C94700	98.7
C94800	98.7
C94900	99.4
C95200	99.0
C95300	99.0
C95400	99.5
C95410	99.5
C95500	99.5
C95600	99.0
C95800	99.5
C97300	99.0
C97600	99.7
C97800	99.6
C99400	99.7
C99500	99.7

6.3 It is recognized that residual elements may be present in cast copper alloys. Analysis shall be made for residual elements only when specified in the purchase order.

7. Mechanical Properties

7.1 Mechanical properties shall be determined from separately cast test bars, and shall conform with the requirements shown in [Table 4](#).

8. Sampling

8.1 Copper Alloy UNS Nos. C86200, C86300, C86400, C86500, C86700, C95200, C95300, C95400, C95410, C95500, C95600, C95800, C99400, and C99500 test bar castings shall be cast to the form and dimensions shown in Figs. 1 or 2 of Practice [B 208](#). For all other alloys listed in this specification test bars shall be cast to the form and dimensions shown in Figs. 2, 3 or 4 of Practice [B 208](#).

9. Test Methods

9.1 Analytical chemical methods are given in Specification [B 824](#) (Test Methods section).

9.2 Brinell hardness readings, if specified on the purchase order, shall be taken in the grip end of the tension test bar and shall be made in accordance with Test Method [E 10](#), except that a 3000-kg load shall be used.

10. Casting Repair

10.1 Copper Alloy UNS Nos. C95200, C95300, C95400, C95410, C95500, C95600, and C95800 included in this specification are generally weldable. Weld repairs may be made at the manufacturer's discretion provided each excavation does not exceed 20 % of the casting section or wall thickness or 4 % of the casting surface area.

10.2 Excavations that exceed those described in [10.1](#) may be made at the manufacturer's discretion except that when specified in the ordering information ([4.2.3](#)), the weld procedure shall be approved by the purchaser and the following records shall be maintained:

- 10.2.1 A sketch or drawing showing the dimensions, depth, and location of excavations,
- 10.2.2 Post-weld heat treatment, when applicable,
- 10.2.3 Weld repair inspection results,
- 10.2.4 Casting identification number,
- 10.2.5 Weld procedure identification number,
- 10.2.6 Welder identification, and
- 10.2.7 Name of inspector.

10.3 The casting shall not be impregnated without approval of the purchaser.

10.4 The castings shall not be plugged.

10.5 Other Copper Alloy UNS Numbers in this specification are not weldable.

11. Keywords

11.1 copper alloy castings; copper-base alloy castings; valve castings

TABLE 4 Mechanical Requirements

Copper Alloy UNS No.	Tensile Strength, min		Yield Strength, ^A min		Elongation in 2 in. (50 mm), min, %	Brinell Hardness No. ^B (3000-kg Load), min
	ksi ^C	MPa ^{B,D}	ksi ^C	MPa ^{B,D}		
C83450	30	207	14	97	25	...
C83800	30	207	13	90	20	...
C84400	29	200	13	90	18	...
C84800	28	193	12	83	16	...
C85200	35	241	12	83	25	...
C85400	30	207	11	76	20	...
C85700	40	276	14	97	15	...
C86200	90	621	45	310	18	...
C86300	110	758	60	414	12	...
C86400	60	414	20	138	15	...
C86500	65	448	25	172	20	...
C86700	80	552	32	221	15	...
C87300	45	310	18	124	20	...
C87400	50	345	21	145	18	...
C87500	60	414	24	165	16	...
C87600	60	414	30	207	16	...
C87610	45	310	18	124	20	...
C89844	28	193	13	90	15	...
C90300	40	276	18	124	20	...
C90500	40	276	18	124	20	...
C92300	36	248	16	110	18	...
C92600	40	276	18	124	20	...
C93200	30	207	14	97	15	...
C93500	28	193	12	83	15	...
C93700	30	207	12	83	15	...
C93800	26	179	14	97	12	...
C94300	24	165	...	...	10	...
C94700	45	310	20	138	25	...
C94700(HT)	75	517	50	345	5	...
C94800	40	276	20	138	20	...
C94900	38	262	15	103	15	...
C95200	65	450	25	170	20	110
C95300	65	450	25	170	20	110
C95300(HT)	80	550	40	275	12	160
C95400	75	515	30	205	12	150
C95400(HT)	90	620	45	310	6	190
C95410	75	515	30	205	12	150
C95410(HT)	90	620	45	310	6	190
C95500	90	620	40	275	6	190
C95500(HT)	110	760	60	415	5	200
C95600	60	415	28	195	10	...
C95800 ^E	85	585	35	240	15	...
C97300	30	207	15	103	8	...
C97600	40	276	17	117	10	...
C97800	50	345	22	152	10	...
C99400	60	414	30	207	20	...
C99500	70	483	40	276	12	...

^A Yield strength shall be determined as the stress producing an elongation under load of 0.5 %, that is 0.01 in. (0.254 mm) in a gage length of 2 in. (50.8 mm).

^B For information only.

^C ksi = 1000 psi.

^D See appendix.

^E As cast or temper annealed.

TABLE 5 Suggested Heat Treatments for Specific Copper Alloys

Copper Alloy UNS No.	Solution Treatment (not less than 1 h followed by water quench), °F (°C)	Annealing Treatment (not less than 2 h followed by air cool), °F (°C)
C95300	1585–1635 (860–890)	1150–1225 (620–660)
C95400		
C95410	1600–1675 (870–910)	1150–1225 (620–660)
C95500	Solution Treatment (not less than 2 h followed by water quench)	Precipitation Hardening (5 h)
C94700	1425–1475 (775–800)	580–620 (305–325)

APPENDIX

(Nonmandatory Information)

X1. METRIC EQUIVALENTS

X1.1 The SI unit for strength properties now shown is in accordance with the International System of Units (SI). The derived SI unit for force is the newton (N), which is defined as that force when applied to a body having a mass of one kilogram gives it an acceleration of one metre per second squared ($N = \text{kg} \cdot \text{m}/\text{s}^2$). The derived SI unit for pressure or

stress is the newton per square metre (N/m^2), which has been named the pascal (Pa) by the General Conference on Weights and Measures. Since $1 \text{ ksi} = 6\,894\,757 \text{ Pa}$ the metric equivalents are expressed as megapascal (MPa) which is the same as MN/m^2 and N/mm^2 .

SUMMARY OF CHANGES

Committee B05 has identified the location of selected changes to this standard since the last issue (B 763 – 08) that may impact the use of this standard. (Approved Oct. 1, 2008.)

- (1) Added UNS Alloy Nos. C89530 and C89535 to **Tables 1-3**. .20 to .09; C87500 from .50 to .09; C87600 from .50 to .09;
- (2) Changed lead level for the following alloys: C87300 from C99400 from .25 to .09; C99500 from .25 to .09.

Committee B05 has identified the location of selected changes to this standard since the last issue (B 763 – 04) that may impact the use of this standard. (Approved April 1, 2008.)

- (1) Revised the lead entries for C87610 and C94700 in **Table 2**.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).