



Standard Specification for Nickel-Chromium-Iron-Molybdenum-Tungsten Alloy (UNS N06920) Plate, Sheet, and Strip¹

This standard is issued under the fixed designation B 814; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ε) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This specification covers nickel-chromium-iron-molybdenum-tungsten alloy UNS N06920 in the form of rolled plate, sheet, and strip for general corrosion service.

1.2 The following products are covered under this specification:

1.2.1 *Sheet and Strip*—Hot or cold rolled, annealed and descaled unless solution-annealing is performed in an atmosphere yielding a bright finish; and

1.2.2 *Plate*—Hot rolled, solution-annealed, and descaled.

1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

B 906 Specification for General Requirements for Flat-Rolled Nickel and Nickel Alloys Plate, Sheet, and Strip

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *plate, n*—material $\frac{3}{16}$ in. (4.76 mm) and over in thickness.

3.1.2 *sheet and strip, n*—material under $\frac{3}{16}$ in. (4.76 mm) in thickness.

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved Dec. 1, 2006. Published January 2007. Originally approved in 1991. Last previous edition approved in 2002 as B 814 – 02.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

TABLE 1 Chemical Requirements

Element	Composition Limits, %
Chromium	20.5–23.0
Iron	17.0–20.0
Molybdenum	8.0–10.0
Tungsten	1.0–3.0
Carbon, max	0.03
Cobalt, max	5.0
Manganese, max	1.0
Phosphorus, max	0.040
Sulfur, max	0.030
Silicon, max	1.0
Nickel	Remainder

4. General Requirements

4.1 Materials furnished under this specification shall conform to the applicable requirements of Specification **B 906** unless otherwise provided herein.

5. Ordering Information

5.1 It is the responsibility of the purchaser to specify all requirements that are necessary for the safe and satisfactory performance of material ordered to this specification. Examples of such requirements include, but are not limited to, the following:

5.1.1 *Alloy*.

5.1.2 *Dimensions*—Thickness (in decimals of an inch), width, and length (inch or fraction of an inch).

5.1.3 *Certification*—State whether a report of test results is required (Specification **B 906**).

5.1.4 *Optional Requirement*—Plate; state how the plate is to be cut (see **8.8.1** and Specification **B 906**, Table A2.3).

5.1.5 *Purchase Inspection*—State which tests or inspections are to be witnessed (Specification **B 906**).

5.1.6 *Samples for Product (Check) Analysis*—State whether samples shall be furnished (Specification **B 906**).

6. Chemical Composition

6.1 The material shall conform to the chemical composition requirements prescribed in **Table 1**.

6.2 If a product (check) analysis is made by the purchaser, the material shall conform to the product (check) analysis variations in accordance with Specification **B 906**.



TABLE 2 Mechanical Property Requirements

Tensile Strength, min, ksi (MPa)	95 (655)
Yield Strength, min, ksi (MPa)	35 (240)
Elongation in 2 in. (50.8 mm) or 4D ^A , min, %	35

^AD refers to the diameter of the tension specimen.

8.4.2 *Sheet and Strip*—Sheet and strip may be ordered to cut lengths, in which case a variation of $\frac{1}{8}$ in. (3.175 mm) over the specified length shall be permitted, with a 0 minus tolerance.

8.5 Straightness:

8.5.1 The edgewise curvature (depth of chord) of flat sheet,

TABLE 3 Permissible Variations in Thickness for Wide Plates^A

Specified Thickness ^B , in. (mm)	Width, in. (mm)			
	Over 48 (1219 mm) to 84 (2134), incl	Over 84 (2134) to 120 (3048), incl	Over 120 (3048) to 144 (3658), incl	Over 144 (3658)
	Tolerance Over Specified Thickness ^C , in. (mm)			
$\frac{3}{8}$ (9.52) to $\frac{1}{4}$ (19.05), excl	0.055 (1.40)	0.060 (1.52)	0.075 (1.90)	0.090 (2.29)
$\frac{1}{4}$ (19.05) to 1 (25.40), excl	0.060 (1.52)	0.065 (1.65)	0.085 (2.16)	0.100 (2.54)
1 (25.40) to 2 (50.80), excl	0.070 (1.78)	0.075 (1.90)	0.095 (2.41)	0.115 (2.92)

^AThickness is measured along the longitudinal edges of the plate at least $\frac{3}{8}$ in. (9.52 mm), but not more than 3 in. (76.20 mm), from the edge.

^BPlates over 2 in. (50.80 mm) thick are produced. Thickness tolerances for such plates are not included.

^CFor circles, the over thickness tolerances in this table apply to the diameter of the circle corresponding to the width ranges shown. For plates of irregular shape, the over thickness tolerances apply to the greatest width corresponding to the width ranges shown. For plates up to 2 in. (50.80 mm), inclusive, in thickness, the tolerance under the specified thickness is 0.010 in. (0.25 mm).

7. Mechanical Properties and Other Requirements

7.1 *Tensile Properties*—The material shall conform to the room temperature tensile properties prescribed in Table 2.

8. Dimensions, Mass, and Permissible Variations

8.1 For the purposes of calculating the weight of the material covered by this specification, a density of 0.303 lb/in.³ (8.39 g/cm³) shall be used.

8.2 Thickness:

8.2.1 *Plate*—The permissible variations in thickness of plate shall be as prescribed in Specification B 906 Table A2.1 and Table 3.

8.2.2 *Sheet and Strip*—The permissible variations in thickness of sheet and strip shall be as prescribed in Specification B 906 Table A2.2. The thickness shall be measured with the micrometer spindle $\frac{3}{8}$ in. (9.525 mm) or more from any edge for material 1 in. (25.4 mm) or over in width and at any place on material under 1 in. (25.4 mm) in width.

8.3 Width:

8.3.1 *Plate*—The permissible variations in width of rectangular plates shall be as prescribed in Specification B 906 Table A2.3.

8.3.2 *Sheet and Strip*—The permissible variations in width for sheet and strip shall be as prescribed in Specification B 906 Table A2.4.

8.4 Length:

8.4.1 *Plate*—Permissible variations in the length of rectangular plate shall be as prescribed in Specification B 906 Table A2.3.

strip, and plate shall not exceed the product of 0.05 in. multiplied by the length in feet (0.04 mm multiplied by the length in centimetres).

8.5.2 Straightness for coiled strip is subject to agreement between the manufacturer and the purchaser.

8.6 *Squareness (Sheet)*—For sheets of all thicknesses and widths of 6 in. (152.4 mm) or more, the angle between adjacent sides shall be $90 \pm 0.15^\circ$ ($\frac{1}{16}$ in. in 24 in. or 2.6 mm/m).

8.7 *Flatness*—Plate, sheet, and strip shall be commercially flat.

8.8 Edges:

8.8.1 Plates shall have sheared, abrasive cut, or plasma-torch-cut edges as specified.

8.8.2 Sheet and strip shall have sheared or slit edges.

9. Product Marking

9.1 Each plate, sheet, or strip shall be marked on one face with the specification number, heat number, manufacturer's identification, and size. The markings shall have no deleterious effect on the material or its performance and shall be sufficiently stable to withstand normal handling.

9.2 Each bundle or shipping container shall be marked with this specification number; the size; gross, tare, and net weight; consignor and consignee address; contract or order number; and such other information as may be defined in the contract or order.

10. Keywords

10.1 plate; sheet; strip; UNS N06920



APPENDIX

(Nonmandatory Information)

X1. HEAT TREATMENT

X1.1 Proper heat treatment during or subsequent to fabrication is necessary for optimum performance, and the manufacturer shall be consulted for details.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).