



Standard Specification for Powder Metallurgy (PM) Boron Stainless Steel Structural Components¹

This standard is issued under the fixed designation B853; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers stainless steel powder metallurgy (PM) structural components with a 7.7-g/cm³ minimum density that are fabricated from prealloyed powder consisting primarily of iron, chromium, nickel, molybdenum, and boron² and are intended for use in corrosive service.

1.2 With the exception of the values for density and the mass used to determine density, for which the use of the gram per cubic centimetre (g/cm³) and gram (g) units is the long-standing industry practice, the values in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

2. Referenced Documents

2.1 ASTM Standards:³

- A262 Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels
- B117 Practice for Operating Salt Spray (Fog) Apparatus
- B243 Terminology of Powder Metallurgy
- B311 Test Method for Density of Powder Metallurgy (PM) Materials Containing Less Than Two Percent Porosity
- E8 Test Methods for Tension Testing of Metallic Materials
- E354 Test Methods for Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys
- E572 Test Method for Analysis of Stainless and Alloy Steels by X-ray Fluorescence Spectrometry
- E1019 Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel, Iron, Nickel, and Cobalt Alloys by Various Combustion and Fusion Techniques

¹ This specification is under the jurisdiction of ASTM Committee B09 on Metal Powders and Metal Powder Products and is the direct responsibility of Subcommittee B09.11 on Near Full Density Powder Metallurgy Materials.

Current edition approved Nov. 15, 2012. Published November 2012. Originally approved in 1994. Last previous edition approved in 2007 as B853 – 07. DOI: 10.1520/B0853-12.

² U.S. Patents 3980444, 4014680, 4032336.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E1086 Test Method for Atomic Emission Vacuum Spectrometric Analysis of Stainless Steel by Point-to-Plane Excitation Technique

G48 Test Methods for Pitting and Crevice Corrosion Resistance of Stainless Steels and Related Alloys by Use of Ferric Chloride Solution

3. Terminology

3.1 *Definitions*—Definitions of powder metallurgy terms can be found in Terminology B243. Additional descriptive information is in the Related Material section of Volume 02.05 of the *Annual Book of ASTM Standards*.

4. Ordering Information

4.1 Orders for components under this specification shall include the following information:

- 4.1.1 Dimensions (see Section 9),
- 4.1.2 Chemical composition (see Section 6, 10.1, and Table 1),
- 4.1.3 Density (see Section 7),
- 4.1.4 Mechanical properties (see Section 8, 10.2, and Table 2),
- 4.1.5 Certification (see Section 13),
- 4.1.6 Reference to the standard.

5. Materials and Manufacture

5.1 Structural components shall be made by cold pressing and sintering prealloyed powder.

5.2 The sintering temperature is dependent on the chemical composition of the powder.

6. Chemical Composition

6.1 The material shall conform to the composition limits specified in Table 1.

6.2 Chemical analysis should be made in accordance with Test Methods E354, E572, E1019, and E1086.

7. Physical Properties

7.1 Density:

- 7.1.1 The sintered density shall be 7.7 g/cm³ minimum.
- 7.1.2 Density shall be determined in accordance with Test Method B311.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Chemical Composition Requirements

Element	Composition Limits, Mass %
Carbon	0.05 max
Manganese	2.00 max
Phosphorus	0.03 max
Sulfur	0.03 max
Silicon	1.0 max
Chromium	22.0 to 24.0
Nickel	17.0 to 19.0
Molybdenum	3.0 to 4.0
Boron	0.20 to 0.50
Nitrogen	0.10 max
Iron ^A	balance

^A Iron shall be determined arithmetically by difference.

TABLE 2 Typical Mechanical Properties^A

0.2 % Offset yield strength	33 000 psi (228 MPa)
Ultimate tensile strength	76 000 psi (520 MPa)
Elongation in one inch	23 %
Apparent Hardness	75 HRB

^A Determined on a cold-pressed and vacuum-sintered standard flat unmachined test specimen for powder metallurgy (PM) products (see Test Methods E8).

8. Mechanical Properties

8.1 The purchaser and manufacturer shall agree upon the method to be used to verify the typical yield or tensile strength in the finished parts. The preferred method for verifying the tensile or yield strength is for the manufacturer and purchaser to agree upon a qualification test to be performed on the actual part. The specific test should be determined after consideration of the function of the part. An example would be measuring the force needed to break teeth off a gear, using a prescribed fixture.

8.2 The tensile properties of the material may also be verified using specifically prepared bars, compacted from the same mixed powder lot as the purchased parts, and sintered along with the parts.

8.3 Typical tensile values for 0.2 % offset yield strength, ultimate strength, and percent elongation in 1-in. gage length for as-sintered standard flat unmachined tension test specimens for powder metallurgy (PM) products (see Test Methods E8) are in Table 2.

9. Dimensions and Tolerances

9.1 Dimensions and tolerances of the structural components shall be indicated on drawings accompanying the purchase order or contract.

10. Sampling

10.1 *Chemical Analysis*—If required by purchase agreement, at least one sample for chemical analysis shall be taken from each lot. A representative sample of chips may be obtained by dry-milling, drilling, or crushing at least two pieces without lubrication using clean dry tools.

10.2 *Mechanical Testing*—If required by the purchase agreement, the manufacturer and purchaser shall mutually agree on the number of specimens for mechanical testing from each lot. This number shall be based on good practice of statistical quality control.

11. Inspection

11.1 Unless otherwise specified, inspection of components supplied on contract shall be made by the purchaser.

12. Rejection and Rehearing

12.1 Components that fail to conform to the requirements of this specification may be rejected. Rejection shall be reported to the producer or supplier promptly and in writing. In case of dissatisfaction with test results, the producer or supplier may make a claim for rehearing.

13. Certification

13.1 When specified in the purchase order or contract, a producer's certification of compliance document shall be reported to the purchaser, verifying that the components manufactured were sampled, tested, and inspected in accordance with this specification and have met the requirements. When specified in the purchase order or contract, a report of test results shall be furnished.

13.2 Certification by an independent third party indicating conformance to the requirements of this specification may be considered upon the request of the purchaser.

13.3 The purchase order or contract shall specify whether or not the certification includes a report of chemical analysis.

14. Keywords

14.1 cold pressing; density; powder metallurgy (PM); pre-alloyed powder; sintering; stainless steel; structural (PM) components

**SUPPLEMENTARY REQUIREMENTS**

The following supplementary requirements shall apply only when specified by the purchaser in the inquiry, contract, or order. The supplier and the purchaser should agree upon a minimum number of hours survival for the requested corrosion test.

S1. Intergranular Corrosion Test

S1.1 When specified, material shall pass intergranular corrosion tests conducted by the manufacturer in accordance with Practices **A262**.

S2. Salt Spray (Fog) Testing

S2.1 When specified, material shall pass the salt spray corrosion test conducted by the manufacturer in accordance with Practice **B117**.

S3. Pitting and Crevice Corrosion Test

S3.1 When specified, material shall pass pitting and crevice corrosion tests conducted by the manufacturer in accordance with Test Methods **G48**.

SUMMARY OF CHANGES

Committee B09 has identified the location of selected changes to this standard since the last issue (B853-07) that may impact the use of this standard.

(1) Changed the statement on units in Section 1.2.

(2) Removed the reference to IEEE/ASTM SI 10 from Section 2.1.

(3) Deleted the word "representative" from section 10.2.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).