



# Standard Specification for Metal Injection Molding (MIM) Ferrous Materials<sup>1</sup>

This standard is issued under the fixed designation B883; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

<sup>ε</sup><sup>1</sup> NOTE—Footnotes were editorially added to Tables 2–6 in May 2013.

## 1. Scope

1.1 This specification covers ferrous metal injection molded materials fabricated by mixing elemental or pre-alloyed metal powders with binders, injecting into a mold, debinding, and sintering, with or without subsequent heat treatment.

1.2 This specification covers the following injection molded materials.

### 1.2.1 Compositions:

- 1.2.1.1 MIM-2200, low-alloy steel
- 1.2.1.2 MIM-2700, low-alloy steel
- 1.2.1.3 MIM-4605, low-alloy steel
- 1.2.1.4 MIM-4140, low-alloy steel
- 1.2.1.5 MIM-316L, austenitic stainless steel
- 1.2.1.6 MIM-17-4 PH, precipitation hardening stainless steel
- 1.2.1.7 MIM-420, ferritic stainless steel
- 1.2.1.8 MIM-430L, ferritic stainless steel

1.3 Chemical composition limits are specified in [Table 1](#).

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

- [B243](#) Terminology of Powder Metallurgy
- [B311](#) Test Method for Density of Powder Metallurgy (PM) Materials Containing Less Than Two Percent Porosity
- [B933](#) Test Method for Microindentation Hardness of Powder Metallurgy (PM) Materials
- [B962](#) Test Methods for Density of Compacted or Sintered Powder Metallurgy (PM) Products Using Archimedes' Principle
- [E8](#) Test Methods for Tension Testing of Metallic Materials
- [E18](#) Test Methods for Rockwell Hardness of Metallic Materials

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B09 on Metal Powders and Metal Powder Products and is the direct responsibility of B09.11 on Near Full Density Powder Metallurgy Materials.

Current edition approved Dec. 1, 2010. Published March 2011. Originally approved in 1997. Last previous edition approved in 2010 as B883 – 10. DOI: 10.1520/B0883-10E01.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[E350](#) Test Methods for Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

[E415](#) Test Method for Analysis of Carbon and Low-Alloy Steel by Spark Atomic Emission Spectrometry

[E1019](#) Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel, Iron, Nickel, and Cobalt Alloys by Various Combustion and Fusion Techniques

[E1086](#) Test Method for Analysis of Austenitic Stainless Steel by Spark Atomic Emission Spectrometry

[E1621](#) Guide for Elemental Analysis by Wavelength Dispersive X-Ray Fluorescence Spectrometry

[F1089](#) Test Method for Corrosion of Surgical Instruments

### 2.2 MPIF Standards:<sup>3</sup>

[MPIF Standard 35](#) Material Standards for Metal Injection Molded Parts

[MPIF Standard 50](#) Method for Preparing and Evaluating Metal Injection Molded (MIM) Debound and Sintered/Heat Treated Tension Test Specimens

[MPIF Standard 51](#) Method for Determination of Microindentation Hardness of Powder Metallurgy Materials

[MPIF Standard 59](#) Method for Determination of Charpy Impact Energy of Unnotched Metal Injection Molded (MIM) Test Specimens

[MPIF Standard 62](#) Method for Determination of the Corrosion Resistance of MIM Grades of Stainless Steel Immersed in 2 % Sulfuric Acid Solution

[MPIF Standard 63](#) Method for Density Determination of Metal Injection Molded (MIM) Components (Gas Pycnometer)

## 3. Terminology

### 3.1 Definitions:

3.1.1 Definitions of powder metallurgy terms can be found in Terminology [B243](#). Additional descriptive information is available in the Related Material Section of Vol. 02.05 of the Annual Book of ASTM Standards.

<sup>3</sup> Available from Metal Powder Industries Federation (MPIF), 105 College Rd. East, Princeton, NJ 08540-6692, <http://www.mpif.org>.

## 4. Ordering Information

4.1 Orders for parts conforming to this specification may include the following:

- 4.1.1 ASTM designation,
- 4.1.2 Alloy composition including carbon content (see Table 1),
- 4.1.3 Heat treatment condition and hardness (see Tables 2-5),
- 4.1.4 Functional or mechanical property testing (see 7.3 – 7.7 and Tables 2-5),
- 4.1.5 Corrosion resistance testing (see 8.1 – 8.1.4 and Table 6),
- 4.1.6 Purchaser or purchaser's representative desire to witness the inspection and testing of material prior to shipment (see 10.2),
- 4.1.7 Requirement for certification of material and a report of test results (see 12.1),
- 4.1.8 Requirement for full or partial chemical analysis (see Section 6), and
- 4.1.9 Other special requirements as mutually agreed.

## 5. Materials and Manufacture

5.1 Parts shall be made by injection molding mixtures of metal powder with binders, debinding, and sintering, with or without subsequent heat treatment. The material shall conform to the designations in 1.2.1 and meet the chemical composition specified in Table 1.

## 6. Chemical Composition

6.1 Metal injection molded material shall conform to the chemical requirements prescribed in Table 1.

6.2 Chemical analysis for the elements copper, chromium, molybdenum, and nickel shall be determined in accordance with Test Methods E415 (preferred method), E350, E1086, E1621, Inductively Coupled Plasma–Atomic Emission Spectrometry (ICP-AES), Atomic Absorption (AA), or any such method as shall be agreed upon between buyer and seller. Analysis of the element carbon shall be determined in accordance with Test Methods E1019, via optical emission spectroscopy, or other method agreed upon between the purchaser and seller.

## 7. Mechanical and Physical Property Requirements

7.1 The preferred method of verifying the acceptable performance of a finished part is a qualification test to be performed on an actual part. The specific test should be determined following consideration of the function of the part, and should be agreed upon between manufacturer and purchaser.

7.2 Mandatory and typical mechanical properties of materials covered by this specification are shown in Tables 2-5.

### 7.3 Tensile Properties:

7.3.1 The tensile properties of MIM materials shall be measured using test specimens prepared and evaluated in accordance with MPIF Standard 50.

7.3.2 *Tensile Test Method*—When requested in the purchase order, tensile specimens shall be prepared and processed along

with production parts. Tensile specimens shall be tested in accordance with Test Methods E8. Yield strength shall be determined by the 0.2% offset method. MPIF Standard 50 governs the manufacture of the test bars, while Test Methods E8 governs the testing procedure.

### 7.4 Impact Energy Properties:

7.4.1 Typical impact energy properties of materials covered by this specification are shown in Tables 2-5.

7.4.2 The impact energy properties of MIM materials shall be measured using test specimens prepared and evaluated in accordance with MPIF Standard 59.

7.4.3 *Impact Energy Test Method*—When requested in the purchase order, impact energy specimens shall be prepared and processed along with production parts.

### 7.5 Density:

7.5.1 The density of MIM materials shall be measured in accordance with Test Method B311 or MPIF Standard 63. If a test specimen gains mass when immersed in water, it shall be tested in accordance with Test Method B962.

7.6 *Apparent Hardness*—The apparent hardness of MIM materials shall be measured in accordance with Test Methods E18.

7.7 *Microindentation Hardness*—The microindentation hardness of MIM materials shall be measured in accordance with Test Method B933 or MPIF Standard 51.

## 8. Corrosion Resistance Requirements

### 8.1 Corrosion Resistance:

8.1.1 The preferred method of verifying the acceptable performance of a finished part is a qualification test to be performed on an actual part. The specific test should be determined following consideration of the function of the part, and should be agreed upon between manufacturer and purchaser.

8.1.2 Typical corrosion resistance of materials covered by this specification is shown in Table 6.

8.1.3 The corrosion resistance of MIM materials shall be measured using test specimens prepared in accordance with MPIF Standard 59.

8.1.4 *Corrosion Resistance Test Method*—When requested in the purchase order, corrosion resistance specimens shall be prepared and processed along with production parts. MPIF Standard 59 governs the manufacture of specimens, but Test Method F1089 governs corrosion resistance testing for copper sulfate and boiling water. MPIF Standard 62 governs corrosion resistance testing for sulfuric acid.

## 9. Sampling

9.1 *Lot*—Unless otherwise specified, a lot is a quantity of product produced under similar conditions so that the product within the lot is expected to be homogeneous in all significant attributes and submitted for inspection at one time.

9.2 *Testing*—The manufacturer and purchaser shall mutually agree upon the number of specimens to represent the lot for qualification, chemical, mechanical, or corrosion resistance property testing.

## 10. Inspection

10.1 Inspection of the parts supplied under this specification shall be the responsibility of the manufacturer or a mutually agreed upon third party.

10.2 If the purchaser desires that a representative witness the inspection and testing of the material prior to shipment, such a requirement shall be part of the purchase order.

## 11. Rejection

11.1 Parts that fail to conform to the requirements of this specification may be rejected. Rejection should be reported to the manufacturer or supplier promptly and in writing.

## 12. Certification

12.1 When specified in the purchase order, a manufacturer's certification shall be furnished to the purchaser that the parts

were manufactured, samples tested, and inspected in accordance with this specification and found to meet its requirements. When specified in the purchase order, a report of the test results shall be furnished.

## 13. Keywords

13.1 corrosion resistance; low-alloy steels; mechanical properties; metal injection molded parts; metal injection molded steels; metal injection molding (MIM); metal powders; MIM; PIM; powder injection molding; sintered steels; stainless steels; unnotched Charpy impact energy

**TABLE 1 Chemical Composition Requirements For Metal Injection Molded Materials**

| Material Designation |      | Fe   | Ni  | Cr   | Co | Mo  | C    | Cu | Si  | Mn  | Nb + Ta | V | Other |
|----------------------|------|------|-----|------|----|-----|------|----|-----|-----|---------|---|-------|
| MIM-2200             | Min. | Bal. | 1.5 | -    | -  | -   | -    | -  | -   | -   | -       | - | -     |
|                      | Max. | Bal. | 2.5 | -    | -  | 0.5 | 0.1  | -  | 1.0 | -   | -       | - | 1.0   |
| MIM-2700             | Min. | Bal. | 6.5 | -    | -  | -   | -    | -  | -   | -   | -       | - | -     |
|                      | Max. | Bal. | 8.5 | -    | -  | 0.5 | 0.1  | -  | 1.0 | -   | -       | - | 1.0   |
| MIM-4605             | Min. | Bal. | 1.5 | -    | -  | 0.2 | 0.4  | -  | -   | -   | -       | - | -     |
|                      | Max. | Bal. | 2.5 | -    | -  | 0.5 | 0.6  | -  | 1.0 | -   | -       | - | 1.0   |
| MIM-4140             | Min. | Bal. | -   | 0.8  | -  | 0.2 | 0.3  | -  | -   | -   | -       | - | -     |
|                      | Max. | Bal. | -   | 1.2  | -  | 0.3 | 0.5  | -  | 0.6 | 1.0 | -       | - | 1.0   |
| MIM-316L             | Min. | Bal. | 10  | 16   | -  | 2   | -    | -  | -   | -   | -       | - | -     |
|                      | Max. | Bal. | 14  | 18   | -  | 3   | 0.03 | -  | 1.0 | 2.0 | -       | - | 1.0   |
| MIM-420              | Min. | Bal. | -   | 12   | -  | -   | 0.15 | -  | -   | -   | -       | - | -     |
|                      | Max. | Bal. | -   | 14   | -  | -   | 0.4  | -  | 1.0 | 1.0 | -       | - | 1.0   |
| MIM-430L             | Min. | Bal. | -   | 16   | -  | -   | -    | -  | -   | -   | -       | - | -     |
|                      | Max. | Bal. | -   | 18   | -  | -   | 0.05 | -  | 1.0 | 1.0 | -       | - | 1.0   |
| MIM-17-4PH           | Min. | Bal. | 3   | 15.5 | -  | -   | -    | 3  | -   | -   | 0.15    | - | -     |
|                      | Max. | Bal. | 5   | 17.5 | -  | -   | 0.07 | 5  | 1.0 | 1.0 | 0.45    | - | 1.0   |

**TABLE 2 Mandatory and Typical Mechanical and Physical Properties of Metal Injection Molded Low-Alloy Steels<sup>A</sup>**  
**Inch-Pound Units**

| Material Designation                                | Minimum Mandatory Values<br>Tensile Properties |                     |                        | Typical Values<br>Tensile Properties |                     |                        | Elastic Constants   |                    | Density<br><br>g/cm <sup>3</sup> | Typical Values<br>Hardness |                                   | Unnotched<br>Charpy<br>Impact<br>Energy <sup>B</sup><br><br>ft-lbf |
|-----------------------------------------------------|------------------------------------------------|---------------------|------------------------|--------------------------------------|---------------------|------------------------|---------------------|--------------------|----------------------------------|----------------------------|-----------------------------------|--------------------------------------------------------------------|
|                                                     | Ultimate<br>Strength                           | Yield<br>Strength   | Elongation<br>in 1 in. | Ultimate<br>Strength                 | Yield<br>Strength   | Elongation<br>in 1 in. | Young's<br>Modulus  | Poisson's<br>Ratio |                                  | Macro<br>(apparent)        | Micro<br>(converted) <sup>C</sup> |                                                                    |
|                                                     | 10 <sup>3</sup> psi                            | 10 <sup>3</sup> psi | %                      | 10 <sup>3</sup> psi                  | 10 <sup>3</sup> psi | %                      | 10 <sup>6</sup> psi |                    |                                  | Rockwell                   |                                   |                                                                    |
| MIM-2200<br>(as-sintered)                           | 37                                             | 16                  | 20                     | 42                                   | 18                  | 40                     | 28                  | 0.28               | 7.6                              | 45 HRB                     | N/D                               | 100                                                                |
| MIM-2700<br>(as-sintered)                           | 55                                             | 30                  | 20                     | 60                                   | 37                  | 26                     | 28                  | 0.28               | 7.6                              | 69 HRB                     | N/D                               | 130                                                                |
| MIM-4605<br>(as-sintered)                           | 55                                             | 25                  | 11                     | 64                                   | 30                  | 15                     | 29                  | 0.28               | 7.5                              | 62 HRB                     | N/D                               | 50                                                                 |
| MIM-4605 <sup>D</sup><br>(quenched and<br>tempered) | 215                                            | 190                 | ≤1                     | 240                                  | 215                 | 2                      | 29.5                | 0.28               | 7.5                              | 48 HRC                     | 55 HRC                            | 40                                                                 |
| MIM-4140<br>(quenched and<br>tempered)              | 200                                            | 155                 | 3                      | 240                                  | 180                 | 5                      | 29.5                | 0.28               | 7.5                              | 46 HRC                     | N/D                               | 55                                                                 |

<sup>A</sup> Reprinted by permission from MPIF Standard 35, "Materials Standard for Metal Injection Molded Parts," 2007, Metal Powder Industries Federation, 105 College Road East, Princeton, NJ 08540-6692.

<sup>B</sup> MPIF Standard 59 specimens are 0.197 × 0.394 × 2.155 in. The results were not normalized to 0.394 × 0.394 × 2.165 in. since this would have resulted in higher impact energy values.

<sup>C</sup> N/D indicates a value was not determined for the purpose of this standard.

<sup>D</sup> These data were measured on test bars tempered for 1 h at 350°F.

**TABLE 3 Mandatory and Typical Mechanical and Physical Properties of Metal Injection Molded Low-Alloy Steels<sup>A</sup>**  
**SI Units**

| Material Designation                                | Minimum Mandatory Values<br>Tensile Properties |                   |                          | Typical Values<br>Tensile Properties |                   |                          | Elastic Constants  |                    | Density<br><br>g/cm <sup>3</sup> | Typical Values<br>Hardness |                                   | Unnotched<br>Charpy<br>Impact<br>Energy <sup>B</sup><br><br>J |
|-----------------------------------------------------|------------------------------------------------|-------------------|--------------------------|--------------------------------------|-------------------|--------------------------|--------------------|--------------------|----------------------------------|----------------------------|-----------------------------------|---------------------------------------------------------------|
|                                                     | Ultimate<br>Strength                           | Yield<br>Strength | Elongation<br>in 25.4 mm | Ultimate<br>Strength                 | Yield<br>Strength | Elongation<br>in 25.4 mm | Young's<br>Modulus | Poisson's<br>Ratio |                                  | Macro<br>(apparent)        | Micro<br>(converted) <sup>C</sup> |                                                               |
|                                                     | MPa                                            | MPa               | %                        | MPa                                  | MPa               | %                        | GPa                |                    |                                  | Rockwell                   |                                   |                                                               |
| MIM-2200<br>(as-sintered)                           | 255                                            | 110               | 20                       | 290                                  | 125               | 40                       | 190                | 0.28               | 7.65                             | 45 HRB                     | N/D                               | 135                                                           |
| MIM-2700<br>(as-sintered)                           | 380                                            | 205               | 20                       | 415                                  | 255               | 26                       | 190                | 0.28               | 7.6                              | 69 HRB                     | N/D                               | 175                                                           |
| MIM-4605<br>(as-sintered)                           | 380                                            | 170               | 11                       | 440                                  | 205               | 15                       | 200                | 0.28               | 7.5                              | 62 HRB                     | N/D                               | 70                                                            |
| MIM-4605 <sup>D</sup><br>(quenched and<br>tempered) | 1480                                           | 1310              | <1                       | 1655                                 | 1480              | 2                        | 205                | 0.28               | 7.5                              | 48 HRC                     | 55 HRC                            | 55                                                            |
| MIM-4140<br>(quenched and<br>tempered)              | 1380                                           | 1070              | 3                        | 1650                                 | 1240              | 5                        | 205                | 0.28               | 7.5                              | 46 HRC                     | N/D                               | 75                                                            |

<sup>A</sup> Reprinted by permission from MPIF Standard 35, "Materials Standards for Metal Injection Molded Parts," 2007, Metal Powder Industries Federation, 105 College Road East, Princeton, NJ 08540-6692. SI values converted from inch-pound units in Table 2.

<sup>B</sup> MPIF Standard 59 specimens are 5 × 10 × 55 mm. The results were not normalized to 10 × 10 × 55 mm since this would have resulted in higher impact energy values.

<sup>C</sup> N/D indicates a value was not determined for the purpose of this standard.

<sup>D</sup> These data were measured on test bars tempered for 1 h at 177°C.

**TABLE 4 Mandatory and Typical Mechanical and Physical Properties of Metal Injection Molded Stainless Steels<sup>A</sup>**  
**Inch-Pound Units**

| Material Designation                    | Minimum Mandatory Values<br>Tensile Properties |                                       |                          | Typical Values<br>Tensile Properties     |                                       |                          | Elastic Constants                       |                 | Density | Typical Values<br>Hardness   |                                            | Unnotched Charpy Impact Energy <sup>B</sup><br>ft-lbf |
|-----------------------------------------|------------------------------------------------|---------------------------------------|--------------------------|------------------------------------------|---------------------------------------|--------------------------|-----------------------------------------|-----------------|---------|------------------------------|--------------------------------------------|-------------------------------------------------------|
|                                         | Ultimate Strength<br>10 <sup>3</sup> psi       | Yield Strength<br>10 <sup>3</sup> psi | Elongation in 1 in.<br>% | Ultimate Strength<br>10 <sup>3</sup> psi | Yield Strength<br>10 <sup>3</sup> psi | Elongation in 1 in.<br>% | Young's Modulus<br>10 <sup>10</sup> psi | Poisson's Ratio |         | Macro (apparent)<br>Rockwell | Micro (converted) <sup>C</sup><br>Rockwell |                                                       |
| MIM-316L (as-sintered)                  | 65                                             | 20                                    | 40                       | 75                                       | 25                                    | 50                       | 28                                      | 0.28            | 7.6     | 67 HRB                       | N/D                                        | 140                                                   |
| MIM-420 <sup>D</sup> (heat treated)     | 180                                            | <sup>E</sup>                          | <sup>F</sup>             | 200                                      | 174                                   | <1                       | 28                                      | 0.30            | 7.4     | 44 HRC                       | 50 HRC                                     | 30                                                    |
| MIMI-430L (as-sintered)                 | 50                                             | 30                                    | 20                       | 60                                       | 35                                    | 25                       | 30                                      | 0.29            | 7.5     | 65 HRB                       | N/D                                        | 110                                                   |
| MIM-17-4 PH (as-sintered)               | 115                                            | 94                                    | 4                        | 130                                      | 106                                   | 6                        | 28                                      | 0.29            | 7.5     | 27 HRC                       | N/D                                        | 100                                                   |
| MIM-17-4 PH <sup>G</sup> (heat treated) | 155                                            | 140                                   | 4                        | 172                                      | 158                                   | 6                        | 28                                      | 0.29            | 7.5     | 33 HRC                       | 40 HRC                                     | 100                                                   |

<sup>A</sup> Reprinted by permission from MPIF Standard 35, "Materials Standards for Metal Injection Molded Parts," 2007, Metal Powder Industries Federation, 105 College Road East, Princeton, NJ 08540-6692.

<sup>B</sup> MPIF Standard 59 specimens are 0.197 × 0.394 × 2.165 in. The results were not normalized to 0.394 × 0.394 × 2.165 in. since this would have resulted in higher impact energy values.

<sup>C</sup> N/D indicates a value was not determined for the purpose of this standard.

<sup>D</sup> Heat treated MIM-420 parts were austenitized and tempered at 400°F (204°C) for a minimum of 1 hour.

<sup>E</sup> Heat Treated MIM-420 may not show any yield point based on a 0.2 % offset.

<sup>F</sup> There may be no measurable elongation for the MIM-420 heat treated material.

<sup>G</sup> These data were measured on test bars aged at 900°F (heat treated to H900).

**TABLE 5 Mandatory and Typical Mechanical and Physical Properties of Metal Injection Molded Stainless Steels<sup>A</sup>**  
**SI Units**

| Material Designation                    | Minimum Mandatory Values<br>Tensile Properties |                       |                            | Typical Values<br>Tensile Properties |                       |                            | Elastic Constants      |                 | Density | Typical Values<br>Hardness   |                                            | Unnotched Charpy Impact Energy <sup>B</sup><br>J |
|-----------------------------------------|------------------------------------------------|-----------------------|----------------------------|--------------------------------------|-----------------------|----------------------------|------------------------|-----------------|---------|------------------------------|--------------------------------------------|--------------------------------------------------|
|                                         | Ultimate Strength<br>MPa                       | Yield Strength<br>MPa | Elongation in 25.4 mm<br>% | Ultimate Strength<br>MPa             | Yield Strength<br>MPa | Elongation in 25.4 mm<br>% | Young's Modulus<br>GPa | Poisson's Ratio |         | Macro (apparent)<br>Rockwell | Micro (converted) <sup>C</sup><br>Rockwell |                                                  |
| MIM-316L                                | 450                                            | 140                   | 40                         | 520                                  | 175                   | 50                         | 190                    | 0.28            | 7.6     | 67 HRB                       | N/D                                        | 190                                              |
| MIM-420 <sup>D</sup> (heat treated)     | 1240                                           | <sup>E</sup>          | <sup>F</sup>               | 1380                                 | 1200                  | <1                         | 190                    | 0.30            | 7.4     | 44 HRC                       | 50 HRC                                     | 40                                               |
| MIM-430L                                | 345                                            | 205                   | 20                         | 415                                  | 240                   | 25                         | 210                    | 0.29            | 7.5     | 65 HRB                       | N/D                                        | <sup>E</sup>                                     |
| MIM-17-4 PH                             | 795                                            | 650                   | 4                          | 900                                  | 730                   | 6                          | 190                    | 0.29            | 7.5     | 27 HRC                       | N/D                                        | 70                                               |
| MIM-17-4 PH <sup>G</sup> (heat treated) | 1070                                           | 965                   | 4                          | 1185                                 | 1090                  | 6                          | 190                    | 0.29            | 7.5     | 33 HRC                       | 40 HRC                                     | <sup>E</sup>                                     |

<sup>A</sup> Reprinted by permission from MPIF Standard 35, "Materials Standards for Metal Injection Molded Parts," 2007 Metal Powder Industries Federation, 105 College Road East, Princeton, NJ 08540-6692. SI values converted from inch-pound units in Table 4.

<sup>B</sup> MPIF Standard 59 specimens are 5 × 10 × 55 mm. The results were not normalized to 10 × 10 × 55 mm since this would have resulted in higher impact energy values.

<sup>C</sup> N/D indicates a value was not determined for the purpose of this standard.

<sup>D</sup> Heat treated MIM-420 parts were austenitized and tempered at 400°F (204°C) for a minimum of 1 hour.

<sup>E</sup> Heat Treated MIM-420 may not show any yield point based on a 0.2 % offset.

<sup>F</sup> There may be no measurable elongation for the MIM-420 heat treated material.

<sup>G</sup> These data were measured on test bars aged at 482°C (heat treated to H900).

**TABLE 6 Typical Corrosion Resistance Properties of Metal Injection Molded Stainless Steels<sup>A</sup>**  
**SI Units**

| Material Designation                    | H <sub>2</sub> SO <sub>4</sub> <sup>B</sup><br>g/dm <sup>2</sup> /day | Typical Values<br>CUSO <sub>4</sub> | Boil Test in H <sub>2</sub> O |
|-----------------------------------------|-----------------------------------------------------------------------|-------------------------------------|-------------------------------|
|                                         |                                                                       |                                     |                               |
| MIM-316L (as-sintered)                  | <0.005<br><sup>C</sup>                                                | Pass<br><sup>C</sup>                | Pass<br><sup>C</sup>          |
| MIM-430L (as-sintered)                  |                                                                       |                                     |                               |
| MIM-17-4 PH (as-sintered)               | <0.005                                                                | Pass                                | Pass                          |
| MIM-17-4 PH <sup>D</sup> (heat treated) | <0.005                                                                | Pass                                | Pass                          |

<sup>A</sup> Reprinted by permission from MPIF Standard 35, "Materials Standards for Metal Injection Molded Parts," 2007 Metal Powder Industries Federation, 105 College Road East, Princeton, NJ 08540-6692.

<sup>B</sup> MPIF Standard 59 test specimens were tested in 2 % H<sub>2</sub>SO<sub>4</sub> for 1000 h at 22°C ± 2°C. These test specimens were tested in accordance with MPIF Standard 62.

<sup>C</sup> Additional data will appear in subsequent editions of this specification.

<sup>D</sup> These data were measured on test bars aged at 482°C (heat treated to H900).

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*