



Standard Test Method for Determination of Coercivity (H_{cs}) of Cemented Carbides¹

This standard is issued under the fixed designation B 887; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

ε¹ NOTE—The units statement in subsection 1.2 was corrected editorially in April 2008.

1. Scope

1.1 This test method covers the determination of magnetization coercivity (H_{cs}) of cemented carbide materials and products using coercive force instrumentation. It is patterned after ISO 3326.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

A 340 Terminology of Symbols and Definitions Relating to Magnetic Testing

B 243 Terminology of Powder Metallurgy

2.2 ISO Standard:³

ISO 3326 Hardmetals - Determination of (the Magnetization) Coercivity

3. Terminology

3.1 Definitions:

3.1.1 For definition of terms used in this procedure refer to Terminology A 340 and Terminology B 243.

3.1.2 *dc*—direct current.

4. Summary of Test Method

4.1 A test sample is positioned in the dc magnetic field of the test apparatus and magnetized to technical saturation. The magnetic field polarity is then reversed and the test sample is demagnetized by increasing the energy of the reversed magnetic field until the test sample reaches zero magnetism. The coercive force (H_c) is the magnetizing force required to return the saturated magnetic induction to zero.

5. Significance and Use

5.1 Measurement of coercivity provides a relative comparison of carbide grain size, binder content, and possibly carbon deficiency for a given graded carbide material or product, and may be employed as a non-destructive measurement indicating deviation from a specified norm.

5.2 This test method allows the non-destructive estimate of average carbide grain size in sintered cemented carbide hardmetals. It is appropriate for a wide range of compositions and tungsten carbide (WC) WC grain sizes, and can be used for acceptance of material or product to specification.

6. Interferences

6.1 H_{cs} measurement is a non-destructive “bulk” measurement that is averaged over the specimen volume. Bi-modal grain size distributions will give approximately the same H_c value as would be obtained from a normal grain size distribution about the same mean value.

6.2 Large test specimens must be sized to fit within the magnetic field coil spacing available for the apparatus employed.

6.3 Small test specimens may be immeasurable if their size prohibits detection by the magnetic field coils for the apparatus employed.

6.4 Specimen shape, that is, symmetry and aspect ratio, influence H_c measurement values and repeatability of results. Test specimens should be positioned with their long axis in the direction of the magnetic field. Asymmetrically shaped test specimens should be tested in several positions, the measurement values recorded, and the average value reported.

¹ This test method is under the jurisdiction of ASTM Committee B09 on Metal Powders and Metal Powder Products and is the direct responsibility of Subcommittee B09.06 on Cemented Carbides.

Current edition approved April 1, 2008. Published April 2008. Originally approved in 1998. Last previous edition approved in 2003 as B 887–03.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

7. Apparatus

7.1 Instrumentation capable of the dc magnetization of appropriately sized test samples to technical saturation and accurate measurement of the energy required to restore the magnetic induction to zero.

8. Procedure

8.1 For commercial instrumentation, refer to the equipment operators manual and follow the manufacturer's operating instructions.

8.2 Position the test sample in the center of the magnetic field. The test sample should be positioned with its long axis in the direction of the magnetic field (see 6.4).

8.3 Magnetize the test sample to technical saturation.

8.4 Reverse the magnetic field polarity and demagnetize the test sample to zero.

8.5 Record the H_c measurement, that is, energy required to demagnetize the test sample.

8.6 Replicate measurement of the same test sample shall be made, reversing the polarity of the saturation and demagnetizing magnet fields, where possible.

8.7 For asymmetric sample shapes, repeat measurements shall be made by repositioning the specimen in the dc magnetic field of the instrumentation with consideration being given to the shape, that is, symmetry of the test sample, and to its aspect ratio, that is, length versus width.

9. Report

9.1 Report the following information:

9.1.1 Test sample identification,

9.1.2 Average H_{cs} coercivity (amp per metre (A/m) or oersteds), and

9.1.3 Range of measured H_c values, especially for replicate measurements of asymmetric sample shapes.

10. Precision and Bias

10.1 *Precision*—Measurement of coercive force is a relative comparison against well characterized reference materials (see Section 8). No statement about precision can be made due to the effects of test specimen shape, variations in the binder content that are within material or product specification, and the presence of carbon deficiency.

10.2 *Bias*—Measurement of coercive force is a relative comparison against well characterized reference materials (see Section 8). No statement about bias can be made due to the effects of test specimen shape, variations in the binder content that are within material or product specification, and the presence of carbon deficiency.

10.3 No certified cemented carbide standards are available for coercive force measurement. Most common practice is the development of (internal) reference materials representative of the product(s) being evaluated.

11. Keywords

11.1 cemented carbide; coercive force; coercivity; magnetization

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).