



Standard Specification for Unalloyed Magnesium Ingot and Stick For Remelting¹

This standard is issued under the fixed designation B92/B92M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification covers magnesium in the form of ingot and stick for remelting: 9980A is available in ingot and stick form, and 9980B, 9990A, 9995A, and 9998A are generally available only in ingot form.

1.2 The values stated in SI units are to be regarded as a separate standard. The values stated in each system are not exact equivalents, therefore each system must be used independently of the other.

2. Referenced Documents

2.1 ASTM Standards:²

B951 Practice for Codification of Unalloyed Magnesium and Magnesium-Alloys, Cast and Wrought

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E35 Test Methods for Chemical Analysis of Magnesium and Magnesium Alloys (Withdrawn 2008)³

E88 Practice for Sampling Nonferrous Metals and Alloys in Cast Form for Determination of Chemical Composition

3. Terminology

3.1 Definitions:

3.1.1 *ingot*—a cast form suitable for remelting.

3.1.2 *stick*—an extruded form substantially uniform in cross section cut to desired length or weight.

4. Ordering Information

4.1 Orders for ingot and stick under this specification shall include the following information:

4.1.1 Grade (Section 6 and Table 1),

4.1.2 Quantity, in pieces or pounds [kilograms], and

4.1.3 Form; by agreement between the purchaser and the manufacturer the approximate form and weight of each piece or ingot may be specified.

4.1.4 For inch-pound orders specify B92, for metric orders specify B92M. Do not mix units.

5. Materials and Manufacture

5.1 No scrap shall be used in the production of magnesium ingot and stick, except such as shall accumulate at the manufacturer's plants from material of similar composition and of his own manufacture.

6. Chemical Composition

6.1 *Limits*—The material shall conform to the requirements as to chemical composition prescribed in Table 1.

6.2 Sampling:

6.2.1 Sufficient samples shall be taken by the manufacturer to assure conformance to the chemical composition requirements of the alloy. Samples may be taken from the molten metal when the ingot is poured or from the ingot. Samples shall be representative of the material.

6.2.2 In case of dispute, the sampling for chemical analysis shall be according to the requirements of Practice E88. If the ingots are shipped in carload lots of the same alloy, not less than four ingots shall be taken at random from the carload for sampling. If the shipment is in less than carload lots, one ingot shall be taken for sampling for each 10 000 lb [4500 kg] or fraction thereof.

6.3 *Methods of Analysis*—Any suitable method of chemical analysis may be used. In case of dispute, the analysis shall be made by methods given in Test Methods E35, or any other standard methods of analysis approved by ASTM unless some other method is agreed upon by the purchaser and vendor.

7. General Quality

7.1 Magnesium ingot and stick shall have a clean surface and shall be commercially free from dirt, slag, or other foreign material.

¹ This specification is under the jurisdiction of the ASTM Committee B07 on Light Metals and Alloys and is the direct responsibility of Subcommittee B07.04 on Magnesium Alloy Cast and Wrought Products.

Current edition approved May 1, 2011. Published June 2011. Originally approved in 1933. Last previous edition approved in 2007 as B92/B92M–07. DOI: 10.1520/B0092_B0092M-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.



TABLE 1 Chemical Requirements

NOTE 1—Analysis shall regularly be made only for the elements specifically mentioned in this table. If, however, the presence of other elements is suspected or indicated in the course of routine analysis, further analysis shall be made to determine that the total of these other elements is not in excess of the limits specified in the last column of the table.

NOTE 2—The following applies to all specified limits in this table: For purposes of acceptance and rejection, an observed value or a calculated value obtained from analysis should be rounded to the nearest unit in the last right-hand place of figures used in expressing the specified limit (see Practice E29).

Designation		Chemical Composition, % max unless shown as a range or as a min											
Practice	UNS	Magnesium	Aluminum	Copper	Iron	Lead	Manganese	Nickel	Silicon	Sodium	Tin	Titanium	Other Elements Each ^{A,B}
9980A	M19980	99.80 min	...	0.02	...	0.01	0.10	0.001	...	0.006	0.01	...	0.05
9980B	M19991	99.80 min	...	0.02	...	0.01	0.10	0.005	...	...	0.01	...	0.05
9990A ^C	M19990	99.90 min	0.003	...	0.04	...	0.004	0.001	0.005	...	...	...	0.01
9995A ^C	M19995	99.95 min	0.01	...	0.003	...	0.004	0.001	0.005	...	...	0.01	0.005
9998A ^C	M19998	99.98 min	0.004	0.0005	0.002	0.001	0.002	0.0005	0.003	...	...	0.001	0.005

^A For specific applications, other minor impurities may be required to be controlled to limiting maxima by agreement between the purchaser and the seller.

^B Includes elements for which no specific limit is shown.

^C For nuclear applications, the cadmium and boron (high-capture cross-section elements) shall be specified as follows:

Cadmium, max, %	0.0001 or 0.00005
Boron, max, %	0.00007 or 0.00003

8. Rejection

8.1 Material that does not conform to the requirements of this specification may be rejected, and if rejected the conditions of replacement shall be as agreed upon between the purchaser and the seller. The seller's responsibility shall be limited to a period of six months from shipping date unless other agreement is made by the purchaser and seller.

9. Packaging, Marking, and Shipping

9.1 The material shall be packaged in such a manner as to prevent damage in ordinary handling and transportation. The type of packaging and gross weight of individual containers shall be left to the discretion of the seller unless otherwise agreed upon. Packaging methods and containers shall be so

selected as to permit maximum utility of mechanical equipment in unloading and subsequent handling. Each package or container shall contain only one size and form of material when packed for shipment unless otherwise agreed upon.

9.2 Packages or containers shall be such as to ensure acceptance by common or other carriers for safe transportation at the lowest rate to the point of delivery.

9.3 Each package or container shall be marked with the purchase order number, form, quantity, specification number, gross and net weights, and the name of the manufacturer.

10. Keywords

10.1 chemical specifications; compositional limits; contaminants; contents; grades; magnesium; pure; unalloyed

SUMMARY OF CHANGES

B07 has identified the location of selected changes to this standard since the last issue (June 2007) that may impact the use of this standard. (Approved May 1, 2011)

(1) Revised Table 1.

B07 has identified the location of selected changes to this standard since the last issue (April 2001) that may impact the use of this standard. (Approved June 1, 2007)

(1) Replaced B275 with new B951.



ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).