



Standard Specification for Copper-Silicon Alloy Plate, Sheet, Strip, and Rolled Bar for General Purposes and Pressure Vessels¹

This standard is issued under the fixed designation B96/B96M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification establishes the requirements for copper-silicon alloy plate, sheet, strip, and rolled bar for drawing, forming, stamping, bending, and general engineering applications, and for pressure vessel applications. The alloys involved are copper alloys UNS Nos. C65100, C65400, and C65500.

1.2 When product is ordered for ASME Boiler and Pressure Vessel Code applications, consult the Code² for applicable alloys.

1.3 *Units*—The values stated in either inch-pound or SI units are to be regarded separately as standard. Within the text, SI units are shown in brackets. The values in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the specification.

2. Referenced Documents

2.1 *ASTM Standards*:³

B248 Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar

B248M Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar (Metric)

B601 Classification for Temper Designations for Copper and Copper Alloys—Wrought and Cast

B846 Terminology for Copper and Copper Alloys

E54 Test Methods for Chemical Analysis of Special Brasses

and Bronzes (Withdrawn 2002)⁴

E62 Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods) (Withdrawn 2010)⁴

E118 Test Methods for Chemical Analysis of Copper-Chromium Alloys (Withdrawn 2010)⁴

E478 Test Methods for Chemical Analysis of Copper Alloys

3. General Requirements

3.1 The following sections of either Specification **B248** or **B248M** constitute a part of this specification:

3.1.1 Terminology (see also Terminology **B846**),

3.1.2 Materials and Manufacture,

3.1.3 Dimensions, Mass, and Permissible Variations,

3.1.4 Workmanship, Finish, and Appearance,

3.1.5 Sampling,

3.1.6 Number of Tests and Retests,

3.1.7 Test Specimens,

3.1.8 Test Methods,

3.1.9 Significance of Numerical Limits,

3.1.10 Inspection,

3.1.11 Rejection and Rehearing,

3.1.12 Certification,

3.1.13 Mill Test Report,

3.1.14 Product Identification

3.1.15 Packing and Package Marking, and

3.1.16 Supplementary Requirements.

3.2 In addition, when a section with a title identical to that referenced in **3.1** appears in this specification, it contains additional requirements which supplement those appearing in either Specification **B248** or **B248M**.

4. Terminology

4.1 For definitions of terms related to copper and copper alloys, refer to Terminology **B846**.

5. Ordering Information

5.1 Include the following specified choices when placing orders for product under this specification, as applicable:

⁴ The last approved version of this historical standard is referenced on www.astm.org.

¹ This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.01 on Plate, Sheet, and Strip.

Current edition approved Oct. 1, 2011. Published November 2011. Originally approved in 1934. Last previous edition approved in 2006 as B96/B96M – 06. DOI: 10.1520/B0096_B0096M-11.

² For ASME Boiler and Pressure Vessel Code applications, see related Specification SB-96 in Section 11 of that Code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- 5.1.1 ASTM designation and year of issue,
- 5.1.2 Copper Alloy UNS No. designations (Section 1),
- 5.1.3 Temper (Section 7),
- 5.1.4 Dimensions: Thickness, Width, and Length (Section 11),
- 5.1.5 Finish (section 12.2),
- 5.1.6 Type of edge, if required: slit, sheared, sawed, square corners, rounded corners, rounded edges or full rounded edges (11.6),
- 5.1.7 How furnished (straight lengths or coils),
- 5.1.8 Weight (11.7),
- 5.1.9 Intended application.

5.2 The following options are available, but may not be included unless specified at the time of placing the order, when required.

- 5.2.1 Mill test (Section 18),
- 5.2.2 Certification (Section 17),
- 5.2.3 Product identification for ASME Boiler and Pressure Vessel Code applications (Specifications B248 or B248M),
- 5.2.4 If product is ordered for ASME Boiler and Pressure Vessel Code application, (1.2, 11.1, 11.2.1, and 11.7.1),
- 5.2.5 Whether 0.2 % yield strength is required (Table 3),
- 5.2.6 If product is purchased for agencies of the U.S. Government (Section 10).
- 5.2.7 If specification number must be shown on package marking (Section 19.2.2).

6. Chemical Composition

6.1 The material shall conform to the chemical composition requirements prescribed in Table 1 for the copper alloy UNS No. designation specified in the ordering information.

6.2 These composition limits do not preclude the presence of other elements. By agreement between manufacturer or supplier and the purchaser, limits may be established and analysis required for unnamed elements.

6.2.1 For alloys in which copper is listed as “remainder”, copper is the difference between the sum of the results of all the elements determined and 100 %.

6.2.2 When all the elements in Table 1 are determined, the sum of results shall be 99.5 % min.

7. Temper

7.1 The standard tempers for products described in this specification are in Tables 2-5.

7.2 Tempers, as defined in Classification B601 available under this specification are:

- 7.2.1 O61 (annealed),
- 7.2.2 O50 (light anneal),
- 7.2.3 H01 (quarter hard),
- 7.2.4 H02 (half-hard),
- 7.2.5 H03 (three-quarter hard),
- 7.2.6 H04 (hard),
- 7.2.7 H06 (extra-hard),
- 7.2.8 H08 (spring),
- 7.2.9 H10 (extra-spring),
- 7.2.10 H14 (super-spring),
- 7.2.11 M20 (as hot-rolled), and
- 7.2.12 M25 (as hot-rolled and rerolled).

8. Grain Size for Annealed Tempers

8.1 The approximate grain size values for annealed tempers given in Tables 2-5 are for general information and shall not be used as a basis for product rejection.

9. Mechanical Property Requirements

9.1 *Tensile Strength Requirements* —The tension test shall be the standard test for all tempers of rolled, annealed, and hot-rolled materials. Acceptance or rejection based on mechanical properties shall depend only on the tensile properties, which shall conform to the requirements prescribed in Table 2, Table 3, Table 4 or Table 5. Tension test specimens shall be taken so the longitudinal axis of the specimen is parallel to the direction of rolling.

9.1.1 For Pressure Vessel Code Applications, the tensile requirements are prescribed in Tables 4 and 5.

9.1.2 For general purpose applications, the tensile requirements are prescribed in Tables 2 and 3.

9.2 *Rockwell Hardness Requirements* —The approximate Rockwell hardness values given in Tables 2-5 are for general information and assistance in testing and shall not be used as a basis for product rejection.

10. Purchases for U.S. Government Agencies

10.1 If the product ordered is for an agency of the U.S. Government, when specifically stipulated in the contract or purchase order, the product furnished shall conform to the conditions specified in the Supplementary Requirements section of Specifications B248 or B248M.

11. Dimensions, Mass, and Permissible Variations

11.1 The dimensions and tolerances for product described by this specification shall be as specified in Specifications B248 or B248M with particular reference to the following tables and related paragraphs in that specification (exceptions for ASME Pressure Vessel Code applications are noted):

11.2 *Thickness*—Table 2.

11.2.1 *Pressure Vessel Code Applications*—The thickness of any plate or sheet shall not be more than 0.01 in. under the thickness specified.

11.3 *Width*:

11.3.1 *Slit Metal and Slit Metal with Rolled Edges*—Table 4.

TABLE 1 Chemical Requirements

Element	Composition, %		
	Copper Alloy UNS No.		
	C65100	C65400	C65500
Copper, incl silver	remainder	remainder	remainder
Silicon	0.8–2.0	2.7–3.4	2.8–3.8
Manganese	0.7 max	...	0.50–1.3
Tin	...	1.2–1.9	...
Chromium	...	0.01–0.12	...
Zinc, max	1.5	0.50	1.5
Iron, max	0.8	...	0.8
Nickel, max ^A	...	...	0.6
Lead, max	0.05	0.05	0.05

^A Incl cobalt.

**TABLE 2 Tensile Strength Requirements and Approximate Rockwell Hardness and Grain Size Values, Inch-pound**

Temper Designation		Tensile Strength, ksi	Approximate Rockwell Hardness		Approximate Grain Size, mm
Code	Name		F Scale	B Scale	
Copper Alloy UNS No. C65100					
O61	Annealed	38–45	45–55	...	0.050–0.120
O50	Light anneal	40–50	50–75	...	0.060 max ^A
H01	Quarter-hard	42–52	...	48–63	...
H02	Half-hard	47–57	...	64–73	...
H04	Hard	60–70	...	74–82	...
H06	Extra-hard	67–76	...	78–85	...
H08	Spring	71–79	...	81–86	...
Copper Alloy UNS Nos. C65500					
O61	Annealed	52–58	70–82	...	0.110 max ^A
O50	Light anneal	55–64	76–93	...	0.055 max ^B
H01	Quarter-hard	60–74	...	65–80	...
H02	Half-hard ^B	72–86	...	79–91	...
H04	Hard ^B	85–99	...	88–96	...
H06	Extra-hard ^B	95–109	...	93–98	...
H08	Spring ^B	102–116	...	94–99	...
M20	As hot-rolled	55–72	72 min	...	...
M25	As hot-rolled and rerolled	58–72	...	60-80	...
Copper Alloy UNS No. C65400			Superficial 30T	B Scale	
O61	Annealed	65–80	...	...	0.040 ^B max
H01	Quarter hard ^B	75–90	64–77	72–91	...
H02	Half hard ^B	86–101	75–79	89–95	...
H03	Three-quarter hard ^B	97–112	77–81	94–97	...
H04	Hard ^B	108–120	80–81	96–98	...
H06	Extra hard ^B	116–126	81–82	97–100	...
H08	Spring ^B	124–133	81–82	99–101	...
H10	Extra spring ^B	131–140	81 min	100–102	...
H14	Super spring ^B	137 min	81 min	101 min	...

^A No minimum grain size requirement is specified, but all annealed material shall be fully recrystallized.^B Commercially supplied only as strip. The manufacturer should be consulted where these tempers are desired in sheet or plate.**TABLE 3 Tensile Strength Requirements and Approximate Rockwell Hardness and Grain Size Values, SI**

Temper Designation		Tensile Strength, MPa	Approximate Rockwell Hardness		Approximate Grain Size, mm
Code	Name		F Scale	B Scale	
Copper Alloy UNS No. C65100					
O61	Annealed	260–310	45–55	...	0.050–0.120
O50	Light anneal	275–345	50–75	...	0.060 max ^A
H01	Quarter-hard	290–360	...	48–63	...
H02	Half-hard	325–395	...	64–73	...
H04	Hard	415–485	...	74–82	...
H06	Extra-hard	460–525	...	78–85	...
H08	Spring	490–545	...	81–86	...
Copper Alloy UNS Nos. C65500					
O61	Annealed	360–400	70–82	...	0.110 max ^A
O50	Light anneal	380–440	76–93	...	0.055 max ^B
H01	Quarter-hard	415–510	...	65–80	...
H02	Half-hard ^B	495–595	...	79–91	...
H04	Hard ^B	585–685	...	88–96	...
H06	Extra-hard ^B	655–750	...	93–98	...
H08	Spring ^B	705–800	...	94–99	...
M20	As hot-rolled	380–500	72 min	...	...
M25	As hot-rolled and rerolled	400–500	...	60-80	...
Copper Alloy UNS No. C65400			Superficial 30T	B Scale	
O61	Annealed	450–550	...	...	0.040 ^B max
H01	Quarter hard ^B	520–620	64–77	72–91	...
H02	Half hard ^B	590–700	75–79	89–95	...
H03	Three-quarter hard ^B	670–770	77–81	94–97	...
H04	Hard ^B	745–830	80–81	96–98	...
H06	Extra hard ^B	800–870	81–82	97–100	...
H08	Spring ^B	855–920	81–82	99–101	...
H10	Extra spring ^B	905–965	81 min	100–102	...
H14	Super spring ^B	945 min	81 min	101 min	...

^A No minimum grain size requirement is specified, but all annealed material shall be fully recrystallized.^B Commercially supplied only as strip. The manufacturer should be consulted where these tempers are desired in sheet or plate.11.3.2 *Square-Sheared Metal*—Table 5.11.3.3 *Sawed Metal*—Table 6.

**TABLE 4 Tensile Strength Requirements and Approximate Rockwell Hardness and Grain Size Values for Pressure Vessel Applications, Inch-Pound**

Temper Designation		Tensile Strength, ksi	Yield Strength at 0.5 % Extension Under Load, ksi min	Yield Strength ^A at 0.2 % offset, min, ksi	Elongation, min % ^B	Approximate Rockwell F Hardness	Approximate Grain Size, mm
Code	Name						
Copper Alloy UNS No. C65500							
O61	Annealed	50–67	18	18	40	70–82	0.110 max ^C

^A See 5.2.5.^B Elongation in 2 in.^C No minimum grain size requirement is specified, but all annealed material shall be fully recrystallized.**TABLE 5 Tensile Strength Requirements and Approximate Rockwell Hardness and Grain Size Values for Pressure Vessel Applications, SI**

Temper Designation		Tensile Strength, MPa	Yield Strength at 0.5 % Extension Under Load, MPa min	Yield Strength ^A at 0.2 % offset, min, MPa	Elongation, min % ^B	Approximate Rockwell F Hardness	Approximate Grain Size, mm
Code	Name						
Copper Alloy UNS No. C65500							
O61	Annealed	345–460	125	125	40	70–82	0.110 max ^C

^A See 5.2.5.^B Elongation in 50 mm.^C No minimum grain size requirement is specified, but all annealed material shall be fully recrystallized.**11.4 Length:**11.4.1 *Schedule of Lengths (Specific and Stock) With Ends*—Table 7.11.4.2 *Length Tolerances for Square-Sheared Metal*—Table 9.11.4.3 *Length Tolerances for Sawed Metal*—Table 10.11.4.4 *Minimum and Maximum Weight of Ends*—Table 8.**11.5 Straightness:**11.5.1 *Slit Metal or Slit Metal Either Straightened or Edge-Rolled*—Table 11.11.5.2 *Square-Sheared Metal*—Table 12.11.5.3 *Sawed Metal*—Table 13.**11.6 Edges:**11.6.1 *Square Edges*—Table 14.11.6.2 *Rounded Corners*—Table 15.11.6.3 *Rounded Edges*—Table 16.11.6.4 *Full-Rounded Edges*—Table 17.**11.7 Weight, Hot-Rolled Sheet and Plate**—Table 18.11.7.1 *ASME Pressure Vessel Code Applications*—Table 6 of this specification.**12. Workmanship, Finish, and Appearance**

12.1 For workmanship and appearance requirements, refer to either Specification B248 or B248M.

12.2 *Finish*—The material is supplied regularly in the following finishes:12.2.1 *Black*—After hot rolling retains all of the oxides.12.2.2 *Plain Pickled*—Sulfuric acid pickle only, brick red oxide; has cuprous and silicon oxides still adherent.12.2.3 *Specially Cleaned*—Commercially free of all oxides; has the golden color of the alloy.12.2.4 *Sand Blasted*—Commercially free of all oxides; has a dull gray color.**13. Sampling**

13.1 Refer to sampling section in Specification B248 or B248M.

14. Test Methods14.1 *Chemical Analysis:***TABLE 6 Lot Weight Tolerances in Percentage of Theoretical Weight for Pressure Vessel Applications—All Plus**

Thickness, in. [mm]	Permissible Excess in Average Weight of Lots, Expressed in Percentage of Normal Weight					
	48 in. [1200 mm] and Under in Width	Over 48 to 60 in. [1200 to 1500 mm] in Width	Over 60 to 72 in. [1500 to 1800 mm] in Width	Over 72 to 96 in. [1800 to 2500 mm] in Width	Over 96 to 120 in. [2500 to 3000 mm] in Width	Over 120 to 132 in. [3000 to 3500 mm] incl in Width
1/8 to 3/16, incl [3.0 to 5.0]	6.5	8	9	11	...	...
Over 3/16 to 1/4, incl [6.0 to 8.0]	6.5	8	9	11	12	...
Over 1/4 to 5/16, incl [8.0 to 10]	6.5	7.75	8.75	11	12	13
Over 5/16 to 3/8, incl [9.0 to 10]	6.25	7.5	8.5	11	12	13
Over 3/8 to 7/16, incl [10 to 12]	6	7.25	8.25	11	12	13
Over 7/16 to 1/2, incl [12 to 14]	6	7	8	10	11	12
Over 1/2 to 5/8, incl [14 to 16]	5.75	6.5	7.5	9	10	11
Over 5/8 to 3/4, incl [16 to 20]	5.5	6	7	8	9	10
Over 3/4 to 1, incl [20 to 25]	5	5	6.25	7	8	9
Over 1 to 2, incl [25 to 50]	3.5	4	5	6	7	8

14.1.1 In cases of disagreement, test methods for chemical analysis shall be subject to agreement between the manufacturer or supplier and the purchaser:

14.1.2 The following table is a list of published test methods, some of which are considered by ASTM as no longer viable. These and others not listed may be used subject to agreement.

Element	Test Method
Copper	E478
Silicon	E54; Perchloric acid dehydration
Manganese	E62
Tin	E478; Titrimetric
Chromium	E118
Zinc	E478; Atomic absorption
Iron	E478

Nickel
Lead

E478; Photometric
E478; Atomic absorption

14.1.3 Test methods to be followed for the determination of other elements resulting from contractual or purchase order agreement shall be as agreed upon between the manufacturer or supplier and purchaser.

14.2 Other Tests:

14.2.1 *Mechanical Properties (Tensile, Rockwell, and Grain)*—Refer to the appropriate test method in either Specification **B248** or **B248M**.

15. Keywords

15.1 copper-silicon alloy rolled bar; copper-silicon alloy plate; copper-silicon alloy pressure vessels; copper-silicon alloy sheet; copper-silicon alloy strip; UNS Alloy No. C65100; UNS Alloy No. C65400; UNS Alloy No. C65500

SUMMARY OF CHANGES

Committee B05 has identified the changes to this specification since the 2006 issue, as follows:

(1) Revised to comply with the B950-11, Standard Guide for Editorial Procedures and Form of Product Specifications for Copper and Copper Alloys.

(2) Divided Table 2 into Tables 2 and 3, and Table 3 into Tables 4 and 5, so that inch-pound and SI units could be expressed separately.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/