



Standard Specification for Fiber-Cement Roofing Shingles, Shakes, and Slates¹

This standard is issued under the fixed designation C1225; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers fiber-cement shingles, shakes, and slates (roofing products) of nominally uniform thickness (non-tapered) and texture, including accessories designed to provide the weather-exposed surfaces on roofs of buildings.

1.2 This specification is not applicable to asbestos-cement roofing shingles (Specification C222), non-asbestos fiber-cement roofing shakes, shingles, and slates with designed varying profiles and thicknesses (Specification C1530), particle board (Terminology D1554), or cement-bonded particleboards (Specification BS 5669: Part 4) and (ISO 8335).

1.3 This specification does not include details of product installation or installed system performance. Refer to the manufacturer's installation literature for proper installation instructions, to Specification C1459 for roofing systems performance, and to Test Methods E108 for levels of fire resistance.

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

2. Referenced Documents

2.1 ASTM Standards:²

C222 Specification for Asbestos-Cement Roofing Shingles
C1154 Terminology for Non-Asbestos Fiber-Reinforced Cement Products

C1185 Test Methods for Sampling and Testing Non-Asbestos Fiber-Cement Flat Sheet, Roofing and Siding Shingles, and Clapboards

C1459 Specification for Performance of Non-Asbestos Fiber-Reinforced Cement Shake, Shingle, and Slate Roofing Systems

¹ This specification is under the jurisdiction of ASTM Committee C17 on Fiber-Reinforced Cement Products and is the direct responsibility of Subcommittee C17.02 on Non-Asbestos Fiber Cement Products.

Current edition approved Nov. 1, 2012. Published November 2012. Originally approved in 1993. Last previous edition approved in 2008 as C1225 – 08. DOI: 10.1520/C1225-08R12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

C1530 Specification for Non-Asbestos Fiber-Cement Roofing Shakes, Shingles, and Slates with Designed Varying Profiles and Thicknesses

D1554 Terminology Relating to Wood-Base Fiber and Particle Panel Materials

E108 Test Methods for Fire Tests of Roof Coverings

2.2 *British Standards*:³

BS 5669: Specification for cement bonded particleboard

2.3 *International Standards*:³

ISO 8335 Cement-bonded particleboards—Boards of Portland or equivalent cement reinforced with fibrous wood particles³

3. Terminology

3.1 *Definitions*—Refer to Terminology C1154.

4. Manufacture and Composition

4.1 *Manufacture*—These products may be formed either with or without pressure and cured, either under natural or accelerated conditions, to meet the physical requirements of this specification.

4.2 *Composition*—This specification is applicable to fiber cement roofing products consisting essentially of an inorganic hydraulic binder or a calcium silicate binder formed by the chemical reaction of a siliceous material and a calcareous material reinforced by organic fibers, inorganic non-asbestos fibers, or both. Process aids, fillers, and pigments which are compatible with fiber cement may be added.

5. Mechanical and Physical Properties

5.1 Mechanical and physical properties shall be determined on uncoated products wherever practical. Where products are supplied coated, this material shall also be tested with the results identified as applying to coated material. Failure of the coating as a consequence of the mechanical testing shall not constitute failure of the product. Accessory products shall be excluded from these requirements.

5.1.1 Sampling and inspection for mechanical and physical properties shall be conducted in accordance with Test Methods C1185.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

6. Requirements

6.1 Mechanical Requirements:

6.1.1 *Flexural Strength*—When tested in accordance with Test Methods C1185, the product shall be classified according to its modulus of rupture. The product modulus of rupture and breaking moment in the primary strength direction shall be not less than that specified in Table 1.

6.1.2 Where a manufacturer states a minimum product modulus of rupture, it shall be at the 4 % acceptable quality level (AQL) at the 90 % confidence limit as are the values of Table 1.

6.1.3 The primary strength direction is that heaviest loaded direction which will resist wind uplift when the product is installed.

6.1.3.1 *Known Orientation of Installation*—Where the system design ensures or dictates that the product orientation at installation is known, and the product is manufactured such that its strongest direction coincides with the primary strength direction, then classification of product shall be based on its strongest strength direction.

6.1.3.2 *Unknown Orientation of Installation*—Where a system design does not ensure or dictate that the product orientation at installation is known, then classification of the product shall be based on its weakest strength direction.

6.1.4 The product modulus of rupture in the weakest direction shall not be less than 50 % of the modulus of rupture in the strongest direction.

6.2 Physical Requirements:

6.2.1 *Density*—Nominal values and tolerances for density shall be stated by the manufacturer, when tested in accordance with the method specified in Test Methods C1185.

6.2.2 *Water Absorption*—Calculate the amount of water absorbed from the increase in weight of the dried specimen during submersion for a period of 48 h. Express water absorption as the percentage by weight when tested in accordance with Test Methods C1185.

6.2.3 *Moisture Content*—State the percentage of moisture content of the fiber-cement shingle when conditioned at 50 ± 5 % relative humidity and a temperature of $73 \pm 4^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$) in accordance with Test Methods C1185.

7. Dimensions and Permissible Variations

7.1 *Nominal Length, Width and Thickness*—The shapes, size, and thickness shall be specified by the manufacturer.

7.2 *Length and Width Tolerance*—The permissible variation from the nominal width and length shall be $\pm 1/4$ in. (± 6.4 mm). The method of measurement shall be in accordance with Test Methods C1185.

TABLE 1 Strength Classification

NOTE 1—Values in the table are lower limit values based on an acceptable quality level (AQL) of 4 % at a 90 % confidence level.

Minimum Saturated Modulus of Rupture	
psi	(MPa)
798	(5.5)
Minimum Saturated Breaking Moment	
ft lbf/ft	(Nm/m)
5.6	(25)

7.3 *Thickness Tolerance*—The thickness variation from the nominal thickness shall not exceed $-10\% + 25\%$. The method of measurement shall be in accordance with Test Methods C1185.

8. Workmanship and Finish

8.1 *Workmanship*—The surface of the product to be exposed shall be free of defects that impair serviceability.

8.2 *Finish*—The surface of the product to be exposed may be smooth, grained, granulated, coated, or otherwise textured.

8.3 *Color*—The exposed surface of the product may be the natural color of the fiber-cement product or may be colored by the addition of mineral pigments, chemical impregnation, pigmented coatings, veneers, or embedded mineral granules.

8.4 *Holes for Nails and Supplemental Fasteners*—Holes for nails and supplemental fasteners may be provided in the units during manufacture and, if so, shall be placed as to provide the required lap and allow for proper application of necessary supplemental fasteners.

8.5 *Efflorescence*—Efflorescence that may appear on fiber-cement product is not a defect.

8.6 *Weathering*—It should be noted that on exposure a colored product will be affected by weathering which may vary with site location pitch and exposure. Any change in finish does not in itself detract from the minimum mechanical or physical characteristics as specified in this standard or from the function of the product.

9. Supplementary Shapes

9.1 Supplementary shapes such as starter pieces, hip, and ridge finishing pieces, and ridge rolls, shall have the same general characteristics as the product they are designed to complement.

10. Inspection and Acceptance

10.1 Inspection of material, if required, shall be at the point of shipment. The inspector representing the purchaser shall have authorized access to the carriers being loaded for shipment to the purchaser. The purchaser shall be afforded all reasonable and available facilities at the point of shipment for

TABLE 2 Frost Resistance Classification

Grade	No. of Cycles	Retained Strength	Use Limitations
1	0	N/A	To regions where the mean annual rainfall does not exceed 20 in. (508 mm) and the average of the daily lows for any month is at least 35°F (2°C) - and - Consult the manufacturer for geographical recommendations
2	25	75%	To regions where the mean annual rainfall does not exceed 40 in. (1016 mm) and the average of the daily lows for any month is at least 30°F (-1°C) - and - Consult the manufacturer for geographical recommendations
3	100	75%	No limitations

sampling and inspection of the material, which shall be conducted so as not to interfere unnecessarily with the loading of the carriers.

10.2 Third party certification, either continuous or at regular intervals, shall be recognized as an alternative to lot inspection.

10.3 Failure to conform to any one of the requirements of this specification shall constitute grounds for nonacceptance.

11. Additional Requirements

11.1 Additional requirements shall consist of once only tests with manufacturer's statement of results provided upon customer's request. Fundamental changes in formulation or methods of manufacture, or both, shall require subsequent retesting.

11.2 *Water Tightness*—The specimen, when tested in accordance with Test Methods C1185, may show traces of moisture on the underside of the sheet, but in no instance shall there be any formation of drops of water.

11.3 *Frost Resistance (Freeze/Thaw)*—The specimens shall be tested in accordance with Test Methods C1185, Section 16. The ratio of strengths, before and after exposure as calculated

from test results, shall be as described in Table 2. Fiber-cement roofing products installation shall be limited to the parameters described in the column labeled "Use Limitations."

11.4 *Warm Water Resistance*—The specimens, when tested in accordance with Test Methods C1185, shall not show visible cracks or structural alteration, such as to affect their performance in use. The ratio of strengths, before and after exposure as calculated from test results, shall be $\geq 80\%$.

11.5 *Heat/Rain Resistance*—The specimens, when tested in accordance with Test Methods C1185, (Part 15) for 25 cycles shall not show visible cracks or structural alteration of the roofing such as to affect their performance in use.

12. Keywords

12.1 breaking moment; color; density; efflorescence; fiber-cement; fiber-reinforced; finish; frost resistance; heat/rain test; inorganic fibers; inspection; length; mechanical properties; modulus of rupture; moisture content; non-asbestos; organic fibers; physical properties; roofing; sampling; shakes; shingles; slates; thickness; tolerance; water absorption; water tightness; width; workmanship

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).