



Standard Practice for Application of Exterior Insulation and Finish Systems Class PI¹

This standard is issued under the fixed designation C1535; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This practice covers the minimum requirements and procedures for field or prefabricated application of Class PI Exterior Insulation and Finish Systems (EIFS). Class PI EIFS are systems applied over polyisocyanurate insulation board, in which the base coat ranges from not less than 1/16 in. (1.6 mm) to 1/4 in. (6.4 mm) in dry thickness, depending upon the number of nonmetallic reinforcing mesh layers encapsulated in the base coat. The base coat is then covered with a finish coat of various thickness in a variety of textures and colors. The insulation board shall be applied over a substrate or over open framing.

1.2 This practice does not cover Class PI EIFS with drainage. Consult the EIFS producer for information.

1.3 The values stated in inch-pound units are to be regarded as the standard. The SI (metric) values given in parentheses are approximate and are provided for information purposes only.

1.4 The text of this standard references notes and footnotes that provide explanatory material. These notes and footnotes shall not be considered as requirements of the standard.

1.5 *This standard may involve hazardous materials, operations and equipment. This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

C11 Terminology Relating to Gypsum and Related Building Materials and Systems

¹ This practice is under the jurisdiction of ASTM Committee C11 on Gypsum and Related Building Materials and Systems and is the direct responsibility of Subcommittee C11.05 on Application of Exterior Insulating and Finish Systems and Related Products.

Current edition approved Dec. 1, 2011. Published June 2012. Originally approved in 2002. Last previous edition approved in 2005 as C1535 – 05. DOI: 10.1520/C1535-05R11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

C79/C79M Specification for Gypsum Sheathing Board
(Withdrawn 2004)³

C150 Specification for Portland Cement

C1063 Specification for Installation of Lathing and Furring to Receive Interior and Exterior Portland Cement-Based Plaster

C1177/C1177M Specification for Glass Mat Gypsum Substrate for Use as Sheathing

C1186 Specification for Flat Fiber-Cement Sheets

C1278/C1278M Specification for Fiber-Reinforced Gypsum Panel

C1280 Specification for Application of Exterior Gypsum Panel Products for Use as Sheathing

C1289 Specification for Faced Rigid Cellular Polyisocyanurate Thermal Insulation Board

C1325 Specification for Non-Asbestos Fiber-Mat Reinforced Cementitious Backer Units

C1382 Test Method for Determining Tensile Adhesion Properties of Sealants When Used in Exterior Insulation and Finish Systems (EIFS) Joints

C1472 Guide for Calculating Movement and Other Effects When Establishing Sealant Joint Width

C1481 Guide for Use of Joint Sealants with Exterior Insulation and Finish Systems (EIFS)

E1825 Guide for Evaluation of Exterior Building Wall Materials, Products, and Systems

E2110 Terminology for Exterior Insulation and Finish Systems (EIFS)

3. Terminology

3.1 Definitions used in this standard shall be in accordance with Terminologies **C11** and **E2110**.

4. Significance and Use

4.1 This practice provides minimum requirements for the application of Class PI EIFS. The requirements for materials, mixtures, and details shall be contained in the project plans and specifications. See Guide **E1825** for guidance.

³ The last approved version of this historical standard is referenced on www.astm.org.

*A Summary of Changes section appears at the end of this standard

5. Delivery of Materials

5.1 All materials shall be delivered in packages, containers, or bundles with the identification and markings intact.

6. Inspection

6.1 Inspection of the materials shall be agreed upon and be a part of the purchase agreement.

6.2 Inspection shall include the determination that the materials supplied are as required for the Class PI EIF System specified. Mixing of materials from different manufacturers is not allowed.

7. Rejection

7.1 Materials that are damaged, frozen or defective shall not be used. Rejection of materials shall be promptly reported verbally to the producer and immediately reported in writing. The notice of rejection shall contain a statement documenting the basis for material rejection.

8. Certification

8.1 When specified in the contract documents, the producer shall furnish a report certifying that the materials are in conformance with product and material standards and contract documents.

8.2 Insulation Boards:

8.2.1 Insulation boards shall be in compliance with Specification **C1289**, Type II, Class 2.

8.2.2 Insulation boards shall have been subjected to a third party quality control inspection and shall be marked as approved for use within the EIFS and in accordance with applicable building code.

8.2.3 Prior to installation, the insulation board shall be inspected for conformance with contract documents. Nonconforming insulation board shall not be used.

8.2.4 The insulation board producer shall furnish, for each shipment, a written certificate of conformance with the EIFS producer's specifications.

9. Storage of Materials

9.1 All materials shall be kept dry by storage under cover and protected from the weather. When outside storage is required, materials shall be stacked off the ground, supported on a level platform and protected from the weather, surface contamination or physical damage in accordance with the EIFS producer's written instructions.

9.2 Materials shall be protected from exposure to direct sunlight and temperatures less than 40 °F (4 °C) unless otherwise specified by the manufacturer.

9.3 Portland Cement shall meet Specification **C150** and shall be kept dry until ready for use. It shall be kept off the ground, under cover and away from damp walls and surfaces.

9.4 Insulation board shall be stacked flat with care taken to avoid damage to edges, ends, or surfaces; or exposure to direct sunlight (ultraviolet radiation).

10. Environmental Conditions

10.1 Cold Weather Conditions:

10.1.1 Wet materials shall not be applied when the temperature is less than 40 °F (4 °C) unless otherwise specified by the manufacturer or unless temporary heat and enclosures are provided to maintain minimum 40 °F (4 °C) for a minimum period of not less than 24 hours before, during and after application. (See **X1.8.3**)

10.1.2 Materials shall not be applied to a base containing frost. Substrate surface temperature shall be not less than 40 °F (4 °C). Mixtures for application shall not contain any frozen ingredients.

11. Assessment of Condition of Substrates to Receive Exterior Insulation and Finish Systems

11.1 The substrate shall be as required by the project plans and specifications and as recommended by the EIFS producer for the particular system specified.

11.1.1 Polyisocyanurate boards for use over open framing in conformance with the EIFS producer's specification shall not be less than 1.0 in. (25.4 mm) in thickness.

11.1.2 Polyisocyanurate boards for use over a substrate in conformance with the EIFS producer's specification shall not be less than 5/8 in. (15.9 mm) in thickness.

NOTE 1—Polyisocyanurate board thickness shall conform to building code requirements.

11.2 The substrate shall be inspected by the applicator and general contractor to assure that it meets the project plans and specifications and the requirements of **11.3-11.8**.

11.3 Sheathing materials shall be inspected to ensure the following:

11.3.1 The specified sheathing thickness has been installed for the stud spacing used.

11.3.2 Fastener type and fastener spacing are as specified.

11.3.3 All Specification **C79/C79M** gypsum sheathing boards have a water-resistant treated core.

11.3.4 Tongue and groove water-resistant core gypsum sheathing boards conforming to Specification **C79/C79M** are installed with the tongue edge oriented to the top.

11.3.5 Gypsum sheathing shall be installed with the face paper exposed in accordance with Specification **C1280**.

11.3.6 Gypsum sheathing shall be protected from moisture at all penetrations and terminations.

11.3.7 Glass mat gypsum sheathing complying with Specification **C1177/C1177M** shall be installed in accordance with the sheathing producer's written installation instructions, which include details of framing type and spacing, fastener type and spacing, and sheathing orientation and spacing.

11.3.8 Plywood shall be not less than 1/2 in. (12.7 mm) nominal in thickness, exterior or exposure 1 panel sheathing. The plywood shall be installed with a 1/8 in. (3.2 mm) space between sheets at edges and ends.

11.3.9 Fiber-Cement sheets complying with Specification **C1186**, Type A, shall be installed in accordance with the sheet producer's written installation instructions, which include details of stud type and spacing, fastener type and spacing, and sheet spacing recommendations.

11.3.10 Water-resistant exterior fiber-reinforced gypsum sheathing complying with Specification **C1278/C1278M** shall be installed in accordance with the sheathing producer's

written installation instructions, which include details of framing type and spacing, fastener type and spacing, and sheathing orientation and spacing.

11.3.11 Fiber-mat reinforced cement sheets complying with Specification **C1325**, type A, shall be installed in accordance with the sheet producer's written installation instructions, which include details of framing type and spacing, fastener type and spacing, and sheet orientation and spacing.

11.3.12 Sheathing shall be continuous.

11.4 *Alignment*—All substrate surfaces shall be straight and true within $\frac{1}{4}$ in./10 ft (2 mm/m). More stringent requirements by the EIFS producer shall supersede the above stated requirements.

11.5 *Suitability for Use*—The substrate shall be firm, sound, and undamaged in order to receive the EIFS.

11.6 *Cleanliness*—The surface of all substrates shall be clean and free from any foreign materials such as paint, form release agents, curing compounds, dust, dirt, frost, oil or grease, efflorescence and laitance that would affect the EIFS application.

11.7 *Dryness*:

11.7.1 Newly constructed concrete or masonry surfaces shall be allowed to cure not less than 28 days prior to application of the EIFS. Repaired areas on existing (aged) walls shall meet the same 28-day curing time.

11.7.2 Substrate surfaces shall be free of visible water.

11.8 *Metal Lath or Furring and Accessories*—If metal lath or furring and accessories are used, they shall be installed in conformance with Specification **C1063**, except lath edges and ends shall be butted and not lapped. Metal lath shall be 3.4 lb/yd² (1.3 kg/m²) self-furring, galvanized.

11.8.1 Metal members shall be properly attached, straight, and true unless otherwise required by the system design.

11.8.2 Metal members shall be free of rust, oil, or other foreign matter or contaminants, which cause bond failure or unsightly discoloration.

12. Insulation Board Installation

12.1 Method of Attachment shall be approved by the system producer and be in accordance with applicable building code.

12.2 *Mechanical Attachment Method*:

12.2.1 Mechanical fasteners shall be installed into the framing or nailable substrate.

12.2.2 Mechanical fasteners shall be corrosion resistant. Fastener type and spacing shall be in accordance with system producer's current published instructions.

NOTE 2—Specific consideration of building code wind load requirements shall be given for mechanically fastened systems.

12.3 Placement of a weather resistive barrier, if specified, shall be as required by the system producer.

13. General Requirements

13.1 Insulation boards shall be placed from a level base line with vertical joints staggered in a running bond pattern and

butted tightly. Over open framing, joints shall occur over framing or horizontal blocking.

13.2 Insulation board joints at all inside and outside corners shall be staggered and interlocked.

13.3 Insulation boards must abut without gaps, eliminating space for base coat intrusion between the board edges and ends.

13.4 Fenestration opening corners and other wall penetrations shall be cut out of a single insulation board. Board joints shall not be aligned at corners with head, sill or jams of windows, doors, similar openings, and aesthetic reveals.

13.5 *Mechanically Fastened*:

13.5.1 Insulation board joints shall be offset from sheathing board joints.

13.5.2 When the boards are attached only with mechanical fasteners, they shall be affixed to a nailable substrate or structural members with the proper fasteners, ensuring that all boards abut tightly. Fastening pattern shall be in accordance with the EIFS producer's recommendation and local building code requirements. When installed, the washer shall be left flush with the face of the insulation board and shall not fracture the face or core of insulation board.

14. Aesthetic Reveals

14.1 Aesthetic reveals shall be cut into the insulation board prior to applying the reinforcing mesh.

14.2 The insulation board thickness at the bottom of a reveal shall be not less than $\frac{3}{4}$ in. (19.0 mm). Over open framing, aesthetic reveals shall occur over framing or blocking.

14.3 Aesthetic reveals shall be cut true and straight.

14.4 Horizontal aesthetic reveal configuration shall provide for outward positive drainage.

14.5 Aesthetic reveals shall not occur at the abutment of two pieces of insulation board.

14.6 The reveal shall be reinforced with base coat and reinforcing mesh prior to application of the full base coat and reinforcing mesh.

15. Reinforced Base Coat Application

15.1 Inspect the insulation board surface to ensure that it is clean, dry, free of all foreign materials, and damage of any type. Insulation board planar irregularities of more than $\frac{1}{16}$ in. (1.6 mm) shall be corrected. All board joints shall be tightly abutted or shall be filled with an insulating material.

15.2 *Base Coat Preparation*—All materials requiring field preparation shall be mixed in accordance with the EIFS producer's specifications.

15.3 *Base Coat Application*—The prepared base coat shall be uniformly spread over the entire surface of the insulation board.

15.4 *Non Metallic Reinforcing Mesh*—The single layer reinforcing mesh shall be fully encapsulated in the field of the wall, at corners, edges, and joints. Trowel from the center to the

edge of the reinforcing mesh to avoid wrinkles. The single layer reinforcing mesh shall be continuous at all corners.

15.4.1 The surface shall be free of voids, projections, trowel marks and other surface irregularities. The base coat thickness shall be not less than $\frac{1}{16}$ in. (1.6 mm) dry as measured from the surface of the insulation board. The base coat shall be applied in two applications unless otherwise recommended by the EIFS's producer.

NOTE 3—The recommended method is to apply the base coat in two applications.

15.5 *Reinforcing Mesh Overlap*—All reinforcing mesh edges shall be overlapped not less than 2 $\frac{1}{2}$ in. (64 mm).

15.6 *Impact Layers*—When required, higher impact performance shall be achieved with multiple layers of reinforcing mesh or by incorporating heavier weight reinforcing mesh. All areas requiring higher impact performance shall be detailed on the project plans and specifications. When overlapping of high impact mesh is not required, a complete second layer of reinforcing mesh shall be applied over the layer of high impact mesh.

15.7 *Corners*—Reinforcing mesh shall not be lapped within 8 in. (200 mm) of any corner.

15.8 *Wall Penetrations*—All edges of the insulation board at penetrations of the EIFS, such as at windows, doors, HVAC sleeves, pipes, ducts, electrical boxes, and at the base of the wall shall be wrapped with either the base coat and reinforcing mesh or trim, or as specified by the project plans and specifications. Wall openings such as doors, windows, HVAC sleeves, shall be diagonally reinforced at corners with mesh not less than 9 in. (230 mm) by 12 in. (305 mm).

15.8.1 The corners of returns to windows, doors, and similar wall openings shall have reinforcing mesh the full width of the return and extending not less than 2 $\frac{1}{2}$ in. (64 mm) on both sides of the corner.

15.9 *Expansion Joints*—All edges of the insulation board at expansion joints shall be wrapped with either the base coat and reinforcing mesh or trim as specified by the EIFS producer for the particular EIFS. The reinforcing mesh shall be fully encapsulated.

15.10 *Aesthetic Reveal*—The reinforcing mesh shall be continuous and care shall be taken to ensure that the reinforcing mesh is fully encapsulated into the reveal and that the reinforcing mesh shall not be cut during application of the base coat.

15.11 *Reinforced Base Coat*—The reinforcing mesh shall be fully encapsulated in the base coat throughout the field of the wall, at corners, edges, and joints. The surface shall be free of voids, projections, trowel marks and other surface irregularities.

15.12 *Special Insulation Shapes*—When special insulation shapes are installed over EIFS, nonmetallic reinforcing mesh encapsulated in the base coat shall be used to cover the shape.

16. Finish Coat Application

16.1 The reinforced base coat shall be allowed to dry and harden for not less than 24 h prior to finish coat application unless specifically allowed by the EIFS producer.

16.2 *Material Preparation*—The finish coat shall be mixed in accordance with the EIFS producer's specifications. Only clean potable water shall be added to adjust workability. Always add the same amount of water to each container within a given lot of finish.

16.3 *Execution*—Finish shall be applied with a stainless steel trowel or appropriate equipment as specified by the EIFS producer. Tools and equipment shall be kept clean at all times. Finish shall be applied continuously to a natural break such as corners, joints or tape line. Apply finish to the base coat maintaining a wet edge. Sufficient manpower and scaffolding shall be provided to continuously finish a distinct wall area. Scaffolding shall be spaced a distance from the wall, consistent with safety standards, that will allow uniform texturing of the finish without staging marks. On hot windy days, misting is permitted with clean, potable water to cool the wall. Work shall precede the sun whenever possible. Water shall not be added to the finish once it is applied to the wall. Use the same tool and hand motion and match the texture of the surrounding area. The finish coat thickness shall be as specified by the EIFS producer. Protect all finish work from damage until fully dried.

16.4 *Sealant Joints*—The application of finish into the sealant joint is not allowed.

17. Curing Time Between Application Steps

17.1 Manufacturer's recommendations for climatic conditions, mixing and application practices to allow respective coats sufficient time to cure or dry before any subsequent coats are applied shall be followed. Each application step shall be cured or dried to prevent degradation to the system integrity with subsequent steps.

17.2 Auxiliary protection (tenting, supplemental heat, shading) from adverse environmental conditions shall be utilized to provide curing and drying conditions as recommended by the producer (see X1.8).

17.3 All substrates shall be sound and cured or dry before continuing on to the next application step.

18. Clean Up

18.1 Adjacent materials, surfaces and the work area shall be cleaned of foreign materials resulting from the work.

18.2 All excess EIFS materials shall be removed from the job site.

19. Keywords

19.1 Class PI; EIFS; exterior insulation and finish system

APPENDIXES**(Nonmandatory Information)****X1. GENERAL INFORMATION****INTRODUCTION**

These appendixes give general information and also suggestions for inclusions to be made elsewhere by the specifier. They are not part of this practice.

X1.1 General

X1.1.1 The work includes all labor, materials, services, equipment and scaffolding required to complete the EIFS installation on the project in accordance with the project drawings and specifications, except electrical power and potable water.

X1.1.2 Where a specific fire resistance rating is required for the EIFS assemblies and construction, details of construction shall be in accordance with official reports of tests conducted by recognized testing laboratories and a part of approved plans and specifications.

X1.1.3 The installation of the EIFS is to be coordinated by the owner's authorized agent with work of other trades.

X1.1.4 Surfaces and accessories to receive EIFS components shall be examined and accepted as provided in 11.2 before the EIFS components are installed thereto. The proper authorities shall be notified about unacceptable conditions. The unsatisfactory conditions shall be corrected prior to the application of the EIFS components. Unsatisfactory conditions shall be corrected by the party or parties responsible for such conditions.

X1.1.5 The construction specifier shall describe, in the proper section of the project specifications, the physical characteristics of the surfaces to receive the EIFS.

X1.2 Design Considerations

X1.2.1 EIFS are attached to outside surfaces of all types of structures to provide weather resistant, energy efficient, and durable claddings. The claddings will be subjected to various exposures such as abrasion, vibration, moisture, freezing, thawing, negative and positive wind loading, ultraviolet light, acid rain, thermally induced expansion and contraction, and impact.

X1.2.2 Provide sufficient slope on faces of EIFS surfaces to prevent water, snow or ice from accumulating or standing. A minimum 6 in. (152 mm) in 12 in. (305 mm) (1:2) pitch is recommended. Length of sloped surfaces shall not be more than 12 in. (305 mm).

X1.2.3 Provide parapet cap made only from corrosion resistant materials. The parapet cap shall extend not less than 2½ in. (64 mm) over the faces of the EIFS, not including wood blocking and include a drip edge detail. Detailed requirements for furnishing and installing the parapet cap shall be in the appropriate section of the project specifications. Parapet caps

shall be clearly shown in large scale details. Parapet caps shall be installed as soon as practical after the installation of the EIFS.

X1.2.4 Provide for sealing of expansion joints, panel joints, system terminations and all interfaces of the EIFS with other building components.

X1.2.5 At soffits, window and door heads provide for a drip edge.

X1.2.6 Windows installed in EIFS walls shall have a sill pan flashing of corrosion-resistant material.

X1.2.7 The specifier shall evaluate the potential of the EIFS surface being subjected to abnormal stresses or impacts.

X1.2.8 Wall assemblies have properties that in certain applications make a dew point analysis critical to ensure successful performance of the wall system. The specifier shall evaluate these conditions.

X1.2.9 Sheathing must be continuous over floor slabs, intersecting walls, columns, beams and similar constructions. The EIFS shall not be installed over areas without sheathing. If the sheathing cannot be continuous, the installation of expansion joints shall be considered.

X1.2.10 Where the sheathing is interrupted or out of plane, corrections must be made prior to EIFS application.

X1.2.11 A weather resistive barrier and flashings may be required and specified in moisture and water sensitive construction. The EIFS producer, architect, and specifier shall evaluate the conditions and determine the need.

X1.3 Relief From Stress

X1.3.1 Where the EIFS and dissimilar types of substrates, materials and building components interface, provide for appropriate size and location of expansion joints.

X1.3.2 Where roof elevations change, provide for appropriate size and location of expansion joints.

X1.4 Bonding Agents

X1.4.1 Bonding compounds or agents are sometimes applied to the insulation board surface prior to base coat application. Follow the EIFS producer's instructions and specifications for their use.

X1.5 Mechanical Fasteners

X1.5.1 The types of mechanical fasteners used and the methods of installation will vary depending upon the substrate to which the insulation boards are to be fastened.

X1.5.2 Fastener washers shall be installed flush with the insulation board surface.

X1.5.3 Fastener spacing shall be specified by the design professional consistent with wind load requirements and the local building code on the specific project.

X1.6 Reinforced Base Coats

X1.6.1 Base coat thickness is permitted to exceed $\frac{1}{16}$ in. (1.6 mm) dry depending on the type of base coat used and the impact resistance specified.

X1.6.2 A small amount of base coat shrinkage is normal. Due to color variations, a very slight telegraphing of the reinforcing mesh pattern may appear after the base coat cures. Bare mesh shall not be visible and the mesh pattern shall not be tactile.

X1.6.3 The producer's instructions shall be followed to ensure that the base coat and cement are properly proportioned. The proper portioning of cement-based material is important. Excess cement may cause the base coat to become hard and stiff as the cement hydrates over time.

X1.6.4 The minimum amount of mix water to form a workable mix shall be used. Excess mix water causes the base coat to be porous, less weather resistant, and contribute to shrinkage. Never add more water than recommended by the producer. Measure water in containers of known volume.

X1.6.5 Mix materials only at low speed with paddles designed to reduce air entrapment.

X1.6.6 Generally, when applying 2 layers of mesh, the second base coat layer is applied as soon as the first layer has dried sufficiently to receive the second base coat application. Depending upon material composition and weather conditions, this sometimes occurs within the first 24 h after the completion of the application of the initial base coat, and, in some cases, it will require waiting until the following day.

X1.6.7 Trowel aesthetic reveals and corners with a trowel shaped to fit the profiles.

X1.7 Finish Textures

X1.7.1 Textures, as a description of surface appearance, generally are identified with the method and tools used to achieve the finish appearance. Texture is sometimes varied by the size and shape of the aggregate contained in the finish, equipment or tools employed, the consistency of the finish mix, the condition of the base to which it is applied and by decorative and protective treatments.

X1.7.2 With almost limitless variations possible for finish appearance or texture, the same term sometimes does not have the same meaning to the specifier, contractor or applicator. Sample panels of sufficient size including components and features specified shall be constructed using the methods, tools and techniques to be used in the actual construction. It is recommended that in the case of prefabrication, two panels be constructed. One panel remains at the jobsite. One panel remains at the fabrication site. The samples shall be approved by the architect and owner in writing.

X1.7.3 To provide some guidance, the following categories are generally understood and recognized to imply a particular method of application or finished appearance.

X1.7.3.1 *Sand Finish*—A finish material devoid of coarse aggregate applied in a thin coat completely covering the base coat and floated to a true plane, yielding a relatively fine-textured finish.

X1.7.3.2 *Trowel Texture*—A freshly applied finish is given various textures, designs or stippled effects by hand motion and trowel used. The effects achieved are individualized and it is sometimes difficult for different applicators to duplicate.

X1.7.3.3 *Standard Finish*—A finish with various size aggregates, applied in a thin coat completely covering the base coat and floated in a random pattern. The applicators are cautioned to use the same type texturing tools to help ensure a consistent texture.

X1.7.3.4 *Exposed Aggregate*—Varying sizes of natural or manufactured stone, gravel, shell or ceramic aggregates are embedded by hand or by machine propulsion into a freshly applied "bed coat." The size of the aggregate shall not be more than $\frac{1}{2}$ in. (12.7 mm) diameter. The size of the aggregate determines the thickness of the bedding coat. The bedding coat shall be no less than one-half the thickness of the aggregate to be embedded.

X1.7.3.5 *Spray Texture*—A machine applied finish material. The texture achieved depends on many factors some of which are the consistency of the sprayed mixture, the angle and distance of the spray nozzle to the surface, the pressure of the machine, orifice size used, operator expertise, climatic conditions (wind specifically), and base coat conditions.

X1.7.3.6 *Miscellaneous Types*—Similar to trowel textures except that the freshly applied finish is textured with instruments other than a trowel, such as swept with a broom or brush, or corrugated by raking or combing. A variation of texturing a finish involves waiting until the applied finish has partially dried and then lightly troweling the unevenly applied finish. The effects achieved are sometimes difficult for different applicators to duplicate.

X1.8 Conditions for EIFS Application

X1.8.1 The amount of water used to mix materials is to be within the allowable range published by the EIFS producer. Factors such as the drying conditions and finishing operations must be considered in determining water usage. The applicator is cautioned that the use of excessive water results in fall off or slide off, excessive shrinkage, higher porosity, lower strength, and inconsistent color.

X1.8.2 Timing between coats will vary with climatic conditions and types of materials used. Temperature and relative humidity extend or reduce the curing and drying time. Cold or wet weather lengthens and hot or dry weather shortens the drying period. Moderate changes in temperature and relative humidity are overcome by providing additional heating during cold weather and by pre-wetting the base during hot, dry weather.

X1.8.3 Heated enclosures require adequate air circulation to prevent hot or cold spots that allow too rapid drying or freezing. When using heated enclosures it is important to

control the relative humidity as well as the temperature. Maintain relative humidity at not more than 90 %.

X1.8.4 Staining and discoloration of finishes or other building components that are caused by free water draining from

one plane to another, dissimilar materials, or other building components, are minimized by providing sufficient depth and angle for drip caps and drip edges.

X2. SEALANT SYSTEMS

X2.1 The size and location of joints and selection of the sealant to be used is the responsibility of the design professional and shall be consistent with project conditions and guidelines of the EIFS producer. See Guide **C1472** for guidance.

X2.2 The sealant system must be tested for compatibility with the specified EIFS by an independent laboratory and found to be compatible with the EIFS. See Test Method **C1382** for guidance.

X2.3 The sealant system is recommended by the EIFS and sealant producer. Non-recommended sealant systems must be jointly approved by the architect and the sealant producer.

X2.4 Base the joint design and surface preparation on the sealant producer's recommendations and project conditions. See Guide **C1481** for guidance.

X2.5 Allow the EIFS material to cure prior to sealant system installation.

SUMMARY OF CHANGES

Committee C11 has identified the location of selected changes to this practice since the last issue, C1535 – 04, that may impact the use of this practice. (Approved October 1, 2005)

(1) Added Specification **C1325** to Referenced Documents.

(2) Added new paragraph **11.3.11**.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).