



Standard Specification for Adhered Manufactured Stone Masonry Veneer Units¹

This standard is issued under the fixed designation C1670/C1670M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

The purpose of this standard is to establish the minimum product specifications for adhered manufactured stone masonry veneer units. These units are manufactured using a wet cast concrete mixture and finished to simulate stone, rocks found in nature, and other textures.

1. Scope*

1.1 This specification covers the minimum product requirements for adhered manufactured stone masonry veneer units applied as an adhered veneer to exterior and interior walls and structures suitable to receive units.

1.2 The property requirements of this specification apply at the time of delivery. This standard does not address the physical evaluation of installed units removed from service.

1.3 The units described by this specification are manufactured from a mixture of cement, normal or lightweight aggregates (or a combination of both), water, admixtures, other cementitious materials and other components which are wet-cast into shapes simulating the appearance of natural stone and other textures.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.5 The text of this specification references notes and footnotes which provide explanatory material. These notes and footnotes shall not be considered as requirements of the standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use of units.*

NOTE 1—When particular features are desired such as surface textures

¹ This test method is under the jurisdiction of ASTM Committee C15 on Manufactured Masonry Units and is the direct responsibility of Subcommittee C15.03 on Concrete Masonry Units and Related Units.

Current edition approved Aug. 1, 2014. Published September 2014. Originally approved in 2013. Last previous edition approved in 2013 as C1670/C1670M – 13a. DOI: 10.1520/C1670_C1670M-14.

or color these features should be specified separately. Suppliers should be consulted as to the availability of units having the desired features.

2. Referenced Documents

2.1 ASTM Standards:

- C31/C31M Practice for Making and Curing Concrete Test Specimens in the Field
- C33 Specification for Concrete Aggregates
- C39/C39M Test Method for Compressive Strength of Cylindrical Concrete Specimens
- C140 Test Methods for Sampling and Testing Concrete Masonry Units and Related Units
- C150 Specification for Portland Cement
- C207 Specification for Hydrated Lime for Masonry Purposes
- C260 Specification for Air-Entraining Admixtures for Concrete
- C330 Specification for Lightweight Aggregates for Structural Concrete
- C331 Specification for Lightweight Aggregates for Concrete Masonry Units
- C426 Test Method for Linear Drying Shrinkage of Concrete Masonry Units
- C482 Test Method for Bond Strength of Ceramic Tile to Portland Cement Paste
- C494/C494M Specification for Chemical Admixtures for Concrete
- C595 Specification for Blended Hydraulic Cements
- C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
- C666/C666M Test Method for Resistance of Concrete to Rapid Freezing and Thawing
- C979 Specification for Pigments for Integrally Colored Concrete
- C989 Specification for Slag Cement for Use in Concrete and Mortars
- C1116/C1116M Specification for Fiber-Reinforced Concrete
- C1157 Performance Specification for Hydraulic Cement

*A Summary of Changes section appears at the end of this standard



C1232 Terminology of Masonry

C1240 Specification for Silica Fume Used in Cementitious Mixtures

3. Terminology

3.1 Terminology defined in Terminology C1232 shall apply for this specification.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *adhered manufactured stone masonry veneer unit, n*—a non-load bearing masonry unit that is produced by wet-cast blending of cementitious material, lightweight and other aggregates, pigments and admixtures, designed to be applied with a cementitious mortar to a backing surface.

3.2.2 *unit profile, n*—the combination of units that represent the range of shapes and sizes provided in the specified veneer.

3.2.3 *average thickness, n*—the mean of the depth measurement of the unit as measured from the back side to the face side.

3.2.4 *designated area, n*—the area of a completed wall section that is used to verify compliance.

3.2.5 *saturated density, n*—the water saturated weight of the cured specimen divided by the volume of the specimen.

3.2.6 *wet cast, adj*—manufactured from a measurable slump concrete.

4. Materials

4.1 Cementitious materials shall conform to the following applicable specifications:

4.1.1 *Portland Cement*—Specification C150.

4.1.2 *Blended Hydraulic Cements*—Specification C595.

4.1.3 *Pozzolans*—Specification C618.

4.1.4 *Slag Cement*—Specification C989.

4.1.5 *Hydraulic Cement*—Specification C1157.

4.1.6 *Silica Fume*—Specification C1240.

4.1.7 *Hydrated Lime*—Specification C207.

4.2 *Aggregates*—Aggregates shall conform to the following specifications:

4.2.1 *Normal Weight Aggregates*—Specification C33.

4.2.2 *Lightweight Aggregates*—Specification C330 or C331.

4.3 *Air-Entraining Admixtures*—Specification C260.

4.4 *Concrete Admixtures*—Specification C494/C494M.

4.5 *Coloring Pigments*—Specification C979.

4.6 *Reinforcement Fibers*—Specification C1116/C1116M.

4.7 *Other Constituents:*

4.7.1 Other constituent materials shall be shown by test of experience or history of performance under equivalent conditions not to be detrimental to the durability of the adhered manufactured stone masonry veneer unit, or adhered manufactured stone masonry veneer construction, or both.

5. Compressive Strength

5.1 From each manufacturing location, obtain representative samples from standard production of each concrete mix used for units in accordance with 5.2.

5.1.1 Sample and test the concrete mixes used for units no more than twelve months prior to production of units. More frequent testing shall be required if there is any change in the manufacturing process including changes in cementitious materials or their sources, aggregates or their sources, water-cementitious materials ratio, mix design, manufacturing process or curing. This does not include producing units of varying shapes, configurations or sizes of units.

5.2 Sample the concrete mix at the manufacturing facility from standard production mix. Form compressive strength and absorption specimens in accordance with Practice C31/C31M; except that the time requirements for transportation do not apply when specimens are shipped to the testing laboratory.

5.2.1 For compressive strength testing, prepare five 4-in. diameter by 8 in. [100 mm by 200 mm] cylinders and test in accordance with 5.3. Do not disturb the curing cylinders for a minimum of 48 hours after casting. De-mold them at an age of seven days.

5.3 Test specimens at an age of 28 days in accordance with Test Method C39/C39M.

5.4 The average compressive strength of five specimens shall be a minimum of 2100 psi [15 MPa] with no individual specimen having a measured compressive strength less than 1800 psi [12 MPa].

6. Freeze-Thaw Durability

6.1 From each manufacturing location, obtain representative samples from standard production of each concrete mix used for units in accordance with 6.2.

6.1.1 Sample and test the concrete mixes used for units no more than twelve months prior to production of units. More frequent testing shall be required if there is any change in the manufacturing process including changes in cementitious materials or their sources, aggregates or their sources, water-cementitious materials ratio, mix design, manufacturing process or curing. This does not include producing units of varying shapes, configurations or sizes of units.

6.2 Sample the concrete mix at the manufacturing facility from standard production mix in accordance with Practice C31/C31M except that the time requirements for transportation do not apply when specimens are shipped to the testing laboratory.

6.2.1 For freeze/thaw durability testing, prepare five 3 in. by 3 in. by 11 in. [75 mm by 75 mm by 275 mm] beams. The molded beams shall be de-molded 24–32 hours after casting and shall be air cured for 28 days.

6.3 *Testing Requirements:*

6.3.1 No single specimen in a group of five specimens shall exhibit a mass loss greater than 1.5 % or show any fracture completely through the cross section when tested in accordance with Test Method C666/C666M, Procedure A, with the following modifications:

6.3.1.1 The molded beams are subjected to 50 consecutive cycles of freezing and thawing.

6.3.2 Determine mass loss in accordance with the following procedure:

6.3.2.1 Following immersion in water for a period of 48 hours, the initial specimen mass shall be measured. Excess surface water shall be immediately removed by blotting with damp cloth or fabric towel prior to mass measurement;

6.3.2.2 Following the completion of 50 freeze thaw cycles in accordance with Test Method **C666/C666M**, Procedure A, the specimens shall be removed from the containers and excess surface water shall be removed by blotting with damp cloth or fabric towel;

6.3.2.3 The Percent Mass Loss (PWL) for each specimen shall be determined at 50 cycles and be calculated as follows:

$$\text{PWL (beam), \%} = [(M_0 - M_1)/M_0] \times 100$$

where:

PWL (beam) = percent mass loss of beam
 M_0 = initial mass of beam following 48-hour saturation
 M_1 = final mass of beam following 50 freeze/thaw cycles

6.3.2.4 Any test specimen which fractures completely through the cross section into two or more discrete sections shall be recorded as a failure.

6.3.3 In the case of specimen failure under **6.3.2.4**, the failure mode must be reported in detail.

NOTE 2—Freeze-thaw testing is conducted on prism samples cast from representative concrete mix designs. While each manufacturer takes precautions to ensure that the surface color is durable, this freeze-thaw testing does not include a colored prism sample.

7. Shear Bond

7.1 From each manufacturing location, obtain a minimum of five (5) samples of units that are representative of the unit profile from which they are selected, using the same cementitious materials, aggregates, mix design, manufacturing process and curing.

7.1.1 Sampling and testing should be performed at least annually to meet the requirements of this standard.

7.2 Each unit tested shall develop a shear bond strength with the mortar substrate of not less than 50 psi [350 kPa] when tested in accordance with Test Method **C482** with the following modifications (listed in **7.2.1** through **7.2.5**):

7.2.1 Test a minimum of five (5) units at a minimum age of 28 days after manufacture.

NOTE 3—Test Method **C482** requires curing for seven (7) days following fabrication of test specimens. It is acceptable to begin fabrication of shear bond specimens 21 days following manufacture of the units.

7.2.2 Use the mortar substrate for non-vitreous tile (water absorption greater than 7 %).

7.2.3 Use a unit that can be cut into a sample with minimum dimensions of 2 ¼ in. by 2 ¼ in. [60 mm by 60 mm] and maximum dimensions of 4 in. by 4 in. [100 mm by 100 mm], with a thickness no greater than 2 ⅝ in. [70 mm]. This sample is to be cut containing the back pattern of the unit throughout the entire back face.

7.2.4 Use a ½ in. [13 mm] by ½ in. [13 mm] steel bar (in place of the key) whose length shall be sufficient to reach the

outer edges of the sample unit across its length. The steel bar shall be placed adjacent and parallel to the sample mortar interface.

7.2.5 Evaluate shear bond results of actual bonding surface of unit as manufactured. If the back surface of the unit used for testing has a directional back pattern, this back pattern shall be parallel to the direction of loading.

8. Water Absorption and Density

8.1 From each manufacturing location, obtain a minimum of three (3) samples of units that are representative of the unit profile from which they are selected, using the same cementitious materials, aggregates, mix design, manufacturing process and curing.

8.1.1 Sampling and testing should be performed at least annually to meet the requirements of this standard.

8.2 Absorption:

8.2.1 At a minimum age of 28 days after manufacture, average absorption of three units shall be tested in accordance with Test Methods **C140**. Units shall be permitted to be cut with a saw if the testing facility cannot accommodate a full-sized unit.

8.3 Density:

8.3.1 The saturated density of the units shall be determined from the weights obtained during absorption testing (in accordance with Test Methods **C140** and **8.2.1**) using the following calculation:

Saturated Density, lb/ft³, $((W_s)/(W_s - W_i)) \times 62.4$ for inch-pound units
 Saturated Density, kg/m³, $((W_s)/(W_s - W_i)) \times 1000$ for SI units

where:

W_s = saturated weight of specimen, lb [kg]
 W_i = immersed weight of specimen lb [kg]

8.3.2 The weight per square foot of the unit shall be determined by multiplying the saturated density of the unit by the average thickness, and shall not exceed 15 lb/ft² [73 kg/m²].

9. Dimensional Tolerances

9.1 From each manufacturing location, obtain a minimum of six (6) samples of units that are representative of the unit profile from which they are selected, using the same cementitious materials, aggregates, mix design, manufacturing process and curing.

9.1.1 Sampling and testing should be performed at least annually to meet the requirements of this standard.

9.2 Dimensions:

9.2.1 Units shall have a minimum thickness of ¼ in. [6 mm] except those parts of a unit within 0.5 in. [13 mm] of the unit perimeter.

9.2.2 The average thickness² of each unit shall be less than or equal to 2 ⅝ in. [67 mm].

9.2.3 Units shall not exceed 36 in. [915 mm] in any face dimension and shall not exceed more than 5 ft² [0.5 m²] in total face area.

² Annex A1 contains one method for determining average thickness.



9.3 Linear Drying Shrinkage:

9.3.1 At the time of delivery to the purchaser, the linear shrinkage of the specimen sample shall not exceed 0.065 % when tested in accordance with Test Method C426.

10. Finish and Appearance

10.1 The finish and appearance requirements shall apply to units at the time of delivery to the jobsite and acceptance by the purchaser.

10.2 Units shall not show defects, deficiencies or protrusions on any surface that interfere with installation or significantly impair the performance of the construction.

10.3 Unit profile names, color range and textures of the units shall be specified by the purchaser. The finished faces shall conform to approved samples representing the range of textures and colors selected.

NOTE 4—An approved sample typically consists of manufacturer's samples, individual units, or field mock-ups when specified.

10.4 Finished faces shall not have any chips with a dimension exceeding 0.75 in. [20 mm] or an aggregate length of chips that exceed 10 % of the perimeter of the finished face of the unit.

10.5 Finished faces of the unit shall not contain cracks, crazing, scuffing, or other imperfections that detract from the appearance of the designated area when viewed from a distance of 20 ft [6 m] under diffused lighting.

10.6 A shipment shall not contain more than 5 % of units, including broken units, that do not meet the requirements of 10.2, 10.3, 10.4, and 10.5.

NOTE 5—Many broken units are usable during installation. Units are commonly broken or saw-cut by the installer to fit into particular areas of the construction.

11. Product Identification and Packaging

11.1 Each package shall identify the manufacturer's name, profile name, location of manufacture, minimum quantity contained, and statement of product conformity to this specification.

12. Reporting

12.1 A complete report with testing completed within twelve (12) months of manufacture of units, consisting of the following shall be made available upon request:

12.1.1 Sampling information.

12.1.2 Date, time, and name of individual molding or selecting specimens for test or both.

12.1.3 Density as determined in 8.3.

12.1.4 The weight per ft² [m²] of unit as determined in 8.3.

12.1.5 The maximum compressive load imposed on each sample along with the compressive strength in pounds per square inch as determined in 5.3.

12.1.6 The maximum load and shear bond strength as determined in Section 7.

12.1.6.1 Dimensions (maximum and minimum values), including average thickness of the test sample.

12.1.6.2 The location of failure of each specimen; indicate whether it is in the unit itself, between specimen and bond coat, between bond coat and mortar setting bed, or in the setting bed itself.

12.1.7 Absorption to the nearest 0.1 lb/ft³ [1 kg/m³] as determined in 8.2.

12.1.8 Freeze-thaw results as determined in 6.3.

13. Keywords

13.1 adhered; cementitious; concrete; manufactured; manufactured stone; masonry; veneer

ANNEX

(Mandatory Information)

A1. PROCEDURE FOR DETERMINING AVERAGE THICKNESS

A1.1 Scope

A1.1.1 This annex provides information on determining the average unit thickness of adhered manufactured stone masonry veneer units.

NOTE A1.1—Other methods than the one presented here for determining average thickness may exist. These other methods should be verified by comparing results to the method provided here.

A1.2 Sample Size

A1.2.1 From each manufacturing location, obtain a minimum of three (3) samples of units that are representative of the materials, concrete mix design, manufacturing process and curing method.

A1.3 Volume Measurement

A1.3.1 The net volume of each unit shall be determined by dividing the saturated weight (W_s) by the saturated density determined in accordance with 8.3.

A1.4 Area Measurement

A1.4.1 Determine the area of the unit using A1.4.2, A1.4.3, or A1.4.4.

A1.4.2 *Rectangular Units*—For rectangular units, measure the minimum and maximum length and width of each unit to the nearest 0.1 in. [2.5 mm]. Average the measured lengths and widths of each unit and calculate the average area of each unit by multiplying the average length and average width

A1.4.3 Circular or Oval Units—For circular or oval units, measure the length (defined as the largest diameter of each unit) and the width (defined as the smallest diameter of each unit) to the nearest 0.1 in. [2.5 mm]. Calculate the average area of each unit as follows:

$$\text{Area, in.}^2 [\text{mm}^2] = \Pi \times \left(\frac{\text{length}}{2} \right) \times \left(\frac{\text{width}}{2} \right)$$

A1.4.4 Non-Rectangular Units—For non-rectangular units the area of a unit shall be determined using **A1.4.4.1** or **A1.4.4.2**.

A1.4.4.1 Trace the outline of each unit onto graph paper. Count the number of squares inside the outline. Estimate the number of partial squares that are contained inside the outline. Add the total number of squares and determine the area of each unit by multiplying the number of squares counted by the area of each square on the graph paper.

A1.4.4.2 Cut a large, rectangular piece of graph paper to serve as control paper. Measure and record its area and mass. Divide the mass by area to compute the mass per unit area. Trace the outline of each unit onto graph paper. Cut out traced area and take weight of the paper cut out. Divide by weight by the mass per unit area of the control paper to calculate unit area.

A1.5 Average Thickness Calculation

A1.5.1 Determine the average thickness of each unit by dividing the unit volume determined in accordance with **A1.3** by the unit area determined in accordance with **A1.4**. The average of the three ACMV unit thicknesses shall be reported as the average unit thickness for the lot.

SUMMARY OF CHANGES

Committee **C15** has identified the location of selected changes to this standard since the last issue (C1670/C1670M – 13a) that may impact the use of this standard. (August 1, 2014)

- (1) Re-organized standard to more easily understand and apply the requirements.
- (2) Revised **5.1.1** and **6.1.1** to change phrase ‘volume of water’ to ‘water-cementitious materials ratio.’
- (3) Revised specimen forming requirements in **5.2** and **6.2**.
- (4) Added **Note 1** regarding specifying particular features.
- (5) Added **Note 3** regarding time frame for fabrication of shear bond specimens.

- (6) Revised **8.2.1** to remove the 10 % variability requirement for absorption; and revised **12.1.7** to require reporting absorption in lb/ft³.
- (7) The procedure in **Annex A1** for determining average thickness was updated.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/