



Standard Specification for Epoxy-Resin-Base Bonding Systems for Concrete¹

This standard is issued under the fixed designation C881/C881M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers two-component, epoxy-resin bonding systems for application to portland-cement concrete, which are able to cure under humid conditions and bond to damp surfaces.

1.2 This specification does not cover epoxy-resin-base bonding systems that have been modified by addition of components such as cement, fine aggregate, or fiber reinforcement. Additional testing may be required to meet applicable specifications for these applications.

1.3 This specification does not address the effects of creep on epoxy-resin-base bonding systems while under load or the potential for creep rupture. Additional testing is required for applications where creep and creep rupture are critical.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. Some values have only SI units because the inch-pound equivalents are not used in practice. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with this standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific hazards statements, see Section 9.

2. Referenced Documents

2.1 ASTM Standards:²

C882 Test Method for Bond Strength of Epoxy-Resin Systems Used With Concrete By Slant Shear

¹ This specification is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.25 on Organic Materials for Bonding.

Current edition approved Nov. 15, 2014. Published January 2015. Originally approved in 1978. Last previous edition approved in 2013 as C881/C881M-13. DOI: 10.1520/C0881_C0881M-14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

C884/C884M Test Method for Thermal Compatibility Between Concrete and an Epoxy-Resin Overlay
D570 Test Method for Water Absorption of Plastics
D638 Test Method for Tensile Properties of Plastics
D648 Test Method for Deflection Temperature of Plastics Under Flexural Load in the Edgewise Position
D695 Test Method for Compressive Properties of Rigid Plastics
D2556 Test Method for Apparent Viscosity of Adhesives Having Shear-Rate-Dependent Flow Properties Using Rotational Viscometry
D2566 Test Method for Linear Shrinkage of Cured Thermosetting Casting Resins During Cure (Withdrawn 1993)³

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *binder, n*—the cementitious part of a grout, mortar, or concrete that binds the aggregate or filler into a cohesive mass.

3.1.2 *bonding system, n*—the product resulting from the combination of all the components supplied for use as a bonding material.

3.1.3 *component, n*—a constituent that is intended to be combined with one or more other constituents to form a bonding system.

3.1.4 *contact strength, n*—bond strength measured by slant shear after a specified contact and cure time.

3.1.5 *contact time, n*—specified time between when the epoxy system is applied and when the two segments are bonded together and still achieve a specified bond strength after a specified curing time and temperature.

3.1.6 *curing agent, n*—a substance that causes the conversion of a fluid resin system to a solid cured resin by means of a chemical reaction.

3.1.7 *epoxy equivalent, n*—the weight of resin containing one molecular weight of epoxy groups.

3.1.8 *epoxy resin, n*—a resin that contains or did contain epoxy groups principally responsible for its polymerization.

³ The last approved version of this historical standard is referenced on www.astm.org.

*A Summary of Changes section appears at the end of this standard



3.1.9 *filler, n*—a finely divided solid, predominantly passing the No. 200 [75- μ m] sieve, that is used to improve certain properties of the bonding system or to reduce cost.

3.1.10 *formulator, n*—the agency responsible for preparing the separate components and for recommending the proportions to be used in preparing the final bonding system.

3.1.11 *lot or batch, n*—that quantity of manufactured material which has been subjected to the same unit chemical or physical processes intended to make the final product substantially uniform.

3.1.12 *manufacturer, n*—a producer of a basic constituent part of a component.

3.1.13 *reactive diluent, n*—a relatively free flowing liquid used to reduce the viscosity of the liquid resin or resin mixture, and which contains reactive groups that cause it to become an integral part of the cured resin.

3.1.14 *working (pot) life, n*—the time after mixing during which a bonding system or mixture containing it retains sufficient workability for proper use.

4. Classification

4.1 This specification provides for the classification of epoxy-resin bonding systems by type, grade, class, and color.

4.2 *Types*—Seven types of systems that are distinguished by the requirements of Table 1 are recognized:

4.2.1 *Type I*—For use in non-load bearing application for bonding hardened concrete to hardened concrete and other materials, and as a binder in epoxy mortars or epoxy concretes.

4.2.2 *Type II*—For use in non-load bearing applications for bonding freshly mixed concrete to hardened concrete.

4.2.3 *Type III*—For use in bonding skid-resistant materials to hardened concrete and as a binder in epoxy mortars or epoxy concretes used on traffic bearing surfaces (or surfaces subject to thermal or mechanical movements).

4.2.4 *Type IV*—For use in load bearing applications for bonding hardened concrete to hardened concrete and other materials and as a binder for epoxy mortars and concretes.

4.2.5 *Type V*—For use in load bearing applications for bonding freshly mixed concrete to hardened concrete.

4.2.6 *Type VI*—For bonding and sealing segmental precast elements, as in segment-by-segment erection, and for span-by-span erection when temporary post tensioning is applied.

4.2.7 *Type VII*—For use as a nonstress carrying sealer for segmental precast elements when temporary post tensioning is not applied as in span-by-span erection.

NOTE 1—Epoxy resin systems will adhere to a wide variety of materials, including wood, metals, masonry, and most plastics. Polyethylene, TFE-fluorocarbon, cellophane, and greased or waxed surfaces are among the few materials to which these systems will not adhere.

4.3 *Grades*—Three grades of systems are defined according to their flow characteristics and are distinguished by the viscosity and consistency requirements of Table 1.

4.3.1 *Grade 1*—Low viscosity.

4.3.2 *Grade 2*—Medium viscosity.

4.3.3 *Grade 3*—Non-sagging consistency.

4.4 *Classes*—Classes A, B, and C are defined for Types I through V, and Classes D, E, and F are defined for Types VI and VII, in accordance with the range of temperatures for which they are suitable (Note 2).

4.4.1 *Class A*—For use below 40 °F [4 °C] the lowest allowable temperature to be defined by the manufacturer of the product.

4.4.2 *Class B*—For use between 40 and 60 °F [4 and 15 °C].

4.4.3 *Class C*—For use above 60 °F [15 °C] the highest allowable temperature to be defined by the manufacturer of the product.

4.4.4 *Class D*—For use between 40 and 65 °F [4 and 18 °C] for Type VI and VII applications.

4.4.5 *Class E*—For use between 60 and 80 °F [15 and 30 °C] for Type VI and VII applications.

4.4.6 *Class F*—For use above 75 °F [25 °C] for Type VI and VII applications, the highest allowable temperature to be defined by the manufacturer of the product.

NOTE 2—The temperature in question is usually that of the surface of the hardened concrete to which the bonding system is to be applied. This temperature may be considerably different from that of the air. Where unusual curing rates are desired it is possible to use a class of bonding agent at a temperature other than that for which it is normally intended. For example, a Class A system will cure rapidly at room temperature.

4.5 *Color*—Epoxy resin systems are normally unpigmented, but they can be colored or darkened. If a specific color is desired, it should be so stated by the purchaser.

5. Ordering Information

5.1 The purchaser shall specify the type, grade, class, and color of bonding system desired and the size of units in which the components shall be furnished. Special requirements regarding filling of either the components or the final bonding system should be stated. The product furnished under this specification is intended to be resistant to moisture and therefore should be suitable for either indoor or outdoor exposure.

5.2 The purchaser may specify a minimum gel time of 5 min for Types I and IV when automatic proportioning, mixing, and dispensing equipment are used.

6. Materials and Manufacture

6.1 The systems covered by this specification shall be furnished in two components for combining immediately prior to use in accordance with written instructions of the formulator. Component A shall contain an epoxy resin with or without a reactive diluent. Component B shall contain one or more curing agents, which on mixing with Component A shall cause the mixture to harden. A suitable inert filler may be uniformly incorporated in one or both components. The filler shall be either nonsettling or readily dispersible in any component in which it is incorporated. All systems shall cure under humid conditions, and bond to damp surfaces.

7. Chemical Composition

7.1 The epoxy resin constituent of Component A shall have an epoxy equivalent of 155 to 275.



TABLE 1 Physical Requirements of Bonding Systems

Property	Type						
	I	II	III	IV	V	VI	VII
Viscosity, P [Pa·s]:							
Grade 1, max	20[2.0]	20[2.0]	20[2.0]	20[2.0]	20[2.0]	...	...
Grade 2, min	20[2.0]	20[2.0]	20[2.0]	20[2.0]	20[2.0]	...	...
max	100[10]	100[10]	100[10]	100[10]	100[10]	...	...
Consistency, in [mm]:							
Grade 3, Types I, II, III, IV, V, VI, VII, max	¼ [6.0]	¼ [6.0]	¼ [6.0]	¼ [6.0]	¼ [6.0]	¼ [6.0]	¼ [6.0]
Gel time, minutes, min	30	30	30	30	30	30	30
Bond strength, min, psi [MPa]:							
2 days (moist cure)	1000[7.0]	...	...	1000[7.0]	...	1000[7.0]	...
14 days (moist cure)	1500[10.0]	1500[10.0]	1500[10.0]	1500[10.0]	1500[10.0]	...	1000[7.0]
Absorption, 24 h max, %	1	1	1	1	1	...	...
Heat Deflection Temperature, min, °F [°C]:							
7 days	...	...	...	120[50]	120[50]	...	...
14 days	...	...	...	...	...	120[50]	120[50]
Thermal compatibility	...	...	passes test	...	...	...	...
Linear coefficient of shrinkage on cure, max	0.005	0.005	...	0.005	0.005	...	...
Compressive Yield Strength, min, psi [MPa]:							
24 h	...	...	...	...	...	2000[14.0]	...
36 h	...	...	...	...	...	...	1000[7.0]
48 h	...	...	...	...	...	6000[40.0]	...
72 h	...	...	...	...	...	...	2000[14.0]
7 days	8000[55.0]	5000[35.0]	...	10 000[70.0]	8000[55.0]	...	...
Compressive Modulus, psi [MPa]							
Min	150 000[1000]	90 000[600]	...	200 000[1400]	150 000[1000]	...	...
Max	...	...	130 000[896]	...	...	...	...
Tensile Strength, 7 days min, psi [MPa] ^A	5000[35.0]	2000[14.0]	...	7000[50.0]	6000[40.0]	...	...
Elongation at Break, %, min ^A	1	1	30	1	1	...	...
Contact strength, psi [MPa] min							
2 days	...	...	...	...	...	1000[7.0]	...
14 days	...	...	...	...	...	...	1000[7.0]

^ANot required for Viscosity Grade 3 Systems.

8. Physical Properties

8.1 A mixture of Components A and B in the proportions recommended by the formulator shall conform to the properties prescribed in Table 1.

9. Safety Hazards

9.1 **Caution:** Epoxy resins contain irritants, especially to the skin, eyes, and respiratory system. Persons handling these materials shall use appropriate protective clothing, including rubber or plastic gloves. If an epoxy resin should contact the

skin, it shall be removed immediately with a dry cloth or paper towel, and the area of contact washed thoroughly with soap and water. Solvents shall *not* be used, because they carry the irritant into the skin. Cured epoxy resins are innocuous.

10. Sampling

10.1 Take a representative sample of each of the two components from a well-blended lot prior to packaging or by withdrawing samples from no fewer than 5 % of the containers comprising the lot or shipment. Unless the samples of the same

component taken from containers show visual evidence of variability, they may be combined into a single composite sample. In place of the foregoing, packaged materials may be sampled by a random selection of containers of each component from each lot, provided such a procedure is acceptable to the purchaser.

11. Test Methods

11.1 *Consistency*—Test Method to Determine The Consistency of an Epoxy Resin System.

11.1.1 *Scope*—This test provides a method for determining the consistency of Grade 3 epoxy resin systems.

11.1.2 *Significance and Use*—This test method is used to determine compliance with the requirements of the specification.

11.1.3 *Apparatus*:

11.1.3.1 *Paper cup*—Approximately 3 oz. [approximately 0.100L] unwaxed paper cup.

11.1.3.2 *Mixing blade*—Ordinary wooden tongue depressor or stick of similar size.

11.1.3.3 *Glass panel*.

11.1.4 *Conditioning*—Condition the individual components and any equipment with which they will come in contact to the following temperatures: Class A, $32 \pm 2^\circ\text{F}$ [$0 \pm 1^\circ\text{C}$]; Class B, $50 \pm 2^\circ\text{F}$ [$10 \pm 1^\circ\text{C}$]; Class C, $73 \pm 2^\circ\text{F}$ [$23 \pm 1^\circ\text{C}$]; Class D, $65 \pm 2^\circ\text{F}$ [$18 \pm 1^\circ\text{C}$]; Class E, $80 \pm 2^\circ\text{F}$ [$27 \pm 1^\circ\text{C}$]; Class F, $90 \pm 2^\circ\text{F}$ [$32 \pm 1^\circ\text{C}$] or to the temperature at which the material will be used (Note 2).

11.1.5 *Procedure*—Prepare approximately 30 cm³ of the bonding system. Weigh the necessary amounts of the components to an accuracy of 1 % into a single 3-oz [approximately 100-cm³] unwaxed paper cup. Mix immediately with a wooden tongue depressor or stick of similar size. Note the time at which mixing begins. Mix for 3 min, taking care to scrape the side and bottom of the cup periodically. Immediately apply about 2 cm³ of the mixture to a glass panel. Form a semicylindrical bead of the bonding system by drawing the applicator blade through the sample in a straight line with the panel horizontal. Immediately raise the panel to a position inclined at no greater than 10° from vertical and with the bead horizontal. Maintain the panel and sample at their original temperature until the bonding system has cured, as determined by an inability to indent it appreciably with a pencil point or fingernail. Determine the consistency by measuring the flow of the lower edge of the bead from its original position at three points along its length.

11.1.6 *Report*—Report the average value to the nearest 1/8 in. [1 mm].

11.1.7 *Precision and Bias*:

11.1.7.1 *Precision*—The precision of the procedure in this test method for consistency is being determined.

11.1.7.2 *Bias*—This test method has no bias since the values determined can only be defined in terms of this test method.

11.2 *Gel Time*:

11.2.1 Test Method to Determine the Gel Time of an Epoxy Resin System.

11.2.2 *Scope*—This test method determines the time after mixing when an epoxy resin system gels.

11.2.3 *Significance and Use*—This test method is used to determine compliance with the requirements of the specification.

11.2.4 *Apparatus*:

11.2.4.1 *Paper cup*—8 oz. [approximately 250 cm³] unwaxed paper cup

11.2.4.2 *Mixing blade*—Ordinary wooden tongue depressor or stick of similar size.

11.2.5 *Conditioning*—Condition the individual components and any equipment with which they will come in contact to the temperatures set forth in 11.1, depending on the class of system in question, or to the temperature at which the material will be used, providing that temperature is within the ranges established in 4.4 for Types I, II, III, and V. For Type VI and VII use the highest temperature of the specified class (Note 2). Prepare 60 g of the bonding system for Types I through V and 1 gal [4.0 L] for Types VI and VII using the procedures set forth in 11.1.

11.2.6 *Procedure*—Transfer as much as possible of the sample into an 8-oz [approximately 250-cm³] unwaxed paper cup and set it on a wooden surface in a location maintained at the original conditioning temperature and not subject to abnormal room air movement. Determine the time at which a soft, gelatinous mass forms in the center of the sample by probing every 2 min with a wooden tongue depressor or similar device, starting 8 min after the beginning of mixing.

11.2.7 *Report*—The gel time is the interval between the beginning of mixing and the formation of the gelatinous mass.

11.2.8 *Precision and Bias*:

11.2.8.1 *Precision*—The precision of the procedure in this test method for gel time is being determined.

11.2.8.2 *Bias*—This test method has no bias since the values determined can only be defined in terms of this test method.

11.3 *Viscosity*—Determine the viscosity of the freshly mixed resin system by means of Test Method D2556, except that the determination shall be made at the temperature given in 11.1 for the class of material in question and measurement at only one rotational speed is required.

11.4 *Absorption*—Determine the absorption by means of Test Method D570. The test specimens shall have the shape and dimensions specified for molded plastics, shall be cured for 14 days at a temperature of $73 \pm 2^\circ\text{F}$ [$23 \pm 1^\circ\text{C}$], shall be tested in accordance with the procedure for 24-h immersion and shall be reconditioned, if necessary, as directed in Test Method D570.

11.5 *Bond Strength*—Determine the bond strength in accordance with Test Method C882.

11.5.1 *Types I, III, IV, and VII Systems*—Condition the mortar sections soaking in water and all equipment that will contact the resin to the lowest application temperature of the specified class. For Class A, use a temperature of $35 \pm 2^\circ\text{F}$ [$2 \pm 1^\circ\text{C}$] for the water soaking to prevent freezing. Condition and mix the resin components at $73 \pm 2^\circ\text{F}$ [$23 \pm 1^\circ\text{C}$]. Apply the mixed epoxy to the mortar sections in accordance with Test Method C882. Cure the specimens at the lowest application temperature of the specified class. No more than 10 min shall elapse between the start of mixing and the placement of the specimens in the curing chamber.



11.5.2 *Type II and Type V Systems*—Because Type II and Type V resins are appropriate for use only at temperatures that permit strength gain of the freshly prepared concrete, only the conditioning temperature for a Class C resin, $73 \pm 2^\circ\text{F}$ [$23 \pm 1^\circ\text{C}$], need be provided.

11.6 *Thermal Compatibility*—Determine the thermal compatibility in accordance with Test Method C884/C884M.

11.7 *Heat Deflection Temperature*—Determine the heat deflection temperature in accordance with Test Method D648, except condition, mix, cure, and start testing the resin components at $73 \pm 2^\circ\text{F}$ [$23 \pm 1^\circ\text{C}$].

11.8 *Linear Coefficient of Shrinkage*—Determine the linear coefficient of shrinkage in accordance with Test Method D2566, except condition, mix, cure, and test the resin components at $73 \pm 2^\circ\text{F}$ [$23 \pm 1^\circ\text{C}$].

11.9 *Compressive Yield Strength and Modulus*—Determine the compressive yield strength and modulus in accordance with Test Method D695. Condition and mix the resin components at $73 \pm 2^\circ\text{F}$ [$23 \pm 1^\circ\text{C}$] and cure the specimens at the lowest application temperature of the specified class. No more than 10 min shall elapse between the start of mixing and the placement of the specimens in the curing chamber. After the specified cure time shown in Table 1, test at $73 \pm 2^\circ\text{F}$ [$23 \pm 1^\circ\text{C}$] without delay (See Note 3). Use of a $1 \times 1 \times 2$ -in. [$25 \times 25 \times 50$ -mm] specimen is also acceptable.

11.10 *Tensile Strength and Elongation at Break*—Determine the tensile strength and elongation at break in accordance with Test Method D638. Condition and mix the resin components at $73 \pm 2^\circ\text{F}$ [$23 \pm 1^\circ\text{C}$] and cure the specimens at the lowest application temperature of the specified class. No more than 10 min shall elapse between the start of mixing and the placement of the specimens in the curing chamber. After the specified cure time shown in Table 1, test at $73 \pm 2^\circ\text{F}$ [$23 \pm 1^\circ\text{C}$] without delay (See Note 3).

11.11 *Contact Strength*—Determine the contact strength in accordance with Test Method C882 except condition the material and the specimens at the highest application temperature of the specified class and apply the bonding system at a thickness of $\frac{1}{16}$ in. [2 mm] on the slanted surface of each half cylinder. Maintain at the highest application temperature and assemble the two half cylinders after 1 h for Type VI and 8 h for Type VII. Cure at the assembly temperature for the specified cure time shown in Table 1 and test at $73 \pm 2^\circ\text{F}$

[$23 \pm 1^\circ\text{C}$] without delay (See Note 3). Contact strength is expressed in units of strength (pounds per square inch or MPa) obtained after the specified time of cure shown in Table 1.

NOTE 3—The curing temperatures of these tests is not $73 \pm 2^\circ\text{F}$ [$23 \pm 1^\circ\text{C}$], but the test shall be run at $73 \pm 2^\circ\text{F}$ [$23 \pm 1^\circ\text{C}$] to allow laboratories without testing chambers to run the tests. The testing shall be run without delay after the specimens are removed from the curing chamber.

12. Rejection and Rehearing

12.1 The purchaser has the right to reject material that fails to conform to the requirements of this specification. Rejection shall be reported to the producer or supplier promptly and in writing. In case of dissatisfaction with the results of the test, the producer or supplier has the right to a rehearing.

12.2 If all requirements of this specification are met, except those pertaining to bond strength, the bond tests shall be repeated. If the sample again fails to meet the bond strength requirements, the entire lot shall be rejected.

12.3 *Retest*—Lots of material that have been rejected may be reworked by the producer to correct the defects and resubmitted for test provided specific approval of the purchaser has been obtained for such resubmission. Before resubmission of the material, full particulars concerning the action taken to correct the defects in the original material shall be made available to the purchaser.

13. Packaging and Package Marking

13.1 *Packaging*—The two components furnished under this specification shall be supplied in separate containers that are nonreactive with the contents. They are usually supplied in amounts such that the recommended proportions of the final mixture can be obtained by combining one container of Component A with one container of Component B.

13.2 *Marking*—Containers shall be identified as “Component A—Contains Epoxy Resin” and “Component B—Contains Curing Agent” and shall show the type, grade, class, and color. Each container shall be marked with the name of the formulator, the lot number, the date of packaging, the quantity contained therein, and the recommended mixing ratio, by both weight and volume.

14. Keywords

14.1 bonding; bonding systems; contact strength; contact time; epoxy resin



SUMMARY OF CHANGES

Committee C09 has identified the location of selected changes to this specification since the last issue, C881/C881M–13, that may impact the use of this specification. (Approved Nov. 15, 2014)

(1) Revised 2.1 and 11.3.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>