



Standard Test Method for Flexural Strength of Soil-Cement Using Simple Beam with Third-Point Loading¹

This standard is issued under the fixed designation D1635/D1635M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers the determination of the flexural strength of soil-cement by the use of a simple beam with third-point loading.

NOTE 1—For methods of molding soil-cement specimens, see Practice D1632.

1.2 All observed and calculated values shall conform to the guidelines for significant digits and rounding established in Practice D6026 unless superseded by this standard.

1.3 *Units*—The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard. The SI units are presented in brackets.

1.3.1 The gravitational system of inch-pound units is used when dealing with inch-pound units. In this system, the pound (lbf) represents a unit of force (weight), while the unit for mass is slugs. The rationalized slug unit is not given, unless dynamic ($F = ma$) calculations are involved.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards*:²

D653 Terminology Relating to Soil, Rock, and Contained Fluids

D1632 Practice for Making and Curing Soil-Cement Com-

pression and Flexure Test Specimens in the Laboratory
D3740 Practice for Minimum Requirements for Agencies
Engaged in Testing and/or Inspection of Soil and Rock as
Used in Engineering Design and Construction
D6026 Practice for Using Significant Digits in Geotechnical
Data
E4 Practices for Force Verification of Testing Machines

3. Terminology

3.1 For common definitions of terms in this standard, refer to Terminology D653.

4. Significance and Use

4.1 This test method is used to determine the flexural strength of soil-cement. Flexural strength is significant in pavement design and is used to determine slab thickness.

NOTE 2—The quality of the result produced by this standard is dependent on the competence of the personnel performing it, and the suitability of the equipment and facilities used. Agencies that meet the criteria of Practice D3740 are generally considered capable of competent and objective testing/sampling/inspection/etc. Users of this standard are cautioned that compliance with Practice D3740 does not in itself assure reliable results. Reliable results depend on many factors; Practice D3740 provides a means of evaluating some of those factors.

5. Apparatus

5.1 *Testing Machine*—The testing machine may be of any type having sufficient capacity and control to provide the rate of loading (prescribed in 7.2). It shall conform to the requirements of Section 15 of Practices E4. The testing machine shall be equipped with a spherically seated head block having a bearing surface of at least 75 % of the width of the beam but not greatly in excess of the width of the beam. The movable portion of this block shall be held closely in the spherical seat, but the design shall be such that the bearing face may be rotated freely and tilted through small angles in any direction.

5.2 The third-point loading method used in making flexure tests of soil-cement shall employ bearing blocks that will ensure that forces applied to the beam will be vertical only and applied without eccentricity. A diagrammatic drawing of an apparatus that accomplishes this purpose is shown in Fig. 1. The apparatus shall be designed to incorporate the following principles:

¹ This test method is under the jurisdiction of ASTM Committee D18 on Soil and Rock and is the direct responsibility of Subcommittee D18.15 on Stabilization With Admixtures.

Current edition approved May 1, 2012. Published June 2012. Originally approved in 1959. Last previous edition approved in 2000 as D1635-00(2006). DOI: 10.1520/D1635_D1635M-12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.



5.2.4 The directions of loads and reactions may be maintained parallel by judicious use of linkages, rocker bearings, and flexure plates. Eccentricity of loading can be avoided by use of spherical bearings.

6.3 Check the smoothness of the side faces of the beams at the points where loads will be applied with a straightedge. If necessary, cap the faces to meet the requirements of Section 15 of Practice **D1632**.

$$R = \frac{PL}{bd^2}$$



TABLE 1 Precision

	Average flexural strength, lbf/in. ² [MPa]	Standard deviation, lbf/in. ² [MPa]	Coefficient of variation, %
Specimens with 6 % cement	94 [0.65]	6 [0.04]	6.4
Specimens with 14 % cement	157 [1.08]	9 [0.06]	5.7

where:

R = modulus of rupture, lbf/in.² [MPa],

P = maximum applied load, lbf [N],

l = span length, in. [mm],

b = average width of specimen, in. [mm], and

d = average depth of specimen, in. [mm].

NOTE 4—Mass of the beam is not included in the above calculation.

9.2 If the fracture occurs outside the middle third of the span length by not more than 5 % of the span length, calculate the modulus of rupture as follows:

$$R = \frac{3Pa}{bd^2}$$

where:

a = distance between line of fracture and the nearest support, measured along the center line of the bottom surface of the beam, in. [mm].

9.3 If the fracture occurs outside the middle third of the span by more than 5 % of the span length, discard the results of the test.

10. Report

10.1 The report shall include the following:

10.1.1 Specimen identification number,

10.1.2 Average width and depth at section of failure to the nearest 0.01 in. [0.25 mm],

10.1.3 Maximum load, to the nearest 10 lbf [40 N],

10.1.4 Modulus of rupture, calculated to the nearest 5 lbf/in.² [0.05 MPa],

10.1.5 Defects, if any, in specimen,

10.1.6 Age of specimen, and

10.1.7 Details of curing and conditioning periods, and water content at time of test.

11. Precision and Bias

11.1 *Precision*—The precision of this test method has not been established by an interlaboratory test program. However, based on test data that are available, the following may serve as a guide to the variability of flexural strength test results.

11.1.1 Tests were performed in a single lab on a silt loam soil with 92 % passing the No. 200 [75-μm] sieve. Liquid limit and plasticity index of soil were 26 and 7, respectively. The series of tests consisted of 24 specimens, 12 at 6 % cement, 12 at 14 % cement. The specimens were cured in a moist room at 73 °F [23 °C] for 28 days. Results³ of the tests are given in Table 1.

11.2 *Bias*—There is no accepted reference value for this test method, therefore, bias cannot be determined.

12. Keywords

12.1 flexural strength; soil-cement; soil stabilization

³ Felt, E. J., Abrams, M. S., *Strength and Elastic Properties of Compacted Soil-Cement Mixtures*, ASTM STP 206, ASTM, 1957.

SUMMARY OF CHANGES

Committee D18 has identified the location of selected changes to this test method since the last issue, D1635–00(2006), that may impact the use of this test method. (Approved May 1, 2012)

(I) Revised the standard as a combined units test method with SI units presented in brackets, including revision to Fig. 1.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).