



Standard Test Method for Thermal Endurance of Electrical Insulating Varnishes by the Helical Coil Method¹

This standard is issued under the fixed designation D3145; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This test method covers the determination of the thermal endurance of electrical insulating varnishes alone or in combinations with magnet wire insulation. Changes in the helical coil bond strength are used as the test criteria. The coils are made from bare aluminum or copper wire, or from film- or fiber-insulated magnet wire.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

NOTE 1—There is no similar or equivalent IEC standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For a specific precautionary statement, see Section 7.

2. Referenced Documents

2.1 ASTM Standards:²

- D618 Practice for Conditioning Plastics for Testing
- D1711 Terminology Relating to Electrical Insulation
- D1932 Test Method for Thermal Endurance of Flexible Electrical Insulating Varnishes
- D2307 Test Method for Thermal Endurance of Film-Insulated Round Magnet Wire
- D2519 Test Method for Bond Strength of Electrical Insulating Varnishes by the Helical Coil Test

¹ This test method is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.01 on Electrical Insulating Varnishes, Powders and Encapsulating Compounds.

Current edition approved Nov. 1, 2013. Published December 2013. Originally approved in 1973. Last previous edition approved in 2008 as D3145 – 08. DOI: 10.1520/D3145-13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D3251 Test Method for Thermal Endurance Characteristics of Electrical Insulating Varnishes Applied Over Film-Insulated Magnet Wire

D5423 Specification for Forced-Convection Laboratory Ovens for Evaluation of Electrical Insulation

2.2 *International Electrotechnical Commission Publications:*³

IEC 60216-1 Guide for the Determination of Thermal Endurance Properties of Electrical Insulation Materials (Part 1)

3. Terminology

3.1 Definitions

3.1.1 For definitions of terms used in the test method, refer to Terminology D1711.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *bond strength, n*—a measure of the force required to separate surfaces which have been bonded together.

3.2.2 *magnet wire, n*—a metal electrical conductor, covered with electrical insulation, for use in the assembly of electrical inductive apparatus such as coils for motors, transformers, generators, relays, magnets, etc.

3.2.2.1 *Discussion*—The electrical insulation is usually composed of a film covering formed from a magnet wire enamel applied over a bare conductor. In some specific applications, fibrous coverings, either taped or linear filament served, are also used as electrical insulation.

3.2.3 *varnish, electrical insulating, n*—a liquid resin system that is applied to and cured on electrical components providing electrical, mechanical and environmental protection.

3.2.3.1 *Discussion*—There are two types of electrical insulating varnishes—solvent-containing and solventless. Solvent-containing types are solutions, dispersions or emulsions of a polymer or a mixture of polymers in a volatile, nonreactable liquid. Solventless types are liquid resin systems free of volatile, nonreactable solvents.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

*A Summary of Changes section appears at the end of this standard

4. Summary of Test Method

4.1 Flexural strength of the helical coils is measured periodically after exposure to several exposure temperatures. The time to reach an arbitrarily selected value of bond strength at each exposure temperature is determined. The logarithms of these times in hours are plotted as a function of the reciprocal temperature (1/K) to give an Arrhenius plot.

5. Significance and Use

5.1 This test method is used to determine the effect of exposure to elevated temperatures on the bond strength of combinations of magnet wire insulations and electrical insulating varnishes. The results are used as a guide for the comparison and selection of varnishes and combinations of varnishes and magnet wire insulation for specific applications. Test Methods [D1932](#) and [D3251](#) describe additional tests for determining the thermal endurance of insulating varnishes. A comprehensive evaluation of thermal characteristics includes a comparison of the thermal endurance determined in these different ways.

5.2 This test method is useful for research and product qualifications purposes.

6. Apparatus

6.1 *Testing Machine*, see Test Method [D2519](#).

6.2 *Test Fixture*, see Test Method [D2519](#).

6.3 *Ovens*, see Specification [D5423](#), Type II.

7. Hazards

7.1 It is unsafe to use varnish at temperatures above flash point without adequate ventilation, especially if the possibility exists that flames or sparks are present. Store varnish in sealed containers.

8. Test Specimen

8.1 Prepare 60 or more specimens for each exposure temperature, following the procedure specified in Test Method [D2519](#).

9. Selection of Test Temperatures

9.1 Expose the material to at least three temperatures. Choose the lowest temperature such that it is not more than

25°C higher than the estimated temperature index. Separate exposure temperatures from each other by at least 10°C, preferably 20°C.

9.2 Select exposure temperatures in accordance with those shown in [Table 1](#) as indicated by the anticipated temperature index of the material under test. It is recommended that exploratory tests be first made at the highest temperature to obtain data establishing the 100 h minimum endpoint time requirement, and that this be used as a guide for the selection of the lower test temperatures.

9.3 Choose the exposure temperature so that any essentially linear portions of the Arrhenius plot (log of time to failure versus the reciprocal of the absolute temperature) is well established; that is, confirm the suspicion of significant non-linearity by test at one or more additional temperatures. Generally the additional temperatures are lower than the ones previously tested.

10. Procedure

10.1 Suspend at least 20 sets of coils containing at least 3 coils in each set vertically in each oven.

10.2 Periodically remove one set of coils and condition 2 h at standard laboratory conditions in accordance with Practice [D618](#). Measure flexural strength at room temperature in accordance with Test Method [D2519](#).

10.3 The length of the exposure period and the number of coils tested per cycle will depend on the deterioration rate at each exposure temperature. The exposure period will be longer at the start, shorter as the deterioration rate increases.

10.4 Continue the test until the breaking strength reaches less than 22 N (5 lbf). The end point is that point where the curve intersects the 22-N (5-lbf) line, or other specified value.

11. Calculation

11.1 Plot the breaking strength value after each exposure period versus time in hours on a three-decade semilog paper with time as the ordinate.

11.2 From the curve, pick the 22-N (5-lbf) point, or specified value, and record the number of hours to reach this point. This is to be done for each temperature and will be known as the end point at that temperature.

TABLE 1 Suggested Exposure Temperatures and Cycle Durations^A

Cycle Duration, day	Temperatures Corresponding to the Estimated Temperature Index Range, °C ^{B,C}													
	Class 105		Class 130		Class 155		Class 180		Class 200		Class 220			
	100 to 109	110 to 119	120 to 129	130 to 139	140 to 149	150 to 159	160 to 169	170 to 179	180 to 189	190 to 199	200 to 209	210 to 219	220 to 229	230 to 239
1	170	180	190	200	210	220	230	240	250	260	270	280	290	300
2	160	170	180	190	200	210	220	230	240	250	260	270	280	290
4	150	160	170	180	190	200	210	220	230	240	250	260	270	280
7	140	150	160	170	180	190	200	210	220	230	240	250	260	270
14	130	140	150	160	170	180	190	200	210	220	230	240	250	260
28	120	130	140	150	160	170	180	190	200	210	220	230	240	250
49	110	120	130	140	150	160	170	180	190	200	210	220	230	240

^A Taken from IEC Publication 60216-1.

^B Exposure temperatures above and below those given are to be selected by experimentation.

^C Range to which the temperature is assumed to correspond to an extrapolated 20 000 h time to failure.

11.3 In order to calculate the temperature index, data must be available from a minimum of three exposure temperatures. The highest exposure temperature must have a thermal end-point time of at least 100 h. The endpoint time at the lowest exposure temperature must have a thermal life of at least 5000 h.

11.4 Plot the end points at each temperature on graph paper having a logarithmic time scale as the ordinate and the reciprocal of the absolute temperature as the abscissa. Draw the best fit straight line through all points. For definition of how to draw the best fit line, see the Annex of Test Method **D2307** for calculation of the regression line.

11.5 The temperature where the line crosses the specified hour line is the temperature index for the combination used for the test. Unless otherwise specified, use an hour line of 20 000 h.

12. Report

12.1 Report the following information:

12.1.1 Identification of the varnish,

12.1.2 Identification of the magnet wire insulation,

12.1.3 Cure schedule used,

12.1.4 Exposure temperatures, and

12.1.5 Temperature index.

13. Precision and Bias

13.1 *Precision*—Data from a between-laboratory study⁴ involving three laboratories testing a single unsaturated polyester resin yielded:

Average temperature index	204
Range of values	8
Standard deviation	4

13.2 *Bias*—This test method has no bias because the value for the thermal endurance of insulating varnish using the helical coil method is defined in terms of this test method.

14. Keywords

14.1 electrical insulating; helical coil; magnet wire; thermal endurance; varnish

⁴ Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:D09-1033.

SUMMARY OF CHANGES

Committee D09 has identified the location of selected changes to this test method since the last issue, D3145 – 08, that may impact the use of this test method. (Approved Nov. 1, 2013)

(1) Deleted references to Test Method D3850 and Practice D6054.

(2) Added reference to Practice D618.

Committee D09 has identified the location of selected changes to this test method since the last issue, D3145 – 03, that may impact the use of this test method. (Approved May 1, 2008)

(1) Revised the text throughout to remove nonmandatory language.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).