



Standard Terminology Relating to Rubber and Rubber Latices—Abbreviations for Chemicals Used in Compounding¹

This standard is issued under the fixed designation D3853; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This terminology is a compilation of abbreviations for accelerators, vulcanizing agents, activators, antidegradants, plasticizers, softeners, processing aids, blowing agents, retarders, isocyanates, peroxides, and antireversion agents used in the compounding of rubber products. Abbreviations for rubbers are listed in Practice D1418 and a numbering system for various grades of carbon blacks is described in Classification D1765.

2. Referenced Documents

2.1 *ASTM Standards*:²

D1418 Practice for Rubber and Rubber Latices—Nomenclature

D1600 Terminology for Abbreviated Terms Relating to Plastics

D1566 Terminology Relating to Rubber

D1765 Classification System for Carbon Blacks Used in Rubber Products

2.2 *ISO Standard*:³

ISO 6472 Rubber Compounding Ingredients—Abbreviations

3. Significance and Use

3.1 These abbreviations are to be used in technical writing where the full chemical name of the substance is used initially, followed by the abbreviation found in this terminology. Later references to this substance may then use the abbreviation only.

¹ This terminology is under the jurisdiction of ASTM Committee D11 on Rubber and is the direct responsibility of Subcommittee D11.08 on Terminology.

Current edition approved Jan. 1, 2012. Published February 2012. Originally approved in 1979. Last previous edition approved in 2008 as D3853 – 08^{ε1}. DOI: 10.1520/D3853-12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

4. Form and Style

4.1 Although generally accepted references^{3,4,5} for naming chemicals provide the basis for these abbreviations, common usage has dictated the particular choice for the abbreviations set forth in this terminology.

4.2 Conventions used in this terminology are:

4.2.1 The symbol B will be used for butyl in the case of accelerators and vulcanizing agents and for butylidene in the case of bisphenol materials (see 4.2.6.2).

4.2.2 The symbol Bz will be used for benzyl groups.

4.2.3 When possible, a number will be used to denote long chain hydrocarbons, that is, 5 for penta, 88 for dioctyl, etc. If the length of the hydrocarbon chain is ten or higher, the number shall be placed in parenthesis, that is (12) for dodecyl, etc. The letter “i” shall be used to denote an iso structure.

4.2.4 The chemical symbol for metallic components will be used whenever possible. This will usually occur at the beginning of the abbreviation.

4.2.5 The symbol C will be used for dithiocarbamate accelerators and for cyclohexyl in the case of sulfenamide accelerators and bisphenol antioxidants.

4.2.6 Commercial bisphenol antioxidants are made up of two alkyl/cyclohexyl substituted phenol rings linked in the ortho or para position. The following conventions will be used in this nomenclature scheme:

4.2.6.1 *o*—ortho

m—meta

p—para

Bp—bisphenol structure

4.2.6.2 M—methylene

B—butylidene

IB—isobutylidene

IP—isopropylidene

T—thio

⁴ *A Guide to IUPAC Nomenclature of Organic Compounds*, CRC Press, Boca Raton, FL, 1993.

⁵ Fox, R. B., *Nomenclature of Organic Compounds*, American Chemical Society, Washington, DC, 2001.

- 4.2.6.3 1—methyl
- 2—ethyl
- 4—*t*-butyl
- 9—nonyl
- C—cyclohexyl

4.2.7 For diphenylamine antidegradants use numbers for the identification of alkyl substituents on the diphenylamine rings.

5. Abbreviations

ACCELERATORS AND VULCANIZING AGENTS

BA—butyraldehyde–aniline condensate.
 BiDMC—bismuth dimethyldithiocarbamate.
 BMTS—bis-morpholino–thiocarbamyl sulfenamide.
 CBS—*N*-cyclohexyl-2-benzothiazyl sulfenamide.
 CdDEC—cadmium diethyldithiocarbamate.
 CdDMC—cadmium dimethyldithiocarbamate.
 Cd5MC—cadmium pentamethylenedithiocarbamate.
 CEA—cyclohexylethylamine.
 CuDIP—copper diisopropyldithiophosphate.
 CuDMC—copper dimethyldithiocarbamate.
 CuMBT—copper 2-mercaptobenzothiazole.
 DBA—dibutylamine.
 DBQD—*p,p'*-dibenzoyl-*p*-benzoquinone dioxime.
 DBTU—1,3-dibutylthiourea.
 DBXD—dibutyl xanthogen disulfide.
 DBzA—dibenzylamine.
 DCBS—*N,N*-dicyclohexyl-2-benzothiazyl sulfenamide.
 DEPTD—sym. diethyldiphenylthiuram disulfide *N,N'*-diethyl-*N,N'*-diphenylthiuram disulfide.
 DETU—1,3-diethylthiourea.
 DMPTD—dimethyl diphenyl thiuram disulfide.
 DIBS—*N,N*-diisopropyl-2-benzothiazyl sulfenamide.
 DOTG—di-tolylguanidine.
 DPG—diphenylguanidine.
 DPTD—dipentamethylenethiuram disulfide.
 DPTH—dipentamethylenethiuram hexasulfide.
 DPTM—dipentamethylenethiuram monosulfide.
 DPTT—dipentamethylene thiuram tetrasulfide.
 DPTU—*N,N'*-diphenylthiourea (thiocarbamilide).
 DTDM—4,4'-dithiomorpholine.
 DTTU—*N,N'*-di-*o*-tolylthiourea.
 EFA—ethyl chloride, formaldehyde, and ammonia reaction product.
 ETU—ethylene thiourea.
 HMD—hexamethylenediamine.
 HMDC—hexamethylenediamine carbamate.
 HMMA—*N,N'*-hexamethylene-bis-methacrylamide.
 HMT—hexamethylenetetramine.
 MBSS—4-morpholinyl-2-benzothiazyl disulfide.
 MBS—2-(morpholiniothio)benzothiazole.
 MBSS—2-benzothiazole-*N*-morpholydisulfide.
 MBT—2-mercaptobenzothiazole.
 MBTS—dibenzothiazyl disulfide.
 M-*o*-CA—4-4'-methylene-bis-(chloroaniline).
 m-PBM—*N, N'*-*m*-phenylene-bis-maleimide.
 MPTD—*N,N'*-dimethyl-*N,N'*-diphenylthiuram disulfide.
 MTT—3-methyl-thiazolidine-thione-2.
 NaDMC—sodium dimethyldithiocarbamate.

NaDBC—sodium dibutyldithiocarbamate.
 NaDEC—sodium diethyldithiocarbamate.
 NaIX—sodium isopropylxanthate.
 OTBG—*o*-tolylbiguanide.
 OTOS—*N*-oxydiethylene thiocarbamyl-*N'*-oxydiethylene sulfenamide.
 PbDAC—lead diamyldithiocarbamate.
 PbDMC—lead dimethyldithiocarbamate.
 PBQD—*p*-benzoquinone dioxime.
 P5MC—piperidinium pentamethylenedithiocarbamate.
 SeDEC—selenium diethyldithiocarbamate.
 SeMDC—selenium dimethyldithiocarbamate.
 TAC—triallyl cyanurate.
 TAIC—triallyl isocyanurate.
 TBBS—*N*-*t*-butyl-2-benzothiazyl sulfenamide.
 TBSI—*t*-butyl-2-benzothiazyl sulfenimide.
 TBTD—tetrabutylthiuram disulfide.
 TBTU—*N,N,N'*-tributylthiourea.
 TBzTD—tetrabenzylthiuram disulfide.
 TCT—tricrotonylidenetetramine.
 TeDEC—tellurium diethyldithiocarbamate.
 TeDMC—tellurium dimethyldithiocarbamate.
 TIBTD—tetraisobutylthiuram disulfide.
 TETD—tetraethylthiuram disulfide.
 TMTD—tetramethylthiuram disulfide.
 TMTM—tetramethylthiuram monosulfide.
 TU—thiourea.
 ZnBX—zinc butylxanthate.
 ZnDBC—zinc dibutyldithiocarbamate.
 ZnDBP—zinc dibutyldithiophosphate.
 ZnDBzC—zinc dibenzylthiocarbamate.
 ZnDEC—zinc diethyldithiocarbamate.
 ZnDIBC—zinc diisobutylthiocarbamate.
 ZnDMC—zinc dimethyldithiocarbamate.
 ZnEHBP—zinc ethylhexyl-*n*-butyldithiophosphate.
 ZnEPC—zinc ethylphenyldithiocarbamate.
 ZnEX—zinc ethylxanthate.
 ZnIX—zinc isopropylxanthate.
 ZnMBT—zinc-2-mercaptobenzothiazole.
 Zn5MC—zinc pentamethylenedithiocarbamate.

PEROXIDES

BBPIB—1, 4-bis-(*t*-butylperoxyisopropyl) benzene.
 BPO—benzoyl peroxide.
 BPV—*n*-butyl bis (4,4-*tert*-butylperoxy) valerate.
 DBPC—1,1-bis (butylperoxy)-3,5,5-trimethyl-cyclohexane.
 DCPB—2,4-dichlorobenzoyl peroxide.
 DCP—dicumyl peroxide.
 DMBPHA—2,5-dimethyl-2,5-di-(butyl peroxy) hexane.
 DMBPHY—2,5-dimethyl-2,5-di-(butyl peroxy) hexyne-3.
 DTBP—di-*t*-butyl peroxide.
 EBPB—ethyl-3,3 bis (butyl peroxy) butyrate.
 MBPP—4-methyl-2,2-bis-(butyl peroxy) pentane.
 TBCP—butyl cumyl peroxide.
 TSS—toluene sulfonylsemicarbazide

ANTIDEGRADANTS (ANTIOXIDANTS AND ANTIOZONANTS)

AANA—aldol- α -naphthylamine.

ADPA—acetone diphenylamine condensation product
 APPD—*N*-alkyl-*N'*-phenyl-*p*-phenylenediamine.
 p-BBp14—4,4'-butylidene-bis-(6-*t*-butyl-*m*-cresol).
 BHA—butylated hydroxyanisole.
 BHT—2, 6-di-butyl-4-methylphenol (butylated hydroxy toluene).
 CPPD—*N*-cyclohexyl-*N'*-phenyl-*p*-phenylenediamine.
 DBHQ—2,5-di-*tert*-butylhydroquinone.
 DLTPD—dilauryl thiodipropionate.
 I88PD—*N,N'*-bis-(1-methylheptyl)-*p*-phenylenediamine.

NOTE 1—This is a specific isomer of *N,N'*-dioctyl-*p*-phenylenediamine (see ISO 6472).

DNPD—*N,N'*-di-2-naphthyl-*p*-phenylenediamine.
 DOPD—*N,N'*-dioctyl-*p*-phenylenediamine.
 DPA—diphenylamine.
 DPPD—*N,N'*-diphenyl-*p*-phenylenediamine.
 DSTDP—distearylthiodipropionate
 DTPD—*N,N'*-ditolyl-*p*-phenylenediamine.
 ETMQ—6-ethoxy-1,2-dihydro-2,2,4-trimethylquinoline.
 o-IBBp11—2,2'-isobutylidene-bis-(4,6-di-methylphenol).
 p-IPBp(4)_n—polybutylated bisphenol A.
 IPPD—*N*-isopropyl-*N'*-phenyl-*p*-phenylenediamine.
 MBI—2-mercaptobenzimidazole.
 o-MBp1C—2,2'-methylene-bis-(4-methyl-6-cyclohexylphenol).
 o-MBp1(1C)—2,2'-methylene-bis-[6-(1-methylcyclohexyl)*p*-cresol].
 o-MBp14—2,2'-methylene-bis-(4-methyl-6-*t*-butylphenol).
 o-MBp19—2,2'-methylene-bis-(4-methyl-6-nonylphenol).
 o-MBp24—2,2'-methylene-bis-(4-ethyl-6-*t*-butylphenol).
 p-MBp44—4,4'-methylene-bis-(2,6-di-*t*-butylphenol).
 MMBI—methyl-2-mercaptobenzimidazole.
 NiDBC—nickel dibutyldithiocarbamate.
 8DPA—octylated diphenylamine.
 PAN—*N*-phenyl-*alpha*-naphthylamine.
 PBN—*N*-phenyl-*beta*-naphthylamine.
 i-8PPD—*N*-phenyl-*N'*-2-octyl-*p*-phenylenediamine.
 P3DPA—*p*-isopropoxylateddiphenylamine.
 SPDA—styrenated diphenylamine.
 SPH—styrenated phenol.
 p-BBp14—4,4'-butylidene-bis-(2-*t*-butyl-*m*-cresol).
 p-TBp14—4,4'-thio-bis-(2-*t*-butyl-*m*-cresol).
 TAHQ—2,5-di-*amyl*hydroquinone.
 TMQ—2,2,4-trimethyl-1,2-dihydroquinoline (oligomer).
 TNPP—tri(nonylphenyl)phosphite.
 ZnDPT—zinc dialkylphosphorodithioate
 ZnMBI—zinc-2-mercaptobenzimidazole.
 ZnMMBI—zinc-methyl-2-mercaptobenzimidazole.
 6PPD—*N*-(1,3-dimethylbutyl)-*N'*-phenyl-*p*-phenylenediamine.
 6QDI—*N*-phenyl-*N'*-(1,3-dimethylbutyl)-2,5-cyclohexadiene-1,4-diimine.
 7PPD—*N*-(1,4-dimethylpentyl)-*N'*-phenyl-*p*-phenylenediamine.
 77PD—*N,N'*-bis-(1,4-dimethylpentyl)-*p*-phenylenediamine.
 8PPD—*N*-octyl-*N'*-phenyl-*p*-phenylenediamine.
 88PD—*N,N'*-dioctyl-*p*-phenylenediamine.
 9DPA—nonylated diphenylamine.

29DPA—ethylated/nonylated diphenylamine.
 48DPA—butylated/octylated diphenylamine

PLASTICIZERS AND SOFTENERS

(See Terminology D1600)

BOP—butyl octyl phthalate.
 DBP—dibutyl phthalate.
 DBS—dibutyl sebacate.
 DCHP—dicyclohexyl phthalate
 DEP—diethyl phthalate.
 DIBA—diisobutyl adipate.
 DIBP—diisobutyl phthalate.
 DIDA—diisodecyl adipate.
 DIDP—diisodecyl phthalate.
 DIOA—diisooctyl adipate.
 DIOP—diisooctyl phthalate.
 DMP—dimethyl phthalate.
 DMS—dimethyl sebacate.
 DOA—dioctyl adipate.
 DOP—dioctyl phthalate or di-(2-ethylhexyl) phthalate.
 DOS—dioctyl sebacate.
 DOTP—dioctyl terephthalate-or-di-(2-ethylhexyl) terephthalate.
 DPCF—diphenyl cresyl phosphate
 DPOF—diphenyl octyl phosphate
 DPP—diphenyl phthalate.
 DUP—diundecyl phthalate.
 ELO—epoxidized linseed oil.
 ESO—epoxidized soya bean oil.
 ODA—octyl decyl adipate.
 TCEF—trichloroethyl phosphate
 TCF—cresyl phosphate
 TOF—trioctyl phosphate
 TOTM—trioctyl trimellitate.

ACTIVATORS AND PROCESSING AIDS

DEA—diethanolamine.
 DEG—diethylene glycol.
 GTMA—glyceryl trimethacrylate.
 PEG—polyethylene glycol.
 PPG—polypropylene glycol.
 PVME—polyvinyl methyl ether.
 NaPCP—sodium pentachlorophenate.
 TEA—triethanolamine.
 ZnEH—zinc 2-ethylhexanoate (zinc octoate).

BLOWING AGENTS

ADC—azodicarbonamide.
 BDSH—benzene-1,3-disulfonylhydrazide.
 BSH—benzene sulfonylhydrazide.
 DNPT—dinitrosopentamethylenetetramine.
 OBSH—oxy-bis-(benzene sulfonylhydrazide)
 TSH—toluene sulfonylhydrazide
 TSS—toluene sulfonylsemicarbazide

ISOCYANATES

CHDI—1,4-cyclohexane diisocyanate.
 HDI—1,6-hexamethylene diisocyanate.
 HMDI—4,4'-dicyclohexylmethane diisocyanate.

IPDI—sophorone diisocyanate.
 MDI—4,4'-diphenylmethane diisocyanate.
 NDI—naphthalene-1,5-diisocyanate.
 PMPPI—polymethylene polyphenyl isocyanate.
 PPDI—p-phenylene diisocyanate.
 TDI—toluene diisocyanate.
 TMDI—2,2,4- and 2,4,4-trimethyl hexamethylene diisocyanate.
 TMXDI—m-tetramethylxylylene diisocyanate.
 TTI—4,4',4''-triphenylmethane triisocyanate.
 TIPT—tris-(p-iscyanatophenyl)-thiophosphate.

RETARDERS

CTP—*N*-(cyclohexylthio)phthalimide.

NDPA—*N*-nitroso diphenylamine
 PTA—phthalic anhydride.
 SA—salicylic acid.

ANTIREVERSION AGENTS

DCIMX—1,3-bis(citraconimidomethyl)benzene.
 DHTS—hexamethylene-1,6-bis(thiosulfate) disodium salt dihydrate.

6. Keywords

accelerators; activators; antidegradants; antioxidants; antiozonants; antireversion agents; blowing agents; isocyanates; peroxides; plasticizers; processing aids; retarders; softeners; vulcanizing agents

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).