



Standard Specification for Thermoplastic Chlorinated Polyethylene (CM) Jacket for Wire and Cable¹

This standard is issued under the fixed designation D4363; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers thermoplastic chlorinated polyethylene (CM) compounds suitable for use as an outer covering or jacket on electrical cables.

1.2 These jacket materials are suitable for use on cables which will be installed at temperatures above -35°C .

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

2. Referenced Documents

2.1 *ASTM Standards*:²

D2633 Test Methods for Thermoplastic Insulations and Jackets for Wire and Cable

D1499 Practice for Filtered Open-Flame Carbon-Arc Exposures of Plastics

D1711 Terminology Relating to Electrical Insulation

G153 Practice for Operating Enclosed Carbon Arc Light Apparatus for Exposure of Nonmetallic Materials

3. Terminology

3.1 *Definitions*: For definitions of terms used in this specification refer to Terminology D1711.

¹ This specification is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.18 on Solid Insulations, Non-Metallic Shieldings and Coverings for Electrical and Telecommunication Wires and Cables.

Current edition approved Jan. 1, 2012. Published February 2012. Originally approved in 1987. Last previous edition approved in 2010 as D4363–98(2010). DOI: 10.1520/D4363-12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.2 Definition of Term Specific to This Standard:

3.2.1 *aging, (act of), n*—exposure of materials to air at a temperature of 121°C for 168 h and oil at 100°C for 18 h.

4. Physical Properties

4.1 Thermoplastic jackets shall conform to the requirements for physical properties specified in Table 1.

4.2 When used on single-conductor non-shielded cable rated 2001 to 5000 V phase to phase, the jacket shall also conform to the requirements for surface resistivity and U-bend discharge prescribed in Table 2.

5. Sunlight and Weather Resistance Requirements

5.1 If sunlight and weather resistance are required of the jackets, the jackets shall conform to the requirements specified in Table 3.

6. Sampling

6.1 Sample the jacket in accordance with Methods D2633.

7. Test Methods

7.1 Test the jacket in accordance with Methods D2633. If the sunlight and weather resistance test is required, perform it in accordance with Practice D1499 and Practice G153.

8. Keywords

8.1 chlorinated polyethylene; heat distortion; oil immersion; sunlight resistance; tensile strength; tensile stress; thermoplastic; weather resistance

TABLE 1 Physical Properties for CM Jacket

<i>Physical Requirement (Original):</i>	
Tensile strength, min, psi (MPa)	1400 (9.6)
Tensile stress at 100 % elongation, min, psi (MPa)	1000 (6.9)
Elongation at rupture, min, %	150
Cold bend, ^A -35 ± 1°C	No Cracks
<i>Physical Requirements [after aging in an air-oven at 121 ± 1°C for 168 h]:</i>	
Tensile strength, min, % of original	85
Elongation at rupture, min, % of original	50
<i>Physical Requirements [after oil immersion for 18 h at 100 ± 1°C]:</i>	
Tensile strength, min, % of original	60
Elongation at rupture, min, % of original	60
Heat distortion, 121 ± 1°C, max, %	25

^ARefer to Methods **D2633**, Table 8, Mandrel Requirements for Poly (Vinyl Chloride) Jacket.

TABLE 2 Requirements for Surface Resistivity and U-Bend Discharge

Surface resistivity, min, MΩ ^A	200 000
U-bend discharge at the required cable insulation ac test voltage	No cable failures or cracks in the jacket

^A Reported as megohms since the value is for specified length as required in Methods **D2633**.

TABLE 3 Sunlight and Weather Resistance Requirements

After 720 h in a dual carbon-arc apparatus	<i>min, % Unaged Value</i>
Tensile strength,	80
Elongation at rupture	80

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).