



Standard Specification for Fiberglass Reinforced Styrene-Butadiene-Styrene (SBS) Modified Bituminous Sheets with a Factory Applied Metal Surface¹

This standard is issued under the fixed designation D6298; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers fiberglass reinforced modified bituminous sheet materials that use styrene-butadiene-styrene (SBS) thermoplastic elastomer as the primary modifier and are surfaced with a factory applied continuous metal foil. These materials are intended for use in the fabrication of multiple ply roofing and waterproofing membranes and flashings.

1.2 This specification is intended as a material specification only. Questions regarding the suitability of the specific roof constructions or application techniques are beyond the scope of this specification.

1.3 The specified tests and property limits are intended to establish minimum properties. In place roof system design criteria such as fire resistance, field strength, impact/puncture resistance, material compatibility, uplift resistance, and others, are factors beyond the scope of this specification.

1.4 The values stated in SI units are to be regarded as the standard. The inch-pound units given in parentheses are for information only.

1.5 The following precautionary statement pertains to the test method portion only, Section 8 of this Specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- D1079 Terminology Relating to Roofing and Waterproofing
- D5147 Test Methods for Sampling and Testing Modified Bituminous Sheet Material
- D7051 Test Method for Cyclic Thermal Shock of SBS-Modified Bituminous Roofing Sheets with Factory-Applied Metal Surface

3. Terminology

3.1 *Definitions*— For definitions of terms used in this specification, refer to Terminology D1079.

4. Materials and Manufacture

4.1 In the process of manufacture, the fiberglass reinforcement is impregnated and coated on both sides with a SBS modified bituminous coating. The sheet is surfaced with a continuous metal foil except for any selvage. The SBS modified bituminous coating shall be permitted to be compounded with a mineral stabilizer.

4.2 The metal surfacing shall be omitted on any selvage. To prevent sticking in the roll, the reverse side and any selvage shall be permitted to be covered with a fine mineral surfacing or any other surfacing that will not interfere with adhesion or bonding of the lap during application.

4.3 Foil-faced products intended for use where the application is to be by heat welding (torching) shall meet the minimum back surface coating requirement found in Table 1.

5. Physical Properties

5.1 The sheet material shall conform to the physical properties prescribed in Table 1.

5.2 The finished product shall not crack nor be so sticky as to cause other material damage upon being unrolled at product temperatures between 4 and 60°C (40 and 140°F).

¹ This specification is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.04 on Felts, Fabrics and Bituminous Sheet Materials.

Current edition approved May 1, 2013. Published June 2013. Originally approved in 1998. Last previous edition approved in 2005 as D6298 – 05E01. DOI: 10.1520/D6298-13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

TABLE 1 Properties of SBS Modified Bituminous Sheet Materials Surfaced With a Factory Applied Metal Foil

Description			
Thickness, min mm (mils)	3.4	(134)	
Net Mass per Unit Area, min kg/m ² (lb/100 ft ²)	3.9	(80)	
Back Surface Coating Thickness min, mm (mils)	1	(40)	
Peak Load, MD and XMD,	–18°C (0°F)	28.0	(160)
min, kN/m (lbf/in.)	23°C (73°F)	14.9	(85)
Elongation at Peak Load,	–18°C (0°F)	3	
MD and XMD, min, %	23°C (73°F)	5	
Ultimate Elongation, MD and XMD, min, %	23°C (73°F)	25	
Tensile-Tear Strength, MD and XMD, min kN (lbf)		0.53	(120)
Low Temperature Flexibility max, °C (°F)		–18	(0)
Dimensional Stability, max, %		0.2	
Compound Stability, min passing, °C (°F)		107	(225)
Cyclic Thermal Shock, max, % (mm/m)		2	(0.2)
Water Absorption, max, %		1.0	
Moisture Content, max, %		0.2	

6. Dimensions, Mass, and Permissible Variations

6.1 The width of the roll shall be as agreed between the purchaser and the seller and shall not vary more than $\pm 1\%$.

6.2 The area of the roll shall not be less than as agreed upon between the purchaser and seller.

6.3 The selvage width shall be within ± 6.4 mm ($\frac{1}{4}$ in.) of the nominal value and shall not be less than 57 mm (2.25 in.).

7. Workmanship, Finish, and Appearance

7.1 The finished product shall be completely coated in a continuous, unbroken film and shall be free of such defects as holes, ragged or untrue edges, breaks, cracks, tears, protrusions, delaminations, and indentations.

7.2 The metal surface shall be uniform in surface and texture, that is, free from such defects as holes, breaks tears, protrusions, and indentations (except for intended factory embossing pattern).

7.3 The line of demarcation between the metal-surfaced portion of the weather side and any selvage shall be straight and parallel to the edge of the sheet.

7.4 When unrolled on a smooth plane, the sheet shall be flat, straight, and true so the lap will mate with the adjacent sheet within the tolerance of the lap without wrinkles, buckles, or fishmouths.

8. Sampling and Test Methods

8.1 Sample the material and determine the properties described in this specification in accordance with Test Method **D5147** unless otherwise indicated.

8.2 *Cyclic Thermal Shock*—Sample and test the material in accordance with Test Method **D7051**.

9. Inspection

9.1 *Inspection*—Inspection shall be in accordance with the requirements of this specification.

9.2 *Inspection Alternatives*—Alternative inspection requirements shall be determined by and as agreed upon between the purchaser and supplier.

10. Rejection and Resubmittal

10.1 *Failure to Conform*—Failure to conform to any of the requirements as stated in this specification constitutes grounds for rejection.

10.2 *Rejection Redress*—The supplier shall have the right to inspect the rejected materials. The supplier and the purchaser shall agree to the quantity of rolls deemed unacceptable. The supplier shall then have the right to submit the same number of new rolls as replacement.

11. Packaging and Package Marking

11.1 The finished material shall be furnished as rolls. The rolls shall be securely wrapped to prevent shifting of material and to permit normal handling. There shall be no manufacturing splices in the roll, and there shall be no more than two pieces.

11.2 Unless otherwise agreed upon by the seller and purchaser, each product package shall be plainly marked with the supplier's name, the product brand, the ASTM designation, the net coverage area, and the type bitumen if not evident in the label name of the product.

12. Keywords

12.1 glass reinforcement; metal foil surface; modified bituminous sheet; styrene-butadiene-styrene (SBS); thermoplastic elastomer

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).