



Standard Test Method for Determination of Rolled Erosion Control Product (RECP) Ability to Encourage Seed Germination and Plant Growth Under Bench-Scale Conditions¹

This standard is issued under the fixed designation D7322; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers guidelines, requirements, and procedures for evaluating the effect of Rolled Erosion Control Products (RECPs) on seed germination and vegetation enhancement.

1.2 This test method will evaluate the effects of RECPs on seed germination in a controlled environment.

1.3 This test method utilizes bench-scale testing procedures and shall not be interpreted as indicative of field performance.

1.4 This test method is not intended to replace full-scale simulation or field testing in acquisition of performance values that are required in the design of erosion control measures utilizing RECPs.

1.5 The values stated in SI units are to be regarded as standard. The values given in parentheses are mathematical conversions to inch-pound units that are provided for information only and are not considered standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

[D653 Terminology Relating to Soil, Rock, and Contained Fluids](#)

[D4354 Practice for Sampling of Geosynthetics and Rolled Erosion Control Products\(RECPs\) for Testing](#)

[D5268 Specification for Topsoil Used for Landscaping Purposes](#)

[D6475 Test Method for Measuring Mass Per Unit Area of Erosion Control Blankets](#)

[D6566 Test Method for Measuring Mass per Unit Area of Turf Reinforcement Mats](#)

3. Terminology

3.1 For definitions of terms used in this test method, see Terminology [D653](#).

4. Summary of Test Method

4.1 Containers containing soil are sown with seeds and then covered with an RECP. Additional containers of soil are sown with seed and left uncovered as *controls*. The light, temperature, and humidity are maintained and documented. The amount of germination and growth is measured periodically throughout the test, and the mass of vegetation is calculated at the conclusion of the test.

4.2 Each RECP under consideration as well as control containers of uncovered soil undergo testing in a controlled environment.

5. Significance and Use

5.1 This test method evaluates the effect of an RECP on seed germination and initial plant growth in a controlled environment.

5.2 The results of this test can be used to compare RECPs and other erosion control materials to determine which are the most effective at encouraging the growth of vegetation.

6. Apparatus

6.1 *Germination Containers*—Plastic pots nominally 20 ± 1 cm (8 ± 0.4 in.) inside diameter made from plastic pipe section cylinders and having a height of 10 ± 1 cm (4 ± 0.4 in.). The pots include a perforated bottom to allow drainage.

6.2 *Temperature-, Humidity-, and Light-Controlled Chamber*—Capable of maintaining a constant temperature of $27 \pm 2^\circ\text{C}$, $45 \pm 5\%$ relative humidity, and 900 ± 100 ft-candles, with a light source as outlined in [A1.1](#).

¹ This test method is under the jurisdiction of ASTM Committee D18 on Soil and Rock and is the direct responsibility of Subcommittee D18.25 on Erosion and Sediment Control Technology.

Current edition approved Nov. 1, 2013. Published December 2013. Originally approved in 2007. Last previous edition approved in 2013 as D7322 – 13. DOI: 10.1520/D7322-13A.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

6.3 *Photometer*—Instrument capable of measuring the illumination provided by a fluorescent light source, including both the visible and ultraviolet (UV) spectrum.

6.4 *Thermometer*—Capable of measuring temperature.

6.5 *Hygrometer*—Capable of measuring relative humidity.

7. Test Organisms

7.1 The test should be conducted on one seed mix of tall fescue (Pure Live Seed, PLS = $80 \pm 5\%$). Seed shall be stored in a refrigerator.

NOTE 1—The test seed listed in this test method has been successful for product comparison purposes. However, this test may be used with alternative test organisms based on user needs. If test organisms different from those listed in this procedure are used, agreement should be established between the testing laboratory and the user of the test.

7.2 Unless otherwise requested, use ASTM topsoil. ASTM topsoil shall comply with Specification **D5268**.

8. Sampling

8.1 Perform RECP material sampling in accordance with Practice **D4354**.

8.2 The laboratory RECP sample should be 1 m^2 (3.28 ft^2).

8.3 Cut three specimens from each RECP laboratory sample. The specimen should completely cover the soil in the germination pots.

9. Procedure

9.1 Prepare Germination Containers:

9.1.1 Prepare three pots for each RECP to be tested and three control pots.

9.1.2 Place the soil growing medium in each pot. The growing medium shall be topsoil conforming to Specification **D5268** with an in-place moisture content and unit weight determined as follows:

9.1.2.1 Condition and place the topsoil in each pot at a moist unit weight of $13.3 \pm 0.8 \text{ kN/m}^3$ ($85 \pm 5 \text{ pcf}$) and 35 to 40 % moisture content (approximately 60 % saturation).

9.1.2.2 Randomly select three 5 by 5 cm (2 in. by 2 in.) squares from each pot. Outline or mark, or both, the selected squares in each pot. Data will be periodically collected from within these squares. Alternatively, the entire pot can be used for data collection.

9.1.2.3 Sow each pot with 0.50 seeds per cm^2 (500 seeds per ft^2). This is approximately 176 seeds per pot and 13 seeds per selected square. Distribute the seeds as uniformly as possible throughout each pot.

9.1.2.4 Press the seeds firmly against the soil surface, and apply a thin veneer of cover soil of no more than 3 mm (0.1 in.) thick over the seeds. Compress both the seed and the topsoil using a 50 lb circular mass having a nominal diameter equivalent to the pot inside diameter.

9.1.2.5 Add sufficient water to bring the placed and compacted topsoil to approximately 100 % saturation. (Stop as soon as free water is apparent on the surface.)

9.1.2.6 Each RECP specimen shall be weighed and measured to determine its mass per unit area in accordance with Test Method **D6475** and Test Method **D6566**. Cover each of

three pots with an RECP specimen. Three pots will be left uncovered to be controls. For RECP-covered pots, place the RECP over the pot, and hold firmly in place around the perimeter of the pot.

9.1.2.7 Place the pots in the controlled environmental chamber conditioned at $27 \pm 2^\circ\text{C}$, $45 \pm 5\%$ relative humidity, and $900 \pm 100 \text{ ft-candles}$. The test will proceed for 21 days.

9.2 Test Operation, Maintenance, and Data Collection:

9.2.1 Check and record temperature, relative humidity, and light every day along the length and width of the chamber at locations determined as follows: divide the entire illuminated area in half one way (left to right), then divide into thirds (top to bottom) and measure in the center of each section. Make any necessary adjustments. (See **Fig. 1**.)

9.2.2 Record the number of germinated seeds and the length of the plants within each designated square on days 7, 14, and 21.

9.2.3 At the 7 and 14 day measurement periods, apply an additional quantity of water to each test pot equal to 12.5 mm (0.5 in.) over the area of the pot (410 mL for an 8-in. diameter pot).

9.2.4 At the conclusion of the 21 days, each pot is harvested by cutting the grass at the surface of the soil within each designated 5 cm (2 in.) square measurement zone.

9.2.5 Dry the harvested seedlings in an oven at 100°C (212°F) for 24 h.

9.2.6 Make mass determinations for each pot.

NOTE 2—The test environment used in this test method procedure has been successful for product comparison purposes. However, this test may be used with alternative test environments based on user needs. If test environments different from those listed in this procedure are used, agreement should be established between the testing laboratory and the user of the test method.

10. Calculation

10.1 Find the total for each pot or the mean of the pre-identified squares in each pot of the number of germinated seeds and the average height of the plants for each measuring period. Similarly, determine the biomass after 21 days. The data for each pot should be normalized to the sample roll average index mass per unit area based on the specimen-specific mass per unit area for the pot.

10.2 Average the data from **10.1** for each set of three pots, all prepared in the same manner.

11. Report

11.1 At a minimum, report the following information:

11.1.1 General information, including test facility location, date and time.

11.1.2 Climate and soil pot (including soil weight and water weight added) details recorded before and during the test.

11.1.3 Description of each RECP under consideration.

11.1.4 Soil description.

11.1.5 Test seed description.

11.1.6 Raw data.

11.1.7 A table containing the biomass (will only have data for the last day), seed germination, and plant height averages for each RECP and the control for day of data collection.

Day	Temp 27± 2°C	Humidity 45± 5%RH	Light (14 hrs per day) 900± 100ft-cd	Watering (Initial: 85±5pcf & 35-40%mc) ml	Seeds Germinated (#) / Average Height (ht)																				
					Calibration Pans (20 seeds per pan)			Control Pots / Sample Areas (176 seeds per pot / 13 seeds per sample area)									RECP-Protected Pots / Sample Areas (176 seeds per pot / 13 seeds per sample area)								
								1			2			3			1			2			3		
					1	2	3	1	2	3	1	2	3	1	2	3	1	2	3	1	2	3	1	2	3
0					0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0				
1																									
2																									
3																									
4																									
5																									
6																									
7 #																									
7 ht.																									
8																									
9																									
10																									
11																									
12																									
13																									
14 #																									
14 ht																									
15																									
16																									
17																									
18																									
19																									
20																									
21 #																									
21 ht																									
21 mass*																									

NOTE 1—* Harvest the seedlings in each sample area by cutting them at the soil surface, drying them in an oven at 100°C for 24 h, and weighing them.

FIG. 1 Data Record

11.1.8 Any qualitative observations or conclusions about the performance of the RECPs.

11.1.9 Photographic documentation of each pot taken at days 0, 7, 14, and 21. All photographs shall be taken from the same angle and distance from each pot.

12. Precision and Bias

12.1 *Precision*—The precision of the test method is being determined.

12.2 *Bias*—The bias of the test method, if any, is being determined.

12.3 *Reproducibility*—The reproducibility of the test method is being determined.

13. Keywords

13.1 erosion control; germination; RECP; rolled erosion control product

ANNEX

(Mandatory Information)

A1. ANNEX

A1.1 Standard Climates

A1.1.1 *Light Requirements*—The source of light will be from warm white fluorescent lights producing 900 ± 100 ft-candles at the soil/canopy surface. Typical warm white characteristics for a 48-in. long lamp include:

Light output = 3300 lm
Color Temperature = 3000 K
Color Rendering = 85

A1.1.1.1 Photoperiod should be at least 14 h of light per day.

A1.1.1.2 Illumination should be monitored weekly with a recording photometer. Adjustments to artificial lighting may be necessary.

A1.1.1.3 Intensity should be determined daily with a recording photometer. Adjustments to artificial lighting may be necessary.

A1.1.2 Temperature and Humidity—Record air temperature and humidity at least daily. Air temperature and relative humidity should be continuously monitored.

Test Condition	Temperature	Humidity
Controlled	27 ± 2°C (approximately 81°F)	45 ± 5 % RH

A1.2 Standard Soils—Unless otherwise requested, use topsoil. Topsoil shall comply with Specification **D5268**.

A1.3 Seed Calibration

A1.3.1 Seed for the germination test shall be stored in a refrigerator.

A1.3.2 The seed used in the test shall be subjected to a calibration test simultaneously with the running of the test. The calibration test shall involve the selection of 20 seeds from the same source as those used in the germination test. The 20 seeds are placed on a saturated paper towel, sealed within a plastic transparent container, and exposed to the same temperature/lighting regimen as the germination samples. At 7, 14, and 21 days the number of seeds to germinate shall be noted. At the end of 21 days the percentage of seeds germinated shall be used to interpret the results of the germination test relative to previous tests. If the seed germination rate from the calibration tests drops below 80 %, new seed should be obtained.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).