



Standard Terminology Relating to Industrial Textile Stitches and Seams¹

This standard is issued under the fixed designation D7722; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This terminology covers stitches and seams related to industrial textiles.

1.2 Section 3, Terminology, is categorized into two subsections, specific to the two areas of specialization under this document.

1.2.1 Section 3.1 Relating to Seams.

1.2.2 Section 3.2 Relating to Stitches.

1.3 For other terms relating to textiles refer to Terminology D123.

2. Referenced Documents

2.1 *ASTM Standards*:²

D123 Terminology Relating to Textiles

D1683/D1683M Test Method for Failure in Sewn Seams of Woven Apparel Fabrics

D1908 Test Method for Needle-Related Damage Due to Sewing in Woven Fabrics³

D5646 Terminology Relating to Seams and Stitches Used in Home Sewing

D6193 Practice for Stitches and Seams

3. Terminology

3.1 *Definitions Relating to Seams*:

double-stitched seam-finish, *n*—a finish for the raw edges of a plain seam, in which another row of machine stitching is made through both seam allowances placed together. **D1683/D1683M, D6193**

grin, *v*—*in sewn seams*, to stress a seam so that the individual stitches can be seen.

¹ This terminology is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.54 on Subassemblies.

Current edition approved July 1, 2013. Published August 2013. Originally approved in 2011. Last previous edition approved in 2011 as D7722-11. DOI: 10.1520/D7722-13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Withdrawn. The last approved version of this historical standard is referenced on www.astm.org.

needle damage, *n*—*in sewn fabrics*, the partial or complete yarn severance or fiber fusing caused by a needle passing through a fabric during sewing.

DISCUSSION—This can also be referred to as needle cuts. **D1908-89**

seam, *n*—a line where two or more fabrics are joined, usually near the edge. (See also **sewn seam**. See Terminology D5646 for *glued seam*, *stapled seam*, and *thermally bonded seam*.) **D6193**

seam allowance, *n*—*in sewn fabrics*, the distance from the edge of a fabric to the parallel stitch line furthest from that edge. **D1683/D1683M, D6193**

seam assembly, *n*—the composite structure obtained when fabric(s) are joined by means of a seam. **D1683/D1683M, D6193**

DISCUSSION—A seam assembly may be described in terms of fabric orientation, seam direction, seam type, stitch type, seam allowance, sewing thread tex number(s) and type(s) stitch density, stitch gage, and rows of stitching. **D1683/D1683M**

seam damage, *n*—*in sewn fabrics*, an adverse change in the physical condition of one or more of the components in a seam which would reduce the seam acceptability such as yarn slippage, needle damage, or fabric rupture. **D6193**

seam efficiency, *n*—*in sewn fabrics*, the ratio, expressed as a percentage, of the breaking force required to rupture a sewn seam to that required to rupture the fabric; seam strength to fabric strength. **D1683/D1683M, D6193**

DISCUSSION—For some constructions, yarn strength and stitch type can contribute to a higher seam efficiency value. **D6193**

seam engineering, *n*—*in sewn fabrics*, the procedures used to select a specific combination of sewing thread, stitch type, seam type, and stitch density to achieve the maximum sewn seam strength for a particular fabric type. **D1683/D1683M**

seam failure, *n*—*in sewn fabrics*, that point at which an external force (1) ruptures the sewing thread, (2) ruptures the fabric, (3) causes excessive yarn slippage adjacent to the stitches, or (4) causes any combination of these unacceptable conditions. **D1683/D1683M**

DISCUSSION—Despite the lack of rupture, excessive seam slippage will either significantly reduce seam efficiency, or, result in an unsightly appearance thus creating seam failure. **D1683/D1683M**

seam interaction, *n*—*in sewn fabrics*, the net effect of the relationship between the combination of fabric, seam type, stitch type, and stitch density on seam efficiency. **D1683/D1683M**

seam slippage, *n*—*in sewn fabrics*, a mode of failure in production seams; the displacement of the fabric yarn parallel and adjacent to the stitch line. **D1683/D1683M, D6193**

DISCUSSION—Shown as a transverse ratio of junction strength to fabric strength including the ratio of elongation of fabric to the ratio of elongation at the junction. Seam slippage occurs when fabric yarns parallel to the stitch line move away from the seam. It is caused by the yarns in the fabric pulling out from the stitch line, and manifests itself as a gaping opening. Any movement of the warp and weft yarns away from a seam line under transverse stresses, which exacerbate the potential damage. (See **yarn slippage**.) **D1683/D1683M**

seam type, *n*—*in sewn fabrics*, an alphanumeric designation relating to the essential characteristics of fabric positioning and rows of stitching in a specified sewn fabric seam. **D1683/D1683M, D6193**

DISCUSSION—The first two letters of the designation show seam type; the third and subsequent letters specify a particular mating alignment; the number designation indicates the number of rows of stitches. **D1683/D1683M**

sew, *v*—to unite or fasten with stitches. **D6193**

sewing thread, *n*—a flexible, small-diameter yarn or strand, usually treated with a surface coating, lubricant, or both, intended to be used to stitch one or more pieces of material or an object to a material. **D6193**

sewn seam, *n*—*in sewn fabrics*, a juncture at which two or more planar structures such as textile fabrics, are joined by sewing, usually near the edge. **D1683/D1683M, D6193**

sewn seam strength, *n*—*in sewn fabrics*, the maximum resistance to rupture of the junction formed by stitching together two or more planar structures. **D1683/D1683M**

slippage, *n*—*in sewn fabrics*, the displacement of one or more fabric yarns from their original position, so as to cause differences in alignment, spacing, or both. **D1683/D1683M**

standard seam, *n*—a seam assembly which uses a specific seam type for a designated fabric having specific weight, density and construction. **D1683/D1683M**

stitch, *n*—*in sewn seams*, the repeated unit formed by the sewing thread(s) in the production of seams. **D1683/D1683M**

stitch density, *n*—*in sewn seams*, the number of stitches per unit length in one row of stitching in the seam. **D1683/D1683M, D6193**

DISCUSSION—This is usually expressed as stitches per inch (spi). **D6193**

stitch gage, *n*—*in sewn fabrics*, the perpendicular distance between adjacent parallel rows of stitching. **D1683/D1683M, D6193**

yarn slippage, *n*—a mode of failure of fabrics when sewn using a standard seam. **D1683/D1683M, D6193**

DISCUSSION—The displacement of one or more fabric yarns from the original position(s) so as to cause differences in alignment and spacing of both yarns. **D1683/D1683M**

yarn severance, *n*—a numerical value expressed on a percentage basis from this test that is used as an index of the degree of cutting of fabric yarns by the sewing machine needle in making sewn seams.

3.2 Definitions Relating to Stitches:

stitch, *n*—*in sewing*, the configuration of the interlacing of sewing thread in a specific repeated unit. (See also **stitching**, and **stitch type**.) **D6193**

stitch type, *n*—a numerical designation relating to the essential characteristics of the interlacing of sewing thread(s) in a specified seam type. **D1683/D1683M, D6193**

DISCUSSION—Stitch types are described in Practice **D6193**.

stitching, *n*—a series of stitches embodied in a material or materials of planar structure such as woven textile fabrics usually for ornamental purposes or finishing an edge, or both. **D6193**

4. Keywords

4.1 stitch; seam

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).