



Standard Specification for Aluminum Powder and Paste Pigments for Paints¹

This standard is issued under the fixed designation D962; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers four types and three classes of aluminum pigments for use in paints.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

2. Referenced Documents

2.1 *ASTM Standards*:²

D480 Test Methods for Sampling and Testing of Flaked Aluminum Powders and Pastes

E34 Test Methods for Chemical Analysis of Aluminum and Aluminum-Base Alloys

3. Classification

3.1 *Type I—Leafing Aluminum Pigment Powder:*

3.1.1 *Class A, Fine*—Maximum of 0.1 % retained on a No. 325 (45- μ m) sieve.

3.1.2 *Class B, Medium*—Maximum of 1.5 % retained on a No. 325 (45- μ m) sieve.

3.1.3 *Class C, Coarse*—Maximum of 20 % retained on a No. 325 (45- μ m) sieve.

3.2 *Type II—Leafing Aluminum Pigment Paste:*

3.2.1 *Class A, Fine*—Maximum of 0.1 % retained on a No. 325 (45- μ m) sieve.

3.2.2 *Class B, Medium*—Maximum of 1.0 % retained on a No. 325 (45- μ m) sieve.

3.2.3 *Class C, Coarse*—Maximum of 15 % retained on a No. 325 (45- μ m) sieve.

3.3 *Type III—Nonleafing Aluminum Pigment Powder (Note):*

3.3.1 *Class A, Fine*—Maximum of 1.5 % retained on a No. 325 (45- μ m) sieve.

3.3.2 *Class B, Medium*—Maximum of 6.0 % retained on a No. 325 (45- μ m) sieve.

3.3.3 *Class C, Coarse*—Maximum of 20 % retained on a No. 325 (45- μ m) sieve.

3.4 *Type IV—Nonleafing Aluminum Pigment Paste (Note 1):*

3.4.1 *Class A, Fine*—Maximum of 0.1 % retained on a No. 325 (45- μ m) sieve.

3.4.2 *Class B, Medium*—Maximum of 1.0 % retained on a No. 325 (45- μ m) sieve.

3.4.3 *Class C, Coarse*—Maximum of 11.0 % retained on a No. 325 (45- μ m) sieve.

NOTE 1—The particle size characteristics of the Type 3 and Type 4 pigments of the same class do not correspond with each other; in the case of Types 1 and 2 they do.

4. Composition and Properties

4.1 *Aluminum Pigment Powder (Type 1, Leafing and Type 3, Nonleafing)*—The aluminum pigment powder shall consist of commercially pure aluminum in the form of fine, polished flakes, and a suitable fatty lubricant. It shall contain no filler or extender pigments.

4.2 *Aluminum Pigment Paste (Type 2, Leafing and Type 4, Nonleafing)*—The aluminum pigment paste shall consist of commercially pure aluminum in the form of fine, polished flakes, and a suitable fatty lubricant combined with a volatile thinner. It shall contain no filler or extender pigments.

4.3 The aluminum pigments, powder, and paste of both leafing and nonleafing types shall conform to the requirements given in **Table 1**.

4.4 The paint made from the powder or paste shall be free-flowing and shall give a continuous coating at least equal in smoothness, luster, and general appearance to that of a reference sample mutually agreed upon by the purchaser and the seller.

4.5 The aluminum pigments, powder and paste of both leafing and nonleafing types, stored in unopened original packages within 6 months after shipment shall pass all tests applicable to the respective type and class as described in Test Methods **D480**.

5. Test Methods and Sampling

5.1 Sampling and tests shall be conducted in accordance with Test Methods **D480**. Since several of the methods are

¹ This specification is under the jurisdiction of ASTM Committee **D01** on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee **D01.31** on Pigment Specifications.

Current edition approved Dec. 1, 2014. Published December 2014. Originally approved in 1948. Last previous edition approved in 2008 as D962 – 81 (2008) ^{ϵ 1}. DOI: 10.1520/D0962-81R14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

TABLE 1 Requirements for Aluminum Pigments

	Leafing		Nonleafing	
	Type 1 (Powder)	Type 2 (Paste)	Type 3 (Powder)	Type 4 (Paste)
Nonvolatile matter at 105 to 110°C, min, %	99	65	99	65
Easily extracted fatty and oily matter (polishing lubricant), max, % ^A	4.0	3.0	4.0	3.0
Total impurities other than fatty and oily matter, max, % ^A	1.0	0.7	1.0	1.25
Coarse particles, max, %:				
Class A (total residue retained on a No. 325 (45-μm) sieve)	0.1	0.1	1.5	0.1
Class B (total residue retained on a No. 325 (45-μm) sieve)	1.5	1.0	6.0	1.0
Class C (total residue retained on:				
No. 100 (150-μm) sieve	0.5	0.5	0.5	0.5
No. 325 (45-μm) sieve)	20.0	15.0	20.0	11.0
Leafing, min, %:				
Class A	50	55	absent	absent
Class B	50	50	absent	absent
Class C	50	50	absent	absent

^A Nonleafing pigments may contain metal compounds as dispersants. If required, a complete analysis may be made in accordance with Test Methods E34.

empirical and the results are affected by the method, the specified procedures should be closely followed.

6. Packaging

6.1 Aluminum paste should be packaged in a polyvent container that can be safely vented in case of pressure build-up.

7. Keywords

7.1 aluminum powder; flake; leafing; nonleafing; paste; polishing lubricant

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/