



Standard Test Method for Temperature Calibration of Dynamic Mechanical Analyzers¹

This standard is issued under the fixed designation E 1867; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method describes the temperature calibration of dynamic mechanical analyzers (DMA) from -150 to 500°C .

1.2 SI units are the standard

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific precautionary statements are given in [Note 7](#).

2. Referenced Documents

2.1 *ASTM Standards:*²

[E 473 Terminology Relating to Thermal Analysis and Rheology](#)

[E 1142 Terminology Relating to Thermophysical Properties](#)

3. Terminology

3.1 *Definitions:*

3.1.1 The technical terms used in this test method are defined in Terminology [E 473](#) and Terminology [E 1142](#).

4. Summary of Test Method

4.1 An equation is developed for the linear correlation of experimentally observed program or sensor temperature and the actual melting temperature for known melting reference materials. This is accomplished by loading melting point reference materials into a polymer tube, or wrapping them with polymer tape and subjecting it to a mechanical oscillation at either fixed or resonant frequency. The extrapolated onset of melting is identified by a rapid decrease in the ordinate signal (the apparent storage modulus, stress, inverse strain or probe position). This onset is used for temperature calibration with two melting point reference materials.

5. Significance and Use

5.1 Dynamic mechanical analyzers monitor changes in the viscoelastic properties of a material as a function of temperature and frequency, providing a means to quantify these changes. In most cases, the value to be assigned is the temperature of the transition (or event) under study. Therefore, the temperature axis (abscissa) of all DMA thermal curves must be accurately calibrated by adjusting the apparent temperature scale to match the actual temperature over the temperature range of interest.

6. Interferences

6.1 An increase or decrease in heating rates or change in purge gas type or rate from those specified may alter results.

6.2 Once the temperature calibration procedure has been executed, the measuring temperature sensor position shall not be changed, nor shall it be in contact with the specimen or specimen holder in a way that would impede movement. If the temperature sensor position is changed or is replaced, then the entire calibration procedure shall be repeated.

6.3 Once the temperature calibration has been executed, the geometry deformation (bending study, versus tensile, and the like) shall not be changed. If the specimen testing geometry differs significantly from that of the calibrants, then the calibration shall be repeated in the geometry matching that of specimen testing.

6.4 This method does not apply to calibration for shear or compressive geometries of deformation.

7. Apparatus

7.1 The function of the apparatus is to hold a specimen of uniform dimension so that the specimen acts as the elastic and dissipative element in a mechanically oscillated system. Dynamic mechanical analyzers typically operate in one of several modes as outlined in [Table 1](#).

7.1.1 The apparatus shall consist of the following:

7.1.1.1 *Clamps*—A clamping arrangement that permits gripping of the specimen. This may be accomplished by clamping at both ends (most systems), one end (for example, torsional pendulum) or neither end (for example, free bending between knife edges).

¹ This test method is under the jurisdiction of ASTM Committee [E37](#) on Thermal Measurements and is the direct responsibility of Subcommittee [E37.10](#) on Fundamental, Statistical and Mechanical Properties.

Current edition approved Sept. 1, 2006. Published November 2006. Originally approved in 1997. Last previous edition approved in 2001 as E 1867–01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

TABLE 1 Dynamic Mechanical Analyzer Modes of Operation

Mode	Mechanical Response			
	Tension	Flexural	Torsion	Compression
Free/dec ^A	...	...	X	...
Forced/res/CA ^A	...	X	X	...
Forced/fix/CA ^A	X	X	X	X
Forced/fix/CS ^A	X	X	...	X

^A Free = free oscillation; dec = decaying amplitude; forced = forced oscillation; CA = constant amplitude; res = resonant frequency; fix = fixed frequency; CS = controlled stress.

7.1.1.2 *Device to Apply Oscillatory Stress or Strain*—A device for applying an oscillatory deformation (strain) or oscillatory stress to the specimen. The deformation may be applied and then released, as in freely vibrating devices, or continually applied, as in forced vibration devices.

7.1.1.3 *Detector*—A device or devices for determining the dependent and independent experimental parameters, such as force (stress), deformation (strain), frequency, and temperature. Temperature shall be measurable with an accuracy of ± 0.1 °C, force to ± 1 % and frequency to ± 1 %.

7.1.1.4 *Temperature Controller and Oven*—A device for controlling the specimen temperature, either by heating, cooling (in steps or ramps), or by maintaining a constant experimental environment. The temperature programmer shall be sufficiently stable to permit measurement of specimen temperature to ± 0.1 °C.

7.1.1.5 *Output Device*—Capable of displaying the storage modulus (either linearly or logarithmically) on the *Y*-axis (ordinate) increasing in the upwards direction and temperature on the *X*-axis (abscissa) increasing to the right.

NOTE 1—Some instruments, suitable for this test, may display only linear or logarithmic storage modulus while others may display linear and/or logarithmic storage modulus. Care must be taken to use the same modulus scale when comparing unknown specimens, and in the comparison of results from one instrument to another.

7.2 *PTFE (Polytetrafluoroethylene)*, tubing of 3 mm diameter and wallthickness of 0.5 mm (0.002 in.) ³inner diameter may be used for low temperature standards. The tubing may be sealed with suitable melting temperature wax plugs, or similar sealant.

NOTE 2—PTFE tubing is selected for its flexibility and inert nature for the solvents in use at the temperatures of interest. Furthermore its transitions should not produce any interference in the DMA signal within the range of the suggested calibrant materials. For other temperature ranges, a suitable replacement for the PTFE tubing may be used.

7.3 Where the melting material is to be confined to a tube

7.4 *PTFE Tape*, for wrapping metal point standards.

7.5 *Calibration Materials*—One or more suitable materials presented in Table 2.

7.6 *Calipers* or other length measuring device capable of measuring dimensions (or length) within ± 10 μ m.

8. Reagents and Materials

8.1 Dry nitrogen, helium, or other inert gas supplied for purging purposes and especially to ensure that moisture con-

TABLE 2 Calibration Materials

Material	Transition Temperature ^A		Reference
	°C	K	
Cyclopentane (solid-solid)	-151.16	121.99	X1.1
Cyclopentane (solid-solid)	-135.06	138.09	X1.1
<i>n</i> -Heptane	-90.56	182.65	X1.2
Cyclohexane	-87.06	186.09	X1.3
<i>n</i> -Octane	-56.76	216.39	X1.1
<i>n</i> -Decane	-26.66	246.49	X1.1
<i>n</i> -Dodecane	-9.65	263.5	X1.1
Water	0.01	273.16	X1.4
Cyclohexane	6.54	279.69	X1.3
Indium	156.5985	495.7485	X1.4
Tin	231.928	505.078	X1.4
Lead	327.462	600.612	X1.5
Zinc ^B	419.527	692.677	X1.4

^A The values in this table were determined under special, highly accurate test conditions that are not attainable or applicable to this test method. The actual precision of this test method is given in Section 13.

^B Amalgamates with aluminum. Do not heat above 430°C.

densation and ice formation is avoided when measurements involve temperatures below the dew point.

9. Calibration and Standardization

9.1 Prepare the instrument for operation as described by the manufacturer in the operations manual

10. Procedure

10.1 *Two Point Calibration*—For the purposes of this procedure, it is assumed that the relationship between observed extrapolated onset temperature (T_o) and actual specimen temperature (T_i) is a linear one governed by the equation:

$$T_i = (T_o \times S) + I \quad (1)$$

where: *S* and *I* are the slope and intercept of a straight line, respectively.

10.2 Select two calibration standards near the temperature range of interest. The standards should be as close to the upper and lower temperature limits used for the subsequent test materials as practical.

NOTE 3—In some testing geometries it may be possible to perform the test directly on the metal melting point reference materials without encapsulation.

10.2.1 Encapsulation technique for low temperature (liquid) standards where the melting temperature does not exceed 100 °C.

10.2.1.1 Fill the PTFE tubing with the calibration material or wrap a solid calibrant with PTFE tape. Calibrant must extend to the ends of the clamping geometry and must have uniform dimensions with respect to width.

NOTE 4—For solid calibrants, a wire of dimensions suitable for testing should be used.

10.3 Measure the length and for solid calibrants the diameter as well, of specimens.

10.4 Mount the specimen in accordance with the procedure recommended by the manufacturer.

NOTE 5—For specimen clamping arrangements where the specimen is not gripped on either end (for example, free bending between knife edges) the specimen must be rigid enough at the test start temperature to sustain

³ Lotti, C., Canevarolo, S.V., Polymer Testing, 1998, Vol 17, pp. 523–530. “Temperature Calibration of a Dynamic Mechanical Thermal Analyzer”.

initial loading. Alternatively, the calibration specimen, without encapsulation, can be placed between the knife edge and a substrate.

10.5 Maximum strain amplitude should be within the linear viscoelastic range of the specimens to be subsequently analyzed. Strains of less than 1 % are recommended and should not exceed 5 %.

10.6 Conduct the calibration runs at the heating rate of interest, preferably 1 °C/min but no greater than 5 °C/min and a frequency of 1 Hz. Other heating rates and frequencies may be used but shall be reported.

NOTE 6—Calibration for temperature should always be performed under the conditions of heating rate and frequency at which the unknown specimens will be tested. This method does not address the issues of frequency affects for polymeric transitions (such as the upwards shift of T_g with increasing frequency), and will only compensate for thermal lag within the measuring device.

10.7 Measure and record the ordinate signal, from 30°C below to 20°C above the melting point of the reference material. The calibration specimen may be equilibrated a minimum of 50°C below the melting transition, but adequate time to achieve thermal equilibrium in the specimen must be allowed.

11. Calculation

11.1 Take the transition temperature as the extrapolated onset to the sigmoidal change in the ordinate signal observed in the downward direction (see Fig. 1).

11.1.3 Report the temperature at which these tangent lines intersect as reported as the observed transition temperature (T_o).

11.2 Two Point Calibration:

11.2.1 Using the standard temperature values from Table 2 and the corresponding onset temperatures obtained experimentally, calculate the slope and intercept using the following equations:

$$S = [T_{r1} - T_{r2}] / [T_{o1} - T_{o2}] \quad (2)$$

$$I = [(T_{o1} \times T_{r2} - (T_{r1} \times T_{o2})) / [T_{o1} - T_{o2}]] \quad (3)$$

where

S = slope (nominal value = 1.0000),

I = intercept,

T_{r1} = reference transition temperature for Standard 1 (in Table 2),

T_{r2} = reference transition temperature for Standard 2 (in Table 2),

T_{o1} = experimentally observed transition onset temperatures for Standard 1, and

T_{o2} = experimentally observed transition onset temperature for Standard 2.

NOTE 7—**Caution:** The slope S is a dimensionless number whose value is independent of which temperature scale is used for I and T . I , in all cases, must have the same units as T_{r1} , T_{r2} , T_{o1} , and T_{o2} that are, by necessity, consistent with each other.




FIG. 1 Transition Temperature

11.1.1 Construct a tangent to the ordinate signal curve below the transition temperature.

11.1.2 Construct a tangent to the ordinate signal curve at the inflection point approximately midway through the sigmoidal change associated with the transition.

11.2.2 S should be calculated to ± 0.0001 units while I should be calculated to $\pm 0.1^\circ\text{C}$.

11.2.3 Using the determined values for S and I , Eq 1 may be used to calculate the actual specimen transition temperature (T_i) from any experimentally observed transition temperature (T_o) for the particular DMA instrument employed.

11.3 One Point Calibration:

11.3.1 In this abbreviated procedure, a relationship between the extrapolated onset temperature as observed and the temperature as assigned by a temperature sensor is established. The operator should choose a calibration standard that is near the temperature of the transition or phenomenon under study.

11.3.2 Using the specimen handling techniques in 10.2 through 10.7, obtain the DMA curve for the calibration standard chosen from Table 2.

11.3.3 From the known melting temperature of the calibration material (see Table 2), calculate the value and sign of σ from the following equation:

$$\sigma = T_r - T_o \quad (4)$$

where

T_r = reference transition temperature for standard (in Table 2),

T_o = experimentally observed transition onset temperature for standard, and

σ = correction factor for converting the observed temperature sensor temperature to actual sample temperature.

11.3.4 For the purpose of this abbreviated procedure, it is assumed that the relationship between the observed extrapolated onset temperature (T_o) and the actual specimen temperature is constant over the temperature range of interest. The value of σ is thus added to all observed measurements of transition temperatures for the particular instrument employed. That is:

$$T_i = T_o + \sigma \quad (5)$$

where

T_i = temperature of transition to be assigned.

12. Report

12.1 Report the following information:

12.1.1 Description of the instrument (manufacturer and model number) as well as the data handling device used in these tests,

12.1.2 Complete identification of the temperature reference materials used including source and purity,

12.1.3 Description of the dimensions, geometry, and material of the specimen. A description of the specimen holder should be specified as to composition, geometry and dimensions,

12.1.4 Identification of sample environment by gas flow rate, purity and composition,

12.1.5 Heating rate and description of any coolant used, and

12.1.6 Results of the calibration procedure including values for S and I . If the abbreviated one point calibration procedure was used, then the value of σ is given.

12.1.7 The specific dated version of this method used.

13. Precision and Bias

13.1 The precision and bias of this test method will be determined in an interlaboratory test program currently scheduled for 2007–2008. Anyone wishing to participate in the interlaboratory test should contact the ASTM International E37 Staff Manager.

14. Keywords

14.1 calibration; dynamic mechanical analyzer; temperature; thermal analysis

APPENDIX

(Nonmandatory Information)

X1. ADDITIONAL PUBLICATIONS

X1.1 Aston, J.G., *et.al.*, *J. Amer. Chem. Soc.*, 1943, 65, p. 341.

X1.2 Finke, H.L., *et.al.*, *J. Amer. Chem. Soc.*, 1954, 76, p. 33..

X1.3 Aston, J.G., *et.al.*, *J. Amer. Chem. Soc.*, 1943, 65, p. 1135.

X1.4 Preston–Thomas, H., *Metrologia*, 1990, 27, 99. 3–10.

X1.5 Bedford, R.E., *et al*, *Metrologia*, 1996, 33, pp. 133–154..

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).