



Standard Specification for Insulating Glass Unit Performance and Evaluation¹

This standard is issued under the fixed designation E 2190; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers preassembled permanently sealed insulating glass units with one or two airspaces and preassembled insulating glass units with capillary tubes intentionally left open.

1.2 This specification is applicable only to sealed insulating glass units that are constructed with glass.

1.3 The qualification of test specimens is based on frost/dew point and on the absence of fog after the specified test durations.

1.4 Qualification under this specification is intended to provide a basis for evaluating the durability of sealed insulating glass units.

1.5 This specification is not applicable to sealed insulating glass units containing a spandrel glass coating due to test method limitations.

1.6 This specification does not cover other physical requirements such as appearance, thermophysical properties, heat and light transmission, and glass displacement.

NOTE 1—Sealed insulating glass units qualified according to this specification are not necessarily suitable for structurally glazed applications. Factors such as sealant longevity when exposed to long term ultraviolet light and the structural properties of the sealant must be reviewed for these applications. For more information on the requirements for structural sealant glazing applications, refer to Specification C 1369, Guide C 1249, and Test Method C 1265.

1.7 The values stated in SI units are to be regarded as the standard. The inch-pound values given in parentheses are for information only and are not considered standard.

1.8 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

¹ This specification is under the jurisdiction of ASTM Committee E06 on Performance of Buildings and is the direct responsibility of Subcommittee E06.22 on Durability Performance of Building Constructions.

Current edition approved Oct. 15, 2008. Published November 2008. Originally approved in 2002. Last previous edition approved in 2002 as E 2190 – 02.

2. Referenced Documents

2.1 ASTM Standards:²

C 162 Terminology of Glass and Glass Products

C 717 Terminology of Building Seals and Sealants

C 1036 Specification for Flat Glass

C 1249 Guide for Secondary Seal for Sealed Insulating Glass Units for Structural Sealant Glazing Applications

C 1265 Test Method for Determining the Tensile Properties of an Insulating Glass Edge Seal for Structural Glazing Applications

C 1369 Specification for Secondary Edge Sealants for Structurally Glazed Insulating Glass Units

E 546 Test Method for Frost/Dew Point of Sealed Insulating Glass Units

E 631 Terminology of Building Constructions

E 2188 Test Method for Insulating Glass Unit Performance

E 2189 Test Method for Testing Resistance to Fogging in Insulating Glass Units

3. Terminology

3.1 Definition of Terms:

3.1.1 For definitions of terms found in this Specification, refer to Terminologies C 162, C 717, and E 631.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *sealed insulating glass unit, n*—a preassembled unit, comprising lites of glass, which are sealed at the edges and separated by dehydrated space(s), intended for vision areas of buildings. The unit is normally used for windows, window walls, picture windows, sliding doors, patio doors, or other types of fenestration.

4. Performance Requirements

4.1 The six units that complete the weather cycle and high humidity phases of Test Method E 2188 unbroken shall have the frost/dew point determined and reported.

4.2 Initial, intermediate (after the weather cycle phase) and final frost/dew points (after final high humidity test) shall be determined. For triple pane units, the frost/dew point is

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

determined for all airspaces. The final frost/dew points shall be -40°C or colder when measured in accordance with Test Method **E 546** or equivalent.

4.3 Final frost/dew points shall be determined after 24 h but no later than 7 days.

4.4 *Fog*—No fog shall be visible after testing in accordance with Test Method **E 2189**.

5. Test Specimens

5.1 Specimen design and construction techniques shall be established by Test Method **E 2188**.

5.2 The glass and airspace thickness(es) for qualification under this specification are 4 mm ($\frac{5}{32}$ in.) glass with 12 mm ($\frac{1}{2}$ in.) airspace or 5 mm ($\frac{3}{16}$ in.) glass with 6 mm ($\frac{1}{4}$ in.) airspace.

5.3 Glass or airspace thickness(es), or both, may be increased. (For example, using 6 mm glass with 12 mm airspace.) This may result in a more rigorous test.

5.4 For triple pane units, 4 mm ($\frac{5}{32}$ in.) glass with 6 mm ($\frac{1}{4}$ in.) airspaces are used.

5.5 All of the values in **5.2** and **5.4** are nominal.

5.6 Tolerance of glass thickness shall be in accordance with Specification **C 1036**.

5.7 Airspace tolerance(s) shall be ± 0.8 mm ($\frac{1}{32}$ in.).

5.8 Twelve double-glazed units shall be submitted when testing to this specification.

5.9 Fourteen triple-glazed units shall be submitted when testing to this specification.

6. Test Methods

6.1 Unit Performance Test:

6.1.1 Test six randomly selected specimens for 14 days in the high humidity phase, followed by 63 days in the weather cycle phase followed by 28 days in the high humidity phase in accordance with Test Method **E 2188**.

6.1.2 Breakage of only two specimens is permitted throughout the test.

NOTE 2—Breakage due to laboratory handling is not considered to be

test breakage. Units broken due to handling shall be replaced and tested from the beginning.

6.1.3 If there are more than two broken samples during the test, do not qualify this set of test specimens.

6.1.4 If a specimen has any visible deposits in the air space, do not qualify this set of test specimens for that test except as permitted in **6.1.2** (that is, breakage).

6.2 Fog Test:

6.2.1 Test the two fog test specimens for 7 days in accordance with Test Method **E 2189**.

6.3 The test durations are net testing periods. If the test is interrupted for any reason, the remaining portions shall be completed to qualify for the testing.

7. Qualification

7.1 When all test specimens have met the requirements as described in Section **4**, this set of test specimens shall be deemed to be qualified according to this specification.

7.2 If a specimen fails to meet the requirements as described in Section **4**, this set of specimens shall not be qualified according to this specification.

8. Report

8.1 Test Methods:

8.1.1 Report all information as required in the Report Section of Test Method **E 2188**.

8.1.2 Report all information as required in the Report Section of Test Method **E 2189**.

8.2 Test Durations:

8.2.1 Report the duration of the accelerated weathering test.

8.2.2 Report the duration of the high humidity testing.

8.2.3 Report the duration of the fog testing.

8.3 Report whether or not the set of test specimens meets the qualifications of this specification.

9. Keywords

9.1 insulating glass units; seal durability; sealed insulating glass units; unit performance and evaluation

APPENDIX

(Nonmandatory Information)

X1. EXAMPLE DATA SHEET FOR THIS SPECIFICATION

X1.1 See **Fig. X1.1**.

Date _____
 Manufacturer _____ Code _____ Report No. _____
 Address _____
 Attention _____ Telephone No. _____

Description of Test Specimen:

Size (width by height) _____ Glass Thickness and Type _____
 Type of Spacer and Finish _____
 Type and Amount of Desiccant _____
 Type of Sealant(s) _____
 Other Features (band, barrier coat, corner, etc.) _____
 Manufactured Date (month and year) _____
 Date Received at Laboratory _____ Date Testing Started _____

	Initial Frost/Dew Point	Fogging Test 7 Days	High Heat and Humidity 14 Days	Accelerated Weather Cycle 63 Days	High Heat and Humidity 28 Days
Test Unit #	°C	Fog Present Yes/No	°C	°C	°C
1					
2					
3					
4					
5					
6					
7					
8					
9					
10					

FIG. X1.1 Example Data Sheet

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).