



Standard Test Method for Solar Photometric Transmittance of Sheet Materials Using Sunlight¹

This standard is issued under the fixed designation E 972; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the measurement of solar photometric transmittance of materials in sheet form. Solar photometric transmittance is measured using a photometer (illuminance meter) in an enclosure with the sun and sky as the source of radiation. The enclosure and method of test is specified in Test Method E 1175 (or Test Method E 1084).

1.2 The purpose of this test method is to specify a photometric sensor to be used with the procedure for measuring the solar photometric transmittance of sheet materials containing inhomogeneities in their optical properties.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

E 772 Terminology Relating to Solar Energy Conversion

E 1084 Test Method for Solar Transmittance (Terrestrial) of Sheet Materials Using Sunlight

E 1175 Test Method for Determining Solar or Photopic Reflectance, Transmittance, and Absorptance of Materials Using a Large Diameter Integrating Sphere

2.2 CIE Standard:

Standard Illuminant D65³

¹ These test methods are under the jurisdiction of ASTM Committee E44 on Solar, Geothermal and Other Alternative Energy Sources and is the direct responsibility of Subcommittee E44.05 on Solar Heating and Cooling Systems and Materials.

Current edition approved March 1, 2007. Published July 2007. Originally approved in 1983. Last previous edition approved in 2002 as E 972 – 96 (2002).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Commission Internationale de l'Éclairage (International Commission on Illumination), Bureau Central de la CIE, 4 Av. du Recteur Poincaré, 75-Paris, France.

3. Terminology

3.1 *Definitions*—For definitions of other terms used in this test method, refer to Terminology E 772.

3.1.1 *illuminance, n*—luminous irradiance.

3.1.2 *luminous (photometric), adj*—referring to a radiant (or radiometric) quantity, indicates the weighted average of the spectral radiometric quantity, with the photopic spectral luminous efficiency function (see Annex A1) being the weighting function.

3.1.3 *radiant flux, Φ = dQ/dt* [Watt (W)], *n*—power emitted, transferred, or received in the form of electromagnetic waves or photons. See radiometric properties and quantities.

3.1.4 *reflectance, ρ, Φ_r/Φ_i, n*—the ratio of the reflected flux to the incident flux.

3.1.5 *solar irradiance at a point of a surface, E_s = dΦ/dA, n*—the quotient of the solar flux incident on an element of a surface containing the point, by the area of that element, measured in watts per square metre.

3.1.5.1 *Discussion*—Measured values of transmittance and reflectance depend upon angle of incidence, solid angles of incidence and of transmission and reflection, the method of measurement of the reflected or transmitted flux, and the spectral composition of the incident flux. Because of this dependence, complete information on the technique and conditions of measurement should be specified.

3.1.6 *solar, adj*—(1) referring to a radiometric term, indicates that the quantity has the sun as a source or is characteristic of the sun. (2) referring to an optical property, indicates the weighted average of the spectral optical property, with the solar spectral irradiance $E_{s\lambda}$ used as the weighting function.

3.1.7 *spectral, adj*—(1) for dimensionless optical properties, indicates that the property was evaluated at a specific wavelength, λ , within a small wavelength interval, $\Delta\lambda$ about λ , symbol wavelength in parentheses, as $L(350\text{ nm}, 3500\text{ Å})$, or as a function of wavelength, symbol $L(\lambda)$. (2) for a radiometric quantity, indicates the concentration of the quantity per unit wavelength or frequency, indicated by the subscript lambda, as $L_\lambda = dL/d\lambda$, at a specific wavelength. The wavelength at which the spectral concentration is evaluated may be indicated by the wavelength in parentheses following the symbol, $L_\lambda(350\text{ nm})$.



3.1.8 *transmittance*, $\tau = \Phi_t / \Phi_i$, n —the ratio of the transmitted flux to the incident radiant flux.

4. Summary of Test Method

4.1 Using sunlight as the source and a photometer as the detector, the specimen is made to be the cover of an enclosure with the plane of the specimen normal to the direct component of the incident solar radiation. Luminous transmittance is measured as the ratio of the transmitted illuminance to the incident illuminance.

5. Significance and Use

5.1 Glazed apertures in buildings are generally utilized for the controlled admission of both light and solar radiant heat energy into the structure. Other devices may also be used to reflect light and solar radiant heat into a building.

5.2 The bulk of the solar radiant energy entering a building in this manner possesses wavelengths that lie from 300 to 2500 nm (3000 to 25 000 Å). Only the portion from 380 to 760 nm (3800 to 7600 Å) is visible radiation, however. In daylighting applications, it is therefore important to distinguish the radiant (solar radiant energy) transmittance or reflectance of these materials from their luminous (light) transmittance or reflectance.

5.3 For comparisons of the energy and illumination performances of building fenestration systems it is important that the calculation or measurement, or both, of solar radiant and luminous transmittance and reflectance of materials used in fenestration systems use the same incident solar spectral distribution.

5.4 Solar luminous transmittance and reflectance are important properties in describing the performance of components of solar illumination systems including windows, clerestories, skylights, shading and reflecting devices, and other passive fenestrations that permit the passage of daylight as well as solar radiant heat energy into buildings.

5.5 This test method is useful for determining the solar luminous transmittance and reflectance of optically inhomogeneous sheet materials and diffusely reflecting materials used in natural lighting systems that are used alone or in conjunction with passive or active solar heating systems, or both. This test method provides a means of measuring solar luminous transmittance under fixed conditions of incidence and viewing. This test method has been found practical for both transparent and translucent materials as well as for those with transmittances reduced by reflective coatings. This test method is particularly applicable to the measurement of luminous transmittance of inhomogeneous, fiber reinforced, patterned, corrugated, or otherwise optically inhomogeneous materials when the transmittance is averaged over an area that is large in comparison to the inhomogeneities.

6. Apparatus

6.1 The apparatus to be used in this test method shall be as described in either Test Method E 1175 or E 1084, with the

exception that the sensing element shall be replaced by the sensing element described by this test method.

6.1.1 The sensing element of this instrument shall be a photometer (illuminance meter) consisting of a suitable radiation detector (such as a silicon photovoltaic device), a filter, and a diffusing element. The filter shall be designed so that the spectral response of the photometer very closely matches that of the standard human observer, as specified by the C.I.E. photopic spectral luminous efficiency function tabulated in Annex A1. The response of the photometer at wavelength λ , divided by its response at 555 nm (5550 Å), shall depart from the spectral luminous efficiency of the standard human observer at wavelength λ by no more than 2 % for all wavelengths from 390 to 750 nm (3900 to 7500 Å). Photometer response shall be essentially zero outside this range.

6.1.2 *Cosine Response*⁴—The response of the photometer to uniform, collimated incident radiation at an angle θ of incidence, divided by its response at normal incidence ($\theta = 0^\circ$), shall depart from the cosine of θ by no more than $(\theta \div 18) \%$, with θ in deg.

6.1.3 The diffusing element and detector electronics shall be designed so that the voltage (or current) output of the sensor is proportional to hemispherical illuminance incident upon it. The photometer shall be located inside the box so that its entrance aperture (the diffusing element) is centered approximately 50 mm (2 in.) below the plane of the rim of the box. Other instructions shall be closely followed.

7. Test Specimens

7.1 The test specimens shall be as described in Test Method E 1175 (or Test Method E 1084).

8. Procedure

8.1 The tests shall be conducted in accordance with the procedure provided in Test Method E 1175 (or Test Method E 1084).

9. Report

9.1 The report shall be prepared in accordance with Test Method E 1175 (or Test Method E 1084) with the exception that the calculated solar luminous transmittance shall be reported to the nearest 0.01 instead of solar (radiant) transmittance and solar illuminance shall be reported instead of solar irradiance.

10. Keywords

10.1 photometer; sheet materials; solar luminous transmittance; solar photometric transmittance; sunlight; transmittance

⁴ Photometers containing so-called cosine-response diffusing attachments are available from: Photo Research (Division of Kollmorgen Corp.) Burbank, CA; International Light, Inc., Newburyport, MA; Optronics Laboratories, Orlando, FL; Tektronix, Beaverton, OR; and Gamma Scientific, Inc., San Diego, CA, and have been found satisfactory for this purpose. Other photometers may be acceptable.



ANNEX

(Mandatory Information)

A1. CIE PHOTOPIC SPECTRAL LUMINOUS EFFICIENCY V_λ AND THE LUMINOUS EFFICACY CONSTANT K_m

A1.1 Values for the spectral luminous efficiency function V_λ for photopic vision as adopted by the International Commission on Illumination in 1924 and by the International Committee for Weights and Measures in 1933 (column for standard values) and intermediate interpolated values (other columns) are given in Table A1.1.

NOTE A1.1—The International Committee for Weights and Measures, meeting at the International Bureau of Weights and Measures near Paris, France, on Sept. 20–22, 1977, approved the value of 683 lm/W for spectral luminous efficacy constant, K_m . This constant is for monochromatic radiation of a wavelength of 555 nm (5550 Å) (where V_λ has its maximum value of 1.0002) in standard air for photopic vision.

TABLE A1.1 Photopic Spectral Luminous Efficiency, V_λ (Unity at Wavelength of Maximum Luminous Efficacy)^A

Wavelength, nm	Standard Values	Values Interpolated at Intervals of 1 nm								
		1	2	3	4	5	6	7	8	9
380	0.00004	0.000045	0.000049	0.000054	0.000059	0.000064	0.000071	0.000080	0.000090	0.000104
390	0.00012	0.000138	0.000155	0.000173	0.000193	0.000215	0.000241	0.000272	0.000308	0.000350
400	0.0004	0.00045	0.00049	0.00054	0.00059	0.00064	0.00071	0.00080	0.00090	0.00104
410	0.0012	0.00138	0.00156	0.00174	0.00195	0.00218	0.00244	0.00274	0.00310	0.00352
420	0.0040	0.00455	0.00515	0.00581	0.00651	0.00726	0.00806	0.00889	0.00976	0.01066
430	0.0116	0.01257	0.01358	0.01463	0.01571	0.01684	0.01800	0.01920	0.02043	0.02170
440	0.023	0.0243	0.0257	0.0270	0.0284	0.0298	0.0313	0.0329	0.0345	0.0362
450	0.038	0.0399	0.0418	0.0438	0.0459	0.0480	0.0502	0.0525	0.0549	0.0574
460	0.060	0.0627	0.0654	0.0681	0.0709	0.0739	0.0769	0.0802	0.0836	0.0872
470	0.091	0.0950	0.0992	0.1035	0.1080	0.1126	0.1175	0.1225	0.1278	0.1333
480	0.139	0.1448	0.1507	0.1567	0.1629	0.1693	0.1761	0.1833	0.1909	0.1991
490	0.208	0.2173	0.2270	0.2371	0.2476	0.2586	0.2701	0.2823	0.2951	0.3087
500	0.323	0.3382	0.3544	0.3714	0.3890	0.4073	0.4259	0.4450	0.4642	0.4836
510	0.503	0.5229	0.5436	0.5648	0.5865	0.6082	0.6299	0.6511	0.6717	0.6914
520	0.710	0.7277	0.7449	0.7615	0.7776	0.7932	0.8082	0.8225	0.8363	0.8495
530	0.862	0.8739	0.8851	0.8956	0.9056	0.9149	0.9238	0.9320	0.9398	0.9471
540	0.954	0.9604	0.9661	0.9713	0.9760	0.9803	0.9840	0.9873	0.9902	0.9928
550	0.995	0.9969	0.9983	0.9994	1.0000	1.0002	1.0001	0.9995	0.9984	0.9969
560	0.995	0.9926	0.9898	0.9865	0.9828	0.9786	0.9741	0.9691	0.9638	0.9581
570	0.952	0.9455	0.9386	0.9312	0.9235	0.9154	0.9069	0.8981	0.8890	0.8796
580	0.870	0.8600	0.8496	0.8388	0.8277	0.8163	0.8046	0.7928	0.7809	0.7690
590	0.757	0.7449	0.7327	0.7202	0.7076	0.6949	0.6822	0.6694	0.6565	0.6437
600	0.631	0.6182	0.6054	0.5926	0.5797	0.5668	0.5539	0.5410	0.5282	0.5156
610	0.503	0.4905	0.4781	0.4658	0.4535	0.4412	0.4291	0.4170	0.4049	0.3929
620	0.381	0.3690	0.3570	0.3449	0.3329	0.3210	0.3092	0.2977	0.2864	0.2755
630	0.265	0.2548	0.2450	0.2354	0.2261	0.2170	0.2082	0.1996	0.1912	0.1830
640	0.175	0.1672	0.1596	0.1523	0.1452	0.1382	0.1316	0.1251	0.1188	0.1128
650	0.107	0.1014	0.0961	0.0910	0.0862	0.0816	0.0771	0.0729	0.0688	0.0648
660	0.061	0.0574	0.0539	0.0506	0.0475	0.0446	0.0418	0.0391	0.0366	0.0343
670	0.032	0.0299	0.0280	0.0263	0.0247	0.0232	0.0219	0.0206	0.0194	0.0182
680	0.017	0.01585	0.01477	0.01376	0.01281	0.01192	0.01108	0.01030	0.00956	0.00886
690	0.0082	0.00759	0.00705	0.00656	0.00612	0.00572	0.00536	0.00503	0.00471	0.00440
700	0.0041	0.00381	0.00355	0.00332	0.00310	0.00291	0.00273	0.00256	0.00241	0.00225
710	0.0021	0.001954	0.001821	0.001699	0.001587	0.001483	0.001387	0.001297	0.001212	0.001130
720	0.00105	0.000975	0.000907	0.000845	0.000788	0.000736	0.000688	0.000644	0.000601	0.000560
730	0.00052	0.000482	0.000447	0.000415	0.000387	0.000360	0.000335	0.000313	0.000291	0.000270
740	0.00025	0.000231	0.000214	0.000198	0.000185	0.000172	0.000160	0.000149	0.000139	0.000130
750	0.00012	0.000111	0.000103	0.000096	0.000090	0.000084	0.000078	0.000074	0.000069	0.000064
760	0.00006	0.000056	0.000052	0.000048	0.000045	0.000042	0.000039	0.000037	0.000035	0.000032

^AIES Lighting Handbook, 1981 Reference Volume, Illuminating Engineering Society of North America, 345 East 47th Street, New York, NY 10017, Figs. 3–7, pp. 3–5.



E 972 – 96 (2007)

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).