



Standard Specification for PVC Hub and Elastomeric Seal (Gasket) Tee Connection for Joining Plastic Pipe to Insitu Pipelines and Manholes¹¹

This standard is issued under the fixed designation ; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the minimum performance and material requirements for a three piece tee connector for connection between plastic pipe and insitu pipes, manholes and wastewater structures in sanitary and storm sewer applications.

1.1.1 The three piece seal system consists of a 4 through 30-in. PVC (polyvinyl chloride) hub pipe, an elastomeric seal (gasket) and a mechanical band (Fig. 1). The system is installed in either a bored or cast hole opening in the host pipe or structure to a specific dimension that corresponds to the combined diameter of the PVC pipe outside diameter/tolerance and the elastomeric seal thickness.

1.2 These tee connectors are designed to provide a non-pressure (gravity flow) watertight connection between the incoming pipe and an insitu pipe or manhole/structure to the limits defined in this standard.

NOTE 1—Connections covered by this specification are adequate for laboratory hydrostatic pressures up to 13 psi (30 ft of head) without leakage when tested in accordance with the provisions of this standard. Infiltration or exfiltration quantities for an installed system are dependent upon many factors other than the connections between incoming pipe and the insitu pipe or manhole structure, and allowable quantities may need to be covered by other specifications and suitable testing of the installed pipeline and system. Where connections are made to concrete manhole sections refer to Specification C923.

NOTE 2—These connectors are not resilient connectors, and as such, allow for only a limited amount of lateral movement due to the tight compression seal between the PVC hub and insitu pipe/structure. Since these connectors are not rigid fittings, a significant amount of axial movement can be accommodated, but the degree of intrusion into the host pipe/structure must be regulated to minimize the impact on flow characteristics or hydraulic design conditions.

1.3 *The following precautionary caveat pertains only to the test methods portion, Section 7, of this specification: This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. For a specific precaution statement, see Section 7.*

¹ This test method is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.20 on Joining. Current edition approved Aug. 1, 2012. Published September 2012. DOI: 10.1520/F2946-12

2. Referenced Documents

2.1 ASTM Standards:²

- A493 Specification for Stainless Steel Wire and Wire Rods for Cold Heading and Cold Forging
- A666 Specification for Annealed or Cold-Worked Austenitic Stainless Steel Sheet, Strip, Plate, and Flat Bar
- C822 Terminology Relating to Concrete Pipe and Related Products
- C923 Specification for Resilient Connectors Between Reinforced Concrete Manhole Structures, Pipes, and Laterals
- D1566 Terminology Relating to Rubber
- D1785 Specification for Poly(Vinyl Chloride) (PVC) Plastic Pipe, Schedules 40, 80, and 120
- D2665 Specification for Poly(Vinyl Chloride) (PVC) Plastic Drain, Waste, and Vent Pipe and Fittings
- D3034 Specification for Type PSM Poly(Vinyl Chloride) (PVC) Sewer Pipe and Fittings
- F412 Terminology Relating to Plastic Piping Systems
- F477 Specification for Elastomeric Seals (Gaskets) for Joining Plastic Pipe
- F679 Specification for Poly(Vinyl Chloride) (PVC) Large-Diameter Plastic Gravity Sewer Pipe and Fittings
- F1417 Practice for Installation Acceptance of Plastic Non-pressure Sewer Lines Using Low-Pressure Air
- F2487 Practice for Infiltration and Exfiltration Acceptance Testing of Installed Corrugated High Density Polyethylene Pipelines

2.2 AWWA Standard:³

- C900 Polyvinyl Chloride (PVC) Pressure Pipe and Fabricated Fittings, 4 in. Through 12 in. (100 mm Through 300 mm), for Water Transmission and Distribution

3. Terminology

3.1 Definitions:

3.1.1 Terms relating to plastics and rubber shall be as defined in Terminologies F412 and D1566, respectively.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American Water Works Association (AWWA), 6666 W. Quincy Ave., Denver, CO 80235, <http://www.awwa.org>.




FIG. 1 Three-Piece Sealing System (Connector)

3.1.2 Terms relating to precast concrete pipe, manholes, and related products shall be as defined in Terminology C822.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *connector, n*—the entire assembly including pipe hub, elastomeric seal and mechanical band.

3.2.2 *insitu, adj*—reflects the condition of the pipe, manhole or waste water structure that serves as the host to the connector. These facilities are existing structures that has been excavated for the purposes of tapping or connecting into the line.

3.2.3 *mechanical band, n*—metallic or nonmetallic mechanical device used for compressing an elastomeric seal against a pipe's outside diameter wall, typically a stainless steel worm screw clamp.

3.2.4 *pipe hub, n*—a short section of pipe used to made a watertight connection to the incoming pipeline. This pipe hub is typically made from the same pipe material and meeting the same ASTM standard as the incoming pipeline.

4. Materials and Manufacture

4.1 All materials shall conform to the following requirements:

4.1.1 *Elastomeric Seals*—Gasket materials for connectors shall meet the requirements of F477.

4.2 *Mechanical Device or Band*—Take-up devices used for mechanically compressing the resilient portion of the connector against the pipe, manhole or wastewater structure shall be made from a material or materials in combination that will ensure durability, strength, resistance to corrosion, and have properties that will ensure continued resistance to leakage. All metallic mechanical devices, including castings and bolt assemblies used to mechanically deform elastomeric seals shall be constructed of corrosion resistant materials meeting the physical properties and chemical composition requirements of Specifications A493 and A666, Type 302 through Type 316.

The minimum torque requirement for securing the band around the PVC hub shall be 60 in-lbs.

4.3 *PVC Hubs*—PVC pipe and joint sections that constitute the hub component of this system shall be fabricated from pipe and joint that meet the requirements of either Specification D1785, D2665, D3034, F679 or AWWA C900.

NOTE 3—Experience has shown that successful performance of this product depends on the type of bedding and backfill and the care in the field installation of the manhole or wastewater structure and connecting pipes. The owner is cautioned that field inspection at the construction site may be necessary.

5. Principles of Design

5.1 The design of the connector shall be such that positive seal is accomplished at two locations: (1) between the elastomeric seal and the wall of the insitu pipe, manhole or wastewater structure and (2) between the elastomeric seal and the pipe hub. The watertight seal between the insitu pipe, manhole or waste water structure is made by the compression of the gasket between the insitu structure and the pipe hub.

5.1.1 The seal between the connector and the wall of the insitu pipe, manhole or wastewater structure shall be made by mechanical means, compression of the elastomeric seal between the outside surface of the pipe hub and the opening in the wall of the insitu pipe, manhole or wastewater structure.

5.1.2 The seal between the connector and the pipe hub shall be made by mechanical means by compression of the elastomeric material against the outside of the pipe hub with a mechanical devise or band. Devices used to effect mechanical seals shall conform to the requirements specified in Section 4.

5.2 All pipe stubs installed shall allow for future connection to the insitu pipe, manhole or wastewater structure, and be mechanically restrained from movement by means of the elastomeric connectors. If an internal and external lip or seal is made with the insitu pipe, manhole or waste water structure

with the elastomeric seal, this seal shall not extend more than 0.25 in. (6.25 mm) into the flow channel or void area of the insitu structure.

6. Basis of Acceptance

6.1 Laboratory Testing:

6.1.1 For each connector diameter, type and configuration at least one connector shall be laboratory tested per year in accordance with the procedures in Section 7. Tests shall be conducted on each combination of size, connector, pipe material, and pipe/structure.

6.1.2 The acceptability of the resilient connector shall be determined by the results of the physical tests prescribed in this specification, if and where required, and by inspection, to determine whether the connector conforms to the specification with regards to design and freedom from defects.

6.1.3 When requested, a current certification shall be furnished as the basis of acceptance. The certification shall consist of third party test report, accompanied by a copy of the test results, that the connector has been tested and inspected in accordance with the provisions of Section 4 and Section 7. Each certification so furnished shall be signed by the connector manufacturer or an authorized agent.

6.1.4 Certification shall be deemed current, if it represents present design, and bears a date that is no more than one year older than the current date.

6.2 Tee Bending Test:

6.2.1 *Tees*—The tee connector shall be subjected to a load as illustrated in Fig. 2. The load shall result in a minimum bending moment of 100 ft·lbf (136 Nm). The procedure may be modified providing the resultant bending moment is maintained.

NOTE 4—The tee bending test is intended to insure the connector when installed in the insitu pipe/structure has adequate strength to prevent dislodging during installation and construction. It is not intended to validate the structural capacity of the either the connector or host structure.

6.3 Field Testing:

6.3.1 When required in the project documents, field air tests of connectors placed into insitu pipelines shall be conducted

according the requirements of Specification F1417. Only the connector needs to be evaluated, the incoming lateral pipe, which adjoins the connector, or the insitu pipe does not need to constitute part of this test.

NOTE 5—When field pressure testing joint connections, extreme care needs to be taken to insure all bulkheads and plugs are properly secured and braced to prevent movement. This standard does not address all the field related procedures necessary to conduct a safe test.

6.3.2 In lieu of the requirements in section 6.3.1, if the pipe used in the insitu pipeline is within the scope of Specification F2487, it is permitted to evaluate the performance and acceptance of the connector as part of the infiltration and exfiltration test of the pipeline in accordance with the requirements of Specification F2487. The performance of the pipeline shall, as a minimum, be 200 gal/in/day (18.5 L/mm of internal diameter) or the project requirements, whichever is more severe or has the higher requirement.

NOTE 6—Field performance depends greatly on the accuracy of the field cored hole in the host pipe, and the relative condition of the host pipe with regards to its overall deformation and deflection.

7. Test Methods and Requirements

7.1 Install a pipe(s) and the connector(s) to be tested in the base section of a pipe, manhole or wastewater structure. Subject the assembly to the prescribed hydrostatic pressure in 7.2 at the centerline of the connector for a period of 10 min for each test condition. Restrain the pipe against axial movement during the tests.

NOTE 7—The user of this specification is advised that if manhole bases greater than 48 in. inside diameter are required to accommodate large diameter connectors for the test, all safety requirements and procedures should be reviewed prior to the test.

7.1.1 Install a lateral and connector to be tested into the pipe. Subject the assembly to the prescribed hydrostatic pressure in 7.2 for a period of 10 min for each test condition. Restrain the lateral against axial movement during the tests.

7.2 There shall be no leakage under any of the following conditions:




FIG. 2 Tee Bending Test (Schematic Representation)

7.2.1 Straight alignment of the pipe(s)/lateral(s) subjected to a hydrostatic pressure of 15 psi (35 ft) for 10 min.

7.3 Leakage shall be construed to mean freely dripping water emanating at the interface between the connector and base of the manhole or wastewater structure, or the pipe; between the connector and the filler rings; or through the body of the connector and the filler rings; or through the body of the connector itself.

7.4 Moisture appearing at random locations on the base of the outlet in the form of patches or beads adhering to the surfaces shall not be considered leakage.

8. Rejection and Rehearing

8.1 If the results of any test(s) do not meet the requirements of this specification, the test(s) shall be conducted again in accordance with an agreement between the owner and the manufacturer. There shall be no agreement to lower the minimum requirement of the specification by such means as omitting tests that are a part of the specification, substituting or modifying a test method, or by changing the specification limits. In retesting, the product requirements of this specification shall be met, and the test methods designated in this specification shall be followed. If, upon retest, failure occurs, the quantity of product represented by the test(s) does not meet the requirements of this specification.

9. Certification

9.1 When specified in the purchase order or contract, a manufacturer's or independent laboratory's certification shall be furnished to the owner that the products shipped, as

identified by the lot description of Section 10, were manufactured, sampled, tested, and inspected at the time of manufacture in accordance with this specification and have been found to meet the requirements. When specified in the purchase order or contract, a report of the test results shall be furnished.

10. Markings

10.1 *Elastomeric Seal*—Each elastomeric seal component of the sealing system shall be marked legibly, not less than 1/4-in. in height, with this F2946 designation, the manufacturer's name, date of manufacture and the size designation or part number.

10.2 *Hub*—Each hub component shall be marked with the manufacturer's logo or name.

11. Quality Assurance

11.1 When the product is marked with this designation (ASTM F2946), the manufacturer affirms that the product was manufactured, inspected, sampled, and tested in accordance with this specification and has been found to meet the requirements of this specification.

12. Packaging and Package Marking

12.1 All pipe, couplings and bands shall, unless otherwise specified, be packaged for standard commercial shipment.

13. Keywords

13.1 elastomeric seal; rubber gasket; service connection; sewer tap; watertight seal

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).