



Standard Specification for Chromium-Iron Sealing Alloys with 18 or 28 Percent Chromium¹

This standard is issued under the fixed designation F256; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers two chromium-iron alloys, the former, (UNS K91800), nominally 18 % chromium, balance iron, the latter, (UNS K92801), nominally 28 % chromium, in strip, bar, wire, and rod forms intended primarily for sealing to glass in electronic applications.

NOTE 1—UNS K92801 should only be considered for use at service temperatures below 300°C. The alloy is prone to sigma phase formation at temperatures close to 620°C, and exhibits brittle mechanical behavior after prolonged exposures at temperatures close to 475°C.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 The following hazard caveat pertains only to the test method portion, Sections 16 and 17, of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- A370 Test Methods and Definitions for Mechanical Testing of Steel Products
- E3 Guide for Preparation of Metallographic Specimens
- E18 Test Methods for Rockwell Hardness of Metallic Materials
- E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E38 Methods for Chemical Analysis of Nickel-Chromium

¹ This specification is under the jurisdiction of ASTM Committee F01 on Electronics and is the direct responsibility of Subcommittee F01.03 on Metallic Materials.

Current edition approved Oct. 1, 2010. Published November 2010. Originally approved in 1951 as F256 – 51 T. Last previous edition approved in 2005 as F256 – 94 (2005)^{ε1}. Consolidated with F257 in 1972. DOI: 10.1520/F0256-05R10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

and Nickel-Chromium-Iron Alloys

E228 Test Method for Linear Thermal Expansion of Solid Materials With a Push-Rod Dilatometer

F14 Practice for Making and Testing Reference Glass-Metal Bead-Seal

F140 Practice for Making Reference Glass-Metal Butt Seals and Testing for Expansion Characteristics by Polarimetric Methods

F144 Practice for Making Reference Glass-Metal Sandwich Seal and Testing for Expansion Characteristics by Polarimetric Methods

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 bar:

3.1.1.1 hot-finished rounds, squares, and hexagons, ¼ in. (6.4 mm) and over in diameter or size.

3.1.1.2 hot-finished flats, ¼ in. to 10 in. (6.4 to 254 mm), inclusive, in width and ⅛ in. (3.2 mm) and over in thickness.

3.1.1.3 cold-finished rounds, squares, octagons, hexagons and shapes, over ½ in. (12.7 mm) in diameter or size.

3.1.1.4 cold-finished flats, ⅜ in. (9.5 mm) and over in width and ⅛ in. (3.2 mm) and over in thickness (see Discussions).

Discussion—Widths less than ⅜ in. (9.5 mm) and thicknesses less than ⅜ in. (4.8 mm) are generally described as flat wire.

Discussion—Thicknesses of ⅛ in. (3.2 mm) to under ⅜ in. (4.8 mm) can also be described as cold-rolled strip or, if in cut lengths, bar.

3.1.2 rod—hot-rolled, or hot-rolled, annealed, and pickled, rounds, squares, octagons, hexagons and shapes, in coils, for subsequent cold drawing or cold rolling, ¼ in. or ⅜ in. (6.4 or 19.0 mm) in diameter or size.

3.1.3 strip—cold-finished coils or cut lengths, under 24 in. (610 mm) down to and including ⅜ in. (4.8 mm) in width, and under ⅜ in. down to and including 0.005 in. (0.13 mm) in thickness.

3.1.4 No. 1 edge—a rolled edge either round or square as specified.

3.1.5 No. 3 edge—an edge produced by slitting.

3.1.6 No. 5 edge—an approximately square edge produced by rolling or filing after slitting.

Discussion—Cold-finished product 0.005 in. (0.13 mm) in thickness and under 24 in. (609.6 mm) in width is sometimes identified as foil.

3.1.7 wire:

3.1.7.1 cold finished only, round or square, ½ in. (12.7 mm) and under in diameter or size.

3.1.7.2 cold finished only, flat wire of ¼ in. (1.6 mm) to under ⅜ in. (9.5 mm) in width and 0.010 in. (0.25 mm) to under ⅜ in. (4.8 mm) in thickness.

4. Classification

4.1 The alloys covered by this specification are classified by nominal chemical composition, specifically by chromium content, in two types:

4.1.1 *Type I*—18 % chromium (UNS K91800) and

4.1.2 *Type II*—28 % chromium (UNS K92801).

5. Ordering Information

5.1 Orders for material under this specification shall include the following information:

5.1.1 Quantity (weight (Note 2) or number of pieces),

5.1.2 Name of material (chromium-iron alloy),

5.1.3 Type (Section 4),

5.1.4 Form (Section 3),

5.1.5 Temper and finish (Section 7),

5.1.6 Permissible variations in dimensions for rod (Section 13),

5.1.7 Certification if required (Section 21),

5.1.8 Packaging required (Section 22),

5.1.9 Dimensions (width, thickness, diameter, etc.),

5.1.10 ASTM designation: F256, and

5.1.11 Exceptions to the specification or special requirements.

NOTE 2—The term “weight” is temporarily used in this standard because of established trade usage. The word is used to mean both “force” and “mass,” and care must be taken to determine which is meant in each case (SI unit for force = newton and for mass = kilogram).

5.2 If possible, the intended end use of the item should be given on the purchase order especially when the item is ordered for a specific end use or uses. Such information will enable the manufacturer to produce a material more satisfactory for the purchaser’s process and product.

NOTE 3—A typical ordering description is as follows: 2000 kg, chromium-iron alloy, Type II, wire, annealed, cold drawn, commercial packaging, ¼ in. (6.4 mm) round by coil, ASTM F256, end use-redraw.

6. Process

6.1 The purchaser shall specify that the alloy be made by one or more of the following processes: electric-arc, electric-induction, or other process approved by the purchaser.

7. Temper and Finish

7.1 The desired temper of the material shall be specified on the purchase order as follows:

7.1.1 Annealed for forming (strip),

7.1.2 Annealed for deep drawing (strip),

7.1.3 Cold rolled or cold drawn to a specified mechanical property level, or

7.1.4 As hot rolled.

7.2 The desired surface of the material shall be specified on the purchase order as follows:

7.2.1 Pickled,

7.2.2 Cold drawn (wire and bar),

7.2.3 Centerless ground (wire and bar), or

7.2.4 Cold rolled (strip).

8. Chemical Composition

8.1 The material shall conform to the chemical composition specified in Table 1.

TABLE 1 Chemical Requirements

NOTE 1—Round observed or calculated values to the nearest unit in the last right-hand place of figures used in expressing the limiting value, in accordance with the rounding-off method of Practice E29.

Element	Composition, %	
	Type I	Type II
Carbon, max	0.08	0.12
Manganese, max	1.00	1.00
Silicon, max	0.75	0.75
Phosphorus, max	0.040	0.040
Sulfur, max	0.030	0.030
Chromium, nominal	18.0	28.0
Nickel, max	0.50	0.50
Nitrogen, max	...	0.20
Titanium	^A	...
Iron	remainder	remainder

^AFive times the carbon content, minimum, and 0.60, max.

8.2 *Ladle Analysis*—A ladle analysis of each heat of steel shall be made by the manufacturer to determine the percentages of the elements specified in Table 1. The analysis shall be made from test castings made during the pouring of the heat. The chemical composition thus determined shall conform to the requirements specified in Table 1.

8.3 *Check Analysis*—If check analysis is made by the purchaser, the chemical composition thus determined shall conform to the requirements specified in Table 1 subject to the permissible tolerances of Table 2.

TABLE 2 Check Analysis Tolerances

Element	Tolerances over maximum or under minimum limits, percentage points
Carbon	0.01
Manganese	0.03
Phosphorus	0.005
Sulfur	0.005
Silicon	0.05
Nickel	0.03
Nitrogen	0.01
Titanium	0.05

9. Chemical Analysis

9.1 Chemical analysis shall be made in accordance with Method E38 or equivalent methods.

10. Thermal Expansion Requirements

10.1 The material shall conform to the thermal expansion requirements prescribed in Table 3.

TABLE 3 Thermal Expansion Requirements^{A,B}

Temperature Range, °C	Mean Coefficient of Linear Thermal Expansion, $\mu\text{m/m} \cdot ^\circ\text{C}$	
	UNS K91800	UNS K92801
30 to 530	11.3 to 11.7	10.8 to 11.4

^ATypical thermal expansion data for the alloys covered by this specification are given for information only in the Appendix.

^BThese requirements apply to specimens heat treated prior to test in accordance with Section 16.

11. Mechanical Property Requirements

11.1 The material shall conform to the mechanical property requirements prescribed in Table 4. Rockwell hardness shall be

TABLE 4 Mechanical Property Requirements^A

Thickness, in. (mm)	Rockwell Hardness (or equivalent) (max)	Tensile Strength, max.	
		ksi	MPa
Under 0.015 (0.38)	...	85	590
0.015 (0.38) to 1 (25.4), incl	B85	...	...
Over 1 (25.4)	B88	...	...

^AApplicable to strip in the annealed condition only. All other mechanical properties as agreed upon between purchaser and manufacturer.

determined in accordance with Test Method E18.

12. Transformation Requirements

12.1 The material shall show no evidence of transformation to martensite. For Type I alloy, the austenite formed during heat treating will transform to martensite at or above room temperature. The presence of austenite, as may be noted in Type II alloy, is acceptable if the thermal expansion requirement is met.

13. Permissible Variations in Dimensions

13.1 Material furnished under this specification, except rod, shall conform to the dimensional requirements of Tables 5-15.

13.2 Permissible variations in dimensions for rod for re-drawing or rerolling shall be as agreed upon between purchaser and manufacturer.

14. Workmanship, Finish, and Appearance

14.1 The material shall be commercially smooth and uniform in cross section, composition, and temper; it shall be free of scale corrosion, cracks, seams, scratches, slivers, processing lubricants, and other defects as best commercial practice will permit.

15. Number of Tests and Retests

15.1 Test specimens for thermal expansion and phase-transformation requirements shall be selected on the basis of a minimum of one specimen per heat.

TABLE 5 Permissible Variations in Size of Cold-Finished Round Bars

Specified Size, in. (mm)	Permissible Variations from Specified Size, in. (mm) ^{A,B}	
	Over	Under
Over ½ (12.7) to 1 (25.4), excl	0.002 (0.05)	0.002 (0.05)
1 (25.4) to 1½ (38.1), excl	0.0025 (0.064)	0.0025 (0.064)
1½ (38.1) to 4 (101.6), incl ^C	0.003 (0.08)	0.003 (0.08)

^A Unless otherwise specified, size tolerances are over and under as shown in the above table. When required, however, they may be specified all over and nothing under, or all under and nothing over, or any combination of over and under, if the total spread in size tolerance for a specified size is not less than the total spread shown in the table.

^B When it is necessary to heat treat or heat treat and pickle after cold finishing, size tolerances are double those shown in the table.

^C Cold-finished bars over 4 in. (101.6 mm) in diameter are produced; size tolerances for such bars have not been evolved.

TABLE 6 Permissible Variations in Length of Hot-Finished or Cold-Finished Bars^A

Specified Size of Rounds, Squares, Hexagons, Octagons, and Widths of Flats, in. (mm) ^B	Permissible Variations in Length, in. (mm)			
	For Lengths up to 12 ft (3.7 m), incl		For Lengths over 12 ft (3.7 m), to 25 ft (7.6 m), incl	
	Over	Under	Over	Under
To 2 (50.8), incl	½ (12.7)	0	¾ (19.0)	0
Over 2 (50.8) to 4 (101.6), incl	¾ (19.0)	0	1 (25)	0
Over 4 (101.6) to 6 (152.4), incl	1 (25)	0	1¼ (32)	0
Over 6 (152.4) to 9 (228.6), incl	1¼ (32)	0	1½ (38)	0
Over 9 (228.6) to 12 (304.8), incl	1½ (38)	0	2 (51)	0

^AThe order should specify random lengths or specific lengths. When random lengths are ordered, the length tolerance is not less than 2 ft (609.6 mm). When specific lengths are ordered, Table 8 or Table 9 shall apply.

^BThe maximum width of bar flats is 10 in. (254.0 mm).

15.2 Test specimens for mechanical properties shall be selected on the basis of a minimum of one specimen per size, each heat, each lot annealed or otherwise heat treated under the same conditions, and each lot with like processing.

15.3 If any test specimen shows defective machining or develops flaws, it may be discarded and another specimen substituted.

15.4 If the results of any test lot are not in conformance with the requirements of this specification, such lots may be retreated at the option of the manufacturer. The material shall be acceptable if the results of tests on the retreated material are within the requirements of this specification.

16. Specimen Heat Treatment

16.1 The specimens for thermal-expansion and phase-transformation tests shall be heat treated prior to testing as follows:

16.1.1 *Type I*—Heat the specimen to $1200 \pm 10^\circ\text{C}$ and hold at temperature for 15 min. Air cool to room temperature.

16.1.2 *Type II*—Heat the specimen to $1100 \pm 10^\circ\text{C}$ and hold at temperature for 15 min. Air cool to room temperature. The cooling rate is recommended to be faster than 300°C per hour between 600 and 300°C . Slower cooling rates could lead to brittle mechanical behavior.

TABLE 7 Permissible Variations in Straightness of Machine-Straightened Hot-Finished or Cold-Finished Bars

Measure the length of the maximum gap between the bar and a straightedge of appropriate length when the straightedge is laid along the length of the bar on its concave side. Unless otherwise specified, hot-finished or cold-finished bars for machining purposes are furnished machine straightened to the following tolerances (maximum gap length), in in. (mm):

Hot-Finished

$\frac{1}{8}$ in. (3.2 mm) in any 5 ft (1.5 m), but may not exceed $\frac{1}{8}$ in. (3.2 mm) $\times$ length in ft (m) $\div$ 5 ft (1.5 m)

Cold-Finished

$\frac{1}{16}$ in. (1.6 mm) in any 5 ft (1.5 m), but may not exceed $\frac{1}{16}$ in. (1.6 mm) $\times$ length in ft (m) $\div$ 5 ft (1.5 m)

TABLE 8 Diameter and Out-of-Round Tolerances for Round Wire (Drawn, Polished, Centerless Ground, Centerless Ground and Polished)^{A,B,C}

Specified Diameter, in. (mm)	Diameter Tolerance, in. (mm)	
	Over	Under
0.5000 (12.700)	0.0020 (0.051)	0.0020 (0.051)
Under 0.5000 (12.700) to 0.3125 (7.938), incl	0.0015 (0.038)	0.0015 (0.038)
Under 0.3125 (7.938) to 0.0440 (1.118), incl	0.0010 (0.025)	0.0010 (0.025)
Under 0.0440 (1.118) to 0.0330 (0.838), incl	0.0008 (0.020)	0.0008 (0.020)
Under 0.0330 (0.838) to 0.0240 (0.610), incl	0.0005 (0.013)	0.0005 (0.013)
Under 0.0240 (0.610) to 0.0120 (0.305), incl	0.0004 (0.010)	0.0004 (0.010)
Under 0.0120 (0.305) to 0.0080 (0.203), incl	0.0003 (0.008)	0.0003 (0.008)
Under 0.0080 (0.203) to 0.0048 (0.122), incl	0.0002 (0.005)	0.0002 (0.005)
Under 0.0048 (0.122) to 0.0030 (0.076), incl	0.0001 (0.003)	0.0001 (0.003)

^A Diameter tolerances are over and under as given in this table. Also, round wire can be produced to tolerances all over and nothing under, or all under and nothing over, or any combination over and under, if the total spread in diameter tolerances for a specified diameter is not less than the total spread given in this table.

^B The maximum out-of-round tolerance for round wire is one half of the total size tolerance given in this table.

^C When it is necessary to heat treat after cold finishing because of special mechanical property requirements, tolerances are commonly double those shown.

TABLE 9 Size Tolerances for Drawn Wire in Hexagons, Octagons, and Squares

Specified Size, in. (mm) ^A	Size Tolerance, in. (mm)	
	Over	Under
$\frac{1}{2}$ (12.7)	0	0.004 (0.10)
Under $\frac{1}{2}$ (12.7) to $\frac{5}{16}$ (7.9), incl	0	0.003 (0.08)
Under $\frac{5}{16}$ (7.9) to $\frac{1}{8}$ (3.2), incl	0	0.002 (0.05)

^A Distance across flats.

17. Test Methods

17.1 **Thermal Expansion** (Note 4)—After heat treatment of the specimen in accordance with Section 16, determine the thermal expansion characteristics in accordance with Test Method E228.

NOTE 4—Although not required, the thermal expansion match between the alloy and a glass may be evaluated by preparing and testing an assembly in accordance with Practices F14, F140, or F144.

17.2 **Transformation**—Cut the specimen from any part of the material, preferably including the entire cross section, degrease it, and then heat treat it as described in Section 16. When cool, polish the cross section of the specimen and etch in accordance with Methods E3 (Note 5). Examine the specimen at a magnification of 150 $\times$ for the presence of the acicular crystals of the martensite phase. Because these crystals may occur only in small localized areas, examine carefully the entire polished cross section.

NOTE 5—A suggested etchant is a solution of 3 parts by volume of concentrated hydrochloric acid and 1 part by volume of concentrated nitric acid saturated with cupric chloride (CuCl₂·2H₂O). This etchant is more effective when allowed to stand for 20 min after mixing. After several

hours it loses its strength and should be discarded at the end of the day. Etching is best accomplished by swabbing the specimen with cotton soaked with the etchant. Etching is usually complete when the surface of the metal appears to have turned dull.

17.3 **Mechanical and Physical Properties**—Determine tensile strength in accordance with Test Methods A370.

18. Inspection

18.1 Inspection of the material by the purchaser may be made at the manufacturer's plant and shall be made as agreed upon by the purchaser and the seller as part of the purchase contract.

19. Rejection

19.1 Unless otherwise specified, any rejection based on tests made in accordance with this specification shall be reported to the manufacturer. Disposition of rejected material shall be a matter of agreement between the manufacturer and the purchaser.

19.2 Material that shows injurious defects subsequent to its acceptance at the manufacturer's works will be rejected, and the manufacturer shall be notified so disposition of the material can be effected.

20. Rehearing

20.1 Specimens tested in accordance with this specification that represent rejected material shall be preserved for 3 weeks from the date of the test report. In case of dissatisfaction with the results of the tests, the manufacturer may make claim for a rehearing within that time.

**TABLE 10 Length Tolerances for Round, Straightened and Cut Wire, Exact-Length Resheared Wire**

Specified Diameter, in. (mm)	Length, ft (m)	Tolerance, in. (mm)	
		Over	Under
0.125 (3.18) and under	Up to 12 (3.7), incl	1/16 (1.6)	0
0.125 (3.18) and under	Over 12 (3.7)	1/8 (3.2)	0
Over 0.125 (3.18) to 0.500 (12.70), incl	Under 3 (0.9)	1/32 (0.8)	0
Over 0.125 (3.18) to 0.500 (12.70), incl	3 (0.9) to 12 (3.7), incl	1/16 (1.6)	0
Over 0.125 (3.18) to 0.500 (12.70), incl	Over 12 (3.7)	1/8 (3.2)	0

TABLE 11 Size Tolerances for Wire for Which the Final Operation is a Surface Treatment for the Purpose of Removing Scale or Drawing Lubricant

Specified Size, in. (mm)	Tolerance, in. (mm)	
	Over	Under
1/2 (12.7)	0.004 (0.10)	0.004 (0.10)
Under 1/2 (12.7) to 5/16 (7.9), incl	0.003 (0.08)	0.003 (0.08)
Under 5/16 (7.9) to 0.044 (1.12), incl	0.002 (0.05)	0.002 (0.05)
Under 0.044 (1.12) to 0.033 (0.84), incl	0.0013 (0.033)	0.0013 (0.033)
Under 0.033 (0.84) to 0.024 (0.61), incl	0.0008 (0.020)	0.0008 (0.020)

TABLE 12 Thickness Tolerances for Cold-Rolled Strip ^{A,B,C}

Specified Thickness, in. (mm)	Thickness Tolerances for Given Range of Width, Over and Under, in. (mm)							
	Width, in. (mm)							
	3/16 (4.8) incl, to 1 (25.4), excl	1 (25.4) incl, to 3 (76.2), excl	3 (76.2) incl, to 6 (152.4), incl	Over 6 (152.4) to 9 (228.6), incl	Over 9 (228.6) to 12 (304.8), incl	Over 12 (304.8) to 16 (406.4), incl	Over 16 (406.4) to 20 (508), incl	Over 20 (508) to 24 (610), excl
Under 3/16 (4.8) to 0.161 (4.09), incl	0.002 (0.05)	0.003 (0.076)	0.004 (0.10)	0.004 (0.10)	0.004 (0.10)	0.005 (0.13)	0.006 (0.15)	0.006 (0.15)
0.160 (4.06) to 0.100 (2.54), incl	0.002 (0.05)	0.002 (0.051)	0.003 (0.08)	0.004 (0.10)	0.004 (0.10)	0.004 (0.10)	0.005 (0.13)	0.005 (0.13)
0.099 (2.52) to 0.069 (1.75), incl	0.002 (0.05)	0.002 (0.051)	0.003 (0.08)	0.003 (0.08)	0.003 (0.08)	0.004 (0.10)	0.004 (0.10)	0.004 (0.10)
0.068 (1.73) to 0.050 (1.27), incl	0.002 (0.05)	0.002 (0.051)	0.003 (0.08)	0.003 (0.08)	0.003 (0.08)	0.003 (0.08)	0.004 (0.10)	0.004 (0.10)
0.049 (1.24) to 0.040 (1.02), incl	0.002 (0.05)	0.002 (0.051)	0.0025 (0.064)	0.003 (0.08)	0.003 (0.08)	0.003 (0.08)	0.004 (0.10)	0.004 (0.10)
0.039 (0.99) to 0.035 (0.89), incl	0.002 (0.05)	0.002 (0.051)	0.0025 (0.064)	0.003 (0.08)	0.003 (0.08)	0.003 (0.08)	0.003 (0.08)	0.003 (0.08)
0.034 (0.86) to 0.029 (0.74), incl	0.0015 (0.038)	0.0015 (0.038)	0.002 (0.05)	0.0025 (0.064)	0.0025 (0.064)	0.0025 (0.064)	0.003 (0.08)	0.003 (0.08)
0.028 (0.71) to 0.026 (0.66), incl	0.001 (0.025)	0.0015 (0.038)	0.0015 (0.038)	0.002 (0.05)	0.002 (0.05)	0.002 (0.05)	0.0025 (0.064)	0.003 (0.08)
0.025 (0.64) to 0.020 (0.51), incl	0.001 (0.025)	0.001 (0.025)	0.0015 (0.038)	0.002 (0.05)	0.002 (0.05)	0.002 (0.05)	0.0025 (0.064)	0.0025 (0.064)
0.019 (0.48) to 0.017 (0.43), incl	0.001 (0.025)	0.001 (0.025)	0.001 (0.025)	0.0015 (0.038)	0.0015 (0.038)	0.002 (0.05)	0.002 (0.05)	0.002 (0.05)
0.016 (0.41) to 0.013 (0.33), incl	0.001 (0.025)	0.001 (0.025)	0.001 (0.025)	0.0015 (0.038)	0.0015 (0.038)	0.0015 (0.038)	0.002 (0.05)	0.002 (0.05)
0.012 (0.30)	0.001 (0.025)	0.001 (0.025)	0.001 (0.025)	0.001 (0.025)	0.0015 (0.038)	0.0015 (0.038)	0.0015 (0.038)	0.0015 (0.038)
0.011 (0.28)	0.001 (0.025)	0.001 (0.025)	0.001 (0.025)	0.001 (0.025)	0.001 (0.025)	0.0015 (0.038)	0.0015 (0.038)	0.0015 (0.038)
0.010 (0.25)	0.001 (0.025)	0.001 (0.025)	0.001 (0.025)	0.001 (0.025)	0.001 (0.025)	0.001 (0.025)	0.0015 (0.038)	0.0015 (0.038)

^A For thicknesses under 0.010 in. (0.25 mm) to 0.005 in. (0.13 mm), incl, in widths up to and including 16 in. (406.4 mm), a tolerance of $\pm 10\%$ of the thickness applies. For thicknesses under 0.010 in. (0.25 mm) to 0.005 in. (0.13 mm), incl, in width over 16 in. (406.4 mm) to 24 in. (609.6 mm), excl, a tolerance of $\pm 15\%$ of the thickness applies.

^B Thickness measurements are taken at least 3/8 in. (9.5 mm) in from edge of the strip, except that on widths less than 1 in. (25.4 mm) the tolerances are applicable for measurements at all locations.

^C The above tolerances do not include crown tolerances.

TABLE 13 Crown Tolerances for Cold-Rolled Strip ^A

Specified Thickness, in. (mm)	Additional Thickness at Middle of Strip Over That Shown in Table 12 for Edge Measurement, for Given Range of Widths, in. (mm)		
	Width, in. (mm)		
	To 5 (127.0), incl	Over 5 (127.0) to 12 (304.8), incl	Over 12 (304.8) to 24 (609.6), excl
0.005 (0.13) to 0.010 (0.25), incl	0.00075 (0.0190)	0.001 (0.03)	0.0015 (0.038)
Over 0.010 (0.25) to 0.025 (0.64), incl	0.001 (0.03)	0.0015 (0.038)	0.002 (0.05)
Over 0.025 (0.64) to 0.065 (1.65), incl	0.0015 (0.038)	0.002 (0.05)	0.0025 (0.064)
Over 0.065 (1.65) to 3/16 (4.8), excl	0.002 (0.05)	0.0025 (0.064)	0.003 (0.08)

^A Cold-rolled strip may be thicker at the middle than at the edges by the amounts given in this table.

21. Certification

21.1 Upon request of the purchaser in the contract or order, a manufacturer's certification that the material was manufac-

tured and tested in accordance with the requirements of the specification for chemical analysis, mechanical properties, and

TABLE 14 Width Tolerances for Cold-Rolled Strip of Edge Numbers 1, 3, and 5

Edge Numbers 1 and 5				
Specified Edge Number	Specified Width, in. (mm)	Specified Thickness, in. (mm)	Width Tolerance, in. (mm)	
			Over	Under
1 and 5	9/32 (7.1) and under	1/16 (1.6) and under	0.005 (0.13)	0.005 (0.13)
1 and 5	Over 9/32 (7.1) to 3/4 (19.0), incl	3/32 (2.4) and under	0.005 (0.13)	0.005 (0.13)
1 and 5	Over 3/4 (19.0) to 5 (127.0), incl	1/8 (3.2) and under	0.005 (0.13)	0.005 (0.13)
5	Over 5 (127.0) to 9 (228.6), incl	1/8 (3.2) to 0.008 (0.20), incl	0.010 (0.25)	0.010 (0.25)
5	Over 9 (228.6) to 20 (508.0), incl	0.105 (2.67) to 0.015 (0.38)	0.010 (0.25)	0.010 (0.25)
5	Over 20 (508.0) to 24 (609.6), excl	0.080 (2.03) to 0.023 (0.58)	0.015 (0.38)	0.015 (0.38)

Edge Number 3						
Specified Thickness, in. (mm)	Width Tolerance for Given Range of Width, Over and Under, in. (mm)					
	Under 1/2 (12.7) to 3/16 (4.8), incl	1/2 (12.7) to 6 (152.4), incl	Over 6 (152.4) to 9 (228.6), incl	Over 9 (228.6) to 12 (304.8), incl	Over 12 (304.8) to 20 (508.0), incl	Over 20 (508.0) to 24 (609.6), excl
Under 3/16 (4.8) to 0.161 (4.09), incl	...	0.016 (0.41)	0.020 (0.51)	0.020 (0.51)	0.031 (0.79)	0.031 (0.79)
0.160 (4.06) to 0.100 (2.54), incl	0.010 (0.25)	0.010 (0.25)	0.016 (0.41)	0.016 (0.41)	0.020 (0.51)	0.020 (0.51)
0.099 (2.52) to 0.069 (1.75), incl	0.005 (0.13)	0.008 (0.20)	0.010 (0.25)	0.010 (0.25)	0.016 (0.41)	0.020 (0.51)
0.068 (1.73) and under	0.005 (0.13)	0.005 (0.13)	0.005 (0.13)	0.010 (0.25)	0.016 (0.41)	0.020 (0.51)

TABLE 15 Length and Camber Tolerances for Cold-Rolled Strip

Length Tolerances		
Specified Length, ft (m)	Tolerance over Specified Length, in. (mm)	
	Over	Under
To 5 (1.5), incl	3/8 (9.5)	0
Over 5 (1.5) to 10 (3.0), incl	1/2 (12.7)	0
Over 10 (3.0) to 20 (6.1), incl	5/8 (15.9)	0

Camber Tolerances ^A	
Specified Width, in. (mm)	Tolerance Per Unit Length of Any 8-ft (2.4-m) Length, in. (mm)
To 1 1/2 (38.1), incl	1/2 (12.7)
Over 1 1/2 (38.1) to 24 (609.6), excl	1/4 (6.4)

^ACamber is the deviation of a side edge from a straight line. To measure camber: place an 8-ft (2.438-m) straightedge on the concave side and measure the greatest distance between the strip edge and the straightedge.

expansion characteristics, together with a report of the test results, shall be furnished at the time of shipment.

22. Packaging and Package Marking

22.1 Packaging shall be subject to agreement between the manufacturer and the purchaser.

22.2 The material as furnished under this specification shall be identified by the name or symbol of the manufacturer and by melt number.

22.3 Protective coatings present on the material as shipped shall be readily removable by any of the common organic degreasing solvents, for example, trichloroethylene.

23. Keywords

23.1 glass-to-metal sealing; iron-chromium alloys; UNS K91800; UNS K92801

APPENDIX

(Nonmandatory Information)

X1. THERMAL EXPANSION

X1.1 **Table X1.1** presents typical thermal expansion data useful for curve plotting. It is included here for information-only and not as a basis of purchase.

TABLE X1.1 Typical Values of Linear Coefficient of Thermal Expansion

Temperature Range, °C	Mean Coefficient of Linear Thermal Expansion, µm/m·°C	
	UNS K91800	UNS K92801
30 to 200	9.9	10.0
30 to 300	10.9	10.3
30 to 400	11.2	10.6
30 to 500	11.5	10.9
30 to 600	11.5	11.2
30 to 700	...	11.6
30 to 800	...	11.6
30 to 900	...	12.8

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>