



Standard Specification for Chlorinated Poly (Vinyl Chloride) (CPVC) Pipe and Fittings for Chemical Waste Drainage Systems¹

This standard is issued under the fixed designation F2618; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the performance requirements of CPVC pipe, fittings and solvent cements used in chemical waste drainage systems.

1.2 A system is made up of pipe, fittings and solvent cement that meet the requirements of this standard.

NOTE 1—Consult the manufacturer's chemical resistance recommendations for chemical waste drainage applications prior to use.

1.3 The text of this specification references notes, footnotes and appendices that provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the specification.

1.4 The pressure tests described in this standard are laboratory hydrostatic tests that are intended to verify joint/system integrity. They are not intended for use as field tests of installed systems.

1.5 Due to inherent hazards associated with testing components and systems with compressed air or other compressed gases, no such testing shall be done unless the component manufacturer gives approval in writing.

NOTE 2—Pressurized (compressed) air or other compressed gases contain large amounts of stored energy, which present serious safety hazards should a system fail for any reason.

1.6 Mechanical joints used for joining pipe and fittings of different materials are provided for in this specification. They include common flanges, couplings, and unions.

1.7 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.8 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appro-*

priate safety and health practices and determine the applicability of regulatory limitations prior to use.

NOTE 3—This specification specifies dimensional, performance, and test requirements for fluid handling applications but does not address venting of combustion gases.

2. Referenced Documents

2.1 ASTM Standards:²

D543 Practices for Evaluating the Resistance of Plastics to Chemical Reagents

D618 Practice for Conditioning Plastics for Testing

D1600 Terminology for Abbreviated Terms Relating to Plastics

D1784 Specification for Rigid Poly(Vinyl Chloride) (PVC) Compounds and Chlorinated Poly(Vinyl Chloride) (CPVC) Compounds

D2122 Test Method for Determining Dimensions of Thermoplastic Pipe and Fittings

D2321 Practice for Underground Installation of Thermoplastic Pipe for Sewers and Other Gravity-Flow Applications

D2412 Test Method for Determination of External Loading Characteristics of Plastic Pipe by Parallel-Plate Loading

D2444 Test Method for Determination of the Impact Resistance of Thermoplastic Pipe and Fittings by Means of a Tup (Falling Weight)

D3311 Specification for Drain, Waste, and Vent (DWV) Plastic Fittings Patterns

F402 Practice for Safe Handling of Solvent Cements, Primers, and Cleaners Used for Joining Thermoplastic Pipe and Fittings

F412 Terminology Relating to Plastic Piping Systems

F493 Specification for Solvent Cements for Chlorinated Poly(Vinyl Chloride) (CPVC) Plastic Pipe and Fittings

F1498 Specification for Taper Pipe Threads 60° for Thermoplastic Pipe and Fittings

F2135 Specification for Molded Drain, Waste, and Vent (DWV) Short-Pattern Plastic Fittings

¹ This specification is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.63 on DWV.

Current edition approved Nov. 1, 2014. Published December 2014. Originally approved in 2009, last previous edition approved in 2009 as F2618-09. DOI: 10.1520/F2618-09R14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 Other Documents:

International Plumbing Code³

Uniform Plumbing Code⁴

Federal Standard 123 Marking for Shipment (Civilian Agencies)⁵

Federal Standard 129 Military Marking for Shipment and Storage⁵

3. Terminology

3.1 Definitions:

3.1.1 Definitions used in this specification are in accordance with the definitions given in Terminology **F412**, and abbreviations are in accordance with Terminology **D1600**, unless otherwise indicated.

3.1.2 The plumbing terminology used in this specification is in accordance with the definitions given in the International Plumbing Code and the Uniform Plumbing Code, unless otherwise indicated.

4. Requirements

4.1 The requirements in this section are intended only for use as quality control tests, not as simulated service tests.

4.1.1 All pipe and fittings shall be homogeneous throughout and be free of visible cracks, holes, foreign inclusions, or other injurious defects. The pipe and fittings shall be as uniform as commercially practicable in color, opacity, density and other physical properties.

4.1.2 Pipe and fittings shall be joined by the use of solvent cement, threading, or mechanical joints meeting the requirements of this standard and as recommended by the manufacturer.

4.1.3 All dimensions shall be determined in accordance with Test Method **D2122**.

4.1.4 All components within a system shall meet the specifications of this standard.

4.1.5 **CPVC Solvent Cement**—The CPVC solvent cement used to join the pipe and fittings covered under this specification shall comply with Section 5 and 9.4. Consult the pipe and fitting manufacturer to determine whether or not a primer is required.

NOTE 4—At lower temperatures (< 40°F, or < 4°C) and for larger diameters of pipe and fittings (>6 in. in diameter), a primer may be recommended by the manufacturer.

4.1.6 Mechanical fittings shall meet the requirements of 7.4.

4.2 Materials:

4.2.1 **CPVC Material**—All pipe and fittings shall be made CPVC compounds meeting or exceeding the requirements of cell classification 23447 as defined in Specification **D1784**.

4.2.2 CPVC materials shall be permitted to contain stabilizers, lubricants, and pigments not detrimental to pipe and

fittings provided that the final compound, and the pipe and fittings produced, meet the requirements of this specification.

4.2.3 **Rework Material**—Clean rework material generated from the manufacturer's own pipe or fittings may be used provided the pipe or fittings produced meet the requirements of this specification.

4.2.4 All thread sealants, gaskets, and seal rings shall be of a material that meets the chemical resistance for the end use application.

5. General Requirements for Solvent Cement

5.1 The solvent cement shall meet the general requirements of standard **F493** and be classified as heavy-bodied, having a minimum viscosity of 1600 cP (1600 MPa-s).

5.2 The cement shall not contain any inorganic fillers.

5.3 CPVC solvent cement meeting the requirements of this standard shall be mustard in color to facilitate identification and minimize unintentional use of other cements that may fail at elevated service temperatures.

NOTE 5—Safe handling of solvent cements: Solvent cements for plastic pipe are made from flammable liquids. Keep them away from all sources of ignition. Maintain proper ventilation to reduce fire hazard and to minimize breathing of solvent vapors. Avoid contact of cement with skin and eyes. Refer to Practice **F402** for information on safe handling of solvent cements.

6. Dimensions and Tolerances

6.1 The patterns, dimensions, and laying lengths of molded fittings, including adaptors, shall meet the requirements of Specifications **D3311** or **F2135** or shall be of a proven design and shall allow a smooth transition of flow from one direction to another. Specialty fittings or fittings with laying lengths not meeting the requirements of Specification **D3311** or Specification **F2135** shall not be excluded. For these fittings, laying lengths shall be provided by the manufacturer.⁶

NOTE 6—ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

6.1.1 The outside diameter and wall thickness of pipe shall meet the requirements of **Table 1** and **Table 2**.

6.1.2 Fitting sockets shall conform to the dimensional requirements as specified in **Table 3**.

6.1.3 The spigot dimensions of fittings shall meet the requirements of **Table 1** and **Table 2**.

6.2 **Cleanouts**—Cleanout plugs, and caps, as commonly used in the manufacturer's laboratory drainage system, shall have a thread size and depth sufficient to ensure that the minimum waterway dimensions are maintained. All CPVC cleanouts having female threads shall be supplied with CPVC plugs.

³ Available from International Code Council (ICC), 500 New Jersey Ave., NW, 6th Floor, Washington, DC 20001-2070, <http://www.iccsafe.org>.

⁴ Available from International Association of Plumbing and Mechanical Officials, 5001 E. Philadelphia St., Ontario, CA 91761, <http://www.iapmo.org>.

⁵ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://www.dodssp.daps.mil>.

⁶ Molded fittings meeting the requirements of Specification **D3311** made from CPVC and used for piping that handles corrosive waste are covered by a patent. Interested parties are invited to submit information regarding the identification of an alternative(s) to this patented item to the ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend.

TABLE 1 Outside Diameters and Tolerances for Pipe and Spigot Ends, in. (mm)

Nominal Pipe Size	Average Outside Diameter	Tolerance	Out-of-Roundness [maximum minus minimum]
1¼	1.660 (42.2)	± 0.005 (±0.13)	0.024 (0.61)
1½	1.900 (48.3)	± 0.006 (±0.15)	0.024 (0.61)
2	2.375 (60.3)	± 0.006 (±0.15)	0.024 (0.61)
3	3.500 (88.9)	± 0.008 (±0.20)	0.030 (0.76)
4	4.500 (114.3)	± 0.009 (±0.23)	0.100 (2.54)
6	6.625 (168.3)	± 0.011 (±0.28)	0.100 (2.54)
8	8.625 (219.1)	± 0.015 (±0.38)	0.150 (3.81)
10	10.750 (273.1)	± 0.015 (±0.38)	0.150 (3.81)
12	12.750 (323.9)	± 0.015 (±0.38)	0.150 (3.81)

TABLE 2 Wall Thickness and Tolerances for Pipe and Fitting Spigot Ends, in. (mm)

Nominal Pipe Size	Minimum	Tolerance
1¼	0.140 (3.56)	+0.020 (+0.51) – 0.000
1½	0.145 (3.68)	+0.020 (+0.51) – 0.000
2	0.154 (3.91)	+0.020 (+0.51) – 0.000
3	0.216 (5.49)	+0.026 (+0.66) – 0.000
4	0.237 (6.02)	+0.028 (+0.71) – 0.000
6	0.280 (7.11)	+0.034 (+0.86) – 0.000
8	0.322 (8.18)	+0.039 (+0.99) – 0.000
10	0.365 (9.27)	+0.044 (+1.12) – 0.000
12	0.406 (10.31)	+0.049 (+1.24) – 0.000

6.3 *Traps*—All traps shall have a minimum water seal of 2 in. (50 mm).

6.4 *Threaded fittings*—for all fittings having taper pipe threads, threads shall conform to standard **F1498**.

7. System Integrity

7.1 *Solvent Cemented Joint Hydrostatic Pressure Test*—Solvent cement joints shall not leak when tested in accordance with **8.4**.

7.2 *Solvent Cement Joint Chemical Resistance Integrity Test*: Solvent cemented joints shall not leak when tested in accordance with **8.3**.

7.3 *CPVC Pipe Flattening Test*: There shall be no evidence of splitting, cracking, or breaking when the pipe is tested in accordance with **8.8**.

7.4 *Impact Resistance*—The impact resistance testing shall be in accordance with **8.9**.

7.5 Mechanical Joints:

7.5.1 *Hydrostatic Pressure Test*—Mechanical joints shall not leak when tested in accordance with **8.5**.

7.5.2 *Mechanical Joint Separation Test*—Mechanical joints shall neither separate nor leak when tested in accordance with **8.6**.

7.6 *CPVC Compound Chemical Resistance*—CPVC compounds used to produce pipe or fittings to this standard shall meet the requirements of **8.2**.

NOTE 7—Before installing a CPVC chemical waste piping system, chemical resistance data for the piping in question should be evaluated. Caution should be taken when mixing chemicals as properties can change. If there is a chemical resistance question, consult the manufacturer(s).

8. Test Methods

8.1 Conditioning:

8.1.1 For routine quality control testing, condition the specimens at the room temperature and humidity of the manufacturers testing facilities for not less than one hour or until the specimens reach room temperature.

8.1.2 For referee purposes, condition and test the specimens before testing, in a standard laboratory atmosphere of $73.4 \pm 3.6^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$) and $50 \pm 5\%$ relative humidity for not less than 40 hours prior to testing in accordance with Procedure A of Practice **D618**.

8.2 *CPVC Compound Chemical Resistance*—Pipe and fitting materials shall be evaluated in accordance with Test Method **D543** practice A, procedures I and II, using the chemicals listed in **Table 4**. Weight change shall not exceed 2% nor shall apparent tensile strength change by more than 10 %. In cases where there is a change in the apparent tensile strength greater than 10%, a further evaluation shall be made after the test specimen is removed from the chemical and conditioned for 72 h. If after 72 h, there is a minimum of 50% recovery of tensile strength as compared to the unexposed specimen, and that figure is within $\pm 10\%$ of the original tensile strength of the unexposed specimen, the test shall be considered acceptable.

8.3 *Solvent Cement Joint Chemical Resistance Integrity Test*—Prepare ten pipe test specimens, each having two sections of pipe connected by a coupling using the manufacturer's specified solvent cement that is used to join the CPVC chemical waste drainage systems. The ten pipe test specimens shall be fitted with test caps on both ends with drain and vent connections to enable the specimens to be filled with chemicals and to subsequently be internally pressurized. Allow the materials to be conditioned at $73.4 \pm 3.6^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$) for 24 h after the joints are completed. After the 24 h conditioning period, completely fill each of the ten specimens with the chemicals listed in **Table 4**. One chemical at the specified concentrations within **Table 4** shall be used per test specimen, making sure that the chemical media completely fills the specimen prior to being capped off. The specimens shall be pre-labeled to identify with which of the chemicals it is filled. Expose each of the ten specimens to the chemicals for one week at $73.4 \pm 3.6^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$) under an internal test pressure of 5 psig (34.5 kPa). After the holding period, remove the specimens and drain the chemical reagents. The specimens shall be rinsed and dried to remove any traces of the chemicals from the inside of the pipe. Each specimen shall then be subjected to a hydrostatic test pressure of a minimum of 50 psig (345 kPa) at $73.4 \pm 3.6^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$) for a minimum duration of 5 min. The pressure test must be completed within 24 h after the specimens have been drained and cleaned.

8.4 *Solvent Cemented Joint Hydrostatic Pressure Test*—Select at random six specimens of pipe, each five times the nominal diameter or a maximum of 18 in. (450 mm) in length, for each size of piping and each type of system being

TABLE 3 Dimensions and Tolerances for Fitting Sockets, in. (mm)

Nominal Pipe	A			B			C	E	Internal Threads	
	Socket Entrance Diameter			Socket Bottom Diameter			Socket Depth min	Wall thickness min ^A	Outside Diameter of Hub, M min	Thread length min
	Average	Tolerance on Avg in. (mm)	Out -of- Roundness	Average	Tolerance on Avg in. (mm)	Out -of- Roundness				
1 ¼	1.675 (42.54)	+0.010/-0.005 (+0.25/-0.13)	0.024 (0.61)	1.655 (42.04)	± 0.005 (± 0.13)	0.024 (0.61)	0.687 (17.44)	0.156 (3.96)	1.871 (47.52)	0.687 (17.44)
1 ½	1.915 (48.64)	+0.010/-0.005 (+0.25/-0.13)	0.024 (0.61)	1.894 (48.11)	± 0.006 (± 0.15)	0.024 (0.61)	0.687 (17.44)	0.156 (3.96)	2.127 (54.03)	0.687 (17.44)
2	2.390 (60.71)	+0.010/-0.005 (+0.25/-0.13)	0.024 (0.61)	2.369 (60.17)	± 0.006 (± 0.15)	0.024 (0.61)	0.750 (19.05)	0.156 (3.96)	2.634 (66.90)	0.750 (19.05)
3	3.520 (89.41)	+0.010/-0.005 (+0.25/-0.13)	0.030 (0.76)	3.492 (88.70)	± 0.008 (± 0.20)	0.030 (0.76)	1.500 (38.10)	0.219 (5.56)	3.841 (97.56)	1.187 (30.15)
4	4.520 (114.8)	+0.010/-0.005 (+0.25/-0.13)	0.030 (0.76)	4.491 (114.1)	± 0.009 (± 0.23)	0.030 (0.76)	1.750 (44.45)	0.250 (6.35)	4.907 (124.6)	1.281 (32.54)
6	6.647 (168.8)	+0.015/-0.010 (+0.38/-0.25)	0.060 (1.52)	6.614 (168.0)	± 0.011 (± 0.28)	0.060 (1.52)	3.000 (76.20)	0.281 (7.14)	7.203 (183.0)	1.500 (38.10)
8	8.655 (219.8)	+0.030/-0.000 (+0.76/-0.00)	0.090 (2.29)	8.610 (218.7)	+0.015/-0.015 (+0.38/-0.38)	0.090 (2.29)	4.000 (101.6)	0.328 (8.33)	^B	^B
10	10.780 (273.8)	+0.025/-0.020 (+0.64/-0.51)	0.120 (3.05)	10.737 (272.7)	± 0.015 (± 0.38)	0.120 (3.04)	5.000 (127.0)	0.365 (9.28)	^B	^B
12	12.780 (324.6)	+0.030/-0.025 (+0.76/-0.64)	0.150 (3.81)	12.736 (323.5)	± 0.015 (± 0.38)	0.150 (3.81)	6.000 (152.4)	0.406 (10.30)	^B	^B

^A The thickness is a minimum value except that a ±10% variation resulting from core shift is allowable. In such case, the average of the two opposite wall thickness shall equal or exceed the value shown in the table.

^B Not applicable for these nominal sizes.

TABLE 4 Chemical List

Chemical Environment	72°F (23°C)	180°F (82°C)
Acetic Acid	100% by volume	50% by volume
Acetone	30% by volume	20% by volume
Methyl Alcohol	100% by volume	50% by volume
Ammonium Hydroxide	15% NH ₃ by weight	Do Not Test
Nitric Acid	70% by weight	30% by weight
Sodium Hydroxide	60% by weight	30% by weight
Sulfuric Acid	98% by weight	85% by weight
Hydrochloric Acid	36% by weight	36% by weight
Hydrogen Peroxide	50% by weight	50% by weight
Sodium Hypochlorite	15% by weight	^A

^A Sodium Hypochlorite is unstable at elevated temperatures.

considered. Also select three suitable couplings at random. Prepare three joined specimens by joining two pipe specimens with one coupling, using the solvent cement, instructions and cure time supplied by the manufacturer of the system. Fill each specimen with water at 73.4°F ± 3.6°F (23°C ± 2°C) and cap, taking care to exclude all air from the system. Fix one end of the specimen to a pressurizing apparatus, and support the free end if necessary. Pressurize each specimen to 50 psi (345 kPa) for a minimum of 5 min and inspect for leaks (laboratory performance test only, not for field use).

8.5 Mechanical Joint Hydrostatic Pressure Test— Perform the pressure test on specimens of mechanical joints in a similar manner to that described in 8.4 using appropriate pipe specimens that are intended to join pipes of similar or dissimilar materials and sizes. Pressurize the assembly to 14.5 psi (100 kPa) for a period of 24 h and inspect for signs of leakage. None of the test specimens shall leak. Apply this test to each size and

type of joint being considered (laboratory performance test only, not for field use).

8.6 Mechanical Joint Separation Test— Using a suitable set-up, apply a minimum of 50 lbf (220 N) of force to a complete mechanical joint assembled in accordance with the manufactures procedures. Apply the force within 5 to- 30 s for a period of 60 s. Remove the force from the test sample and perform a hydrostatic pressure test at 14.5 psi (100 kPa) for a period of 1 h. and inspect for leaks.

8.7 Threads—All taper pipe threads shall be gauged in accordance with Specification **F1498**.

8.8 Flattening—Using Test Method **D2412**, flatten three specimens of pipe 6-in. (152 mm) long, between parallel plates in a suitable press until the distance between the plates is 40% of the original outside diameter of the pipe. The rate of vertical displacement shall be uniform and such that the flattening is completed within 2 to 5 min. On removal of the load, examine the specimens for evidence of splitting, cracking, or breaking.

8.9 Impact Resistance for CPVC pipe and fittings—Determine and test CPVC pipe and fitting impact values in accordance with test method **D2444** using Tup B and the flat plate Holder B. Test fittings with Tup A and Holder B. The level of impact shall be in accordance with data provided by the manufacturer, which shall show impact values for each size at 73°F (23°C) that specifies adequate quality consistent with the CPVC compound used by that manufacturer. Test 10 specimens. When 9 or 10 specimens pass, accept the lot. When 4 or more fail, reject the lot. When 2 or 3 of 10 fail, test 10 additional specimens. When 17 of 20 specimens tested pass, accept the lot. When 7 or more of 20 fail, reject the lot. When

4, 5 or 6 of 20 fail, test 20 additional specimens. When 32 of 40 specimens pass, accept the lot. When 9 or more of 40 specimens fail, reject the lot. Failure in the test specimens shall be shattering or any crack or break extending entirely through the pipe wall visible to the unaided eye.

8.9.1 This test is intended only for use as a quality control test, not as a simulated service test.

8.10 *Retest and Rejection*—If the results of any test(s) do not meet the requirements of this specification, the test(s) may be conducted again in accordance with an agreement between the purchaser and the seller. There shall be no agreement to lower the minimum requirement of the specification by such means as omitting tests that are a part of the specification, substituting or modifying a test method, or by changing the specification limits. In retesting, the product requirements of this specification shall be followed. If upon retest, failure occurs, the quantity of product represented by the test(s) does not meet the requirement of this specification.

9. Product Marking

9.1 *Quality and Content of Marking*—The markings shall be applied to the fittings and pipe in such a manner that they remain legible under normal handling and installation practices.

9.2 *Fittings*—All fittings shall be light grey in color and have the following permanent and legible markings visible on the body or hub:

9.2.1 Manufacturer's name or trademark;

9.2.2 Material designation of "CPVC-CW (chemical waste)."

9.2.3 If listed, the seal or mark of the laboratory making the evaluation for corrosive waste application.

9.2.4 Nominal size (for example, 2 in.)

9.3 *Pipe*—Pipe shall be marked as follows:

9.3.1 All piping shall have the following permanent and legible markings, spaced at intervals of not more than 5 ft (1.5 m), and in lettering not less than 3/16 in. (5mm) high.

9.3.1.1 Manufacturer's name or trademark

9.3.1.2 Material designation of "CPVC-CW (chemical waste)"

9.3.1.3 If listed, the seal or mark of the laboratory making the evaluation for corrosive waste application

9.3.1.4 Nominal pipe size (for example, 2 in.)

9.3.1.5 This ASTM standard designation (F2618)

9.3.1.6 Pipe shall be light gray in color with EITHER a yellow stripe OR marked with a yellow print line and a continuous "chemical waste drainage" print line that is 180° removed.

9.4 Solvent Cement--Marking on the solvent cement container label shall include the following:

9.4.1 Manufacturer or seller's name, address, and trademark,

9.4.2 ASTM designation of **F493** and this standard F2618,

9.4.3 Label shall state "For use in CPVC-CW waste systems only,"

9.4.4 Instructions for use,

9.4.5 If listed, the seal or mark of the laboratory making the evaluation, and

9.4.6 Identification of the lot number (on the label or on the can).

10. Quality Assurance

10.1 When the product is marked with this designation, F2618, the manufacturer affirms that the product was manufactured, inspected, sampled, and tested in accordance with this specification and has been found to meet the requirements of this specification.

11. Keywords

11.1 chemical waste; chemical resistance; drainage; drain pipes; installation; joints; laboratory piped services; pipe fittings; pipes; plastic pipes; chlorinated polyvinyl chloride; thermoplastic polymers; traps (drainage); waste disposal (building)

SUPPLEMENTARY REQUIREMENTS

GOVERNMENT/MILITARY PROCUREMENT

The requirements apply only to Federal/Military Procurement, not domestic sales or transfers.

S1. Responsibility for Inspection

Unless otherwise specified in the contract or purchase order, the producer is responsible for all inspection and test requirements specified herein. The producer may use his own or any other suitable facilities for the performance of the inspection and test requirements specified herein, unless the purchaser disapproves. The purchaser shall have the right to perform any of the inspections and tests set forth in this specification where such inspections are deemed necessary to ensure that material conforms to prescribed requirements.

NOTE S1.1—In U.S. Federal contracts, the contractor is responsible for inspection.

S2. Packaging and marking for U.S. Government Procurement

S2.1 *Packaging*—Unless otherwise specified in the contract, the materials shall be packaged in accordance with the supplier's standard practice in a manner ensuring arrival at the destination in satisfactory condition and which will be acceptable to the carrier at lowest rates. Containers and packing shall comply with Uniform Freight Classification rules or National Motor Freight Classification rules.

S2.2 *Marking*—Marking for shipment shall be in accordance with Fed. Std. No. 123 for civil agencies and MIL-STD-129 for military agencies.

NOTE S2.1— The inclusion of the U.S. Government procurement requirements shall not be construed as an indication that the U.S.

Government uses or endorses the products described in this specification.

ANNEXES

(Mandatory Information)

A1. INSTRUCTIONS

A1.1 The manufacturers of the pipe and fittings shall ensure that instructions needed for properly joining the pipe and fittings are readily obtainable. Consult with each product manufacturer for specific recommendations and installation instructions.

A1.2 CPVC chemical waste drainage systems shall be installed and supported in accordance with the manufacturer's recommendations.

A1.3 Installers shall follow Practice **F402** for the safe handling of solvent cements and primers used in the installation of the system.

A2. JOINING

A2.1 *Field Inspection*—Prior to use, all pipes shall be carefully inspected for cuts, gouges, deep scratches, damaged ends, or other major imperfections. Defective pipe shall be rejected or the damaged sections shall be cut out.

A2.2 Follow the recommended procedures for making solvent-cemented joints with chlorinated poly (vinyl) chloride (CPVC) pipe and fittings as listed in Specification **F493**.

A2.3 *Visibility of Marking*—Always position pipe so that identifying markings are readily visible to inspection when installed. Due to the nature of the solvent cementing procedure, the markings on fittings may become obscured. Validation of the fittings shall be done in a suitable manner.

A2.4 *Threaded Connection*—Do not cut threads on CPVC chemical waste drainage system pipe. Molded threads are permitted. Use of adapter fittings for transition to threaded

construction is necessary except in the case of cleanout plugs. The joint between the CPVC pipe and transition fitting shall be of the solvent cement type. Only thread tape or thread lubricants, specifically recommended by the manufacturer and intended for use with the CPVC chemical waste drainage system piping shall be used.

A2.4.1 Where a thread joint is made, obtain tightness by engaging the threads one to two turns beyond finger tight.

A2.5 *Connections to Traps*—Connect traps by means of threaded trap adapters.

A2.6 *Connection to Non-plastic Pipe*—When connecting plastic pipe to other types of piping, use only types of fittings and adapters designed and recommended for the specific transition intended. Do not roll groove the system piping.

APPENDIXES**(Nonmandatory Information)****X1. STORAGE**

X1.1 Plastic pipe shall be stored on a flat surface or supported in a manner that will prevent sagging or bending. Do not store pipe in direct sunlight.

X1.2 Inventories of plastic pipe and solvent cement shall be used on a first-in, first-out (FIFO) basis.

X1.3 Solvent cements have a shelf life and shall not be used beyond their expiration date.

X2. GENERAL INSTALLATION

X2.1 *Underground Installation*—Underground installations of pipe shall be in accordance with practice **D2321**.

X2.2 Chemical waste drainage pipe shall be installed in conformance with governing building codes. In areas not governed by codes, pipe shall be installed in accordance with accepted engineering practices.

X2.3 *Installation Under Freezing Conditions*—Plastic pipe has decreased resistance to impact under freezing conditions. Increased care shall be exercised if installation is likely to occur under these conditions, particularly during handling, transportation, installation, and backfilling. When possible, installation shall be avoided during freezing conditions. Allowance shall be made for expansion that will occur when the temperature of the pipe is raised.

X2.4 *Alignment and Grade*—Align all piping system components properly without strain. Do not bend or pull pipe into position after being solvent welded. Grade of horizontal drainage and vent piping shall be as specified for other materials in the applicable code.

X2.5 *Supports and Spacing*—Hangers and straps shall not compress, distort, cut, or abrade the piping and shall allow free movement of pipe. Support horizontal piping in accordance with the manufacturer's recommendations. Supports shall allow free movement. Maintain vertical piping in straight alignment with supports at each floor level or at 10-ft (3.1-m) intervals, whichever is less.

X2.6 *Building Drains Under Floor Slabs*—Make trench bottoms smooth and of uniform grade with either undisturbed soil or a layer of selected and compacted backfill so that no settlement will be encountered. Pipe must bear on this material throughout the entire length of its barrel.

X2.7 *Thermal Expansion*—Allow for thermal expansion and movement in all piping installations by the use of approved methods. Support but do not rigidly restrain piping at branches or changes of direction. Do not anchor pipe rigidly in walls. Holes through framing members shall be adequately sized to allow for free movement.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>