



# Standard Test Method for Compressibility and Recovery of Laminated Composite Gasket Materials<sup>1</sup>

This standard is issued under the fixed designation F806; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers determination of the short-time compressibility and recovery at room temperature of laminated composite gasket materials.

1.2 This test method is not intended as a test for compressibility under prolonged stress application, that is “creep,” or for recovery following such prolonged stress application, the inverse of which is generally referred to as “compression set.” Also, it is only intended for tests at room temperature.

1.3 The values stated in SI units are to be regarded as the standard. The inch-pound units given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**F104** Classification System for Nonmetallic Gasket Materials

2.2 *ASTM Adjuncts:*

Testing Machine Drawings<sup>3</sup>

## 3. Significance and Use

3.1 This test method is designed to compare related laminated composite gasket materials under controlled conditions and their short-time compressibility and recovery at room temperature. It measures compressibility with a matched pair

of opposing upper and lower penetrators which provide better precision and bias than methods using an upper penetrator and a lower anvil. It is difficult to prepare undistorted test specimens from laminated composite gasket materials which will lay flat on an anvil. Also, with many composites having rigid inner layers the load on the upper penetrator is distributed over the bottom anvil area resulting in a lower than actual compressibility reading. This test method may be used as a routine test method when agreed upon between the purchaser and the producer.

## 4. Apparatus

4.1 The testing machine<sup>4</sup> shall consist of the following components.

4.1.1 *Penetrators*—A matched pair of opposing steel cylinders (within  $\pm 0.025$  mm (0.001 in.)) specified for the type of material being tested, with the cylinder ends hardened and ground. Penetrator diameters for various types of laminated composite gasket materials are shown in **Table 1**.

4.1.2 *Dial*—An indicating dial, or dials, graduated in 0.025 mm (0.001 in.) to show the thickness of the specimen during the test. Readings shall be estimated to the nearest 0.0025 mm (0.0001 in.).

4.1.3 *Preload*, shall include the weight of the penetrator itself and added weights to give the value specified within  $\pm 1$  %. A 22.2-N (5-lbf) preload shall be used.

4.1.4 *Loading Device*—A device for applying a specified major load to the upper end of the penetrator, which may consist of an arrangement of dead weights, a hydraulic cylinder, an air cylinder, or any other device capable of applying the major load at a slow uniform rate and to an accuracy of  $\pm 1$  %. The major load shall be in addition to the specified preload. Major loads for various types of laminated composite gasket materials are shown in **Table 1**.

## 5. Test Specimen

5.1 The test specimen may be either circular or rectangular in shape. The minimum size shall be 12.7 mm (0.5 in.) larger than the penetrator diameter being used, and the maximum size

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee F03 on Gaskets and is the direct responsibility of Subcommittee F03.20 on Mechanical Test Methods.

Current edition approved Oct. 1, 2009. Published March 2010. Originally approved in 1983. Last previous edition approved in 2003 as F806 – 99a (2003) <sup>$\epsilon$ 1</sup>. DOI: 10.1520/F0806-99AR09.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from ASTM International Headquarters. Order Adjunct No. **ADJF0806**. Original adjunct produced in 1983.

<sup>4</sup> A list of recommended suppliers, by Subcommittee F03.20, is available through ASTM.

**TABLE 1 Conditioning and Test Loads for Laminated Composite Gasket Materials**

NOTE 1—If the nonmetallic layers of the laminated composite are not all the same material, then the test loads may be as agreed upon between the producer and user.

| Procedure | Type of Gasket Material in the Nonmetallic Layers                   | F104<br>Identification <sup>A</sup><br>First Two<br>Numerals of Six-<br>Digit Number | Conditioning Procedure                                                                                                                                           | Penetrator<br>Diameter, mm (in.) | Preload,<br>N (lbf) | Major Load,<br>N (lbf) | Total Load (sum of Major Load and Preload) |             |
|-----------|---------------------------------------------------------------------|--------------------------------------------------------------------------------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------|----------------------------------|---------------------|------------------------|--------------------------------------------|-------------|
|           |                                                                     |                                                                                      |                                                                                                                                                                  |                                  |                     |                        | N (lbf)                                    | MPa (psi)   |
| A         | compressed asbestos sheet; asbestos beater sheet; flexible graphite | F11, F12, F51, F52                                                                   | 1 h at 100 ± 2°C (212 ± 3.6°F); cool in desiccator over anhydrous calcium chloride 21 to 30°C (70 to 85°F)                                                       | 6.4 (0.252)                      | 22.2 (5)            | 1090 (245)             | 1112 (250)                                 | 34.5 (5000) |
| H         | asbestos paper and millboard                                        | F13                                                                                  | 4 h at 100 ± 2°C (212 ± 3.6°F); cool as in Procedure A                                                                                                           | 6.4 (0.252)                      | 22.2 (5)            | 1090 (245)             | 1112 (250)                                 | 34.5 (5000) |
| F         | cork composition, cork and cellular rubber                          | F21, F23                                                                             | At least 46 h at 21 to 30°C (70 to 85°F) and 50 to 55 % relative humidity                                                                                        | 28.7 (1.129)                     | 22.2 (5)            | 423 (95)               | 445 (100)                                  | 0.69 (100)  |
| B         | cork and rubber                                                     | F22                                                                                  | At least 46 h at 21 to 30°C (70 to 85°F) and 50 to 55 % relative humidity                                                                                        | 12.8 (0.504)                     | 22.2 (5)            | 334 (75)               | 356 (80)                                   | 2.76 (400)  |
| G         | treated and untreated papers from cellulose or other organic fibers | F31, F32, F33, F34                                                                   | 4 h at 21 to 30°C (70 to 85°F) over anhydrous calcium chloride followed immediately by at least 20 h at 21 to 30°C (70 to 85°F) and 50 to 55 % relative humidity | 6.4 (0.252)                      | 22.2 (5)            | 1090 (245)             | 1112 (250)                                 | 34.5 (5000) |
| J         | compressed nonasbestos sheet; nonasbestos beater sheet              | F71, F72                                                                             | 1 h at 100 ± 2°C (212 ± 3.6°F); cool in desiccator over anhydrous calcium chloride 21 to 30°C (70 to 85°F)                                                       | 6.4 (0.252)                      | 22.2 (5)            | 1090 (245)             | 1112 (250)                                 | 34.5 (5000) |
| K         | nonasbestos paper and millboard                                     | F73                                                                                  | 4 h at 100 ± 2°C (212 ± 3.6°F); cool as in Procedure A                                                                                                           | 6.4 (0.252)                      | 22.2 (5)            | 1090 (245)             | 1112 (250)                                 | 34.5 (5000) |

<sup>A</sup> Refers to Classification F104.

shall be 38.1 mm (1.5 in.) larger than it. The thickness shall be that of the laminated composite gasket. Take care that the specimen is flat, especially around the planned contact point of the opposing penetrators.

## 6. Conditioning

6.1 When all nonmetallic layers of the laminated composite are the same type, condition in accordance with that type as shown in Table 1.

6.2 When the nonmetallic layers of the laminated composite are of different types, the specimen shall be conditioned for 22 h in a controlled-humidity room or in a closed chamber of air at 21 to 30°C (70 to 85°F) and 50 to 55 % relative humidity. In all cases where testing is conducted outside the area of specified humidity, specimens shall be removed from the chamber one at a time as needed.

6.3 Other conditioning may be as agreed upon between the producer and the user.

## 7. Temperature of Test

7.1 The test shall be conducted with both the specimen and the apparatus at a temperature of 21 to 30°C (70 to 85°F).

## 8. Procedure

8.1 Determine the amount of deflection of the penetrator at each of the loads used in the test with no specimens present. Add the absolute value of this penetrator deflection to the thickness under total load  $M$  in 10.1 to obtain a corrected reading. The values are machine constants which may vary for different instrument designs.

8.2 Center the test specimen upon the bottom penetrator, and apply the preload, guiding the top penetrator in its descent so that it remains parallel to the surface of the bottom penetrator. Maintain for a period of 15 s, and record the preloaded thickness of the specimen. Immediately apply the major load in a slow uniform manner so that the total load is attained within 10 s. Maintain the total load for 60 s, and record the thickness of the specimen. Immediately remove the major load, and after a period of 60 s, record the thickness of the specimen under the original preload. This is the recovered thickness.

## 9. Number of Tests

9.1 A minimum of three tests shall be run on separate specimens taken from the same sample and the results averaged.

## 10. Calculation

10.1 Calculate the compressibility,  $C$ , and recovery,  $D$ , in percent as follows:

$$C = (P - M)/P \times 100$$

$$D = (R - M)/(P - M) \times 100$$

where:

$P$  = thickness under preload, mm (in.),  
 $M$  = thickness under total load, mm (in.), and  
 $R$  = recovered thickness, mm (in.).

10.2 When desired, the resiliency shall be calculated as follows:

$$\text{Resiliency, \%} = [(R - M)/M] \times 100$$

## 11. Precision and Bias<sup>5</sup>

11.1 This precision data is based on tests of four different material samples by six laboratories in 2 days. The compressibility of the samples studied ranged from 3 to 16 %. Precision is expressed in absolute terms, in this case, percent compressibility points.

---

<sup>5</sup> Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:F03-1013.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).*

11.2 *Repeatability*—The repeatability has been estimated to be  $\pm 0.71$  %. Two test results do not differ significantly unless their difference exceeds 1.0 %.

11.3 *Reproducibility*—The reproducibility has been estimated to be  $\pm 2.1$  %. Two test results do not differ significantly unless their difference exceeds 2.9 %.

## 12. Keywords

12.1 compressibility; gasket material composites; gasket material laminates; recovery; resiliency