



Standard Practice for Characterization of Atmospheric Test Sites¹

This standard is issued under the fixed designation G92; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice gives suggested procedures for the characterization of atmospheric test sites. Continuous characterization can provide corrosion data, environmental data, or both which will signal changes in corrosivity of the atmospheric environment. This practice can also provide guidance for classification of future test sites.

1.2 Two methods are defined in this practice for the characterization of atmospheric test sites. The methods are identified as characterization Methods A and B. The preferred characterization technique would require using both Method A and B for concurrent data collection.

1.2.1 Method A is to be used when atmospheric corrosion is monitored on a continuing basis at a test site using specified materials and exposure configurations.

1.2.2 Method B is specified when atmospheric factors are monitored on a continuing basis.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

A36/A36M Specification for Carbon Structural Steel

B6 Specification for Zinc

G1 Practice for Preparing, Cleaning, and Evaluating Corrosion Test Specimens

G50 Practice for Conducting Atmospheric Corrosion Tests on Metals

¹ This practice is under the jurisdiction of ASTM Committee G01 on Corrosion of Metals and is the direct responsibility of Subcommittee G01.04 on Atmospheric Corrosion.

Current edition approved Sept. 1, 2010. Published May 2011. Last previous edition approved in 2003 as G92–86(2003). DOI: 10.1520/G0092-86R10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

G84 Practice for Measurement of Time-of-Wetness on Surfaces Exposed to Wetting Conditions as in Atmospheric Corrosion Testing

G91 Practice for Monitoring Atmospheric SO₂ Deposition Rate for Atmospheric Corrosivity Evaluation

3. Summary of Methods

3.1 Characterization Method A is to be used when atmospheric corrosion data are to be obtained.

3.1.1 Corrosion tests to measure the corrosivity of the test site should follow the procedure established by Practice G50. Additional special instructions are identified in this procedure relating to types of materials for corrosion characterization tests, time of test exposure, positioning of test specimens, removal of test specimens and proper identification, cleaning practices, and reporting of data.

3.2 Characterization Method B is to be used when atmospheric climatological factors influencing the corrosion of metals are to be monitored.

3.2.1 Several atmospheric factors which have been identified as having significant bearing on the corrosion of metals include, but are not limited to, sulfur dioxide, chlorides, temperature, humidity, precipitation, time of wetness, and atmospheric particulate matter.

3.3 The preferred technique utilizes both Methods A and B for concurrent data to be collected.

3.3.1 Should either Method A or B be singled out as the primary technique to be used on a continuing basis, both should be used at some point in time to establish a data base. The availability of computerized weather stations greatly facilitates the collection of reliable atmospheric data.

4. Significance and Use

4.1 This practice gives suggested procedures for characterization of atmospheric test sites. It can be useful to researchers, manufacturers, engineering firms, architects, and construction contractors to provide corrosion and environmental data, materials selection information, and a materials storage practice.

4.2 This practice does not give specific parameters for classifying the type of test site.

PROCEDURES

5. Method A

5.1 Materials:

5.1.1 The materials recommended for conducting atmospheric corrosion characterization studies are copper-bearing structural carbon steel (such as Specification **A36/A36M** with 0.2 % copper min) and high-purity zinc (Specification **B6** high grade).

5.1.2 Materials recommended are the absolute minimum required to serve as a characterization base for test sites. Additional materials should be added to meet individual needs. Sufficient material should be obtained at the start to insure that an ample supply of the same heat is available to complete the characterization test. If tests are on-going and additional materials must be obtained, care should be taken in attempting to match material compositions.

5.1.3 Sufficient specimens should be prepared to comply with the specific criteria for the planned characterization test.

5.2 Material Preparation:

5.2.1 Test specimens should be sheared to size, for example, 100 × 150 mm.

5.2.2 An identifying code should be assigned to each specimen. Locating a permanent code on each test specimen can be accomplished easily by using a code template (**Fig. 1**).


5.2.2.1 Pre-assignment of codes for a definite test period is suggested. After a temporary mark is placed on the specimen, a permanent drilled code (a series of 2.5 mm holes) should perforate the test specimen.

5.2.3 All test specimens of the same alloy should be cleaned by the same procedure to ensure a comparative surface finish following the guidance of Practice **G1**. The recommended practice suggested for cleaning is (a) degrease and pickle, if necessary, to remove grease, mill scale, or other impurities; (b) scrub with pumice and brittle brush until free of water-break; (c) dry with towels; and (d) place in a desiccator for 2 h before weighing.

5.2.4 Specimens should be weighed (± 1.0 mg) and original mass recorded on a data sheet (**Table 1**). Specific information, such as nominal composition, density, and exposed area should also be recorded.

5.2.5 Specimens should be stored in a desiccator or sealed in airtight storage bags until the time of exposure.

5.3 Exposure of Test Specimens:



* Template contains 126 drilled holes

FIG. 1 Sample Atmospheric Specimen Drill Code Identification Template

TABLE 1 Sample Data Sheet for Atmospheric Corrosion Data

		Test Site: Kure Beach (250 m lot)		Latitude: 34° 00' N			
		Exposure Dates: 10/7/61 to 10/6/62		Longitude: 77° 55' W			
Material	Code	Exposure Period (days)	Mass (g)			Mass Loss Per Unit Area (mg/m²)	Corrosion Rate (mm/y)
			Original	Final	Loss		
Cu-steel	A1-B2	365	196.583	187.332	9.251	2.86×10^5	0.0365
Zinc	A2-B2	365	67.521	66.938	0.583	1.84×10^4	0.0026
Test Method Documentation							
		Steel			Zinc		
1. Composition (weight %)		0.15 C, 1.0 Mn, 0.01 P, 0.027 S, 0.24 Si, 0.21 Cu, 0.05 Ni, 0.03 Cr, Balance Fe			0.01 Cu, 0.012 Cd, 0.03 Pb, 0.02 Fe, Balance Zn		
2. Density (g/cm³)		7.85 g/cm³			7.13 g/cm³		
3. Dimensions (mm)		100 × 150 × 2.00 mm			100 × 150 × 2.00 mm		
4. Exposed area (cm²)		322.9 cm²			317.7 cm²		

TABLE 2 Sample Data Sheet for Atmospheric Climatological Data

Test Site: Kure Beach (250 m lot)				Latitude: 34° 00' N					
Dates: 5/1/83 to 5/3/83				Longitude: 77° 55' W					
Date	Temperature (°C)			Relative Humidity (%)			Precipitation (mm)	Time of Wetness (h/day)	
	High	Low	Mean	High	Low	Mean		Skyward	Groundward
5/1/83	25.6	12.8	19.2	100	56	82	0	12	13
5/2/83	26.1	16.7	21.4	97	56	82	0	10	13
5/3/83	26.7	17.8	22.2	100	60	85	1.3	12	14

5.3.1 The frequency at which test specimens should be exposed at a test site is dictated by the specific needs for data.

5.3.2 Triplicate specimens of each material should be exposed for each test period.

5.3.3 An exposure period of one year is suggested as a minimum, multiple periods should be considered, for example, 3, 6, and 12 months; 1 and 2 years or 1, 2, and 4 years. Shorter test periods may be necessary where corrosion is severe and longer test periods where corrosion is less severe.

5.3.3.1 Consideration should also be given to use of test periods which could allow definition of changes in environment corrosivity occurring during an overall longer term evaluation period. For example, exposure of specimens on the schedule, 0–3, 3–6, 6–9, 9–12, 0–6, 6–12, and 0–12 months, would allow some assessment of relative changes in corrosivity at a test site during a one year period. While this is a relatively extensive exposure frequency, it may prove useful in some instances.

5.3.4 A standard atmospheric exposure test rack (see Practice G50), or other appropriate devices, should be positioned at 30° to the horizontal facing south in accordance with Practice G50. The test specimens should be mounted with porcelain insulators or other appropriate insulating materials.

5.3.5 All test specimens should be positioned at approximately the same elevation on the test rack.

5.3.6 It is suggested that the general weather conditions be documented at the time the specimens are exposed, for example, clear, cloudy, or rain.³

5.3.6.1 Initial weather conditions at time of exposure of test specimens may have an effect on long term corrosion behavior (1).⁴

5.4 Removals and Reporting:

5.4.1 After the predetermined exposure period is completed (for example, one year), the specimens should be removed and placed in pre-labeled envelopes. Observations or photographs needed to document appearance can be made at this time or after the specimens reach the laboratory or other process area. Wet specimens should be carefully dried if extended storage (more than 24 h) is anticipated before cleaning.

5.4.2 The test specimens being removed should be identified as to exposure location, exposure period, specimen code, original mass, composition, original dimensions, and exposed area and information documented as shown in Table 1.

5.4.3 As each specimen is clearly identified and observations documented, it can be cleaned, in accordance with Practice G1. Specimens should then be dried and placed in a desiccator for 2 h or more before final weighing.

5.4.4 Each specimen should then be weighed to the nearest milligram and the mass recorded. Also a description of the type of corrosion attack should be recorded, for example, pitting (depth).

5.4.5 After the mass loss has been calculated, a mass loss per unit area (mg/m²) and corrosion rate (mm/y) can be calculated using the following equations (see Practice G1 for further guidance).

³ Also available are data from the National Climate Data Center, NOAA, Asheville, NC.

⁴ The boldface numbers in parentheses refer to a list of references at the end of this standard.

$$M_a = \frac{M}{A} \quad (1)$$

where:

M_a = mass loss per unit area, milligrams per square metre
 M = mass loss, milligrams, and
 A = exposed surface area, metres squared

$$C = \frac{(8.76 \times 10^4) M_l}{a \times t \times d} \quad (2)$$

where:

C = corrosion rate, millimetres per year
 M_l = mass loss, grams
 a = area, centimetres squared
 t = time, hours
 d = density, grams per cubic centimetre

6. Method B

6.1 Several atmospheric factors have been identified as having a significant influence on the corrosion of metals and deterioration of materials. Several of these factors are identified in Table 2 with a suggested format to report these data.

6.2 The atmospheric factors to be monitored are dependent on individual needs, and at what frequency the monitoring devices can be attended. Daily attention is often preferred. Available also are computer monitored systems. Suggestions for monitoring systems requiring minimal attention are listed in Table 3.

TABLE 3 Recommended Methods for Monitoring Atmospheric Factors

Atmospheric Factors	Monitoring Device
Sulfur dioxide	sulfation plate
Chloride ion	wet candle
Temperature/humidity	hygrothermograph (combination of hygograph and thermograph used for recording temperature and humidity)
Precipitation	standard 200 mm rain/snow gage (periodic sampling for pH range)
Time of wetness	Cu/Au sensor (procedure defined in Practice G84)
Climatological data	National Weather Service ^A

^A National Weather Service monitors climatological data in many areas and data are available from the National Climate Data Center, NOAA, Ashville, NC.

6.2.1 Sulfur dioxide can be monitored easily by the use of sulfation plates (see Practice G91) (2). Monthly attention is needed to change the plates.

6.2.2 The hygrothermograph can be used to record temperature and relative humidity. Instruments can be run by either batteries or a hand-wound spring, and will operate for one month unattended.

6.2.3 The standard 200 mm rain gage needs to be visually checked and precipitation (rain, snow) measured after each occurrence. Also samples of precipitation can be collected for laboratory analysis (acidity, pH, contaminants).

6.2.4 Chloride ion concentration can be monitored by the wet candle method (3). This system may require weekly attention to replace evaporated distilled water in the 500-mL flask. Also monthly laboratory analysis is required to obtain chloride analyses.

6.2.5 Time of wetness (see Practice G84) can be monitored by the Sereda miniature moisture sensor (4). This device, with suitable recorder or computer interface, should operate unattended on a monthly basis.

6.2.6 Other monitoring devices can provide useful climatological data to suit special needs (for example, wind speed and direction, solar radiation, barometric pressure, and dust particles).

6.3 Hourly, daily, weekly, and monthly variations in the atmospheric factors are intimately linked with the corrosion process. Quantizing these changes can provide insight into observed corrosion performance. Time averages or other measures of the atmospheric factors over a time span coincident with the corrosion experiment can be used.

6.4 Atmospheric monitoring should be performed at a site as near to the placement of the corrosion specimens exposed in Method A as possible. Microclimatological variations at a given test area could reasonably be expected to exist and thus close proximity of the two methods is important.

6.5 Additional information on atmospheric monitoring is available in selected references (4-10).

7. Keywords

7.1 atmospheric characterization; atmospheric factors; atmospheric testing; identification; mass loss; monitoring; reporting; standard test materials

REFERENCES

- (1) LaQue, F. L., “Corrosion Testing,” *Proceedings of ASTM*, Vol 51, 1951.
- (2) “The Lead Dioxide Estimate of Sulfur Dioxide Pollution,” *Journal of the Air Pollution Control Association*, Vol 18, No. 9, September 1968.
- (3) Foran, M. R., Gibbons, E. V., and Wellington, J. R., “The Measurement of Atmospheric Sulphur Dioxide and Chlorides,” *Chemistry in Canada*, Vol 10, No. 5, May 1958, pp. 33–41.
- (4) Sereda, P. J., Cross, S. G., and Slade, H. F., “Measurement of Time-of-Wetness by Moisture Sensors and Their Calibration,” *Atmospheric Corrosion of Metals*, ASTM STP 767, ASTM, 1982, pp. 267–285.
- (5) Bigelow, D. S., *NADP Instruction Manual-Site Operation*, National Atmospheric Deposition Program, Colorado State University, Fort Collins, CO, January 1982, p. 30.
- (6) Bigelow, D. S., *NADP Instruction Manual-Site Selection and Installation*, National Atmospheric Deposition Program, Colorado State University, Fort Collins, CO, January 1983, p. 21.
- (7) *Code of Federal Regulations*, Title 40-Protection of Environment, Part 50, Office of the Federal Register, National Archives and Records Service, General Services Administration, July 1, 1982, pp. 563–614.
- (8) *Code of Federal Regulations*, Title 40-Protection of Environment, Part 58, Office of the Federal Register, National Archives and Records Service, General Services Administration, July 1, 1982, pp. 144–204.
- (9) *Surface Observation*, Federal Meteorological Handbook No. 1, 3rd Edition, U.S. Department of Commerce, January 1, 1982, p. 251.
- (10) *Joint Automated Weather Observing System*, Proposed Functional Requirement, National Weather Service, U.S. Department of Commerce, February 1981, p. 88.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).