

ANSI/AWS A5.10-92
An American National Standard

**Specification for
Bare Aluminum and
Aluminum Alloy Welding
Electrodes and Rods**



American Welding Society

Keywords — Bare aluminum, filler metal, aluminum rods, aluminum electrodes, gas metal arc welding, gas tungsten arc welding, cast aluminum alloys, oxyfuel gas welding, plasma arc welding, classification, specification

ANSI/AWS A5.10-92
An American National Standard

Approved by
American National Standards Institute
February 28, 1992

Specification for Bare Aluminum and Aluminum Alloy Welding Electrodes and Rods

Supersedes
ANSI/AWS A5.10-88

Prepared by
AWS Committee on Filler Metal

Under the Direction of
Technical Activities Committee

Approved by
AWS Board of Directors

Abstract

This specification prescribes requirements for the classification of bare, wrought and cast aluminum alloy electrodes and rods for use with the gas metal arc, gas tungsten arc, oxyfuel gas, and plasma arc welding processes. Classification is based upon chemical composition of the wire and a usability test. Spooled electrodes are tested by fabricating a groove weld specimen to meet a radiographic soundness requirement. Coiled or straight-length rod is tested by visually inspecting a gas tungsten arc welded bead-on-plate specimen. Standard sizes, finish, winding requirements, package forms and weights, product identification, and chemical composition limits are specified.



American Welding Society

550 N.W. LeJeune Road, P.O. Box 351040, Miami, FL 33135

Statement on Use of AWS Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute. When AWS standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

International Standard Book Number: 0-87171-374-8

American Welding Society, 550 N.W. LeJeune Road, P. O. Box 351040, Miami, Florida 33135

© 1992 by American Welding Society.
All rights reserved

Printed in the United States of America

Note: The primary purpose of AWS is to serve and benefit its members. To this end, AWS provides a forum for the exchange, consideration, and discussion of ideas and proposals that are relevant to the welding industry and the consensus of which forms the basis for these standards. By providing such a forum, AWS does not assume any duties to which a user of these standards may be required to adhere. By publishing this standard, the American Welding Society does not insure anyone using the information it contains against any liability arising from that use. Publication of a standard by the American Welding Society does not carry with it any right to make, use, or sell any patented items. Users of the information in this standard should make an independent investigation of the validity of that information for their particular use and the patent status of any item referred to herein.

With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. However, such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time by the AWS Filler Metal Committee. It must be reviewed every five years and if not revised, it must be either reapproved or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are requested and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS Filler Metal Committee and the author of the comments will be informed of the Committee's response to the comments. Guests are invited to attend all meetings of the AWS Filler Metal Committee to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the Rules of Operation of the Technical Activities Committee. A copy of these Rules can be obtained from the American Welding Society, 550 N.W. LeJeune Road, P. O. Box 351040, Miami, Florida 33135.

Personnel

AWS Committee on Filler Metal

<i>W. L. Wilcox, Chairman</i>	Consultant
<i>D.J. Kotecki, 1st Vice Chairman</i>	The Lincoln Electric Company
<i>D.F. Betz, 2nd Vice Chairman</i>	Crane Midwest Fittings
<i>W.A. Dierschow, Secretary</i>	American Welding Society
<i>Z. Al-Hillal</i>	Liquid Carbonic
<i>D.R. Amos</i>	Westinghouse Turbine Plant
<i>B.E. Anderson</i>	AlcoTec Wire Company
<i>K.E. Banks</i>	Teledyne McKay
<i>J.B. Bolton</i>	Kennametal
<i>J. Caprarola, Jr.</i>	Alloy Rods Corporation
<i>L.J. Christensen*</i>	Consultant
<i>R.J. Christoffel</i>	Consultant
<i>D.A. Del Signore</i>	Westinghouse Electric Company
<i>H.W. Ebert</i>	Exxon Research and Engineering Company
<i>D.A. Fink</i>	Lincoln Electric Company
<i>J. Gonzalez</i>	Lincoln Electric Company
<i>G. Hallstrom, Jr.</i>	USNRC-RII
<i>R.L. Harris*</i>	R.L. Harris Associates
<i>D.C. Helton</i>	Consultant
<i>W.S. Howes</i>	National Electrical Manufacturers Association
<i>J.P. Hunt</i>	Inco Alloys International
<i>P.A. Kammer*</i>	Eutectic Corporation
<i>G.A. Kurisky</i>	Maryland Specialty Wire
<i>R.A. LaFave</i>	Elliott Company
<i>N.E. Larson</i>	Union Carbide Corporation/Linde Division
<i>A.S. Laurensen</i>	Consultant
<i>G.H. MacShane</i>	Consultant
<i>L.M. Malik*</i>	Arctec Canada, Limited
<i>L.B. Matthews</i>	Harley Davidson York, Incorporated
<i>W.F. McLaughlin</i>	Chrysler Corporation
<i>M.T. Merlo</i>	Tri-Mark, Incorporated
<i>G.E. Metzger</i>	AFWAL/MLLS
<i>J.W. Mortimer</i>	Consultant
<i>L.W. Mott</i>	Consultant
<i>C.L. Null</i>	Naval Sea Systems Command
<i>Y. Ogata*</i>	Kobe Steel
<i>J. Payne</i>	Schneider Service International
<i>R.L. Peaslee</i>	Wall Colmonoy Corporation
<i>E.W. Pickering</i>	ABB Combustion Engineering

* Advisor

AWS Committee on Filler Metal

<i>S.D. Reynolds, Jr.*</i>	Westinghouse Electric Corporation
<i>L.F. Roberts</i>	Canadian Welding Bureau
<i>D. Rozet</i>	Consultant
<i>P.K. Salvesen</i>	American Bureau of Shipping
<i>H.S. Sayre*</i>	Consultant
<i>O.W. Seth</i>	CBI Na-Con, Incorporated
<i>R.W. Straiton*</i>	Bechtel Group, Incorporated
<i>R.D. Sutton</i>	L-Tec Welding and Cutting System
<i>J.W. Tackett</i>	Hayes International Incorporated
<i>R.D. Thomas, Jr.</i>	R.D. Thomas and Company
<i>R. Timmerman*</i>	Conarco, S.A.
<i>R.T. Webster</i>	Teledyne Wah Chang
<i>A.E. Wiehe*</i>	Consultant
<i>W.A. Wiehe</i>	Arcos Alloys
<i>F.J. Winsor</i>	Consultant
<i>C.E. Wirsing</i>	IBM-FSD
<i>K.G. Wold</i>	Aqua-Chem, Incorporated
<i>T.J. Wonder</i>	Rexham Aerospace and Defence Group, Incorporated

AWS Subcommittee on Aluminum and Aluminum Alloy Filler Metals

<i>B.E. Anderson, Chairman</i>	AlcoTec Wire Company
<i>A.H. Lentz, Vice Chairman</i>	BMV, Division of Harsco
<i>W.A. Dierschow, Secretary</i>	American Welding Society
<i>H.E. Adkins*</i>	H.E. Adkins and Associates, Incorporated
<i>P.B. Dickerson*</i>	Consultant
<i>W.N. Dietzen</i>	Gulf Wire Corporation
<i>B.W. Folkening</i>	FMC Corporation
<i>R.M. Henson</i>	J.W. Harris Company
<i>L.L. Herl</i>	L-Tec Welding and Cutting System
<i>J. Kosty</i>	Los Alamos National Laboratories
<i>D.W. Rogers</i>	Alcan Wire and Cable
<i>H.S. Sayre*</i>	Consultant
<i>O.W. Seth</i>	CBI Na-Con, Incorporated

* Advisor

Foreword

(This Foreword is not a part of ANSI/AWS A5.10-92, *Specification for Bare Aluminum and Aluminum Alloy Welding Electrodes and Rods*, but is included for information purposes only.)

This document represents the sixth revision of the first bare aluminum filler metal specification issued in 1954 as a joint ASTM/AWS specification. After two revisions and publication as a joint specification, ASTM agreed to accept AWS as the sole society responsible for the development and publication of filler metal specifications.

In recent years, AWS filler metal specifications have been recognized by the American National Standards Institute. The evolution of this specification is shown below.

ASTM B285-54T	Tentative Specification for Aluminum and Aluminum-Alloy Welding Rods and Bare Electrodes
AWS A5.10-54T	
ASTM B285-57T	Tentative Specification for Aluminum and Aluminum-Alloy Welding Rods and Bare Electrodes
AWS A5.10-57T	
AWS A5.10-61T	Tentative Specification for Aluminum and Aluminum-Alloy Welding Rods and Bare Electrodes
ASTM B285-61T	
AWS A5.10-69	Specification for Aluminum and Aluminum Alloy Welding Rods and Bare Electrodes
ANSI W3.10-1973	
ANSI/AWS A5.10-80	Specification for Aluminum and Aluminum Alloy Bare Welding Rods and Electrodes
ANSI/AWS A5.10-88	Specification for Bare Aluminum and Aluminum Alloy Welding Electrodes and Rods

Comments and suggestions for the improvement of this standard are welcome. They should be sent to the Secretary, Filler Metal Committee, American Welding Society, 550 N.W. LeJeune Road, P.O. Box 351040, Miami, Florida 33135.

Official interpretations of any of the technical requirements of this standard may be obtained by sending a request, in writing, to the Director, Standards and Publications, American Welding Society. A formal reply will be issued after it has been reviewed by the appropriate personnel following established procedures.

Table of Contents

	Page No.
<i>Personnel</i>	iii
<i>Foreword</i>	v
<i>List of Tables</i>	viii
<i>List of Figures</i>	viii
1. Scope	1
<i>Part A — General Requirements</i>	1
2. Classification	1
3. Acceptance	1
4. Certification	1
5. Units of Measure and Rounding-Off Procedure	1
<i>Part B — Tests, Procedures, and Requirements</i>	4
6. Summary of Tests	4
7. Retest	4
8. Weld Test Assemblies	4
9. Chemical Analysis	6
10. Radiographic Test	7
11. Bead-on-Plate Test	8
<i>Part C — Manufacture, Identification, and Packaging</i>	9
12. Method of Manufacture	9
13. Standard Sizes	9
14. Finish and Uniformity	9
15. Standard Package Forms	11
16. Winding Requirements	11

17. Filler Metal Identification	13
18. Packaging	13
19. Marking of Packages	13
<i>Appendix — Guide to AWS Specification for Bare Aluminum and Aluminum Alloy Welding</i>	
<i>Electrodes and Rods</i>	15
A1. Introduction	15
A2. Classification System	15
A3. Acceptance	15
A4. Certification	16
A5. Ventilation During Welding	16
A6. Welding Considerations	16
A7. Description and Intended Use of Aluminum Electrodes and Rods	17
A8. Special Tests	18
A9. Chemical Analysis	18
A10. General Safety Considerations	18
<i>AWS Filler Metal Specifications and Related Documents</i>	(Inside Back Cover)

List of Tables

Table		Page No.
1	Chemical Composition Requirements for Aluminum Electrodes and Rods	2
2	Required Tests	6
3	Base Metal for Test Assemblies	7
4	Standard Sizes	10
5	Typical Sizes of Flattened Rods	10
6	Standard Packages, Dimensions, and Weights	11
A1	Guide to the Choice of Filler Metal for General Purpose Welding	19

List of Figures

Figure		Page No.
1	Groove Weld Test Assembly for Radiographic Test	5
2	Radiographic Acceptance Standards for Test Assemblies — Overhead Welding Position	8
3	Radiographic Acceptance Standard for Test Assemblies — Flat Position Welding	9
4	Dimensions of 4 in. (100 mm) Diameter Spool	12
5	Dimensions of 8 and 12 in. (200 and 300 mm) Diameter Spools	12
6	Dimensions of Standard 13-1/2 in. (340 mm) Diameter Spool	13

Specification for Bare Aluminum and Aluminum Alloy Welding Electrodes and Rods

1. Scope

This specification prescribes requirements for the classification of bare aluminum and aluminum alloy welding electrodes and rods for use with the gas metal arc, gas tungsten arc, oxyfuel gas, and plasma arc welding processes.

Part A *General Requirements*

2. Classification

2.1 The electrodes and rods covered by this specification are classified according to the chemical composition of the filler metal as specified in Table 1 and their usability as specified in Section 8, Weld Test Assemblies, and Table 2.

2.2 Any filler metal tested and classified as an electrode shall also be classified as a welding rod. Filler metal tested and classified only as a welding rod shall not be classified as an electrode.

2.3 The electrodes and rods classified under this specification are intended for gas metal arc, gas tungsten arc, oxyfuel gas, and plasma arc welding, but that is not to prohibit their use with any other process for which they are found suitable.

2.4 Filler metal containing more than 0.0008 percent by weight of beryllium shall not be classified as electrode and should not be used as an electrode.

3. Acceptance

Acceptance¹ of the material shall be in accordance with the provisions of ANSI/AWS A5.01, *Filler Metal Procurement Guidelines*.²

4. Certification

By affixing the AWS specification and classification designations to the packaging, or the classification to the product, the manufacturer certifies that the product meets the requirements of this specification.³

5. Units of Measure and Rounding-Off Procedure

5.1 U.S. Customary Units are the standard units of measure in this specification. The SI Units are given as equivalent values to the U.S. Customary Units. The standard sizes and dimensions in the two systems are not identical, and for this reason conversion from a standard size or dimension in one system will not always coincide with a stan-

1. See A3, Acceptance, (in the Appendix) for further information concerning acceptance, testing of the material shipped, and ANSI/A5.01, *Filler Metal Procurement Guidelines*.

2. AWS standards may be obtained from the American Welding Society, 550 N.W. LeJeune Road, P.O. 351040, Miami, Florida 33135.

3. See A4, Certification, (in the Appendix) for further information concerning certification and the testing called for to meet this requirement.

Table 1
Chemical Composition Requirements for Aluminum Electrodes and Rods

AWS Classification	UNS Number ^c	Weight Percent ^{a,b}										Other Elements	
		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Each	Total	Al
ER1100	A91100	d	d	0.05-0.20	0.05	—	—	—	0.10	—	0.05 ^e	0.15	99.0 min ^f
R1100	A91100	d	d	0.05-0.20	0.05	—	—	—	0.10	—	0.05 ^e	0.15	99.0 min ^f
ER1188 ^g	A91188	0.06	0.06	0.005	0.01	0.01	—	—	0.03	0.01	0.01 ^e	—	99.88 min ^f
R1188 ^g	A91188	0.06	0.06	0.005	0.01	0.01	—	—	0.03	0.01	0.01 ^e	—	99.88 min ^f
ER2319 ^h	A92319	0.20	0.30	5.8-6.8	0.20-0.40	0.02	—	—	0.10	0.10-0.20	0.05 ^e	0.15	Remainder
R2319 ^h	A92319	0.20	0.30	5.8-6.8	0.20-0.40	0.02	—	—	0.10	0.10-0.20	0.05 ^e	0.15	Remainder
ER4009	A94009	4.5-5.5	0.20	1.0-1.5	0.10	0.45-0.6	—	—	0.10	0.20	0.05 ^e	0.15	Remainder
R4009	A94009	4.5-5.5	0.20	1.0-1.5	0.10	0.45-0.6	—	—	0.10	0.20	0.05 ^e	0.15	Remainder
ER4010	A94010	6.5-7.5	0.20	0.20	0.10	0.30-0.45	—	—	0.10	0.20	0.05 ^e	0.15	Remainder
R4010	A94010	6.5-7.5	0.20	0.20	0.10	0.30-0.45	—	—	0.10	0.20	0.05 ^e	0.15	Remainder
R4011 ^k	A94011	6.5-7.5	0.20	0.20	0.10	0.45-0.7	—	—	0.10	0.04-0.20	0.05	0.15	Remainder
ER4043	A94043	4.5-6.0	0.8	0.30	0.05	0.05	—	—	0.10	0.20	0.05 ^e	0.15	Remainder
R4043	A94043	4.5-6.0	0.8	0.30	0.05	0.05	—	—	0.10	0.20	0.05 ^e	0.15	Remainder
ER4047	A94047	11.0-13.0	0.8	0.30	0.15	0.10	—	—	0.20	—	0.05 ^e	0.15	Remainder
R4047	A94047	11.0-13.0	0.8	0.30	0.15	0.10	—	—	0.20	—	0.05 ^e	0.15	Remainder
ER4145	A94145	9.3-10.7	0.8	3.3-4.7	0.15	0.15	0.15	—	0.20	—	0.05 ^e	0.15	Remainder
R4145	A94145	9.3-10.7	0.8	3.3-4.7	0.15	0.15	0.15	—	0.20	—	0.05 ^e	0.15	Remainder
ER4643	A94643	3.6-4.6	0.8	0.10	0.05	0.10-0.30	—	—	0.10	0.15	0.05 ^e	0.15	Remainder
R4643	A94643	3.6-4.6	0.8	0.10	0.05	0.10-0.30	—	—	0.10	0.15	0.05 ^e	0.15	Remainder
ER5183	A95183	0.40	0.40	0.10	0.50-1.0	4.3-5.2	0.05-0.25	—	0.25	0.15	0.05 ^e	0.15	Remainder
R5183	A95183	0.40	0.40	0.10	0.50-1.0	4.3-5.2	0.05-0.25	—	0.25	0.15	0.05 ^e	0.15	Remainder
ER5356	A95356	0.25	0.40	0.10	0.05-0.20	4.5-5.5	0.05-0.20	—	0.10	0.06-0.20	0.05 ^e	0.15	Remainder
R5356	A95356	0.25	0.40	0.10	0.05-0.20	4.5-5.5	0.05-0.20	—	0.10	0.06-0.20	0.05 ^e	0.15	Remainder
ER5554	A95554	0.25	0.40	0.10	0.50-1.0	2.4-3.0	0.05-0.20	—	0.25	0.05-0.20	0.05 ^e	0.15	Remainder
R5554	A95554	0.25	0.40	0.10	0.50-1.0	2.4-3.0	0.05-0.20	—	0.25	0.05-0.20	0.05 ^e	0.15	Remainder
ER5556	A95556	0.25	0.40	0.10	0.50-1.0	4.7-5.5	0.05-0.20	—	0.25	0.05-0.20	0.05 ^e	0.15	Remainder
R5556	A95556	0.25	0.40	0.10	0.50-1.0	4.7-5.5	0.05-0.20	—	0.25	0.05-0.20	0.05 ^e	0.15	Remainder

(Continued)

Table 1 (Continued)

AWS Classification	UNS Number ^c	Weight Percent ^{a,b}										Other Elements	
		Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti		Each	Total
ER5654	A95654	i	i	0.05	0.01	3.1-3.9	0.15-0.35	—	0.20	0.05-0.15		0.05 ^e	0.15
R5654	A95654	i	i	0.05	0.01	3.1-3.9	0.15-0.35	—	0.20	0.05-0.15		0.05 ^e	0.15
R-206.0 ^j	A02060	0.10	0.15	4.2-5.0	0.20-0.30	0.15-0.35	—	0.05	0.10	0.15-0.30		0.05	0.15
R-C355.0	A33550	4.5-5.5	0.20	1.0-1.5	0.10	0.40-0.6	—	—	0.10	0.20		0.05	0.15
R-A356.0	A13560	6.5-7.5	0.20	0.20	0.10	0.25-0.45	—	—	0.10	0.20		0.05	0.15
R-357.0	A03570	6.5-7.5	0.15	0.05	0.03	0.45-0.6	—	—	0.05	0.20		0.05	0.15
R-A357.0 ^k	A13570	6.5-7.5	0.20	0.20	0.10	0.40-0.7	—	—	0.10	0.04-0.20		0.05	0.15

Notes:

- The filler metal shall be analyzed for the specific elements for which values are shown in this table. If the presence of other elements is indicated in the course of this work, the amount of those elements shall be determined to ensure that they do not exceed the limits specified for "Other Elements".
- Single values are maximum, except where otherwise specified.
- SAE/ASTM Unified Numbering System for Metals and Alloys.
- Silicon plus iron shall not exceed 0.95 percent.
- Beryllium shall not exceed 0.0008 percent.
- The aluminum content for unalloyed aluminum is the difference between 100.00 percent and the sum of all other metallic elements present in amounts of 0.010 percent or more each, expressed to the second decimal before determining the sum.
- Vanadium content shall be 0.05 percent maximum. Gallium content shall be 0.03 percent maximum.
- Vanadium content shall be 0.05-0.15 percent. Zirconium content shall be 0.10-0.25 percent.
- Silicon plus iron shall not exceed 0.45 percent.
- Tin content shall not exceed 0.05 percent.
- Beryllium content shall be 0.04-0.07 percent.

dard size or dimension in the other. Suitable conversions, encompassing standard sizes of both, can be made, however, if appropriate tolerances are applied in each case.

5.2 For the purpose of determining conformance with this specification, an observed or calculated value shall be rounded to the "nearest unit" in the last right-hand place of figures used in expressing the limiting value in accordance with the rounding-off method given in ASTM E29, *Standard Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications*.⁴

Part B

Tests, Procedures, and Requirements

6. Summary of Tests

The tests required for each classification are specified in Table 2. The purpose of these tests is to determine the chemical composition of the filler metal, soundness of the weld metal produced by gas metal arc welding electrodes, and the deposition characteristics of welding rods. The base metal for the weld test assemblies, the welding and testing procedures to be employed, and the results required are given in Sections 8 through 11.

7. Retest

If the results of any test fail to meet the requirement, that test shall be repeated twice. The results of both retests shall meet the requirement. Material for retest may be taken from the original test sample or from one or two new samples. For chemical analysis, retest need be only for those specific elements that failed to meet the test requirement.

8. Weld Test Assemblies

8.1 Two weld test assemblies are required:

(1) The groove weld in Figure 1 for the usability of electrodes and the soundness of the weld metal

4. ASTM standards can be obtained from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.

(2) The bead-on-plate weld in 8.4.1 for the usability of rods

8.2 Usability tests shall be made using electrodes and welding rods of each size. A filler metal that satisfactorily meets the requirements of the radiographic soundness test, when tested as an electrode, may also be classified as a welding rod without being subjected to the bead-on-plate test required for a welding rod. A filler metal that satisfactorily meets the bead-on-plate weld test requirements, when tested as a welding rod, shall also be tested as an electrode and meet the requirements of the radiographic soundness test in order to be classified as an electrode.

8.3 Groove Weld for Soundness and Usability of Electrodes

8.3.1 A test assembly shall be prepared and welded, as specified in Figure 1 and 8.3.2 through 8.3.4, using base metal of the appropriate type specified in Table 3. The welding position shall be as specified in Figure 1 for the different electrode sizes and classifications. Testing of the assembly shall be as specified in Section 10, Radiographic Test.


8.3.2 Welding of the test assembly shall be done using the gas metal arc welding process with techniques and procedures specified by the manufacturer as to the factors not covered herein.

8.3.3 Dimensions of the groove weld joint and the position of welding shall be as specified in Figure 1 for the electrode diameter being tested. The backing material shall be of the same type of base metal as the test plate base metal.

8.3.4 The test assembly shall be at a temperature of not less than 60°F (16°C) when commencing the initial or subsequent weld passes. Also, the initial or interpass temperatures shall not exceed 150°F (66°C).

8.4 Bead-on-Plate Weld Test for Usability of Welding Rods

8.4.1 The test assembly shall consist of a sheet or plate approximately 6 in. (150 mm) by 12 in. (300 mm) upon which a weld shall be made as specified in 8.4.2, using base metal of the appropriate type specified in Table 3. Examination of the assembly shall be as specified in Section 11, Bead-on-Plate Test.



SI Equivalents

in.	mm
1	25
10	250

Notes:

- Assembly shall be welded employing the gas metal arc welding process.
- Assembly may be machined or extruded as a single piece if the dimensions shown are maintained for the specific electrode size being tested.

Electrode Diameter		Plate Thickness T		Minimum Root Opening R		Welding Position
in.	mm	in.	mm	in.	mm	
0.030	0.8	3/16 or 1/4	4.8	1/4	6.4	Overhead
0.035	0.9		6.4			
3/64	1.2	1/4	6.4	1/4	6.4	Overhead
1/16	1.6	3/8	9.5	3/8	9.5	Overhead
3/32	2.4	3/8	9.5	3/8	9.5	Flat
1/8	3.2	3/8	9.5	1/2	12.7	Flat

Figure 1 — Groove Weld Test Assembly for Radiographic Test

Table 2
Required Tests

AWS Classification	Chemical Analysis	Radiographic Test (Electrode)	Bead-On-Plate Test (Rod)
ER1100	X	X	—
R1100	X	—	X
ER1188	X	X	—
R1188	X	—	X
ER2319	X	X	—
R2319	X	—	X
ER4009	X	X	—
R4009	X	—	X
ER4010	X	X	—
R4010	X	—	X
R4011	X	—	X
ER4043	X	X	—
R4043	X	—	X
ER4047	X	X	—
R4047	X	—	X
ER4145	X	X	—
R4145	X	—	X
ER4643	X	X	—
R4643	X	—	X
ER5183	X	X	—
R5183	X	—	X
ER5356	X	X	—
R5356	X	—	X
ER5554	X	X	—
R5554	X	—	X
ER5556	X	X	—
R5556	X	—	X
ER5654	X	X	—
R5654	X	—	X
R-206.0	X	—	X
R-C355.0	X	—	X
R-A356.0	X	—	X
R-357.0	X	—	X
R-A357.0	X	—	X

* Filler metal meeting the radiographic requirement, when tested as an electrode, is not required to be tested as a rod, as specified in 8.2.

8.4.2 Welding of the assembly shall be done in the flat position with the gas tungsten arc welding process employing alternating current and argon gas shielding. The test plate thickness and the welding current shall be compatible with that with which the rod being tested normally is used.

8.4.3 The completed bead-on-plate welds shall be examined with the unaided eye (corrected to normal vision) and shall meet the requirements specified in Section 11, Bead-on-Plate Test.

8.4.4 A welding rod satisfactorily meeting the bead-on-plate test requirement using gas tungsten

arc welding also is suitable for use with the oxyfuel gas and plasma arc welding processes.

9. Chemical Analysis

9.1 A sample of the filler metal, or the stock from which it is made, shall be prepared for chemical analysis.

9.2 The sample shall be analyzed by accepted analytical methods.⁵ The referee method shall be

5. See A9 (in the Appendix) for further information concerning accepted analytical methods.

Table 3
Base Metal for Test Assemblies

Electrode and Rod (AWS Classification)	Base Metal ¹ (Aluminum Association Designations) ²
ER1100, R1100, ER1188, R1188	1060, 1100, 1350, or 3003
ER2319, R2319, ER4145, R4145	2014, 2219, or 3003
ER4009, R4009, ER4010, R4010 R4011, ER4043, R4043 ER4047, R4047, ER4643, R4643	3003 or 6061
ER5183, R5183, ER5356, R5356 ER5554, R5554, ER5556 R5556, ER5654, R5654	{ 3004, 5052, 5083, 5086 5154, 5454, or 5456
R-206.0	206.0, 2014, 2219, or 3003
R-C355.0	355.0, C355.0, or 3003
R-A356.0, R357.0, R-A357.0	{ 356.0, A356.0, 357.0, A357.0, or 3003

Notes:

1. All wrought base alloys 1060, 1100, 2014, 2219, 3003, 3004, 5052, 5083, 5086, 5154, 5454, and 6061 are included in ASTM B209. Cast base alloys 355.0, C355.0, 356.0, A356.0, 357.0, and A357.0 are included in ASTM B108.
2. The Aluminum Association, Inc., 900 19th Street, N.W., Suite 300, Washington, DC 20006.

ASTM E34, *Standard Methods for Chemical Analysis of Aluminum and Aluminum Alloys*.

9.3 The results of the analysis shall meet the requirements of Table 1 for the classification of electrode or rod under test.

10. Radiographic Test


10.1 The groove weld described in 8.3 and shown in Figure 1 shall be radiographed to evaluate the soundness of the weld metal and to determine the usability of the electrode. In preparation for radiography, the backing shall be removed and both surfaces of the weld shall be machined or ground smooth. Both surfaces of the test assembly, in the area of the weld, shall be smooth enough to avoid difficulty in interpreting the radiograph.

10.2 The weld shall be radiographed in accordance with ASTM E142, *Standard Method for Control-*

ling Quality of Radiographic Testing. The quality level of inspection shall be 2-2T.


10.3 The soundness of the weld metal and the usability of the electrode meet the requirements of this specification if the radiograph shows no cracks, no incomplete fusion, and no rounded indications in excess of those permitted by the radiographic standards in Figure 2 for test assemblies welded in the overhead position for electrode sizes up to and including 1/16 in. (1.6 mm) and Figure 3 for test assemblies welded in the flat position for electrode sizes larger than 1/16 in. (1.6 mm). In evaluating the radiograph, the center 6 in. (150 mm) of the test specimen shall be considered, and all extra weld shall be disregarded.

A rounded indication is an indication on the radiograph whose length is no more than three times its width. Rounded indications may be circular, elliptical, conical, or irregular in shape and they may have tails. The size of the rounded indication is the largest dimension of the indication including any tail that may be present. Indications whose largest



1. In using these standards, the chart that is most representative of the size of the rounded indications present in the test specimen radiograph shall be used for determining conformance to these radiographic standards.
2. Indications which do not exceed 1/64 in. (0.4 mm) diameter or length, or both, shall be disregarded.
3. Total area of porosity in a 6 in. (150 mm) length of weld is 0.0225 sq. in. (14.52 sq. mm) based on 1.5% T per in. (25 mm) where T is the base metal thickness.

(A) RADIOGRAPHIC ACCEPTANCE STANDARD FOR 3/16 in. (4.8 mm) AND 1/4 in. (6.4 mm) THICK TEST ASSEMBLIES



Notes:

1. In using these standards, the chart that is most representative of the size of the rounded indications present in the test specimen radiograph shall be used for determining conformance to these radiographic standards.
2. Indications which do not exceed 1/64 in. (0.4 mm) diameter or length, or both, shall be disregarded.
3. Total area of porosity in a 6 in. (150 mm) length of weld is 0.0337 sq. in. (21.7 sq. mm) based on 1.5% T per in. (25 mm) where T is the base metal thickness.

(B) RADIOGRAPHIC ACCEPTANCE STANDARD FOR 3/8 in. (9.5 mm) THICK TEST ASSEMBLIES

These Radiographic acceptance standards are identical to those previously incorporated in MIL-E-16053L (Amendment 2-20 October 1980) and as Class 3 NAVSEA 0900-LP-003-9000.

Figure 2 — Radiographic Acceptance Standards for Test Assemblies — Overhead Welding Position


dimension does not exceed 1/64 in. (0.4 mm) shall be disregarded. Test assemblies with indications larger than the large indications permitted in the radiographic standards do not meet the requirements of this specification.

10.4 An electrode that produces a groove weld which satisfactorily meets these radiographic requirements may also be classified as a welding rod under this specification without conducting the test specified in 8.4.

11. Bead-on-Plate Test

11.1 Welding rod tested in accordance with 8.4 shall produce weld metal that flows freely and uniformly without sputtering or other irregularities. The resultant weld metal shall be smooth and uniform with no visible evidence of cracks or porosity.

11.2 If a filler metal satisfactorily meets the weld-bead-test requirements when tested as a welding rod, it also shall be tested as an electrode if it is to be classified as an electrode.

**Notes:**

1. In using these standards, the chart that is most representative of the size of the rounded indications present in the test specimen radiograph shall be used for determining conformance to these radiographic standards.
2. Indications which do not exceed 1/64 in. (0.4 mm) diameter or length, or both shall be disregarded.
3. Total area of porosity in a 6 in. (150 mm) length of weld is 0.0225 sq. in. (14.52 sq. mm) based upon 1.0% T per in. (25 mm) where T is the thickness of the base metal.

This radiographic acceptance standard is identical to that previously incorporated in MIL-E-16053L (Amendment 2-20 October 1980) and as Class 1 of NAVSEA 0900-LP-003-9000.

Figure 3 — Radiographic Acceptance Standard for Test Assemblies — Flat Position Welding

Part C

Manufacture, Identification, and Packaging

12. Method of Manufacture

The electrodes and rods classified according to this specification may be manufactured by any method that will produce material that meets the requirements of this specification.

13. Standard Sizes

13.1 Standard sizes for round filler metal in the different package forms of straight lengths, coils

without support, and spools are as shown in Table 4. Diameters of cast rods in straight lengths are approximate with no specified tolerance.

13.2 Typical sizes for flattened shapes of straight length welding rod are shown in Table 5. The cross-sectional area of such shapes shall be equivalent to that of corresponding round rods of the same nominal diameter as listed in Table 5.

14. Finish and Uniformity

14.1 All filler metal shall have a smooth finish that is free from slivers, depressions, scratches, scale, seams, laps, and foreign matter that would adversely affect the welding characteristics, the operation of the welding equipment, or the properties of the weld metal.

Table 4
Standard Sizes^a

Standard Package Form	Diameter		Tolerance ^b	
	in.	mm	in.	mm
Straight lengths ^{b,c} and Coils without support	1/16	(0.0625)	1.6	±0.0015 ±0.04
	3/32	(0.094)	2.4	
	1/8	(0.125)	3.2	
	5/32	(0.156)	4.0	
	3/16	(0.187)	4.8	
	1/4	(0.250)	6.4	
4 in. (100 mm) spools and 8 in. (200 mm) spools	0.030		0.8	{ +0.001 +0.03 -0.002 -0.05
	0.035		0.9	
	3/64	(0.047)	1.2	
	1/16	(0.0625)	1.6	
12 in. (300 mm) spools	0.030		0.8	{ +0.001 +0.03 -0.002 -0.05
	0.035		0.9	
	3/64	(0.047)	1.2	
	1/16	(0.0625)	1.6	
	3/32	(0.094)	2.4	
	1/8	(0.125)	3.2	
13-1/2 in (340 mm) spools	1/16	(0.0625)	1.6	{ +0.001 +0.03 -0.002 -0.05
	3/32	(0.094)	2.4	
	1/8	(0.125)	3.2	

Notes:

- Dimensions, tolerances, and package forms (for round filler metal) other than those shown shall be as agreed by purchaser and supplier.
- There is no specified tolerance for cast rod in straight lengths.
- Length of wrought rods shall be 36 in., +0, -1/2 in. (approximately 900 ± 20 mm).
Length of cast rods shall be 18 in., ± 1/2 in. (approximately 450 ± 12 mm).

Table 5
Typical Sizes of Flattened Rods*

Equivalent Round Diameter		Thickness		Width	
in.	mm	in.	mm	in.	mm
1/16	1.6	0.047	1.2	0.072	1.8
3/32	2.4	0.070	1.8	0.105	2.7
1/8	3.2	0.095	2.4	0.142	3.6
5/32	4.0	0.115	2.9	0.175	4.4
3/16	4.8	0.140	3.6	0.210	5.3
1/4	6.4	0.187	4.8	0.280	7.1

* Standard length shall be 36 in., +0, -1/2 in. (approximately 900 ± 20 mm).

14.2 Each continuous length of filler metal shall be from a single lot of material, and welds, when present, shall have been made so as not to interfere with the uniform, uninterrupted feeding of the filler metal on automatic and semiautomatic equipment.

15. Standard Package Forms

15.1 Standard package forms are straight lengths, coils without support, and spools. Standard package dimensions and weights for each form are given in Table 6. Package forms, sizes and weights other than these shall be as agreed between purchaser and supplier.

15.2 Dimensions of the standard spool sizes shall be as shown in Figures 4, 5, and 6. Spools shall be designed and constructed to prevent distortion of themselves and of the filler metal during normal handling and use and shall be clean and dry enough to maintain the cleanliness of the filler metal.

Spools shall electrically insulate the filler metal from the spindle.

16. Winding Requirements

16.1 Filler metal on spools and in coils without support shall be wound so that kinks, waves, sharp bends, overlapping, or wedging are not encountered, leaving the filler metal free to unwind without restriction. The outside end of the filler metal (the end with which welding is to begin) shall be identified so it can be located readily and shall be fastened to avoid unwinding.

16.2 The outermost layer of spooled electrode or spooled rod shall not be closer than 1/8 in. (3 mm) to the outside diameter of the flanges.


16.3 The cast and helix of filler metal on spools shall be such that the filler metal will feed in an uninterrupted manner in automatic and semiautomatic equipment.

Table 6
Standard Packages, Dimensions, and Weights

Package Form ^a	Nominal Net Weight	
	lb.	kg.
Straight Lengths ^b	5	2.3
	10	4.5
	25	11
	50	23
Coils-Without-Support ^c	25	11
	50	23
Spools^d		
in.	mm	
4	100	1
8	200	5
12	300	10-15
13-1/2	340	30
		0.45
		2.3
		4.5-6.8
		13.6

Notes:


- Filler metal diameters for all forms and lengths are given in Table 4.
- Nomore than one classification or size shall be included in each unit package.
- Dimensions of coils shall be as agreed between purchaser and supplier.
- Dimensions of standard spools are shown in Figure 4, 5, and 6.



Notes:

- All dimensions are in inches.
- Dimension B, outside diameter of barrel, shall be such as to permit proper feeding of the filler metals.
- Dimension C, inside diameter, shall be such that swelling of the barrel or misalignment of the barrel and flanges will not result in the inside diameter of the barrel being less than the inside diameter of the flanges.

Figure 4 — Dimensions of 4 in. (100 mm) Diameter Spool



Notes:

- All dimensions are in inches.
- Dimension B, outside diameter of barrel, shall be such as to permit proper feeding of the filler metals.

Dimensions, in		
Spool size	C	D, maximum
8	2-5/32 ± 1/32	8
12	4 ± 1/16	12

Figure 5 — Dimensions of 8 and 12 in. (200 and 300 mm) Diameter Spools




Figure 6 — Dimensions of Standard 13-1/2 in. (340 mm) Diameter Spool

17. Filler Metal Identification

17.1 The product information and the precautionary information required in Section 19, Marking of Packages, shall also appear on each coil and spool.

17.2 Coils without support shall have a tag containing this information securely attached to the filler metal at the inside end of the coil.

17.3 Spools shall have the information securely affixed in a prominent location on the outside of at least one flange of the spool.

18. Packaging

Filler metal shall be suitably packaged to ensure against damage during shipment and storage under normal conditions.

19. Marking of Packages

19.1 The following product information (as a minimum) shall be legibly marked so as to be visible from the outside of each unit package:

(1) AWS specification and classification designation (year of issue may be excluded)

(2) Supplier's name and trade designation

(3) Size and net weight

(4) Lot, control, or heat number

19.2 The following precautionary information (as a minimum) shall be predominantly displayed in legible print on all packages of welding material, including individual unit packages enclosed within a larger package:

WARNING: Protect yourself and others. Read and understand this label.

FUMES AND GASES can be dangerous to your health.

ARC RAYS can injure eyes and burn skin.

ELECTRIC SHOCK can kill.

- Before use, read and understand the manufacturer's instructions, Material Safety Data Sheets (MSDSs), and your employer's safety practices.
- Keep your head out of the fumes.
- Use enough ventilation, exhaust at the arc, or both, to keep fumes and gases away from your breathing zone and the general area.
- Wear correct eye, ear, and body protection.
- Do not touch live electrical parts.
- See American National Standard Z49.1, *Safety in Welding and Cutting*, published by the American Welding Society, 550 N.W. LeJeune Road, P.O. Box 351040, Miami, Florida 33135; OSHA Safety and Health Standards, 29 CFR 1910, available from the U.S. Government Printing Office, Washington, DC 20402.

DO NOT REMOVE THIS INFORMATION

Appendix A

Guide to Specification for Bare Aluminum and Aluminum Alloy Welding Electrodes and Rods

(This Appendix is not a part of ANSI/AWS A5.10-92, *Specification for Bare Aluminum and Aluminum Alloy Welding Electrodes and Rods*, but is included for information purposes only.)

A1. Introduction

This guide is designed to correlate the filler metal classifications with their intended applications so the specification can be used more effectively. Reference to appropriate base metal alloys is made whenever that can be done and when it would be helpful. Such references are intended as examples rather than complete listings of the materials for which each filler metal is suitable.

A2. Classification System

A2.1 Both welding electrodes and rods are classified upon the basis of the chemical composition of the aluminum filler metal and a usability test. The AWS classifications used in this specification are based as follows:

A2.2 The Aluminum Association alloy designation nomenclature is used for the numerical portion to identify the alloy and thus its registered chemical composition.

A2.3 A letter prefix designates usability of the filler metal. The letter system for identifying the filler metal classifications in this specification follows the standard pattern used in other AWS filler metal specifications. The prefix "E" indicates the filler metal is suitable for use as an electrode and the prefix "R" indicates suitability as welding rod. Since some of these filler metals are used as electrodes in gas metal arc welding, and as welding rods in oxy-fuel gas, gas tungsten arc, and plasma arc welding, both letters, "ER", are used to indicate suitability as an electrode or a rod. In all cases, an electrode, that

meets the tests prescribed in this specification, can be used either as an electrode or a welding rod, but the reverse is not necessarily true.

A2.4 Minor changes in procedures used in the manufacture of aluminum filler metals can affect their surface quality and significantly affect the resultant weld soundness. Usability testing of the electrode is desirable on a periodic basis to assure that the product classified in this specification continues to meet the soundness requirement.

The supplier should perform the usability tests of this specification on an annual basis, as a minimum, to assure that the specified soundness and operating characteristics criteria are maintained. ANSI/AWS A5.01, *Filler Metal Procurement Guidelines*, should be used by a purchaser for definition of lot and frequency of testing references when purchasing aluminum filler metals.

A3. Acceptance

Acceptance of all welding materials classified under this specification is in accordance with ANSI/AWS A5.01, *Filler Metal Procurement Guidelines*, as the specification states. Any testing a purchaser requires of the supplier, for material shipped in accordance with this specification, shall be clearly stated in the purchase order, according to the provisions of ANSI/AWS A5.01, *Filler Metal Procurement Guidelines*. In the absence of any such statement in the purchase order, the supplier may ship the material with whatever testing the supplier normally conducts on material of that classification, as specified in Schedule F, Table 1, of ANSI/AWS A5.01, *Filler Metal Procurement*

Guidelines. Testing in accordance with any other Schedule in that Table must be specifically required by the purchase order. In such cases, acceptance of the material shipped will be in accordance with those requirements.

A4. Certification

The act of placing the AWS specification and classification designations on the packaging enclosing the product or the classification on the product itself, constitutes the supplier's (manufacturer's) certification that the product meets all of the requirements of the specification.

The only testing requirement implicit in this certification is that the manufacturer has actually conducted the tests required by the specification on material that is representative of that being shipped and that the material met the requirements of the specification. Representative material, in this case, is any production run of that classification using the same formulation. "Certification" is not to be construed to mean that tests of any kind were necessarily conducted on samples of the specific material shipped. Tests on such material may or may not have been made. The basis for the certification required by the specification is the classification test of representative material cited above and the "Manufacturer's Quality Assurance Program" in ANSI/AWS A5.01, *Filler Metal Procurement Guidelines*.

A5. Ventilation During Welding

A5.1 Five major factors govern the quantity of fumes in the atmosphere to which welders and welding operators are exposed during welding:

- (1) Dimensions of the space in which welding is done (with special regard to the height of the ceiling)
- (2) Number of welders and welding operators working in that space
- (3) Rate of evolution of fumes, gases, or dust, according to the materials and processes involved
- (4) The proximity of the welder or welding operator to the fumes as they issue from the welding zone, and to the gases and dusts in the space in which the welder or welding operator is working
- (5) The ventilation provided to the space in which the welding is done

A5.2 ANSI/ASC Z49.1, *Safety in Welding and Cutting*, published by the American Welding Society, discusses the ventilation that is required during welding and should be referred to for details. Attention is drawn particularly to the sections of that document covering Ventilation and Confined Spaces.

A6. Welding Considerations

The electrodes and rods described in this specification are primarily for use with the inert gas arc welding processes. However, they may be used with other welding processes such as electron beam or oxyfuel gas welding.

A6.1 The gas metal arc process permits the successful welding of aluminum alloys that are crack-sensitive when welded by oxyfuel gas or other manual welding processes. The reasons for this might be described briefly as follows:

Distortion is reduced to a minimum because the increase in temperature of the parts being welded is confined to a narrow zone. Because the aluminum alloys have high thermal conductivity, the reduction of distortion is greater than would be the case with ferrous base metals. Cracking of welds in the aluminum alloys is reduced if the cooling rate is high.

The gas metal arc process permits the welding of alloys that have a wide melting range, which heretofore have been difficult to weld without cracking.

A6.2 The high melting and solidification rate of the weld metal from the gas metal arc process can result in entrapped gas in the welds. Control of this factor should be understood to obtain good results. Gas in the welds can be caused by contaminating influences, such as grease, hydrocarbon cleaning agents, or moisture on the electrode or on the base metal. Moist air leaking into the inert gas lines may also cause this condition. Improper adjustment of electrode speed, welding current, or other machine variables may have a similar effect. The introduction of gas in the weld metal from any of these causes can result in porosity, because the solidification rate is high and the gas may not have time to escape before the molten metal solidifies.

A6.3 Welds can be made in all positions with the gas metal arc process. Edge preparation similar to that used for gas tungsten arc welding is satisfactory. Either argon or helium shielding is used, or

mixtures of these gases may be used. Semiautomatic welding, in which the welding gun is moved by a welder, is difficult to control on metal thicknesses below 0.080 in. (2 mm) with constant amperage. The use of a pulsed power supply permits the welding of base metal as thin as 0.030 in. (0.8 mm). No upper limit on metal thickness has been established. Welds in plate up to 8 in. (200 mm) in thickness have been made. Automatic gas metal arc welding is suitable for all thicknesses welded, and particularly for less than 1/8 in. (3.2 mm) in thickness.

A6.4 Gas metal arc welding is done with direct current (electrode positive). Almost all drooping volt-ampere characteristic DC motor-generator sets and DC rectifier welding machines used for shielded metal arc welding with covered electrodes are suitable sources of power.

Constant-voltage power supplies are also suitable. An electrode feeding mechanism, in which electrode speed can be adjusted between 50 and 500 ipm (21 and 211 mm/s) is needed. Electrode feeders possessing "touch-start" or "slow run-in" features, or both, are necessary when using a drooping volt-ampere characteristic power supply, and are desirable with constant-voltage power sources.

Radiused top and bottom electrode feed rolls are preferred in both manual and mechanized equipment. Stabilization of the arc with high-frequency current is not required.

A6.5 Gas tungsten arc welds can be made in all positions. Welding travel speed is reduced compared to GMA welding, however, this is beneficial in several aspects. The process is more maneuverable for manually welding small tubes or piping than GMAW; entrapment of gases is minimized to permit production of sound welds; short repair welds can be made more easily; and the reduced concentration of heat input allows welding aluminum base metal thicknesses as thin as 0.020 in. (0.5 mm) or less. Corner and edge joints in sheet gauges can be made more satisfactorily than by GMAW due to the better control of the filler metal additions.

A6.6 Gas tungsten arc welds are most commonly made with alternating-current power and argon gas shielding. Helium additions to the extent of 25 to 50 percent of the mixture with argon are used to increase the rate of initial melting and the amount of melting in thick base metal. Pure tungsten or zirconia-tungsten electrodes are preferred for AC-

GTAW. The positive electrode polarity of the AC power provides an arc cleaning action to remove the surface oxide; however, thick aluminum oxides caused by weathering, thermal treatments, or anodic treatments need to be reduced by chemical or mechanical means prior to welding to obtain uniform results and proper fusion. As stated in A6.2, sources of hydrogen, such as moisture on the base or filler metals or in the gas shielding and residual hydrocarbons on the base or filler metals, must be removed to avoid porosity in the welds.

A6.7 Direct current power also can be used to GTA weld aluminum. DCEP power can be used to weld sheet gauges; however, a 1/4 in. (6.4 mm) diameter tungsten electrode is required to carry the 125 amperes needed to weld 1/8 in. (3.2 mm) thickness, so this polarity is seldom used. DCEN power is used with helium gas shielding and a thoriated tungsten electrode for welding aluminum-base alloys. This negative electrode polarity provides a deep, narrow melting pattern, which is advantageous for repair of thick weldments or castings and for increased welding speeds in all thicknesses. Higher as-welded strength is obtained with DCEN-GTA welds in the heat treatable aluminum alloys due to the reduced heat input compared to AC-GTAW.

Since no arc cleaning action occurs in the DCEN arc, special attention must be given to minimizing the oxide thickness immediately before welding, such as mechanical scraping or arc cleaning all base metal surfaces within the fusion zone.

A7. Description and Intended Use of Aluminum Electrodes and Rods

A7.1 The selection of the proper classification of filler metal depends primarily on the aluminum alloy used in the parts to be welded; and secondly on the welding process, the geometry of the joints, the resistance to corrosion required in service, and on the finish or appearance desired on the welded part. For example, welded vessels for holding hydrogen peroxide require special aluminum alloys, quite frequently a high-purity alloy, in order to have good resistance to corrosion or to prevent contamination of the product contained. In this case, the proper choice of filler metal is an alloy that has at least as high a purity as the base metal. Another example is the foundry welding of castings, where an alloy meeting the composition limits of the castings is, in most cases, the best choice; for example, as in the

repair and fabrication of cast alloys including 206.0, C355.0, A356.0, 357.0, and A357.0.

A7.2 Experience has shown that certain classifications of filler metal are suitable for welding specific base metals and combinations of base metals. These are listed in Table A1. If it is desired to weld other combinations than those listed, they should be evaluated as to suitability for the purpose intended. The alloy combinations listed will be suitable for most environments; some are preferable from one or more standpoints. In the absence of specific information, consultation with the material supplier is recommended. Additional information may be found in the aluminum chapter of Volume 4, Seventh Edition of the *Welding Handbook*.

A7.3 Filler metal in the form of straight lengths and coils without support is used as welding rod with a number of welding processes. These include oxyfuel gas welding, plasma arc welding, and gas tungsten arc welding. The filler metal is usually fed by hand, although mechanized welding in these processes may involve either manual feeding of the welding rod or use of a feeding mechanism.

A7.4 Spooled filler metal is used most commonly as electrode for the gas metal arc welding process. It also is used as filler rod when mechanized feeding systems are employed for gas tungsten arc, plasma-arc welding and other processes. Finite lengths of filler metal can be removed from the spools for use as a high-quality, hand-fed filler rod with manual gas tungsten arc, plasma-arc or oxy-fuel gas welding processes.

A7.5 The cleanliness and minimal surface oxidation of the filler metal are important with all welding processes. Oil, or other organic materials, as well as a heavy oxide film on the rod, will interfere with coalescence of the weld and also are sources of porosity. Because of this, it is necessary to clean the welding rod and electrode before packaging.

A7.6 Proper storage of welding rods and electrodes is essential to avoid contamination which may affect their performance. Packages of filler metal should not be left outdoors or in unheated buildings because the greater variations in temperature and humidity increase the possibility of condensation to create hydrated surface oxides. Experience has demonstrated that undesirable storage conditions may adversely affect filler metal perfor-

mance. Investigation of the effect of storage time on electrode performance indicates that packaged electrodes, stored under good conditions (dry places in heated buildings), are satisfactory after extended storage.

A7.7 Contamination of filler metal from handling or storage may occur. In most cases, the contaminating influences will dictate the cleaning method. The practice of giving the welding rod, if it has been exposed to the shop atmosphere for long periods of time, a rub with stainless steel wool just before welding is quite widely followed.

A8. Special Tests

This specification classifies those aluminum and aluminum alloy filler metals used most extensively at the time of issuance of the specification. It is recognized that supplementary tests may be necessary to determine the suitability of these welding electrodes and rods for applications involving properties not considered in this specification. In such cases, additional tests to determine such specific properties as corrosion resistance, mechanical properties at high and low temperature, wear resistance, and suitability for welding combinations of dissimilar metals may need to be conducted.

A9. Chemical Analysis

The accepted and most widely used method for chemical analysis is ASTM E227, *Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloy by the Point-to-Plane Technique*. This method analyzes a bulk sample and all elements simultaneously. The ASTM E34 standard method prescribes individual test methods for which each element is tested. The ASTM E34 tests methods are used as a referee method if a dispute arises concerning a specific element analysis.

A10. General Safety Considerations

A10.1 Burn Protection. Molten metal, sparks, slag, and hot work surfaces are produced by welding, cutting, and allied processes. These can cause burns if precautionary measures are not used. Workers should wear protective clothing made of

Table A1
Guide to the Choice of Filler Metal for General Purpose Welding

Base Metal	201.0 206.0 224.0	319.0, 333.0, 354.0, 355.0, C355.0	356.0, A356.0, 357.0, A357.0, 413.0, 443.0, A444.0	511.0, 512.0, 513.0, 514.0, 535.0	7004, 7005, 7039, 710.0, 712.0	6009 6010 6070	6005, 6061, 6063, 6101, 6151, 6201, 6351, 6951	5456	5454
1060, 1070, 1080, 1350	ER4145	ER4145	ER4043 ^{a,b}	ER5356 ^{c,d}	ER5356 ^{c,d}	ER4043 ^{a,b}	ER4043 ^b	ER5356 ^d	ER4043 ^{b,d}
1100, 3003, A1c 3003	ER4145	ER4145	ER4043 ^{a,b}	ER5356 ^{c,d}	ER5356 ^{c,d}	ER4043 ^{a,b}	ER4043 ^b	ER5356 ^d	ER4043 ^{b,d}
2014, 2036	ER4145 ^e	ER4145 ^e	ER4145	—	—	ER4145	ER4145	—	—
2219	ER2319 ^a	ER4145 ^e	ER4145 ^{b,c}	ER4043	ER4043	ER4043 ^{a,b}	ER4043 ^{a,b}	—	ER4043 ^b
3004, A1c 3004	—	ER4043 ^b	ER4043 ^b	ER5356 ^f	ER5356 ^f	ER4043 ^b	ER4043 ^{b,f}	ER5356 ^d	ER5356 ^f
5005, 5050	—	ER4043 ^b	ER4043 ^b	ER5356 ^f	ER5356 ^f	ER4043 ^b	ER4043 ^{b,f}	ER5356 ^d	ER5356 ^f
5052, 5652 ⁱ	—	ER4043 ^b	ER4043 ^f	ER5356 ^f	ER5356 ^f	ER4043 ^b	ER5356 ^{c,f}	ER5356 ^f	ER5356 ^f
5083	—	—	ER5356 ^{c,d}	ER5356 ^d	ER5183 ^d	—	ER5356 ^d	ER5183 ^d	ER5356 ^d
5086	—	—	ER5356 ^{c,d}	ER5356 ^d	ER5356 ^d	—	ER5356 ^d	ER5356 ^d	ER5356 ^d
5154, 5254 ⁱ	—	—	ER4043 ^f	ER5356 ^f	ER5356 ^f	—	ER5356 ^f	ER5356 ^f	ER5356 ^f
5454	—	ER4043 ^b	ER4043 ^f	ER5356 ^f	ER5356 ^f	ER4043 ^b	ER5356 ^{c,f}	ER5356 ^f	ER554 ^{c,f}
5456	—	—	ER5356 ^{c,d}	ER5356 ^d	ER5556 ^d	—	ER5356 ^d	ER5356 ^f	ER5556 ^d
6005, 6061, 6063, 6101, 6151, 6201, 6351, 6951	ER4145	ER4145 ^{b,c}	ER4043 ^{b,f,g}	ER5356 ^f	ER5356 ^{c,f}	ER4043 ^{a,b,g}	ER4043 ^{b,f,g}	—	—
6009, 6010, 6070	ER4145	ER4145 ^{b,c}	ER4043 ^{a,b,g}	ER4043	ER4043	ER4043 ^{a,b,g}	—	—	—
7004, 7005, 7039, 710.0, 712.0	—	ER4043 ^b	ER4043 ^{b,f}	ER5356 ^f	ER5356 ^d	—	—	—	—
511.0, 512.0, 513.0, 514.0, 535.0	—	—	ER4043 ^f	ER5356 ^f	—	—	—	—	—
356.0, A356.0, 357.0, A357.0, 413.0, 443.0, A444.0	ER4145	ER4145 ^{b,c}	ER4043 ^{b,h}	—	—	—	—	—	—
319.0, 333.0, 354.0, 355.0, C355.0	ER4145 ^e	ER4145 ^{b,c,h}	—	—	—	—	—	—	—
201.0, 206.0, 224.0	ER2319 ^{a,h}	—	—	—	—	—	—	—	—

(Continued)

Table A1 (Continued)

Base Metal	5154 5254 ⁱ	5086	5083	5052 5652 ^j	5005 5050	3004 Alc. 3004	2219	2036 2036	1100 3003 Alc. 3003	1060 1070 1080 1350
1060, 1070, 1080, 1350	ER5356 ^{c,d}	ER5356 ^d	ER5356 ^d	ER4043 ^{b,d}	ER1100 ^{b,c}	ER4043 ^{b,d}	ER4145 ^{b,c}	ER4145	ER1100 ^{b,c}	ER1188 ^{b,c,h,j}
1100, 3003, Alc 3003	ER5356 ^{c,d}	ER5356 ^d	ER5356 ^d	ER4043 ^{b,d}	ER1100 ^{b,c}	ER4043 ^{b,d}	ER4145 ^{b,c}	ER4145	ER1100 ^{b,c}	
2014, 2036	—	—	—	—	ER4145	ER4145	ER4145 ^c	ER4145 ^e		
2219	ER4043	—	—	ER4043 ^b	ER4043 ^{a,b}	ER4043 ^{a,b}	ER2319 ^a			
3004, Alc 3004	ER5356 ^f	ER5356 ^d	ER5356 ^d	ER5356 ^{c,f}	ER5356 ^{c,f}	ER5356 ^{c,f}				
5005, 5050	ER5356 ^f	ER5356 ^d	ER5356 ^d	ER5356 ^{c,d}	ER5356 ^{c,f}	ER5356 ^{c,f}				
5052, 5652 ⁱ	ER5356 ^f	ER5356 ^d	ER5356 ^d	ER5654 ^{c,f,i}						
5083	ER5356 ^d	ER5356 ^d	ER5183 ^d							
5086	ER5356 ^d	ER5356 ^d								
5154, 5254 ⁱ	ER5654 ^{f,i}									

Notes:

1. Service conditions such as immersion in fresh or salt water, exposure to specific chemicals, or a sustained high temperature (over 150°F (66°C)) may limit the choice of filler metals. Filler metals ER5183, ER5356, ER5556, and ER5654 are not recommended for sustained elevated temperature service.
2. Recommendations in this table apply to gas shielded arc welding processes. For oxyfuel gas welding, only ER1188, ER1100, ER4043, ER4047, and ER4145 filler metals are ordinarily used.
3. Where no filler metal is listed, the base metal combination is not recommended for welding.
 - a. ER4145 may be used for some applications.
 - b. ER4047 may be used for some applications.
 - c. ER4043 may be used for some applications.
 - d. ER5183, ER5356, or ER5556 may be used.
 - e. ER2319 may be used for some applications. It can supply high strength when the weldment is postweld solution heat treated and aged.
 - f. ER5183, ER5356, ER5554, ER5556, and ER5654 may be used. In some cases, they provide: (1) improved color match after anodizing treatment, (2) highest weld ductility, and (3) higher weld strength. ER5554 is suitable for sustained elevated temperature service.
 - g. ER4643 will provide high strength in 1/2 in. (12 mm) and thicker groove welds in 6XXX base alloys when postweld solution heat treated and aged.
 - h. Filler metal with the same analysis as the base metal is sometimes used. The following wrought filler metals possess the same chemical composition limits as cast filler alloys: ER4009 and R4009 as R-C355.0; ER4010 and R4010 as R-A356.0; and R4011 as R-A357.0.
 - i. Base metal alloys 5254 and 5652 are used for hydrogen peroxide service. ER5654 filler metal is used for welding both alloys for service temperatures below 150°F (66°C).
 - j. ER1100 may be used for some applications.

fire resistant material. Pant cuffs, open pockets, or other places on clothing that can catch and retain molten metal or sparks should not be worn. High-top shoes or leather leggings and fire resistant gloves should be worn. Pant legs should be worn over the outside of high-top shoes. Helmets or hand shields that provide protection for the face, neck, and ears, and a head covering to protect the head should be used. In addition, appropriate eye protection should be used.

When welding overhead or in confined spaces, ear plugs to prevent weld spatter from entering the ear canal should be worn in combination with goggles or equivalent to give added eye protection. Clothing should be kept free of grease and oil. Combustible materials should not be carried in pockets. If any combustible substance has been spilled on clothing, a change to clean, fire-resistant clothing should be made before working with open arcs or flame. Aprons, cape-sleeves, leggings, and shoulder covers with bibs designed for welding service should be used.

Where welding or cutting of unusually thick base metal is involved, sheet metal shields should be used for extra protection. Mechanization of highly hazardous processes or jobs should be considered. Other personnel in the work area should be protected by the use of noncombustible screens or by the use of appropriate protection as described in the previous paragraph. Before leaving a work area, hot work pieces should be marked to alert other persons of this hazard. No attempt should be made to repair or disconnect electrical equipment when it is under load. Disconnection under load produces arcing of the contacts and may cause burns or shock, or both. (Note: Burns can be caused by touching hot equipment such as electrode holders, tips, and nozzles. Therefore, insulated gloves should be worn when these items are handled, unless an adequate cooling period has been allowed before touching.)

The following sources are for more detailed information on personal protection:

(1) ANSI/ASC Z49.1, *Safety in Welding and Cutting*, published by the American Welding Society, 550 N. W. LeJeune Road, P. O. Box 351040, Miami, Florida 33135.

(2) *Code of Federal Regulations*, Title 29 Labor, Chapter XVII, Part 1910, OSHA General Industry Standards available from the U. S. Government Printing Office, Washington, DC 20402.

(3) ANSI/ASC Z87.1, *Practice for Occupational and Educational Eye and Face Protection*, Ameri-

can National Standards Institute, 1430 Broadway, New York, NY 10018.

(4) ANSI/ASC Z41.1, *Safety-Toe Footwear*, American National Standards Institute, 1430 Broadway, New York, NY 10018.

A10.2 Electrical Hazards. Electric shock can kill. However, it can be avoided. Live electrical parts should not be touched. The manufacturer's instructions and recommended safe practices should be read and understood. Faulty installation, improper grounding, and incorrect operation and maintenance of electrical equipment are all sources of danger.

All electrical equipment and the workpieces should be grounded. The workpiece lead is not a ground lead. It is used only to complete the welding circuit. A separate connection is required to ground the workpiece. The workpiece should not be mistaken for a ground connection.

The correct cable size should be used, since sustained overloading will cause cable failure and result in possible electrical shock or fire hazard. All electrical connections should be tight, clean, and dry. Poor connections can overheat and even melt. Further, they can produce dangerous arcs and sparks. Water, grease, or dirt should not be allowed to accumulate on plugs, sockets, or electrical units. Moisture can conduct electricity. To prevent shock, the work area, equipment, and clothing should be kept dry at all times. Welders should wear dry gloves and rubber soled shoes, or stand on a dry board or insulated platform.

Cables and connections should be kept in good condition. Improper or worn electrical connections may create conditions that could cause electrical shock or short circuits. Worn, damaged, or bare cables should not be used. Open circuit voltage should be avoided. When several welders are working with arcs of different polarities, or when a number of alternating current machines are being used, the open circuit voltages can be additive. The added voltages increase the severity of the shock hazard.

In case of electric shock, the power should be turned off. If the rescuer must resort to pulling the victim from the live contact, nonconducting materials should be used. If the victim is not breathing, cardiopulmonary resuscitation (CPR) should be administered as soon as contact with the electrical source is broken. A physician should be called and CPR continued until breathing has been restored, or until a physician has arrived. Electrical burns are treated as thermal burns; that is, clean, cold

(iced) compresses should be applied. Contamination should be avoided; the area should be covered with a clean, dry dressing; and the patient should be transported to medical assistance.

Recognized safety standards such as ANSI/ASC Z49.1, *Safety in Welding and Cutting*, and the *National Electrical Code* and *NFPA No. 70*, available from National Fire Protection Association, Batterymarch Park, Quincy, MA 02269, should be followed.

A10.3 Fumes and Gases. Many welding, cutting, and allied processes produce fumes and gases which may be harmful to health. Fumes are solid particles which originate from welding filler metals and fluxes, the base metal, and any coatings present on the base metal. Gases are produced during the welding process or may be produced by the effects of process radiation on the surrounding environment. Management, personnel and welders alike should be aware of the effects of these fumes and gases. The amount and composition of these fumes and gases depend upon the composition of the filler metal and base metal, welding process, flux, current level, arc length, and other factors. Fluxes, used for oxyfuel gas welding of aluminum alloys, are composed primarily of chlorides plus small fluoride additions.

The possible effects of over-exposure range from irritation of eyes, skin, and respiratory system to more severe complications. Effects may occur immediately or at some later time. Fumes can cause symptoms such as nausea, headaches, dizziness, and metal fume fever. The possibility of more serious health effects exists when especially toxic materials are involved. In confined spaces, the shielding gases and fumes might displace breathing air and cause asphyxiation. One's head should always be kept out of the fumes. Sufficient ventilation, exhaust at the arc or flame, or both, should be used to keep fumes and gases from your breathing zone and the general area.

In some cases, natural air movement will provide enough ventilation. Where ventilation may be questionable, air sampling should be used to determine if corrective measures should be applied.

Forced ventilation or exhaust of the welding atmosphere is most desirable when gas metal arc welding with the ER5XXX series aluminum electrodes. The ER5XXX electrodes can create high concentrations of metallic particulates as evidenced by the smokey fumes when GMA welding with these electrodes.

All bare aluminum electrodes possess a compositional control of 0.0008 percent maximum beryllium content. This provides a check by the manufacturer that the filler metal is essentially free of this element and thus avoid the presence of concentrations of this highly toxic metallic particulate during the filler metal transfer across the arc. Since the spooled electrodes are all fabricated as drawn, wrought aluminum wire, the same beryllium control has been applied to all wrought filler metals covered by this ANSI/AWS A5.10 specification where beryllium is not stated as a range (as in R4011). Thus, all wrought aluminum rods except R4011 also possess a 0.0008% Be maximum limit.

When melting the filler metal in the weld pool, as in gas tungsten arc welding, instead of spraying the filler metal across an arc gap, the metallic particulates have been quite low when welding the aluminum alloys. Regardless of this fact however, when welding with R4011 or R-A357.0, which possess beryllium as a deliberately added element, the user should sample the atmosphere under the actual welding conditions to assure that a satisfactory environment exists.

More detailed information on fumes and gases produced by the various welding processes may be found in the following:

(1) The permissible exposure limits required by OSHA can be found in CFR Title 29, Chapter XVII Part 1910. The OSHA *General Industry Standards* are available from the Superintendent of Documents, U. S. Government Printing Office, Washington, DC 20402.

(2) The recommended threshold limit values for these fumes and gases may be found in *Threshold Limit Values for Chemical Substances and Physical Agents in the Workroom Environment*, published by the American Conference of Governmental Industrial Hygienists (ACGIH), 6500 Glenway Avenue, Building D-5, Cincinnati, OH 45211.

(3) The results of an AWS-funded study are available in a report entitled, *Fumes and Gases in the Welding Environment*, available from the American Welding Society, 550 N. W. LeJeune Road, P. O. Box 351040, Miami, Florida 33135.

A10.4 Radiation. Welding, cutting, and allied operations may produce radiant energy (radiation) harmful to health. One should become acquainted with the effects of this radiant energy.

Radiant energy may be ionizing (such as X-rays), or non-ionizing (such as ultraviolet, visible light, or infrared). Radiation can produce a variety of

effects such as skin burns and eye damage, depending on the radiant energy's wavelength and intensity, if excessive exposure occurs.

A10.4.1 Ionizing Radiation. Ionizing radiation is produced by the electron beam welding process. It is ordinarily controlled within acceptance limits by use of suitable shielding enclosing the welding area.

A10.4.2 Non-Ionizing Radiation. The intensity and wavelengths of non-ionizing radiant energy produced depend on many factors, such as the process, welding parameters, electrode and base metal composition, fluxes, and any coating or plating on the base metal. Some processes such as resistance welding and cold pressure welding ordinarily produce negligible quantities of radiant energy. However, most arc welding and cutting processes (except submerged arc when used properly), laser welding and torch welding, cutting, brazing, or soldering can produce quantities of non-ionizing radiation such that precautionary measures are necessary.

Protection from possible harmful effects caused by non-ionizing radiant energy from welding include the following measures:

(1) One should not look at welding arcs except through welding filter plates which meet the requirements of ANSI/ASC Z87.1, *Practice for Occupational and Education Eye and Face Protection*, published by American National Standards Institute, 1430 Broadway, New York, NY 10018. It should be noted that transparent welding curtains are not intended as welding filter plates, but rather are intended to protect a passerby from incidental exposure.

(2) Exposed skin should be protected with adequate gloves and clothing as specified in ANSI/ASC Z49.1, *Safety in Welding and Cutting*, published by American Welding Society, 550 N. W. LeJeune Road, P. O. Box 351040, Miami, Florida 33135.

(3) Reflections from welding arcs should be avoided, and all personnel should be protected from intense reflections. (Note: Paints using pigments of substantially zinc oxide or titanium dioxide have a lower reflectance for ultraviolet radiation.)

(4) Screens, curtains, or adequate distance from aisles, walkways, etc., should be used to avoid exposing passersby to welding operations.

(5) Safety glasses with UV protective side shields

have been shown to provide some beneficial protection from ultraviolet radiation produced by welding arcs.

A10.4.3 Ionizing radiation information sources include:

(1) AWS F2.1-78, *Recommended Safe Practices for Electron Beam Welding and Cutting*, available from the American Welding Society, 550 N. W. LeJeune Road, P. O. Box 351040, Miami, Florida 33135.

(2) Manufacturer's product information literature.

A10.4.4 Non-ionizing radiation information sources include:

(1) J. F. Hinrichs, "Project Committee on Radiation-Summary report," *Welding Journal*, January, 1978.

(2) *Non-Ionizing Radiation Protection Special Study No. 420053-77, Evaluation of the Potential Hazards from Actinic Ultraviolet Radiation Generated by Electric Welding and Cutting Arcs*, available from the National Technical Information Service, Springfield, Virginia 22161. ADA-033768.

(3) *Non-Ionizing Radiation Protection Special Study No. 42-0312-77, Evaluation of the Potential Retina Hazards from Optical Radiation Generated by Electrical Welding and Cutting Arcs*, available from the National Technical Information Service, Springfield, Virginia 22161. ADA-043023.

(4) C. E. Moss and W. E. Murray, "Optical Radiation Levels Produced in Gas Welding, Torch Brazing, and Oxygen Cutting," *Welding Journal*, September 1979.

(5) "Optical Radiation Levels Produced by Air-Carbon Arc Cutting Processes," *Welding Journal*, March 1980.

(6) ANSI Z136.1, *Safe Use of Lasers*, published by American National Standards Institute, 1430 Broadway, New York, New York 10018.

(7) ANSI/ASC Z49.1, *Safety in Welding and Cutting*, published by the American Welding Society, 550 N.W. LeJeune Road, P.O. Box 351040, Miami, Florida 33135.

(8) ANSI/ASC Z87.1, *Practice for Occupational and Educational Eye and Face Protection*, published by American National Standards Institute, 1430 Broadway, New York, New York 10018.

(9) C. E. Moss, "Optical Radiation Transmission Level Through Transparent Welding Curtains," *Welding Journal*, March 1979.

AWS Filler Metal Standards and Related Documents

AWS Designation	Title
FMC	Filler Metal Comparison Charts
A4.2	Standard Procedures for Calibrating Magnetic Instruments to Measure the Delta Ferrite Content of Austenitic Stainless Steel Weld Metal
A4.3	Standard Methods for Determination of the Diffusible Hydrogen Content of Martensitic, Bainitic, and Ferritic Steel Weld Metal Produced by Arc Welding
A5.01	Filler Metal Procurement Guidelines
A5.1	Specification for Carbon Steel Electrodes for Shielded Metal Arc Welding
A5.2	Specification for Carbon and Low Alloy Steel Rods for Oxyfuel Gas Welding
A5.3	Specification for Aluminum and Aluminum Alloy Electrodes for Shielded Metal Arc Welding
A5.4	Specification for Covered Corrosion-Resisting Chromium and Chromium-Nickel Steel Welding Electrodes
A5.5	Specification for Low Alloy Steel Covered Arc Welding Electrodes
A5.6	Specification for Covered Copper and Copper Alloy Arc Welding Electrodes
A5.7	Specification for Copper and Copper Alloy Bare Welding Rods and Electrodes
A5.8	Specification for Filler Metals for Brazing
A5.9	Specification for Corrosion-Resisting Chromium and Chromium-Nickel Steel Bare and Composite Metal Cored and Stranded Welding Electrodes and Welding Rods
A5.10	Specification for Bare Aluminum and Aluminum Alloy Welding Electrodes and Rods
A5.11	Specification for Nickel and Nickel Alloy Welding Electrodes for Shielded Metal Arc Welding
A5.12	Specification for Tungsten Arc Welding Electrodes
A5.13	Specification for Solid Surfacing Welding Rods and Electrodes
A5.14	Specification for Nickel and Nickel Alloy Bare Welding Electrodes and Rods
A5.15	Specification for Welding Electrodes and Rods for Cast Iron
A5.16	Specification for Titanium and Titanium Alloy Welding Electrodes and Rods
A5.17	Specification for Carbon Steel Electrodes and Fluxes for Submerged Arc Welding
A5.18	Specification for Carbon Steel Filler Metals for Gas Shielded Arc Welding
A5.19	Specification for Magnesium Alloy Welding Rods and Bare Electrodes
A5.20	Specification for Carbon Steel Electrodes for Flux Cored Arc Welding
A5.21	Specification for Composite Surfacing Welding Rods and Electrodes
A5.22	Specification for Flux Cored Corrosion-Resisting Chromium and Chromium-Nickel Steel Electrodes
A5.23	Specification for Low Alloy Steel Electrodes and Fluxes for Submerged Arc Welding
A5.24	Specification for Zirconium and Zirconium Alloy Welding Electrodes and Rods
A5.25	Specification for Carbon and Low Alloy Steel Electrodes and Fluxes for Electroslag Welding
A5.26	Specification for Carbon and Low Alloy Steel Electrodes for Electrogas Welding
A5.27	Specification for Copper and Copper Alloy Rods for Oxyfuel Gas Welding
A5.28	Specification for Low Alloy Steel Filler Metals for Gas Shielded Arc Welding
A5.29	Specification for Low Alloy Steel Electrodes for Flux Cored Arc Welding
A5.30	Specification for Consumable Inserts

For additional information, contact the Order Department, American Welding Society, 550 N. W. LeJeune Road, P. O. Box 351040, Miami, Florida 33135.