

**Standard
Welding Procedure
Specification (WPS) for**

**CO₂ Shielded Flux Cored
Arc Welding of Carbon Steel
(M-1/P-1/S-1, Group 1 or 2),
1/8 through 1-1/2 inch Thick,
E70T-1 and E71T-1,
As-Welded Condition**



American Welding Society

Key Words — Welding Procedure Specification,
base metal, allowable joint designs,
filler metal, carbon steel, semi-
automatic, CO₂ shielded flux
cored arc welding

ANSI/AWS B2.1-1-019-94
An American National Standard

Approved by
American National Standards Institute
April 15, 1993

Standard Welding Procedure
Specification (WPS)
CO₂ Shielded Flux Cored Arc Welding of
Carbon Steel (M-1/P-1/S-1, Group 1 or 2)
1/8 through 1-1/2 inch Thick, E70T-1 and E71T-1
As-Welded Condition

Prepared by
AWS Committee on Welding Qualification

Under the Direction of the
AWS Technical Activities Committee

Approved by
AWS Board of Directors

Abstract

This standard contains the essential welding variables for carbon steel in the thickness range of 1/8 through 1-1/2 inch, using semiautomatic CO₂ shielded flux cored arc welding. It cites the base metals and operating conditions necessary to make the weldment, the filler metal specifications, and the allowable joint designs for fillet and groove welds. This WPS was developed primarily for plate and structural applications.



American Welding Society

550 N.W. LeJeune Road, Miami, Florida 33126

Statement on Use of AWS Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute. When AWS standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

International Standard Book Number: 0-87171-428-0

American Welding Society, 550 N.W. LeJeune Road, Miami, Florida 33126

© 1994 by American Welding Society. All rights reserved
Printed in the United States of America

Note: The primary purpose of AWS is to serve and benefit its members. To this end, AWS provides a forum for the exchange, consideration, and discussion of ideas and proposals that are relevant to the welding industry and the consensus of which forms the basis for these standards. By providing such a forum, AWS does not assume any duties to which a user of these standards may be required to adhere. By publishing this standard, the American Welding Society does not insure anyone using the information it contains against any liability arising from that use. Publication of a standard by the American Welding Society does not carry with it any right to make, use, or sell any patented items. Users of the information in this standard should make an independent, substantiating investigation of the validity of that information for their particular use and the patent status of any item referred to herein.

With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. However, such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time by the AWS Welding Qualification Committee. It must be reviewed every five years and if not revised, it must be either reapproved or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are requested and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS Welding Qualification Committee and the author of the comments will be informed of the Committee's response to the comments. Guests are invited to attend all meetings of the AWS Welding Qualification Committee to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the Rules of Operation of the Technical Activities Committee. A copy of these Rules can be obtained from the American Welding Society, 550 N.W. LeJeune Road, Miami, Florida 33126.

Personnel

AWS Committee on Welding Qualification

<i>T. J. Anderson, Chairman</i>	Bechtel Group, Incorporated
<i>D. L. Sprow, Vice Chairman</i>	McDermott, Incorporated
<i>M. J. Houle, Vice Chairman</i>	Welding Engineering Services
<i>D. R. Papenfuss, Vice Chairman</i>	The Boeing Company
<i>L. P. Connor, Secretary</i>	American Welding Society
<i>W. L. Ballis</i>	Columbia Gas Distribution Companies
<i>H. B. Cary</i>	Hobart Brothers Company
<i>J. L. Cooley</i>	Morrison-Knudsen Corporation
<i>P. B. Dickerson**</i>	Aluminum Company of America
<i>W. D. Doty</i>	Doty and Associates
<i>J. J. Falco*</i>	Army Materials and Mechanics Research Center
<i>J. J. Fluckiger</i>	Babcock and Wilcox, Idaho, Inc.
<i>E. H. Gray</i>	U. S. Nuclear Regulatory Commission
<i>J. E. Hinkel</i>	Lincoln Electric Company
<i>R. W. Jackson</i>	Consultant
<i>J. W. McGrew</i>	Babcock and Wilcox
<i>C. L. Null*</i>	Naval Sea Systems Command
<i>A. S. Olivares</i>	The Hartford Steam Boiler Inspection and Insurance Company
<i>G. W. Oyler**</i>	Welding Research Council
<i>S. Panezic</i>	Canadian Welding Bureau
<i>J. J. Sekely</i>	Dick Enterprises, Inc.
<i>A. W. Sindel</i>	C-E Natco
<i>W. R. Smith Sr. ***</i>	Bechtel Group, Incorporated
<i>C. E. Spaeder</i>	Lehigh University
<i>V. W. Sutter</i>	American Welding Institute
<i>G. M. Wisbrock, Jr.</i>	Loral Vought Systems Corporation

*Advisor
 **Retired
 ***Deceased

Foreword

(This Foreword is not a part of the ANSI/AWS B2.1-1-019-94, *Standard Welding Procedure Specification*, but is included for information purposes only.)

The American Welding Society and the Welding Research Council have joined in a cooperative effort to generate standard welding procedures for industry. The need for pretested welding procedures that are supported by adequate test data and that satisfy the technical requirements for the commonly used construction codes and specification has been expressed by many individuals and organizations. The purpose of a welding procedure qualification is to provide test data for assessing the properties of a weld joint.

This Welding Procedure Specification is an outgrowth of the coordinated work of the Welding Procedures Committee of WRC and the Committee on Welding Qualification of the AWS. The Welding Procedures Committee has provided the test data documented on Procedure Qualification Records, which are available from the Welding Research Council.

The welding terms used in this specification shall be interpreted in accordance with the definitions given in the latest edition of ANSI/AWS A3.0, *Standard Welding Terms and Definitions*. Welding symbols shall be those shown in the latest edition of ANSI/AWS A2.4, *Standard Symbols for Welding, Brazing, and Nondestructive Examination*.

The AWS Committee on Welding Qualification was formed in 1979 to provide welding standards concerning the subject of qualification. The primary document developed by this committee is AWS B2.1, *Standard for Welding Procedure and Performance Qualification*. This document established the foundation and framework for Standard Welding Procedure Specifications.

Comments on this publication are most welcome. They should be addressed to: Secretary, AWS Committee on Welding Qualification, American Welding Society, 550 N.W. LeJeune Road, Miami, Florida 33126.

Standard Welding Procedure Specification (WPS)

CO₂ Shielded Flux Cored Arc Welding of Carbon Steel (M-1/P-1/S-1, Group 1 or 2), 1/8 through 1-1/2 inch Thick, E70T-1 and E71T-1, As-Welded Condition

Welding Research Council¹—Supporting PQR Numbers:
003066, 003067, 007008, 007010, 007012, 103030, 103031, 103032,
103033, 103034, 106001, 106002, 200292, 200430, 200763, 200764,
200765, 200767, 200768, 200769, 200770, 200773, 200774, 200775,
200776, 200780, 200781, 200782, 200783, 200784, 200785

Requirements for Application of Standard WPSs

Scope. The data to support this Standard Welding Procedure Specification (WPS) have been derived from the above listed Procedure Qualification Records (PQRs) which were reviewed and validated under the auspices of the Welding Research Council. This Standard WPS is not valid using conditions and variables outside the ranges listed. The American Welding Society considers that this Standard WPS presents information for producing an acceptable weld using the conditions and variables listed. The user needs a significant knowledge of welding and accepts full responsibility for the performance of the weld and for providing the engineering capability, qualified personnel, and proper equipment to implement this Standard Welding Procedure Specification.

Application. This Standard WPS is to be used only as permitted by the applicable fabrication document [such as code, specification, or contract document(s)]. The fabrication document should specify the engineering requirements such as design, need for heat treatment, fabricating tolerances, quality control, and examination and tests applicable to the end product.

User's Responsibility. A Standard WPS does not replace or substitute for fabrication codes, specifica-

tions, contract requirements, or capability and judgment on the part of the user. A Standard WPS is to be used only as permitted by the applicable fabrication code, specification, or contract document.

The ability to produce production welds having properties suitable for the application depends upon supplementing the Standard WPS with appropriate performance qualification tests and sound engineering judgement. The user is responsible for the quality and performance of the final product in accordance with the provisions of the fabrication document.

Supplementary Instructions. To adapt this Standard WPS to a specific application, a user may issue supplementary instructions. Such instructions may consist of tighter fit-up tolerances, higher minimum preheat temperature or any other instructions necessary to produce a weldment that meets the requirements of the fabrication document. These instructions shall not be less restrictive than provided in the Standard WPS.

Safety. Safety precautions shall conform to the latest edition of ANSI/ASC Z49.1, *Safety in Welding and Cutting*, published by the American Welding Society.

This specification may involve hazardous materials, operations, and equipment. The specification does not purport to address all of the safety problems associated with its use. It is the responsibility of the user to establish appropriate safety and health practices. The user should determine the applicability of any regulatory limitations prior to use.

1. Welding Research Council, 345 East 47th Street, New York, NY 10017.

Standard Welding Procedure Specification (WPS)

LIMITATIONS

This procedure is not qualified for Notch Toughness or PWHT applications.
A Constant Voltage (Constant Potential) Welding Power Source is required.

WELDING PROCESSES

Welding Processes: FCAW-G (Flux Cored Arc Welding, Gas-Shielded)
Method of Application: Semiautomatic

BASE METALS

Base Metal:² Carbon Steel, M-1, P-1, or S-1, Group 1 or 2 to M-1, P-1, or S-1, Group 1 or 2
Thickness Range: 1/8 in. through 1-1/2 in. for groove welds,
1/8 in. minimum for fillet welds
Diameter: Groove Welds: 4 in. minimum
Fillet Welds: all diameters

FILLER METALS

Filler Metal Specification:² ANSI/AWS A5.20 or ASME SFA 5.20
A Number 1, F Number 6
Classification: E70T-1 and E71T-1
Deposit Thickness Range: 1-1/2 in. maximum plus reinforcement for groove welds,
1/8 in. through 1-1/2 in. fillet weld size for fillet welds
Supplementary Filler Metal: Not permitted
Supplementary Power: Not permitted

JOINT DESIGNS

Joint Designs: See Figure 1
Backing: When required by Figure 1
Backing Material:² Carbon Steel, M-1, P-1, or S-1, Group 1, 2, or 3. Nonmetallic or nonfusing metal retainers are not permitted

POSITIONS

Permitted Positions: E70T-1: 1G, 2G, 1F, 2F positions
E71T-1: all positions
Vertical Progression: Uphill

PREHEAT AND INTERPASS TEMPERATURES

Preheat Temperature:³ 50°F Minimum
Interpass Temperature:³ 50°F Minimum, 500°F Maximum
Preheat Maintenance: Continuous or special heating not required

2. M, P, and S numbers for base metal and F and A numbers for filler metal and weld metal respectively, are as detailed in AWS B2.1 or ASME *Boiler and Pressure Vessel Code*, Section IX.

3. Preheat and interpass temperatures must be sufficient to prevent crack formation. Temperatures above the minimum shown may be required for highly restrained welds or by the fabrication document(s).

Standard Welding Procedure Specification (WPS)

POSTWELD HEAT TREATMENT

Postweld Heat Treatment: None (Not qualified for PWHT applications)

ELECTRICAL CHARACTERISTICS

Electrode		Current			
Classification	Dia. in.	Volts	Amperes	Polarity	Wire Feed Speed (ipm)
E70T-1 and E71T-1	0.045	24-28	180-280	DCEP (Reverse)	230-440
E70T-1 and E71T-1	0.052	24-29	190-300	DCEP (Reverse)	180-315
E70T-1 and E71T-1	1/16	24-29	210-350	DCEP (Reverse)	120-250
E70T-1 and E71T-1	5/64	26-30	250-400	DCEP (Reverse)	130-300

Pulsing Current: Not permitted
Contact Tube to Work Distance: 3/4 in. ± 1/4 in.
Metal Transfer Mode: Globular or Spray Transfer Mode

GAS

Shielding Gas: Carbon Dioxide
Flow Rate: 30 to 50 ft³/h
Trailing Gas: None
Backing Gas: Not required
Shielding Gas Nozzle Size: 1/2 in. I.D. minimum

TECHNIQUE

Weave or Stringer Bead: Either
Peening: Not required; if used, proceed as permitted by the fabrication document
Initial Cleaning: Chemical or mechanical; joint shall be dry prior to welding
Interpass Cleaning: Mechanical only
Backgouging: Mechanical or thermal when required by Figure 1
Gouging: Mechanical or thermal
Single or Multiple Passes: Either
Maximum Bead Thickness: 1/4 in.

COMPANY NAME _____

In the name of the Company stated above, I accept full responsibility for the application of this Standard WPS for use with:

 Fabrication Document(s): such as Code, Specification or Contract Document


DATE _____ APPROVED BY _____ TITLE _____

Standard Welding Procedure Specification (WPS)

FILLET WELDS: All Joints

GROOVE WELDS: See Joints 1 through 17. Joints having prequalified joint details permitted by the latest edition of ANSI/AWS D1.1, *Structural Welding Code—Steel* are also permitted.


For tubular products, see Joints 1, 2, 6 and 7. In addition, joints having groove designs resulting from end preparations conforming with the latest edition of ANSI/ASME B16.25, *Butt Welding Ends*, are also allowable for application with this WPS.



STRUCTURAL PRODUCTS
 $a = 45^\circ \text{ MIN.}$
 $R = 1/4 \text{ in., } +1/4 - 1/16$
 $f = R/2 \text{ MAX.}$

TUBULAR PRODUCTS
 $a = 60^\circ \text{ MIN.}$
 $R = 3/16 \text{ in., } +1/4 - 1/16$
 $f = R/2 \text{ MAX.}$

JOINT 1




STRUCTURAL PRODUCTS
 $a = 45^\circ \text{ MIN.}$
 $R = 1/4 \text{ in., } +1/4 - 1/16$
 $f = R/2 \text{ MAX.}$

TUBULAR PRODUCTS
 $a = 60^\circ \text{ MIN.}$
 $R = 3/16 \text{ in., } +1/4 - 1/16$
 $f = R/2 \text{ MAX.}$

JOINT 2


Figure 1—Allowable Joint Designs

Standard Welding Procedure Specification (WPS)



$a = 60^\circ \text{ MIN.}$
 $R = 1/8 \text{ in., } +1/16-1/8$
 $f = \text{NOT LIMITED}$

JOINT 3




$a = 60^\circ \text{ MIN.}$
 $R = 1/8 \text{ in., } +1/16-1/8$
 $f = \text{NOT LIMITED}$

JOINT 4


Figure 1 (continued)—Allowable Joint Designs

Standard Welding Procedure Specification (WPS)



a AND b = 60° MIN.
 R = 1/8 in., +1/16-1/8
 f = NOT LIMITED
 S1 = NOT LIMITED
 S2 = NOT LIMITED

JOINT 5




STRUCTURAL PRODUCTS
 a = 45° MIN.
 R = 1/4 in., +1/4 -1/16
 f = R/2 MAX.

TUBULAR PRODUCTS
 a = 60° MIN.
 R = 3/16 in., +1/4 -1/16
 f = R/2 MAX.

JOINT 6

Figure 1 (continued)—Allowable Joint Designs

Standard Welding Procedure Specification (WPS)




STRUCTURAL PRODUCTS

$a = 45^\circ$ MIN.
 $R = 1/4$ in., $+1/4 - 1/16$
 $f = R/2$ MAX.

TUBULAR PRODUCTS

$a = 60^\circ$ MIN.
 $R = 3/16$ in., $+1/4 - 1/16$
 $f = R/2$ MAX.

JOINT 7




$a = 45^\circ$ MIN.
 $R = 1/8$ in., $+1/16 - 1/8$
 $f =$ NOT LIMITED


JOINT 8

Figure 1 (continued)—Allowable Joint Designs

Standard Welding Procedure Specification (WPS)




Standard Welding Procedure Specification (WPS)



$a = 45^\circ$ MIN.
 $R = 1/8$ in., $+1/16-1/8$
 $f =$ NOT LIMITED
 $S1 =$ NOT LIMITED
 $S2 =$ NOT LIMITED

JOINT 11




$a = 45^\circ$ MIN.
 $R = 1/8$ in., $+1/16-1/8$
 $f =$ NOT LIMITED
 $r = 1/4$ in., $+1/8-0$

JOINT 12


Figure 1 (continued)—Allowable Joint Designs

Standard Welding Procedure Specification (WPS)



$a = 45^\circ \text{ MIN.}$
 $R = 1/8 \text{ in., } +1/16-1/8$
 $f = \text{NOT LIMITED}$
 $r = 1/4 \text{ in., } +1/16-1/16$
 $S1 = \text{NOT LIMITED}$
 $S2 = \text{NOT LIMITED}$

JOINT 13




$a = 45^\circ \text{ MIN.}$
 $R = 1/8 \text{ in., } +1/16-1/8$
 $f = \text{NOT LIMITED}$
 $r = 3/8 \text{ in., } +1/16-1/16$

JOINT 14


Figure 1 (continued)—Allowable Joint Designs

Standard Welding Procedure Specification (WPS)



$a = 45^\circ \text{ MIN.}$
 $R = 1/8 \text{ in., } +1/16-1/8$
 $f = \text{NOT LIMITED}$
 $r = 3/8 \text{ in., } +1/16-1/16$

JOINT 15




$a = 45^\circ \text{ MIN.}$
 $R = 1/8 \text{ in., } +1/16-1/8$
 $r = 3/8 \text{ in., } +1/16-1/16$
 $f = \text{NOT LIMITED}$
 $S1 \text{ AND } S2 = \text{NOT LIMITED}$

JOINT 16

Figure 1 (continued)—Allowable Joint Designs

Standard Welding Procedure Specification (WPS)



$a = 45^\circ \text{ MIN.}$
 $R = 1/8 \text{ in., } +1/16-1/8$
 $r = 3/8 \text{ in., } +1/16-1/16$

$f = \text{NOT LIMITED}$
 $S1 = \text{NOT LIMITED}$
 $S2 = \text{NOT LIMITED}$

JOINT 17

Figure 1 (continued)—Allowable Joint Designs

Metric Conversions

in.	mm	°F	°C	ft ³ /h	L/Min
0.045	1.1	50	10	30	15
0.052	1.3	500	260	50	25
1/16	1.6				
5/64	2.0				
1/8	3.2				
3/16	4.8				
1/4	6.4				
1/2	13				
3/4	19				
1-1/2	38				
4	100				