

ANSI/AWS B2.1-1-211-96
An American National Standard

**Standard
Welding Procedure
Specification (WPS) for**

**Gas Tungsten Arc Welding
with Consumable Inserts Followed by
Shielded Metal Arc Welding of Carbon Steel
(M-1/P-1/S-1, Group 1 or 2), 1/8 through
1-1/2 inch Thick, INMs-1, ER70S-2,
and E7018, As-Welded
or PWHT Condition,
Primarily Pipe
Applications**



American Welding Society

Key Words — Welding Procedure Specification,
base metal, allowable joint designs,
consumable insert, filler metal,
carbon steel, manual welding,
gas tungsten arc welding,
shielded metal arc welding

ANSI/AWS B2.1-1-211-96
An American National Standard

Approved by
American National Standards Institute
June 7, 1996

**Standard Welding Procedure
Specification (WPS)
Gas Tungsten Arc (Consumable Insert) Welding
Followed by Shielded Metal Arc Welding of
Carbon Steel (M-1/P-1/S-1, Group 1 or 2)
1/8 through 1-1/2 inch Thick,
INMs-1, ER70S-2, and E7018
As-Welded or PWHT Condition**

Prepared by
AWS Committee on Welding Qualification

Under the Direction of the
AWS Technical Activities Committee

Approved by
AWS Board of Directors

Abstract

This standard contains the essential welding variables for carbon steel in the thickness range of 1/8 through 1-1/2 inch, using manual gas tungsten arc welding with consumable inserts, followed by shielded metal arc welding. It cites the base metals and operating conditions necessary to make the weldment, the filler metal specifications, and the allowable joint designs for fillet and groove welds. This WPS was developed primarily for pipe applications.



American Welding Society

550 N.W. LeJeune Road, Miami, Florida 33126

Statement on Use of AWS Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute. When AWS standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

International Standard Book Number: 0-87171-498-1

American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126

© 1996 by American Welding Society. All rights reserved
Printed in the United States of America

Note: The primary purpose of AWS is to serve and benefit its members. To this end, AWS provides a forum for the exchange, consideration, and discussion of ideas and proposals that are relevant to the welding industry and the consensus of which forms the basis for these standards. By providing such a forum, AWS does not assume any duties to which a user of these standards may be required to adhere. By publishing this standard, the American Welding Society does not insure anyone using the information it contains against any liability arising from that use. Publication of a standard by the American Welding Society does not carry with it any right to make, use, or sell any patented items. Users of the information in this standard should make an independent, substantiating investigation of the validity of that information for their particular use and the patent status of any item referred to herein.

With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. However, such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time by the AWS Welding Qualification Committee. It must be reviewed every five years and if not revised, it must be either reapproved or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are requested and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS Welding Qualification Committee and the author of the comments will be informed of the Committee's response to the comments. Guests are invited to attend all meetings of the AWS Welding Qualification Committee to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the Rules of Operation of the Technical Activities Committee. A copy of these Rules can be obtained from the American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126.

Personnel

AWS Committee on Welding Qualification

<i>J. J. Sekely, Chairman</i>	Eichleay Corporation
<i>G. M. Wisbrock, Jr., Vice Chairman</i>	Loral Vought Systems
<i>J. J. Fluckiger, 2nd Vice Chairman</i>	Lockheed Idaho Technologies Company
<i>P. B. Dickerson, 3rd Vice Chairman</i>	Consultant
<i>L. P. Connor, Secretary</i>	American Welding Society
<i>T. J. Anderson</i>	Bechtel Group, Incorporated
<i>W. L. Ballis</i>	Columbia Gas Distribution Companies
<i>H. B. Cary</i>	Consultant
<i>J. L. Cooley</i>	Morrison-Knudsen Corporation
<i>W. D. Doty</i>	Doty and Associates
<i>K. W. Fordyce</i>	Elliot Company
<i>E. H. Gray</i>	US NRC Region 1
<i>J. E. Hinkel</i>	The Lincoln Electric Company
<i>M. J. Houle</i>	Welding Engineering Services
<i>R. W. Jackson</i>	Consultant
<i>A. W. Johnson</i>	A. W. Johnson and Associates
<i>N. Kanaya</i>	BEAR Testing Laboratory
<i>R. A. LaFave</i>	Elliot Company
<i>B. B. MacDonald</i>	United Association
<i>J. W. McGrew</i>	Babcock and Wilcox
<i>C. L. Null*</i>	Naval Sea Systems Command
<i>A. S. Olivares</i>	The Hartford Steam Boiler Inspection and Insurance Company
<i>G. W. Oyler</i>	Consultant
<i>S. Panzic</i>	Canadian Welding Bureau
<i>J. B. Shore</i>	Brooks Automation
<i>A. W. Sindel</i>	Sindel and Associates
<i>C. E. Spaeder</i>	Aristech Chemical Corporation
<i>D. L. Sprow**</i>	McDermott, Incorporated

*Advisor

**Retired

Foreword

(This Foreword is not a part of the ANSI/AWS B2.1-1-211-96, *Standard Welding Procedure Specification (WPS)*, but is included for information purposes only.)

The American Welding Society and the Welding Research Council have joined in a cooperative effort to generate standard welding procedures for industry. The need for pretested welding procedures that are supported by adequate test data and that satisfy the technical requirements for the commonly used construction codes and specifications has been expressed by many individuals and organizations. The purpose of a welding procedure qualification is to provide test data for assessing the properties of a weld joint.

This Welding Procedure Specification is an outgrowth of the coordinated work of the Welding Procedures Committee of WRC and the Committee on Welding Qualification of the AWS. The summaries of Procedure Qualification Records are available from the Welding Research Council, Room 1301, 345 E. 47 St., New York, NY 10017.

The welding terms used in this specification shall be interpreted in accordance with the definitions given in the latest edition of ANSI/AWS A3.0, *Standard Welding Terms and Definitions*. Welding symbols shall be those shown in the latest edition of ANSI/AWS A2.4, *Standard Symbols for Welding, Brazing, and Nondestructive Examination*.

The AWS Committee on Welding Qualification was formed in 1979 to provide welding standards concerning the subject of qualification. The primary document developed by this committee is AWS B2.1, *Standard for Welding Procedure and Performance Qualification*. This document established the foundation and framework for Standard Welding Procedure Specifications.

Comments on this publication will be most welcome. They should be addressed to the Secretary, AWS Committee on Welding Qualification, American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126.

Standard Welding Procedure Specification (WPS)

Gas Tungsten Arc Welding (Consumable Inserts) Followed by Shielded Metal Arc Welding of Carbon Steel (M-1/P-1/S-1, Group 1 or 2), 1/8 through 1-1/2 inch Thick, INMs-1, ER70S-2, and E7018, As-Welded or PWHT Condition, Primarily Pipe Applications

Welding Research Council¹—Supporting PQR Numbers:

001002, 001007, 001010, 001013, 001014, 001015, 001017, 001024, 001038, 005031, 200266, 200267, 200268, 200269, 200270, 200272, 200273, 200274, 200275, 200530, 200531, 200532, 200534, 200535, 200625, 200626, 200627, 200628, 200629, 200630, 200631, 200632, 200633, 200634, 200635, 200636, 200637, 200638, 200639, 200708, 200709, 200710, 200711, 200712, 200713, 200728, 200835, 200850, 200851, 200852, 001A, 002A, 003B, 004A, 029A, 030A

Requirements for Application of Standard WPSs

Scope. The data to support this Standard Welding Procedure Specification (WPS) have been derived from the above listed Procedure Qualification Records (PQRs) which were reviewed and validated under the auspices of the Welding Research Council. This Standard WPS is not valid using conditions and variables outside the ranges listed. The American Welding Society considers that this Standard WPS presents information for producing an acceptable weld using the conditions and variables listed. The user needs a significant knowledge of welding and accepts full responsibility for the performance of the weld and for providing the engineering capability, qualified personnel, and proper equipment to implement this Standard WPS.

Application. This Standard WPS is to be used only as permitted by the applicable fabrication document(s) [such as code, specification, or contract document(s)]. The fabrication document(s) should specify the engineering requirements such as design, need for heat treatment, fabricating tolerances, quality control, and examination and tests applicable to the end product.

User's Responsibility. A Standard WPS does not replace or substitute for fabrication codes, specifica-

tions, contract requirements, or capability and judgment on the part of the user. A Standard WPS is to be used only as permitted by the applicable fabrication code, specification, or contract document.

The ability to produce production welds having properties suitable for the application depends upon supplementing the Standard WPS with appropriate performance qualification tests and sound engineering judgment. The user is responsible for the quality and performance of the final product in accordance with the provisions of the fabrication document(s).

Supplementary Instructions. To adapt this Standard WPS to a specific application, a user may issue supplementary instructions. Such instructions may consist of tighter fit-up tolerances, higher minimum preheat temperature or any other instructions necessary to produce a weldment that meets the requirements of the fabrication document(s). These instructions shall not be less restrictive than provided in the Standard WPS.

Safety. Safety precautions shall conform to the latest edition of ANSI Z49.1, *Safety in Welding, Cutting, and Allied Processes*, published by the American Welding Society.

This specification may involve hazardous materials, operations, and equipment. The specification does not purport to address all of the safety problems associated with its use. It is the responsibility of the user to establish appropriate safety and health practices. The user should determine the applicability of any regulatory limitations prior to use.

1. Welding Research Council, 345 East 47th Street, New York, NY 10017.

Standard Welding Procedure Specification (WPS)

LIMITATIONS

This procedure is not qualified for Notch Toughness applications. This WPS is not applicable for fillet welds.

WELDING PROCESSES

Welding Processes: GTAW (Gas Tungsten Arc Welding) followed by SMAW (Shielded Metal Arc Welding)
Method of Application: Manual

BASE METALS

Base Metal:² Carbon Steel, M-1, P-1, or S-1, Group 1 or 2 to M-1, P-1, or S-1, Group 1 or 2
Thickness Range: 1/8 in. through 1-1/2 in. for groove welds
Pipe Diameter: All diameters

FILLER METALS

Filler Metal Specification:² ANSI/AWS A5.30 or ASME SFA 5.30 for Consumable Inserts, ANSI/AWS A5.18 or ASME SFA 5.18 for Filler Rod, ANSI/AWS A5.1 or ASME SFA 5.1 for Electrode, A Number 1, F Number 6 for GTAW, and F Number 4 for SMAW
Classification: INMs-1, Class 1 Insert through Class 5 Insert, ER70S-2, and E7018
Deposit Thickness Range: 1-1/2 in. maximum plus reinforcement
Consumable Inserts: Required

JOINT DESIGNS

Joint Designs: See Figure 1
Backing: Consumable Insert only
Backing Material:² Carbon Steel weld metal; nonmetallic or nonfusing metal retainers are not permitted

POSITIONS

Permitted Positions: All, except as noted
Vertical Progression: Uphill

PREHEAT AND INTERPASS TEMPERATURES

Preheat Temperature:³ 50°F Minimum
Interpass Temperature:³ 50°F Minimum, 500°F Maximum
Preheat Maintenance: Continuous or special heating is not required

GAS

Torch Shielding Gas: Welding Grade Argon
Flow Rate: 12 to 25 ft³/h
Root Shielding Gas: Welding Grade Argon. When introducing root shielding gas to initiate the purge; it is necessary to have at least a 6 volume change of atmosphere within the purged zone prior to welding. Root shielding gas shall remain in place until the weld is completed or at least 3/16" weld metal has been deposited.
Flow Rate: A typical flow rate of 5 to 15 ft³/h may be varied depending on component configuration
Torch Gas Nozzle Size: 1/4 to 3/4 in. inside diameter
Trailing Gas: None

2. M, P, and S numbers for base metal and F and A numbers for filler metal and weld metal respectively, are as detailed in AWS B2.1 and ASME *Boiler and Pressure Vessel Code*, Section IX.

3. Preheat and interpass temperatures must be sufficient to prevent crack formation. Temperatures above the minimum shown may be required for highly restrained welds or by the fabrication document(s).

Standard Welding Procedure Specification (WPS)

TUNGSTEN ELECTRODES

Type:

ANSI/AWS A5.12 or ASME SFA 5.12, EWTh-2, EWCe-2, or EWLa-1

Size:

0.060 through 0.125 in. diameter sharpened to a blunt point

ELECTRICAL CHARACTERISTICS

GROOVE WELDS				
Filler Metal			Current	
Layer	Classification	Size (in.)	Amperes ¹	Polarity
Root ³	INMs-1	1/16, 1/8, or 5/32	65-120	DCEN (Straight)
Fill	ER70S-2	1/16	60-100	DCEN (Straight)
Fill	ER70S-2	3/32	80-140	DCEN (Straight)
Fill	ER70S-2	1/8	100-160	DCEN (Straight)
Layer	Classification ²	Size (in.)	Amperes	Polarity
Fill	E7018	3/32	70-100	DCEP (Reverse)
Fill	E7018	1/8	115-165	DCEP (Reverse)
Fill	E7018	5/32	150-220	DCEP (Reverse)
Fill	E7018	3/16 ³	200-275	DCEP (Reverse)

1. Values not to exceed capacity of tungsten electrodes.
 2. The care and storage of electrodes shall be as recommended by the electrode manufacturer to ensure that the low-hydrogen characteristics are maintained.
 3. Flat and Horizontal positions only.

Pulsing Current:

Not permitted

POSTWELD HEAT TREATMENT (PWHT)

Postweld Heat Treatment:

Welds may either be as-welded or postweld heat treated at 1100 to 1200°F or as required by the fabrication document(s). If heat treated, the heat treatment time shall be 1 hour per inch of thickness (15 minutes minimum) unless otherwise noted in the fabrication document(s).

TECHNIQUE

Weave or Stringer Bead:

Either

Peening:

Not permitted

Initial Cleaning:

Chemical or mechanical; joint shall be dry prior to welding

Interpass Cleaning:

Mechanical only

Backgouging:

Not applicable

Single or Multiple Passes:

Multiple

Maximum Bead Thickness:

1/4 in.

Repair:

Defects in welds shall be removed by mechanical or thermal methods. The repair cavity may differ in contour and dimension from a normal joint preparation and may present different restraint conditions. Repair of base metal defects shall be in accordance with the requirements of the fabrication document(s)

COMPANY NAME _____

In the name of the Company stated above, I accept full responsibility for the application of this Standard WPS for use with:


 Fabrication Document(s): (such as Code, Specification, or Contract Document)

Dated _____

DATE _____ APPROVED BY _____ TITLE _____

Standard Welding Procedure Specification (WPS)


GROOVE WELDS: For pipe and tubular products, see Joints 1 through 13. In addition, joints having groove designs resulting from end preparations conforming with ASME/ANSI B16.25, *Butt welding Ends*, are also allowable for application with this WPS.



CLASS 1 INSERT

$a = 22-1/2^\circ \pm 2-1/2^\circ$
 $f = 1/16 \text{ in.} \pm 1/32 \text{ in.}$
 $r = 1/8 \text{ in. TO } 3/16 \text{ in. RADIUS}$
 $R = 1/32 \text{ in. MAX}$
 I.D. MISMATCH = $1/32 \text{ in. MAX.}$

JOINT 1




CLASS 1 INSERT

$a = 37-1/2^\circ, \pm 2-1/2^\circ$
 $f = 1/32 \text{ in.} \pm 1/32 \text{ in.}$
 $R = 1/32 \text{ in. MAX.}$
 I.D. MISMATCH = $1/32 \text{ in. MAX.}$

JOINT 2

Figure 1—Allowable Joint Designs


Standard Welding Procedure Specification (WPS)



CLASS 1 INSERT

$a = 22-1/2^\circ \pm 2-1/2^\circ$
 $b = 37-1/2^\circ \pm 2-1/2^\circ$
 $f = 1/16 \text{ in.} \pm 1/32 \text{ in.}$
 $r = 1/8 \text{ in. TO } 3/16 \text{ in. RADIUS}$
 $R = 1/32 \text{ in. MAX.}$
 I.D. MISMATCH = $1/32 \text{ in. MAX.}$

JOINT 3




CLASS 2 INSERT

$a = 22-1/2^\circ \pm 2-1/2^\circ$
 $f = 1/16 \text{ in.} \pm 1/32 \text{ in.}$
 $r = 1/8 \text{ in. TO } 3/16 \text{ in. RADIUS}$
 $R = 1/32 \text{ in. MAX.}$
 I.D. MISMATCH = $1/16 \text{ in. MAX.}$

JOINT 4

Figure 1 (continued) — Allowable Joint Designs


Standard Welding Procedure Specification (WPS)



CLASS 2 INSERT

$a = 37\text{-}1/2^\circ, \pm 2\text{-}1/2^\circ$
 $f = 1/32 \text{ in.} \pm 1/32 \text{ in.}$
 $R = 1/32 \text{ in. MAX.}$
I.D. MISMATCH = $1/16 \text{ in. MAX.}$

JOINT 5




CLASS 2 INSERT

$a = 22\text{-}1/2^\circ \pm 2\text{-}1/2^\circ$
 $b = 37\text{-}1/2^\circ \pm 2\text{-}1/2^\circ$
 $f = 1/16 \text{ in.} \pm 1/32 \text{ in.}$
 $r = 1/8 \text{ in. TO } 3/16 \text{ in. RADIUS}$
 $R = 1/32 \text{ in. MAX.}$
I.D. MISMATCH = $1/16 \text{ in. MAX.}$

JOINT 6

Figure 1 (continued) — Allowable Joint Designs


Standard Welding Procedure Specification (WPS)



CLASS 3 INSERT

$a = 22-1/2^\circ \pm 2-1/2^\circ$
 $f = 1/16 \text{ in.} \pm 1/32 \text{ in.}$
 $r = 1/8 \text{ in. TO } 3/16 \text{ in. RADIUS}$
 $R = 1/32 \text{ in. MAX}$
 I.D. MISMATCH = $1/16 \text{ in. MAX.}$

JOINT 7




CLASS 3 INSERT

$a = 37-1/2^\circ \pm 2-1/2^\circ$
 $f = 1/32 \text{ in.} \pm 1/32 \text{ in.}$
 $R = 1/32 \text{ in. MAX.}$
 I.D. MISMATCH = $1/16 \text{ in. MAX.}$

JOINT 8

Figure 1 (continued) — Allowable Joint Designs


Standard Welding Procedure Specification (WPS)



CLASS 3 INSERT

$a = 22-1/2^\circ \pm 2-1/2^\circ$
 $b = 37-1/2^\circ \pm 2-1/2^\circ$
 $f = 1/16 \text{ in.} \pm 1/32 \text{ in.}$
 $r = 1/8 \text{ in. TO } 3/16 \text{ in. RADIUS}$
 $R = 1/32 \text{ in. MAX.}$
I.D. MISMATCH = $1/16 \text{ in. MAX.}$

JOINT 9




CLASS 4 INSERT


$a = 37-1/2^\circ \pm 2-1/2^\circ$
 $f = 1/16 \text{ in.} \pm 1/32 \text{ in.}$
 $R = 1/32 \text{ in. MAX.}$
I.D. MISMATCH = $1/16 \text{ in. MAX.}$

JOINT 10

Figure 1 (continued) — Allowable Joint Designs

Standard Welding Procedure Specification (WPS)**CLASS 5 INSERT**


$a = 22-1/2^\circ \pm 2-1/2^\circ$
 $f = 1/16 \text{ in.} \pm 1/32 \text{ in.}$
 $r = 1/8 \text{ in. TO } 3/16 \text{ in. RADIUS}$
 $R = 1/32 \text{ in. MAX}$
 I.D. MISMATCH = $1/32 \text{ in. MAX.}$

JOINT 11**CLASS 5 INSERT**

$a = 37-1/2^\circ \pm 2-1/2^\circ$
 $f = 1/32 \text{ in.} \pm 1/32 \text{ in.}$
 $R = 1/32 \text{ in. MAX.}$
 I.D. MISMATCH = $1/32 \text{ in. MAX.}$

JOINT 12**Figure 1 (continued) — Allowable Joint Designs**

Standard Welding Procedure Specification (WPS)



CLASS 5 INSERT

$a = 22-1/2^\circ \pm 2-1/2^\circ$
 $b = 37-1/2^\circ \pm 2-1/2^\circ$
 $f = 1/16 \text{ in.} \pm 1/32 \text{ in.}$
 $r = 1/8 \text{ in. TO } 3/16 \text{ in. RADIUS}$
 $R = 1/32 \text{ in. MAX.}$
 $\text{I.D. MISMATCH} = 1/32 \text{ in. MAX.}$

JOINT 13

Figure 1 (continued) — Allowable Joint Designs

Metric Conversions

in.	mm	°F	°C	ft ³ /h	L/min
1/32	0.8	50	10	5	2.4
0.060	1.5	500	260	12	5.7
1/16	1.6	1100	595	15	7.1
3/32	2.4	1200	650	25	11.8
0.125	3.2				
1/8	3.2				
3/16	4.8				
1/4	6.4				
3/4	19.0				
1	25.4				
1-1/2	38.0				