

**Standard
Welding Procedure
Specification (WPS) for
Shielded Metal Arc
Welding of Carbon Steel, (M-1, Group 1),
10 through 18 Gauge,
in the As-Welded Condition,
With or Without Backing**



American Welding Society

Keywords — Welding procedure specification,
base metals, allowable joint designs,
sheet metal, electrode, carbon steel,
manual shielded metal arc welding

ANSI/AWS B2.1.012-91
An American National Standard

Approved by
American National Standards Institute
August 27, 1991

**Standard Welding Procedure
Specification (WPS)
for Shielded Metal Arc Welding of Carbon Steel,
(M-1, Group 1), 10 through 18 Gauge,
in the As-Welded Condition,
With or Without Backing**

Prepared by
AWS Committee on Welding Qualification

Under the Direction of
AWS Technical Activities Committee

Approved by
AWS Board of Directors

Abstract

This standard contains the essential welding variables for carbon steel in the thickness range of 10 through 18 gauge using manual shielded metal arc welding. It cites the base metals and operating conditions necessary to make the weldment, the filler metal specifications, and the allowable joint designs for fillet welds and groove welds.



American Welding Society

550 N.W. LeJeune Road, P.O. Box 351040, Miami, FL 33135

Statement on Use of AWS Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute. When AWS standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

International Standard Book Number: 0-87171-366-7

American Welding Society, 550 N.W. LeJeune Road, P. O. Box 351040, Miami, Florida 33135

© 1991 by American Welding Society. All rights reserved
Printed in the United States of America

Note: The primary purpose of AWS is to serve and benefit its members. To this end, AWS provides a forum for the exchange, consideration, and discussion of ideas and proposals that are relevant to the welding industry and the consensus of which forms the basis for these standards. By providing such a forum, AWS does not assume any duties to which a user of these standards may be required to adhere. By publishing this standard, the American Welding Society does not insure anyone using the information it contains against any liability arising from that use. Publication of a standard by the American Welding Society does not carry with it any right to make, use, or sell any patented items. Users of the information in this standard should make an independent investigation of the validity of that information for their particular use and the patent status of any item referred to herein.

With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. However, such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time by the AWS Welding Qualification Committee. It must be reviewed every five years and if not revised, it must be either reapproved or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are requested and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS Welding Qualification Committee and the author of the comments will be informed of the committee's response to the comments. Guests are invited to attend all meetings of the AWS Welding Qualification Committee to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the Rules of Operation of the Technical Activities Committee. A copy of these Rules can be obtained from the American Welding Society, 550 N.W. LeJeune Road, P. O. Box 351040, Miami, Florida 33135.

Personnel

AWS Committee on Welding Qualification

<i>T. J. Anderson, Chairman</i>	Bechtel Group, Incorporated
<i>D. L. Sprow, Vice Chairman</i>	McDermott Incorporated
<i>M. J. Houle, Vice Chairman</i>	Welding Engineering Services
<i>D. R. Papenfuss, Vice Chairman</i>	The Boeing Company
<i>F. X. Neary, Secretary</i>	American Welding Society
<i>W. L. Ballis</i>	Columbia Gas Distribution Companies
<i>H. B. Cary</i>	Hobart Brothers Company
<i>J. L. Cooley</i>	Morrison-Knudsen Corporation
<i>P. B. Dickerson**</i>	Aluminum Company of America
<i>W. D. Doty</i>	Doty and Associates, Incorporated
<i>J. J. Fluckiger</i>	Babcock and Wilcox Idaho, Incorporated
<i>E. H. Gray*</i>	U. S. Nuclear Regulatory Commission
<i>J. E. Hinkel</i>	Lincoln Electric Company
<i>R. W. Jackson</i>	Consultant
<i>J. W. McGrew</i>	Babcock and Wilcox
<i>G. E. Metzger</i>	Air Force Materials Laboratory
<i>C. L. Null*</i>	Naval Sea Systems Command
<i>A. S. Olivares</i>	The Hartford Steam Boiler Inspection and Insurance Company
<i>G. W. Oyler**</i>	Welding Research Council
<i>S. Panezic</i>	Canadian Welding Bureau
<i>J. J. Sekely</i>	Dick Enterprises, Inc.
<i>D. J. Schell*</i>	Westinghouse Idaho Nuclear Company, Incorporated
<i>A. W. Sindel</i>	Natco
<i>W. R. Smith, Sr.**</i>	Bechtel Group, Incorporated
<i>C. E. Spaeder</i>	Aristech Chemical Corporation
<i>V. W. Sutter</i>	American Welding Institute
<i>G. M. Wisbrock, Jr.</i>	LTV Missiles and Electronics Group Missiles Division

*Advisor

**Retired

The Committee offers special thanks to G. R. Olejniczak and the National Training Fund for the Sheet Metal and Air Conditioning Industry for their significant contribution in making qualifications of these procedures possible.

Foreword

(This Foreword is not a part of ANSI/AWS B2.1.012-91, *Standard Welding Procedure Specification (WPS)*, but is included for informational purposes only.)

The American Welding Society and the Welding Research Council have joined in a cooperative effort to generate Standard Welding Procedures for industry. The need for tested welding procedures, that are supported by adequate data and that satisfy the technical requirements for the commonly used construction codes and specifications, has been expressed by many individuals and organizations. The purpose of a welding procedure qualification is to provide test data for assessing the properties of a weld joint.

This Welding Procedure Specification is an outgrowth of the coordinated work of the Welding Procedures Committee of WRC and the Committee on Welding Qualification of AWS. Procedure Qualification Records (PQR's) supporting Standard WPS's need not be maintained by the employer and are not provided by AWS. These PQR's are on file at the Welding Research Council. It is the intent that Standard WPS's will make retention and continual review of PQR's by owners, regulatory bodies, inspection agencies and clients unnecessary.

The welding terms used in this specification shall be interpreted in accordance with the definitions given in the latest edition of ANSI/AWS A3.0, *Standard Welding Terms and Definitions*. Welding symbols shall be those shown in the latest edition of ANSI/AWS A2.4, *Standard Symbols for Welding, Brazing, and Nondestructive Examination*.

The AWS Committee on Welding Qualification was formed in 1979 to provide welding standards concerning the subject of qualification. The primary document developed by this Committee is AWS B2.1, *Standard for Welding Procedure and Performance Qualification*. This document established the foundation and framework for Standard Welding Procedure Specifications.

Comments on this publication will be most welcome. They should be addressed to Secretary, AWS Committee on Welding Qualification, American Welding Society, 550 NW LeJeune Road, P.O. Box 351040, Miami, FL 33135.

Standard Welding Procedure Specification (WPS)

Shielded Metal Arc Welding of Carbon Steel, (M-1, Group 1), 10 through 18 Gauge, in the As-Welded Condition, with or without Backing

**Welding Research Council¹ —
Supporting PQR Numbers: 188A, 189A, 190A, 191C, 192A, 193B, 194A,
195A, 196A, 197A, 198A, 199A**

Application

The data to support this Standard Welding Procedure Specification (WPS) have been derived from two or more Procedure Qualification Records (PQR's) completed according to the requirements in AWS B2.1 under the auspices of the Welding Research Council. This standard WPS is not valid using conditions and variables outside the ranges listed. The American Welding Society considers that this Standard WPS presents information for producing an acceptable weld using the conditions and variables listed. The user needs a significant knowledge of welding and accepts full responsibility for the performance of the weld and for providing the engineering capability, qualified personnel, and proper equipment to implement this Standard Welding Procedure Specification.

The referencing fabrication code or specification and the engineering requirements are intended to specify any requirements related to design, need for heat treatment, fabricating, tolerances, quality control, safe welding and testing

practices, and examinations and tests applicable to the end product.

A Standard WPS does not replace or substitute for fabrication codes, specifications, contract requirements, or capability and judgement on the part of the user. A Standard WPS is to be used only as permitted by the applicable fabrication code, specification, or contract document. The ability to produce production welds having properties suitable for the application depends upon supplementing the Standard WPS with appropriate performance qualification tests and sound engineering judgement.

A Standard WPS may be supplemented by attached or referenced information and instructions that may be necessary to make an acceptable weldment.

Safety precautions shall conform to the latest edition of ANSI/ASC Z49.1, *Safety in Welding and Cutting*, published by the American Welding Society.

This specification may involve hazardous materials, operations, and equipment. The specification does not purport to address all of the safety problems associated with its use. It is the responsibility of the user to establish appropriate safety and health practices. The user should determine the applicability of any regulatory limitations prior to use.

1. Welding Research Council, 345 East 47th Street, New York, NY 10017.

Standard Welding Procedure Specification (WPS)

PROCESS:	SMAW (Shielded Metal Arc Welding)
METHOD OF APPLICATION:	Manual
BASE METAL:	Carbon Steel, ² M-1 Group 1 to M-1 Group 1
BASE METAL THICKNESS RANGE:³	Groove Weld: 18 ga. (0.0478 in.) through 10 ga. (0.1345 in.) Fillet Weld: 18 ga. (0.0478 in.) through 10 ga. (0.1345 in.)
WELD METAL THICKNESS RANGE:	Groove Weld: Base metal thickness plus reinforcement, maximum Fillet Weld Leg: Base metal thickness, minimum
MAXIMUM WELD BEAD THICKNESS:	Base metal thickness plus reinforcement
BACKING:	Optional
BACKING MATERIAL:	Carbon Steel, ² M-1
ALLOWABLE JOINT DESIGNS:	See Figure 1
WELDING POSITION:	All
VERTICAL WELDING PROGRESSION:	Optional
PREHEAT TEMPERATURE:	50°F minimum, 120°F maximum
INTERPASS TEMPERATURE:	No maximum
PREHEAT TEMPERATURE MAINTENANCE:	Continuous or special heating not required
POSTWELD HEAT TREATMENT:	None (not qualified for PWHT)
TECHNIQUE:	Beads: Stringer or weave Peening: No Cleaning: Joint shall be dry prior to welding Initial Cleaning: Mechanical or chemical Interpass Cleaning: Mechanical only
SINGLE OR MULTIPLE ELECTRODE:	Single
SINGLE OR MULTIPLE PASS:	Either
FILLER METAL SPECIFICATION:	ANSI/AWS A5.1 ASME SFA 5.1 AWS/ASME ⁴ F Number 3 (E6010), A Number 1 AWS/ASME ⁴ F Number 2 (E6013), A Number 1
CURRENT (Type and Polarity):	DCEP (E6010) DCEN (E6013)

2. Detailed in AWS B2.1.

3. See ASTM Specification for base metal thickness tolerances.

4. As detailed in AWS B2.1 and ASME B&PV Code, Section IX.

Standard Welding Procedure Specification (WPS)

WELDING PARAMETERS:

Base Metal	FILLER METAL		AMPERES	
	Classification	Dia. (in.)	Groove	Fillet
18 ga. }	E 6013	3/32 max	50-60	55-60
17 ga. }			57-68	60-65
16 ga. }			64-76	65-70
15 ga. }			71-84	70-75
14 ga. }			78-92	75-80
13 ga. }			85-100	80-85
12 ga. }	E 6010	1/8 max	92-108	85-90
11 ga. }			101-116	90-95
10 ga. }			110-125	95-100

COMPANY NAME _____

In the name of the Company stated above, I accept full responsibility for the application of this Standard WPS for use with

Fabrication Document

Dated _____

DATE _____ APPROVED BY _____ TITLE _____

Standard Welding Procedure Specification (WPS)




Figure 1 — Allowable Joint Designs

Standard Welding Procedure Specification (WPS)




Figure 1 (Continued) — Allowable Joint Designs

Standard Welding Procedure Specification (WPS)

Metric Conversions

in.	mm	°F	°C
0.0478	1.214	50	10
0.1345	3.416	120	50
3/32	2.4		
1/8	3.2		

AWS Welding Procedure and Performance Qualification Documents

AWS Designation	Title
B2.1-84	Standard for Welding Procedure and Performance Qualification
B2.1.001-90	Standard Welding Procedure Specification for Shielded Metal Arc Welding of Carbon Steel, (M-1/P-1, Group 1 or 2) 3/16 through 7/8 inch in the As-Welded Condition, with or without Backing
B2.1.002-90	Standard Welding Procedure Specification for Gas Tungsten Arc Welding of Carbon Steel, (M-1/P-1, Group 1 or 2), 3/16 through 7/8 inch in the As-Welded Condition, with or without Backing
B2.1.003-90	Standard Welding Procedure Specification for Gas Metal Arc Welding of Galvanized Steel, 10 through 18 Gage, in the As-Welded Condition, with or without Backing
B2.1.004-90	Standard Welding Procedure Specification for Gas Metal Arc Welding of Carbon Steel, (M-1, Group 1), 10 through 18 Gage, in the As-Welded Condition, with or without Backing
B2.1.005-90	Standard Welding Procedure Specification for Gas Metal Arc Welding of Austenitic Stainless Steel, (M-8 or P-8), 10 through 18 Gage, in the As-Welded Condition, with or without Backing
B2.1.006-90	Standard Welding Procedure Specification for Gas Metal Arc Welding of Carbon Steel to Austenitic Stainless Steel, (M-1 to M-8 or P-8), 10 through 18 Gage, in the As-Welded Condition, with or without Backing
B2.1.007-90	Standard Welding Procedure Specification for Gas Tungsten Arc Welding of Galvanized Steel, 10 through 18 Gage, in the As-Welded Condition, with or without Backing
B2.1.008-90	Standard Welding Procedure Specification for Gas Tungsten Arc Welding of Carbon Steel, (M-1, Group 1), 10 through 18 Gage, in the As-Welded Condition, with or without Backing
B2.1.009-90	Standard Welding Procedure Specification for Gas Tungsten Arc Welding of Austenitic Stainless Steel, (M-8/P-8), 10 through 18 Gage, in the As-Welded Condition, with or without Backing
B2.1.010-90	Standard Welding Procedure Specification for Gas Tungsten Arc Welding of Carbon Steel to Austenitic Stainless Steel, (M-1 to M-8 or P-8), 10 through 18 Gage, in the As-Welded Condition, with or without Backing
B2.1.011-91	Standard Welding Procedure Specification for Shielded Metal Arc Welding of Galvanized Steel, 10 through 18 Gauge, in the As-Welded Condition, with or without Backing
B2.1.012-91	Standard Welding Procedure Specification for Shielded Metal Arc Welding of Carbon Steel, (M-1, Group 1), 10 through 18 Gauge, in the As-Welded Condition, with or without Backing
B2.1.013-91	Standard Welding Procedure Specification for Shielded Metal Arc Welding of Austenitic Stainless Steel, (M-8 or P-8), 10 through 18 Gauge, in the As-Welded Condition, with or without Backing
B2.1.014-91	Standard Welding Procedure Specification for Shielded Metal Arc Welding of Carbon Steel to Austenitic Stainless Steel, (M-1 to M-8 or P-8), 10 through 18 Gauge, in the As-Welded Condition with or without Backing
B2.1.015-91	Standard Welding Procedure Specification for Gas Tungsten Arc Welding of Aluminum, (M-22 or P-22), 10 through 18 Gauge, in the As-Welded Condition, with or without Backing

For additional information, contact the Order Department, American Welding Society, 550 N.W. LeJeune Road, P.O. Box 351040, Miami, Florida 33135, phone 1-800-334-9353.