



BS 302 : Part 5 : 1987

UDC 677.721:622.67

© British Standards Institution. No part of this publication may be photocopied or otherwise reproduced without the prior permission in writing of BSI

British Standard

Stranded steel wire ropes

Part 5. Specification for ropes for hauling purposes

Câbles toronnés en acier
Partie 5. Câbles de hâlage — Spécifications

Litzenseile aus Stahldrähten
Teil 5. Förderseile

British Standards Institution

Foreword

This Part of BS 302 has been prepared under the direction of the Mechanical Handling Standards Committee. It is one Part of a combined revision of BS 302 : 1968, BS 236 : 1968, BS 329 : 1968, BS 330 : 1968, BS 365 : 1968 and BS 3530 : 1968, which are withdrawn. BS 302 is now published in six Parts and takes account of both national and international developments since 1968.

This Part (Part 5) specifies requirements for ropes for hauling purposes additional to the general requirements in Part 1. Other Parts specify the additional requirements for other particular uses of ropes:

- Part 2 Specification for ropes for general purposes
- Part 3 Specification for zinc coated ropes for ships
- Part 4 Specification for ropes for lifts
- Part 6 Specification for ropes for mine hoisting

Two further Parts are in preparation, covering larger diameter ropes (64 mm to 205 mm diameter) and higher strength ropes and will be Parts 7 and 8 respectively.

In line with the principles of international standard ISO 2408, published by the International Organization for Standardization (ISO), the constructions are grouped according to the number of outer wires in the strands. The general requirements of BS 302 : Part 1 and the methods used for calculating breaking loads and approximate masses comply with ISO 2408. In respect of individual usages the ropes in Parts 2 and 3 are fully in accordance with ISO 2408 and those in section two of Part 4 are in accordance with ISO 4344. In each of these Parts however, certain additional ropes still in common use in the UK have been included.

In line with current international practice, the term 'zinc coated' has been adopted in this standard in place of 'galvanized'. The terms are synonymous.

Purchasers ordering to BS 302 are advised to specify in their purchasing contract that the manufacturer operate a quality system in compliance with the appropriate Part of BS 5750, or suitable equivalent, to ensure themselves that products claimed to comply with BS 302 consistently achieve the required level of quality.

Wire rope users will find valuable information in the companion publication BS 6570 'Code of practice for the selection, care and maintenance of steel wire ropes'.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Contents

	Page
Foreword	
Committees responsible	
	Inside front cover
	Back cover
Specification	
1 Scope	2
2 Definitions	2
3 Compliance	2
4 Wire rope constructions and sizes	2
5 Material	2
6 Direction of lay	3
7 Lubrication	3
8 Minimum breaking load	3
Tables	
1 Wire rope constructions	2
2 6 x 7 construction group: round strand	4
3 6 x 19 construction group: round strand	5
4 6 x 8 TS construction group: triangular strand	6
5 6 x 22 TS and 6 x 25 TS construction groups: triangular strand	7

Specification

1 Scope

This Part of BS 302 specifies the requirements for round and triangular strand steel wire ropes for hauling purposes and is for use in conjunction with BS 302 : Part 1.

NOTE 1. Information to be supplied by the purchaser on the enquiry and order is given in appendix F of BS 302 : Part 1 : 1987.

NOTE 2. The titles of the publications referred to in this standard are listed on the inside back cover.

2 Definitions

For the purposes of this Part of BS 302, the definitions given in BS 302 : Part 1 apply.

3 Compliance

Ropes in accordance with BS 302 : Part 5 shall comply with this Part and with BS 302 : Part 1.

4 Wire rope constructions and sizes

Constructions and size ranges shall be as given in table 1.

NOTE. In the absence of a precise indication by the purchaser on the enquiry and order, the choice of construction within a group is at the discretion of the supplier.

5 Material

5.1 Wire

5.1.1 General. The wire used for the manufacture of wire ropes in accordance with BS 302 : Part 5, excluding the wire used in the cores of triangular strands, shall comply with BS 2763 as follows.

(a) For man-riding haulage installations: sections one and three.

(b) For other purposes: sections one and two. For these ropes the reverse bend test clause in BS 2763 shall be applied.

5.1.2 Wire finish. The wire shall be Class Z zinc coated or bright. The zinc coating shall comply with BS 2763.

5.1.3 Tensile grades of wire. All wires except king wires, wires comprising the triangular strand core, and wires of the steel main core shall be of 1570 N/mm²* or 1770 N/mm² tensile grade.

For round strand ropes the king wires shall all be of one tensile grade selected from BS 2763.

For triangular strand ropes the strand core wires shall have a minimum tensile strength of 770 N/mm² in cores comprised of solid triangular wires or three round wires, and a minimum tensile strength of 1270 N/mm² in cores built up from more than three round wires.

NOTE. In order to achieve a required triangular shape some low carbon steel wires may be added.

Table 1. Wire rope constructions and sizes

Rope group	Description	Size range (diameter)	Typical construction
6 x 7	Up to 7 outer wires in a strand, one layer of wire over a king wire.	mm 8 to 38	6 x 7 (6/1)
6 x 19	8 to 12 outer wires in a strand two or three layers over a king wire. Wires equal laid.	13 to 44	6 x 19 (9/9/1)
6 x 8 TS	7 to 9 outer wires in a strand. One layer of wire over a single triangular wire or a multi-wire triangular core.	13 to 35	6 x 8 (7/V) 6 x 9 (8/V) 6 x 10 (9/V)
6 x 22 TS 6 x 25 TS	9 to 12 outer wires in a strand. Two layers of wire over a single triangular wire or a multi-wire triangular core.	13 to 48	6 x 22 (9/12/V) 13 mm to 35 mm 6 x 25 (12/12/V) 13 mm to 48 mm

*1 N/mm² = 1 MPa.

5.2 Rope main core

5.2.1 General. The main core of the rope shall be of fibre or steel.

5.2.2 Fibre core. Fibre cores shall comply with 3.2 of BS 302 : Part 1 : 1987.

5.2.3 Steel core. Where a steel core is used, it shall be an independent wire rope (IWRC) for rope sizes of 13 mm diameter and above. For sizes smaller than 13 mm diameter the steel core shall be either an IWRC or a wire strand (WSC).

All wires forming a steel main core, except king wires, shall be one tensile grade.

6 Direction of lay

Ropes shall be of right-hand or left-hand Lang's lay.

NOTE 1. It will need to be stated by the purchaser on his enquiry and order if left-hand lay is required, otherwise right-hand lay will be supplied.

NOTE 2. In the case of haulage ropes in which a long splice is to be made, the aspects of lay length and preforming require to be taken into consideration. The lay length is at the discretion of the manufacturer, but there may be cases when the purchaser will require to nominate the lay length specifically for long splicing purposes.

7 Lubrication

All cores except those of man-made fibre shall be suitably treated. The rope shall be fully lubricated during stranding and closing. All lubricants shall comply with 3.3 of BS 302 : Part 1 : 1987.



NOTE. The degree and type of lubrication should be agreed between the purchaser and the supplier.

8 Minimum breaking load

The minimum breaking loads shall be as given in tables 2 to 5.

NOTE. For guidance, these tables also give approximate masses of ropes, calculated as in C.2 of BS 302 : Part 1 : 1987.

Table 2. 6 x 7 construction group: round strand

Round strand 6 x 7 (6/1)
Fibre core6 x 7 (6/1) WSC
(sometimes referred to as 7 x 7)

Nominal diameter	Minimum breaking force				Minimum breaking load				Approximate mass	
	1570 N/mm ² tensile grade		1770 N/mm ² tensile grade		1570 N/mm ² tensile grade		1770 N/mm ² tensile grade		Fibre cored	Steel cored
	Fibre cored	Steel cored	Fibre cored	Steel cored	Fibre cored	Steel cored	Fibre cored	Steel cored		
mm	kN	kN	kN	kN	t	t	t	t	kg/100 m	kg/100 m
8	33.4	36.1	37.6	40.7	3.40	3.68	3.83	4.15	22.1	24.4
9	42.2	45.7	47.6	51.5	4.30	4.66	4.85	5.25	28.0	30.9
10	52.1	56.4	58.8	63.5	5.31	5.75	5.99	6.47	34.6	38.1
11	63.1	68.2	71.1	76.9	6.43	6.95	7.25	7.84	41.9	46.1
12	75.1	81.2	84.6	91.5	7.66	8.28	8.62	9.33	49.8	54.9
13	88.1	95.3	99.3	107	8.98	9.71	10.1	10.9	58.5	64.4
14	102	110	115	125	10.4	11.2	11.7	12.7	67.8	74.7
16	133	144	150	163	13.6	14.7	15.3	16.6	88.6	97.5
18	169	183	190	206	17.2	18.7	19.4	21.0	112	123
19	188	203	212	229	19.2	20.7	21.6	23.3	125	138
20	208	225	235	254	21.2	22.9	24.0	25.9	138	152
21	230	249	259	280	23.4	25.4	26.4	28.5	153	168
22	252	273	284	308	25.7	27.8	29.0	31.4	167	184
24	300	325	338	366	30.6	33.1	34.5	37.3	199	219
26	352	381	397	430	35.9	38.8	40.5	43.8	234	258
28	409	442	461	498	41.7	45.1	47.0	50.8	271	299
29	438	474	494	534	44.6	48.3	50.4	54.4	291	320
32	534	577	602	651	54.4	58.8	61.4	66.4	354	390
35	639	690	720	778	65.1	70.3	73.4	79.3	424	467
38	753	814	849	918	76.8	83.0	86.5	93.6	500	550

Table 3. 6 x 19 construction group: round strand

Nominal diameter	Minimum breaking force				Minimum breaking load				Approximate mass	
	1570 N/mm ² tensile grade		1770 N/mm ² tensile grade		1570 N/mm ² tensile grade		1770 N/mm ² tensile grade		Fibre cored	Steel cored
	Fibre cored	Steel cored	Fibre cored	Steel cored	Fibre cored	Steel cored	Fibre cored	Steel cored		
mm	kN	kN	kN	kN	t	t	t	t	kg/100 m	kg/100 m
13	87.6	94.5	98.7	106	8.93	9.63	10.1	10.8	61.0	67.3
14	102	110	114	124	10.4	11.2	11.6	12.6	70.8	78.0
16	133	143	150	161	13.6	14.6	15.3	16.4	92.4	102
18	168	181	189	204	17.1	18.5	19.3	20.8	117	129
19	187	202	211	227	19.1	20.6	21.5	23.1	130	144
20	207	224	234	252	21.1	22.8	23.9	25.7	144	159
21	228	246	258	278	23.2	25.1	26.3	28.3	159	176
22	251	271	283	305	25.6	27.6	28.8	31.1	175	193
24	298	322	336	363	30.4	32.8	34.3	37.0	208	229
26	350	378	395	426	35.7	38.5	40.3	43.4	244	269
28	406	438	458	494	41.4	44.6	46.7	50.4	283	312
29	436	470	491	530	44.4	47.9	50.1	54.0	304	335
32	531	572	598	645	54.1	58.3	61.0	65.7	370	408
35	635	685	716	772	64.7	69.8	73.0	78.7	442	488
36	671	724	757	817	68.4	73.8	77.2	83.3	468	516
38	748	807	843	910	76.2	82.3	85.9	92.8	521	575
40	829	894	935	1008	84.5	91.1	95.3	103	578	637
41	871	940	982	1059	88.8	95.8	100	108	607	669
44	1003	1082	1131	1220	102	110	115	124	699	771





Table 5. 6 x 22 TS and 6 x 25 TS construction groups: triangular strand

Nominal diameter	Minimum breaking force				Minimum breaking load				Approximate mass			
	1570 N/mm ² tensile grade				1770 N/mm ² tensile grade				1770 N/mm ² tensile grade			
	Fibre cored	Steel cored	Fibre cored	Steel cored	Fibre cored	Steel cored	Fibre cored	Steel cored	Fibre cored	Steel cored	Fibre cored	Steel cored
mm	kN	kN	kN	kN	t	t	t	t	t	t	kg/100 m	kg/100 m
13	93.1	98.7	105	111	9.49	10.1	10.7	11.3	69.3	75.5	69.3	75.5
14	108	114	122	129	11.0	11.6	12.4	13.1	80.4	87.6	80.4	87.6
16	141	150	159	169	14.4	15.3	16.2	17.2	105	114	105	114
18	179	189	201	213	18.2	19.3	20.5	21.7	133	145	133	145
19	199	211	224	238	20.3	21.5	22.8	24.3	148	161	148	161
20	220	234	249	263	22.4	23.9	25.4	26.8	164	179	164	179
21	243	258	274	290	24.8	26.3	27.9	29.6	181	197	181	197
22	267	283	301	319	27.2	28.8	30.7	32.5	198	216	198	216
24	317	336	358	379	32.3	34.3	36.5	38.6	236	257	236	257
26	373	395	420	445	38.0	40.3	42.8	45.4	277	302	277	302
28	432	458	487	516	44.0	46.7	49.6	52.6	321	350	321	350
29	463	491	522	554	47.2	50.1	53.2	56.5	345	376	345	376
32	564	598	636	674	57.5	61.0	64.8	68.7	420	458	420	458
35	675	715	761	807	68.8	72.9	77.6	82.3	502	548	502	548
36	714	757	805	853	72.8	77.2	82.1	87.0	531	579	531	579
38	796	843	897	951	81.1	85.9	91.4	96.9	592	645	592	645
40	882	934	994	1054	89.9	95.2	101	107	656	715	656	715
44	1067	1131	1203	1275	109	115	123	130	794	865	794	865
48	1270	1346	1431	1517	129	137	146	155	945	1030	945	1030

Publications referred to

- BS 2763 Specification for round carbon steel wire for wire ropes
- BS 5750* Quality systems
Part 2 Specification for manufacture and installation
- BS 6570* Code of practice for the selection, care and maintenance of steel wire ropes
- ISO 2408* Steel wire ropes for general purposes — Characteristics
- ISO 4344* Steel wire ropes for lifts

*Referred to in the foreword only.

BS 302 : Part 5 : 1987

This British Standard, having been prepared under the direction of the Mechanical Handling Standards Committee, was published under the authority of the Board of BSI and comes into effect on 30 June 1987.

© British Standards Institution, 1987

First published, as BS 302, September 1927

First revision, as BS 302 and 621, December 1957

Second revision, as BS 302, May 1968

Third revision, as BS 302 : Part 5, June 1987.

ISBN 0 580 15667 2

The following BSI references relate to the work on this standard:
Committee reference MHE/2 Draft for comment 85/70789 DC

British Standards Institution. Incorporated by Royal Charter, BSI is the independent national body for the preparation of British Standards. It is the UK member of the International Organization for Standardization and UK sponsor of the British National Committee of the International Electrotechnical Commission.

In addition to the preparation and promulgation of standards, BSI offers specialist services including the provision of information through the BSI Library and Standardline Database; Technical Help to Exporters; and other services. Advice can be obtained from the Enquiry Section, BSI, Milton Keynes MK14 6LE, telephone 0908 221166, telex 825777.

Copyright. Users of British Standards are reminded that copyright subsists in all BSI publications. No part of this publication may be

reproduced in any form without the prior permission in writing of BSI. This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols and size, type or grade designations. Enquiries should be addressed to the Publications Manager, BSI, Linford Wood, Milton Keynes MK14 6LE. The number for telephone enquiries is 0908 220022 and for telex 825777.

Contract requirements. A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Revision of British Standards. British Standards are revised, when necessary, by the issue either of amendments or of revised editions. **It is important that users of British Standards should ascertain that they are in possession of the latest amendments or editions.**

Automatic updating service. BSI provides an economic, individual and automatic standards updating service called **PLUS**. Details are available from BSI Enquiry Section at Milton Keynes, telephone 0908 221166, telex 825777.

Information on all BSI publications is in the *BSI Catalogue*, supplemented each month by *BSI News* which is available to subscribing members of BSI and gives details of new publications, revisions, amendments and withdrawn standards. Any person who, when making use of a British Standard, encounters an inaccuracy or ambiguity, is requested to notify BSI without delay in order that the matter may be investigated and appropriate action taken.

Committees responsible for this British Standard

The preparation of this British Standard was entrusted by the Mechanical Handling Standards Committee (MHE/-) to Technical Committee MHE/2, upon which the following bodies were represented:

Associated Offices Technical Committee
Association of Supervisory and Executive Engineers
British Coal
British Ports Association and the National Association of Ports Employers
British Railways Board
British Steel Industry (Wire Section)
Bureau Veritas

Chain Testers Association of Great Britain
Department of the Environment (Property Services Agency)
Federation of Manufacturers of Construction Equipment and Cranes
Federation of Wire Rope Manufacturers of Great Britain
Health and Safety Executive
Institution of Mechanical Engineers
Institution of Mining Engineers
Institution of Mining and Metallurgy
Ministry of Defence
National Association of Lift Makers
Zinc Development Association

Amendments issued since publication

Amd. No.	Date of issue	Text affected

British Standards Institution · 2 Park Street London W1A 2BS · Telephone 01-629 9000 · Telex 266933