

Specification for

Zinc phosphate pigments for paints

Committees responsible for this British Standard

The preparation of this British Standard was entrusted by the Pigments, Paints and Varnishes Standards Policy Committee (PVC/-) to Technical Committee PVC/1, upon which the following bodies were represented:

- Aluminium Powder and Paste Association
- British Cement Association
- British Railways Board
- Chemical Industries' Association
- Oil and Colour Chemists Association
- Paintmakers Association of Great Britain Ltd.
- Titanium Pigment Manufacturers Technical Committee
- Zinc Development Association

This British Standard, having been prepared under the direction of the Pigments, Paints and Varnishes Standards Policy Committee, was published under the authority of the Standards Board and comes into effect on 30 April 1991

© BSI 11-1999

First published February 1975
Second edition April 1991

The following BSI references relate to the work on this standard:
Committee reference PVC/1
Draft for comment 85/51595 DC

ISBN 0 580 19552 X

Amendments issued since publication

Amd. No.	Date	Comments

Contents

	Page
Committees responsible	Inside front cover
National foreword	ii
1 Scope	1
2 Normative references	1
3 Definition	1
4 Classification	1
5 Required characteristics and associated tolerances	1
6 Sampling	1
7 Determination of loss on ignition	2
8 Determination of zinc content	3
9 Determination of phosphate content	3
10 Test report	6
Table 1 — Essential requirements	2
Table 2 — Conditional requirement	2
Publication(s) referred to	Inside back cover

National foreword

This British Standard has been prepared under the direction of the Pigments, Paints and Varnishes Standards Policy Committee. It is identical with ISO 6745:1990 “*Zinc phosphate pigments for paints — Specifications and methods of test*”, published by the International Organization for Standardization (ISO). It supersedes BS 5193:1975, which is withdrawn.

In the first edition of this standard, only one type of product was specified. In this revision, three types are specified, of which type 1 corresponds to the zinc phosphate dihydrate pigment specified in the first edition. The type 3 pigment corresponds to zinc phosphate tetrahydrate, while the type 2 pigment corresponds to mixtures of the other two types. In specifying products for compliance with this standard, users should stipulate the particular type by stating the number and date of this British Standard and the type in the form BS 5193-1:1991 or BS 5193-2:1991 or BS 5193-3:1991.

Except for the degree of hydration, the requirements for the three types are identical, but there are some differences from those specified in the first edition of this standard. The minimum resistivity of the aqueous extract has been reduced to compensate for a change in the pigment dispersion concentration, and evidence has been presented to show that this minimum resistivity satisfactorily restricts the content of chloride and sulphate ions. The maximum permissible residue on sieve has been increased because a sieve of 63 μm mesh aperture size has been replaced by one of 45 μm . Limits on the permissible density have been introduced as a replacement for an unspecified agreed tamped volume.

Cross-references

International Standard	Corresponding British Standard
ISO 787-5:1980	BS 3483 <i>Methods for testing pigments for paints</i> Part B7:1982 <i>Determination of oil absorption value</i> (Identical)
ISO 787-7:1981	Part B3:1982 <i>Determination of residue on sieve</i> (water method, using a manual procedure) (Identical)
ISO 787-9:1981	Part C4:1982 <i>Determination of pH value of an aqueous suspension</i> (Identical)
ISO 787-14:1973	Part C5:1974 <i>Determination of resistivity of aqueous extract</i> (Technically equivalent)
ISO 842:1984	BS 4726:1986 <i>Methods for sampling raw materials for paints and varnishes</i> (Identical)
ISO 3696:1987	BS 3978:1987 <i>Specification for water for laboratory use</i> (Identical)
ISO 4793:1980	BS 1752:1983 <i>Specification for laboratory sintered or fritted filters including porosity grading</i> (Identical)

The Technical Committee has reviewed the provisions of ISO 385-1:1984, ISO 648:1977 and ISO 787-10:1981, to which reference is made in the text, and has decided that they are acceptable for use in conjunction with this standard. ISO 385-1:1984 is related to BS 846:1985, ISO 648:1977 is related to BS 1583:1986, and ISO 787-10:1981 is related to BS 3483-B8:1982.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, pages i to iv, pages 1 to 6, an inside back cover and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

1 Scope

This International Standard specifies the requirements and the corresponding methods of test for zinc phosphate pigments suitable for use in corrosion-inhibiting paints.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 385-1:1984, *Laboratory glassware — Burettes — Part 1: General requirements*.

ISO 648:1977, *Laboratory glassware — One-mark pipettes*.

ISO 787-5:1980, *General methods of test for pigments and extenders — Part 5: Determination of oil absorption value*.

ISO 787-7:1981, *General methods of test for pigments and extenders — Part 7: Determination of residue on sieve — Water method — Manual procedure*.

ISO 787-9:1981, *General methods of test for pigments and extenders — Part 9: Determination of pH value of an aqueous suspension*.

ISO 787-10:1981, *General methods of test for pigments and extenders — Part 10: Determination of density — Pycnometer method*.

ISO 787-14:1973, *General methods of test for pigments — Part 14: Determination of resistivity of aqueous extract (Printed together with Part 13 and Part 17)*.

ISO 842:1984, *Raw materials for paints and varnishes — Sampling*.

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods*.

ISO 4793:1980, *Laboratory sintered (fritted) filters — Porosity grading, classification and designation*.

3 Definition

For the purposes of this International Standard, the following definition applies.

zinc phosphate pigment

a white corrosion-inhibiting pigment consisting either predominantly of zinc phosphate dihydrate $[\text{Zn}_3(\text{PO}_4)_2 \cdot 2\text{H}_2\text{O}]$ or of a mixture of zinc phosphate dihydrate and zinc phosphate tetrahydrate $[\text{Zn}_3(\text{PO}_4)_2 \cdot 4\text{H}_2\text{O}]$ or predominantly of zinc phosphate tetrahydrate, and free from extenders and other pigments

4 Classification

In this International Standard, zinc phosphate pigments are classified as one of the following three types:

Type 1: consisting predominantly of zinc phosphate dihydrate and exhibiting a loss on ignition at 600 °C of greater than 8,5 % (m/m) but less than or equal to 10,0 % (m/m).

Type 2: consisting essentially of a mixture of zinc phosphate dihydrate and zinc phosphate tetrahydrate and exhibiting a loss on ignition at 600 °C of greater than 10,0 % (m/m) but less than or equal to 13,0 % (m/m).

Type 3: consisting predominantly of zinc phosphate tetrahydrate and exhibiting a loss on ignition at 600 °C of greater than 13,0 % (m/m) but less than or equal to 16,0 % (m/m).

NOTE 1 The corrosion-inhibiting properties of the various types of zinc phosphate pigment may differ.

5 Required characteristics and associated tolerances

5.1 For zinc phosphate pigments complying with this International Standard, the essential requirements are specified in Table 1 and the conditional requirement is listed in Table 2. The conditional requirement shall be specified by agreement between the interested parties.

5.2 The agreed reference pigment referred to in Table 2 shall comply with the requirements of Table 1.

6 Sampling

Take a representative sample of the product to be tested, as described in ISO 842.

7 Determination of loss on ignition

7.1 Apparatus

Use ordinary laboratory apparatus and glassware complying with the requirements of the relevant International Standards (see clause 2), together with the following.

7.1.1 Muffle furnace, capable of being maintained at $600\text{ }^{\circ}\text{C} \pm 20\text{ }^{\circ}\text{C}$.

7.1.2 Silica crucible

7.1.3 Balance, capable of weighing to 0,1 mg.

7.2 Procedure

Carry out the determination in duplicate.

Heat the crucible (7.1.2) for 30 min in the muffle furnace (7.1.1), maintained at $600\text{ }^{\circ}\text{C} \pm 20\text{ }^{\circ}\text{C}$. Allow to cool to room temperature in a desiccator containing an active desiccant and weigh the crucible.

Weigh, to the nearest 0,1 mg, approximately 2 g to 3 g of the sample (see clause 6) into the previously ignited and tared crucible. Heat the crucible and test portion for 30 min in the muffle furnace, maintained at $600\text{ }^{\circ}\text{C} \pm 20\text{ }^{\circ}\text{C}$. Allow to cool to room temperature in the desiccator and reweigh. Repeat the heating, cooling and weighing operations until the results of successive weighings do not differ by more than 1 mg.

NOTE 2 Zinc phosphate, especially the dihydrate, is hygroscopic.

Retain the ignited pigment for the determinations described in clause 8 and clause 9.

7.3 Expression of results

Calculate the loss on ignition LI of the pigment, expressed as a percentage by mass, using the equation

$$\text{LI} = \frac{m_0 - m_1}{m_0} \times 100$$

where

m_0 is the mass, in grams, of the test portion before ignition;

m_1 is the mass, in grams, of the test portion after ignition.

If the two determinations differ by more than 0,2 % (m/m), repeat the procedure.

Calculate the mean of two valid determinations and report the result to the nearest 0,1 % (m/m).

Table 1 — Essential requirements

Characteristic	Unit	Requirement			Method of test
		Type 1	Type 2	Type 3	
Loss on ignition, LI	% (m/m)	$8,5 < \text{LI} \leq 10,0$	$10,0 < \text{LI} \leq 13,0$	$13,0 < \text{LI} \leq 16,0$	See clause 7
Zinc content (based on the ignited test portion), $w(\text{Zn})$	% (m/m)	$50,5 \leq w(\text{Zn}) \leq 52,0$			See clause 8
Phosphate content (based on the ignited test portion), $w(\text{PO}_4)$	% (m/m)	$47,0 \leq w(\text{PO}_4) \leq 49,0$			See clause 9
Resistivity of the aqueous extract	$\Omega\text{ m}$	min. 65			ISO 787-14
pH-value of the aqueous suspension	—	$6,0 \leq \text{pH} \leq 8,0$			ISO 787-9
Density, ρ	g/cm^3	$3,0 \leq \rho \leq 3,6$			ISO 787-10
Residue on sieve (45 μm)	% (m/m)	max. 0,5			ISO 787-7

Table 2 — Conditional requirement

Characteristic	Requirement	Method of test
Oil-absorption value	Shall not differ by more than 10 % from that of the agreed reference pigment (see 5.2)	ISO 787-5

8 Determination of zinc content

8.1 Principle

Dissolution of a test portion in hydrochloric acid. Complexometric titration of the zinc with EDTA solution at pH 5,0.

8.2 Reagents

During the analysis, use only reagents of recognized analytical grade and only water of at least grade 3 purity as defined in ISO 3696.

WARNING — Use the reagents in accordance with the appropriate health and safety regulations.

8.2.1 Hydrochloric acid, diluted 1 + 4.

Add 1 part by volume of concentrated hydrochloric acid [approximately 37 % (m/m), $\rho \approx 1,19$ g/ml] to 4 parts by volume of water.

8.2.2 EDTA, standard volumetric solution, $c(\text{EDTA}) = 0,025$ mol/l.

Dissolve 9,306 3 g of disodium ethylenediamine tetraacetate dihydrate (EDTA disodium salt) in water in a 1 000 ml one-mark volumetric flask, dilute to the mark and mix well.

8.2.3 Xylenol orange mixture

Add 1 g of xylenol orange to 100 g of sodium chloride (or potassium nitrate) and mix well.

8.2.4 Hexamethylene tetramine

8.3 Apparatus

Use ordinary laboratory apparatus and glassware complying with the requirements of the relevant International Standards (see clause 2).

8.4 Procedure

Carry out the determination in duplicate.

8.4.1 Preparation of the test solution

Weigh out, to the nearest 0,1 mg, approximately 1 g of pigment which has been freshly ignited as described in 7.2. Boil this test portion with 50 ml of 1 + 4 hydrochloric acid (8.2.1) for 20 min. After cooling to room temperature, transfer the solution to a 500 ml one-mark volumetric flask, dilute to the mark and mix well.

NOTE 3 This test solution is also used for the determination of the phosphate content as described in 9.1.

8.4.2 Determination

Pipette 50 ml of the test solution prepared in 8.4.1 into a 150 ml beaker. Add 0,1 g of xylenol orange mixture (8.2.3), followed by small portions of hexamethylene tetramine (8.2.4) until the colour changes from yellow to pink. Then add an excess of 0,4 g to 0,5 g of hexamethylene tetramine. Afterwards, whilst stirring, titrate with EDTA solution (8.2.2) until the colour just changes to yellow.

8.5 Expression of results

8.5.1 Calculation

Calculate the zinc content $w(\text{Zn})$ of the pigment, expressed as a percentage by mass, using the equation

$$w(\text{Zn}) = \frac{V \times 10 \times 1,6343 \times 10^{-3}}{m_2} \times 100$$

$$= \frac{V \times 1,6343}{m_2}$$

where

V is the volume, in millilitres, of the EDTA solution (8.2.2) used;

m_2 is the mass, in grams, of the test portion;

$1,6343 \times 10^{-3}$ is the factor for the conversion of millilitres of EDTA solution, $c(\text{EDTA}) = 0,025$ mol/l, to grams of Zn.

If the two determinations differ by more than 0,2 % (m/m), repeat the procedure.

Calculate the mean of two valid determinations and report the result to the nearest 0,1 % (m/m).

8.5.2 Precision

No precision data are currently available.

9 Determination of phosphate content

For the determination of the phosphate content, two methods (one gravimetric, the other titrimetric) are specified.

The method to be used shall be agreed on between the interested parties. The gravimetric method (9.1) shall be used as the referee method in cases of dispute.

9.1 Gravimetric method

9.1.1 Principle

Addition of citromolybdate reagent to a portion of the test solution prepared for the determination of zinc content (see 8.4.1) and weighing of the precipitated quinoline phosphomolybdate.

9.1.2 Citromolybdate reagent

Prepare the reagent as follows:

- Dissolve 70 g of disodium molybdate dihydrate ($\text{Na}_2\text{MoO}_4 \cdot 2\text{H}_2\text{O}$) in 150 ml of water.
- Dissolve 60 g of citric acid monohydrate ($\text{C}_6\text{H}_8\text{O}_7 \cdot \text{H}_2\text{O}$) in 150 ml of water and add 85 ml of concentrated nitric acid [approximately 65 % (m/m), $\rho \approx 1,40 \text{ g/ml}$].
- Add solution a) to solution b), mixing continuously during the addition.
- Add 35 ml of concentrated nitric acid, followed by 5 ml of freshly distilled quinoline, to 100 ml of water.
- Pour solution d) into solution c) and mix well. Allow to stand for at least 12 h (for example, overnight) and filter through a sintered-glass filter crucible (9.1.3.1).
- Add 280 ml of acetone to solution e) and dilute to 1 000 ml with water. Keep this solution in a securely stoppered flask and store away from light, but no longer than 1 week.

9.1.3 Apparatus

Use ordinary laboratory apparatus and glassware complying with the requirements of the relevant International Standards (see clause 2), together with the following.

9.1.3.1 Filter crucibles, with sintered-glass disc, grade P 10, complying with the requirements of ISO 4793.

9.1.3.2 Electric oven, capable of being maintained at $250^\circ\text{C} \pm 10^\circ\text{C}$.

9.1.4 Procedure

Carry out the determination in duplicate.

9.1.4.1 Precipitation and filtration

Pipette 25 ml of the test solution (see 8.4.1) into a 400 ml beaker, dilute with 50 ml of water and add 100 ml of citromolybdate reagent (9.1.2).

Place the beaker, covered with a watch-glass, on a hotplate in a fume cupboard. Warm the beaker until its contents reach $75^\circ\text{C} \pm 5^\circ\text{C}$ and maintain at this temperature for about 30 s.

WARNING — In order to avoid coagulation of the precipitate, do not use a flame and do not mix the contents of the beaker, either during the addition of the reagent or during heating.

Allow to cool to room temperature, stirring three or four times with a glass rod during cooling.

Heat a filter crucible (9.1.3.1) for 15 min in the oven (9.1.3.2), maintained at $250^\circ\text{C} \pm 10^\circ\text{C}$. Allow to cool to room temperature in a desiccator containing an active desiccant and weigh to the nearest 0,1 mg. Decant the liquid through the crucible, placed on a filter flask, and wash the precipitate six times, by decantation, using about 30 ml of water each time. Transfer all the precipitate to the filter crucible by means of a jet of water from a wash bottle.

Wash the precipitate four times, removing each portion of water with the aid of suction.

9.1.4.2 Drying and weighing

Place the filter crucible in the oven, maintained at $250^\circ\text{C} \pm 10^\circ\text{C}$.

Fifteen minutes after the temperature in the oven has stabilized, remove the crucible, allow to cool for not more than 30 min in the desiccator containing an active desiccant and weigh to the nearest 0,1 mg. Repeat the heating, cooling and weighing operations until the results of two consecutive weighings do not differ by more than 1 mg.

9.1.5 Expression of results

9.1.5.1 Calculation

Calculate the phosphate content $w(\text{PO}_4)$ of the pigment, expressed as a percentage by mass, using the equation

$$w(\text{PO}_4) = \frac{m_3 \times 20 \times 42,915 \times 10^{-3}}{m_2} \times 100$$

$$= \frac{m_3 \times 85,83}{m_2}$$

where

m_2 is the mass, in grams, of the test portion taken in 8.4.1;

m_3 is the mass, in grams, of the precipitate;

$42,915 \times 10^{-3}$ is the factor for the conversion of grams of quinoline phosphomolybdate to grams of PO_4 .

If the two determinations differ by more than 0,2 % (m/m), repeat the procedure.

Calculate the mean of two valid determinations and report the result to the nearest 0,1 % (m/m).

9.1.5.2 Precision

No precision data are currently available.

9.2 Titrimetric method

9.2.1 Principle

Dissolution of the phosphate contained in the pigment by means of strong cation-exchange resins and subsequent titration of the phosphoric acid formed.

The trivalent phosphoric acid, formed by strong cation-exchange resins in the hydrogen form, can be considered as a mixture of three monovalent acids with dissociation constants $K_1 = 7,5 \times 10^{-3}$ (pH 4,6), $K_2 = 6,2 \times 10^{-8}$ (pH 9,7) and $K_3 = 5 \times 10^{-13}$ (no specific pH).

To minimize interference from other acidic products present, the phosphate content is calculated from the titration of the acid extract between the pH values corresponding to K_1 and K_2 respectively.

9.2.2 Reagents and materials

During the analysis, use only reagents of recognized analytical grade and only water of at least grade 3 purity as defined in ISO 3696.

WARNING — Use the reagents in accordance with the appropriate health and safety regulations.

9.2.2.1 Hydrochloric acid, diluted 1 + 2.

Add 1 part of concentrated hydrochloric acid [approximately 37 % (m/m), $\rho \approx 1,19$ g/ml] to 2 parts by volume of water.

9.2.2.2 Strong cation-exchange resin, in the hydrogen form, of the sulfonated polystyrene resin type, cross-linked with divinyl benzene, in bead form, particle size in the range 300 μm to 1 200 μm .¹⁾

Resins shall be pretreated before use by the following method:

Place the resin on a clean sieve of nominal mesh aperture 250 μm and wash well with water to remove extraneous matter (for example, insoluble pigments from previous determinations).

Regenerate the separated resin by soaking for 24 h with occasional stirring in 1 + 2 hydrochloric acid (9.2.2.1). After regeneration, wash the resin free from acid by shaking with water for several hours, decanting off the water at 30 min intervals and replacing it with fresh water.

9.2.2.3 Mixed indicator solution, consisting of:

methy1 red	0,2 g/l
bromocresol green	0,6 g/l
<i>o</i> -cresolphthalein	2,4 g/l
metanil yellow	0,3 g/l
xylene cyanol FF	0,1 g/l

Prepare the solution as follows:

Warm 0,06 g of bromocresol green, 0,24 g of *o*-cresolphthalein and 0,03 g of metanil yellow with 50 ml of a mixture of 1 part by volume of 95 % (V/V) ethanol and 1 part by volume of water until dissolved. Add 0,01 g of xylene cyanol FF to the warm solution and swirl until dissolved. Cool and transfer the solution to a 100 ml graduated cylinder. Warm 0,02 g of methyl red in 30 ml of acetone until dissolved, and add the solution to the graduated cylinder. Make up to 100 ml with water and mix well.

9.2.2.4 Sodium hydroxide, standard volumetric solution, $c(\text{NaOH}) = 0,2$ mol/l.

9.2.3 Apparatus

Use ordinary laboratory apparatus and glassware complying with the requirements of the relevant International Standards (see clause 2), together with the following.

9.2.3.1 Mechanical shaker

9.2.3.2 Flask, of capacity 250 ml, with stopper.

9.2.3.3 Glass filter funnel

9.2.4 Procedure

Carry out the determination in duplicate.

9.2.4.1 Test portion

Take a test portion, containing approximately 0.35 g to 0.4 g of zinc phosphate, of pigment which has been freshly ignited as described in 7.2. Weigh, to the nearest 1 mg, the test portion and place it into the 250 ml flask (9.2.3.2).

9.2.4.2 Determination

Add 20 g of the wet cation-exchange resin (9.2.2.2) and 100 ml of water to the flask containing the test portion. Stopper the flask and shake for 1 h on the mechanical shaker (9.2.3.1).

Separate the resin and any insoluble pigment by quantitatively transferring the contents of the flask to the glass filter funnel (9.2.3.3) containing a glass-wool plug. Wash with successive 25 ml portions of water until the washings are no longer acid to litmus paper. Collect the filtrate and washings in a 250 ml conical flask.

Add 8 drops of mixed indicator solution (9.2.2.3) and titrate with sodium hydroxide solution (9.2.2.4) until the first hydrogen end-point is reached, as shown by a colour change from red through very pale red to colourless. Note the volume of sodium hydroxide solution used (V_1).

¹⁾ Suitable resins are available commercially.

Continue the titration to the second hydrogen end-point, as shown by a change in colour from colourless through blue-green to violet-blue. Note the volume of sodium hydroxide solution used (V_2).

9.2.4.3 Blank test

Carry out a blank test in parallel with the determination, following the same procedure and using the same reagents as in the determination, but omitting the test portion.

9.2.5 Expression of results

9.2.5.1 Method of calculation

Calculate the phosphate content $w(\text{PO}_4)$ of the pigment, expressed as a percentage by mass, using the equation

$$w(\text{PO}_4) = \frac{[(V_2 - V_1) - (V_4 - V_3)] \times c \times 9,497}{m_4}$$

where

- V_1 is the volume, in millilitres, of sodium hydroxide solution (9.2.2.4) required to reach the first hydrogen end-point with the test solution;
- V_2 is the volume, in millilitres, of sodium hydroxide solution (9.2.2.4) required to reach the second hydrogen end-point with the test solution;
- V_3 is the volume, in millilitres, of sodium hydroxide solution (9.2.2.4) required to reach the first hydrogen end-point in the blank test;
- V_4 is the volume, in millilitres, of sodium hydroxide solution (9.2.2.4) required to reach the second hydrogen end-point in the blank test;
- c is the actual concentration, in moles of NaOH per litre, of the sodium hydroxide solution (9.2.2.4);
- m_4 is the mass, in grams, of the test portion;
- 9,497 is the factor for the conversion of millilitres of sodium hydroxide solution, $c(\text{NaOH}) = 1,000 \text{ mol/l}$, to centigrams of PO_4 .

If the two determinations differ by more than 0,2 % (m/m), repeat the procedure.

Calculate the mean of two valid determinations and report the result to the nearest 0,1 % (m/m).

9.2.5.2 Precision

No precision data are currently available.

10 Test report

The test report shall contain at least the following information:

- a) all details necessary for the identification of the product tested;
- b) a reference to this International Standard (ISO 6745);
- c) whether the phosphate content was determined by the gravimetric (9.1) or the titrimetric (9.2) method;
- d) the results of the tests and whether or not the product complies with the relevant specification limits;
- e) any deviation from the methods of test specified;
- f) the date(s) of the tests.

Publication(s) referred to

See national foreword.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.