

Sanitary tapware — General specification for electrodeposited coatings of Ni-Cr

The European Standard EN 248:2002 has the status of a
British Standard

ICS 91.140.70

National foreword

This British Standard is the official English language version of EN 248:2002. It supersedes BS EN 248:1992 which is withdrawn.

The UK participation in its preparation was entrusted by Technical Committee B/504, Water supply, to Subcommittee B/504/8, Terminal fittings, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this subcommittee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 29 January 2003

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 9 and a back cover.

The BSI copyright date displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

English version

Sanitary tapware - General specification for electrodeposited coatings of Ni-Cr

Robinetterie sanitaire - Spécifications générales des revêtements électrolytiques de Ni-Cr

Sanitärarmaturen - Allgemeine Anordnungen für elektrolytische Ni-Cr-Überzüge

This European Standard was approved by CEN on 2 September 2002.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword	3
1 Scope	4
2 Normative references	4
3 Terms and definitions.....	4
4 Exposed surfaces	4
4.1 Condition of exposed surfaces	4
4.2 Description of possible defects.....	5
4.3 Visual examination before tests.....	5
4.4 Requirements	5
5 Quality of coating.....	5
5.1 Corrosion resistance test - test with neutral saline spray.....	5
5.2 Test for coating adherence - Test for resistance to thermal shock.....	6
Annex A (informative) Image type extract from EN ISO 10289:2001	8
Annex B (informative) Test temperature tolerances in relation to test duration	9

Foreword

This document (EN 248:2002) has been prepared by Technical Committee CEN /TC 164, "Water supply", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2003 and conflicting national standards shall be withdrawn at the latest by April 2003.

This document supersedes EN 248:1989.

In this European Standard Annexes A and B are informative.

This standard complements product standards already published or draft standards being developed by CEN/TC 164/WG 8. (single taps and combination taps thermostatic mixing valves, jet regulators, mechanical mixing valves, waste outlet fittings....) which refer to this standard.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies:

- the condition of the exposed surfaces of tapware ;
- the characteristics (resistance to corrosion, adherence) of the surface coating ;
- the tests for verifying these characteristics.

It applies to all sanitary fittings (supply or waste fittings) which have a metallic Ni-Cr coating, whatever the nature of the substrate material.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN ISO 10289:2001, *Methods for corrosion testing of metallic and other inorganic coatings on metallic substrates - Rating of test specimens and manufactured articles subjected to corrosion tests (ISO 10289:1999)*

ISO 9227, *Corrosion tests in artificial atmospheres - Salt spray tests.*

3 Terms and definitions

For the purposes of this European Standard, the following terms and definitions apply.

3.1 exposed surfaces

outside surfaces of tapware are the surfaces which are visible in use conditions

3.2 surfaces not considered as exposed surfaces :

- a) internal surfaces of, for example operating members, caps, knobs, etc. ;
- b) parts usually or always hidden by another component, e.g. linkage of a waste outlet fitting.

4 Exposed surfaces

4.1 Condition of exposed surfaces

Exposed surfaces shall be protected against corrosion.

4.2 Description of possible defects

The different types of defects found on exposed surfaces are as follows : (See table 1)

Table 1 — Different types of defects

Yellow colour :	Little or no chrome over the nickel
Stains :	Faults under the nickel plating
Pitting or porosity :	Surface faults in the base metal or emission of gas in treatment baths
Blisters :	Bubbles or raised spots on the plated surface
Wheel marks :	Fine or sharp lines that remain after polishing or buffing
Cracks :	Usually caused by "hot spots" in casting or plated surface flakiness
Splashes :	Lack of "flow" in casting or plastic injection
Dullness :	Lack of full shine
Cuts and scratches :	Scratches due to handling or knocks during transport
Burns :	Roughness and grey appearance of surface
Scaliness :	Lack of "consistent cover" and flakiness of plating
Orange-peel" effect :	defect in smoothness (similar to peel of an orange)
Roughness – grain	Metallic impurities in nickel baths

4.3 Visual examination before tests

The exposed surfaces should be examined with the naked eye, from a distance of about 300 mm for approximately 10 s, without any magnifying device, in a light (diffused and not dazzling) of an intensity of 700 Lux to 1 000 Lux.

4.4 Requirements

During examination, the exposed surfaces should not show any of the defects described in Table 1, with the exception of slight yellowish or bluish marks.

5 Quality of coating

5.1 Corrosion resistance test - test with neutral saline spray

5.1.1 General

The test described is a type test (laboratory test), and not a quality control test carried out during manufacture.

5.1.2 Method

Carry out the test under the conditions described in ISO 9227 specifically for the neutral saline-spray test, in the following way.

Subject the partially-dismantled tapware and its accessories to spraying for 200 h minimum, arranging a rest period of (48 ± 1) h halfway through the treatment, ie after the first $100 \text{ h} \pm 1 \text{ h}$ of spraying. During the rest period, maintain the heat of the tank.

For the duration of the tests, the tank should only be opened to check and maintain the conditions, the maximum rest period in spraying being 30 min per day. The heating should not be interrupted; samples under test should not be handled, washed or checked.

After treatment and before visual examination, rinse the test samples in water to remove any salt residue.

After the test, examine the surfaces with the naked eye, for approximately 10 s, from a distance of about 300 mm, without any magnifying device.

5.1.3 Requirements

After completing the salt-spray test, examine the test samples in the conditions specified in EN ISO 10289 in the following way.

Examine the samples in accordance with 4.2 and 4.3.

From this examination, define the area A covered by defects, as a percentage of the total area of the test piece.

This surface area A should be less than or equal to 0,1 % ($A \leq 0,1 \%$). The defects should not exceed a dimension of 0,3 mm. (For an example see annex A an extract from EN ISO 10289:2001 showing a visual representation of the types of fault which correspond to the limit of 0,1 %).

5.2 Test for coating adherence - Test for resistance to thermal shock

5.2.1 General

The test described is a type test (laboratory test) and not a quality control test carried out during manufacture. It applies only to plastic materials with Ni-Cr coating.

5.2.2 Method

The test consists of subjecting samples to a series of thermal shocks, whereby the number of cycles, temperatures and durations are indicated in Table 2. For the defined cycles, the vector for heating and cooling is air. Before the introduction of the samples, all areas of the test environment should be at the set temperature and within the specified tolerance levels.

The test sample shall be subjected to cycles described in Table 2, see also annex B (informative)

Table 2 — Summary of temperatures of heating and cooling condition times of test pieces

Temperature to be reached	Air (70 ± 2) °C
Time for heating and stabilisation	30 min.
Return to ambient temperature	Air (15 ⁺⁵ ₀) °C
Cooling time to ambient temperature	15 min.
Cooling temperature	Air (-30 ⁺⁵ ₀) °C
Cooling time	30 min
Return to ambient temperature	Air (15 ⁺⁵ ₀) °C
Time to re-heat to ambient temperature	15 min
Number of cycles	5

5.2.3 Visual examination after tests

The exposed surfaces shall be examined with the naked eye, from a distance of about 300 mm for approximately 10 s, without any magnifying device, in a light (diffused and not dazzling) of an intensity of 700 Lux to 1 000 Lux.


5.2.4 Requirements

After testing, no cracks, blisters nor loosening of the coating shall be recorded. (The areas used for marking shall be excluded from the test requirements).

Annex A
(informative)

Image type extract from EN ISO 10289:2001

Examples of surfaces with defects representing 0,1 % of the total area of the test sample.



Annex B (informative)

Test temperature tolerances in relation to test duration




Figure B.1 — Test temperature tolerances in relation to test duration

The tests at high and low temperatures are conducted in circulated, dry air.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.