

Non-destructive testing — Ultrasonic examination —

Part 1: General principles

The European Standard EN 583-1:1998, with the incorporation of amendment A1:2003, has the status of a British Standard

ICS 19.100

National foreword

This British Standard is the official English language version of EN 583-1:1998, including amendment A1:2003.

The UK participation in its preparation was entrusted by Technical Committee WEE/46, Non-destructive testing, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible European committee any enquiries on the interpretation, or proposals for change, and keep UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled International Standards Correspondence Index, or by using the Find facility of the BSI Standards Electronic Catalogue.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 10, an inside back cover and a back cover.

This BSI copyright notice displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments
14969	30 April 2004	Changes to foreword and deletion of Annex ZA

This British Standard, having been prepared under the direction of the Engineering Sector Committee, was published under the authority of the Standards Committee, and comes into effect on 15 March 1999

© BSI 30 April 2004

ICS 19.100

Descriptors: non-destructive tests, industrial products, ultrasonic tests, generalities, equipment, adjustment, preparation

English version

Non-destructive testing — Ultrasonic examination — Part 1: General principles

(includes amendment A1:2003)

Essais non destructifs — Contrôle
ultrasonore — Partie 1: Principes généraux
(inclut l'amendement A1:2003)

Zerstörungsfreie Prüfung —
Ultraschallprüfung — Teil 1: Allgemeine
Grundsätze
(enthält Änderung A1:2003)

This European Standard was approved by CEN on 14 October 1998.
Amendment A1 was approved by CEN on 20 November 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart 36, B-1050 Brussels

Foreword

This European Standard has been prepared by Technical Committee CEN/TC 138, Non-destructive testing, the Secretariat of which is held by AFNOR.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

For relationship with EU Directive(s), see informative annex ZA, which is an integral part of this standard.

This standard consists of the following parts:

EN 583-1, *Non-destructive testing — Ultrasonic examination — Part 1: General principles.*

EN 583-2, *Non-destructive testing — Ultrasonic examination — Part 2: Sensitivity and range setting.*

EN 583-3, *Non-destructive testing — Ultrasonic examination — Part 3: Transmission technique.*

EN 583-4, *Non-destructive testing — Ultrasonic examination — Part 4: Examination for imperfections perpendicular to the surface.*

EN 583-5, *Non-destructive testing — Ultrasonic examination — Part 5: Characterization and sizing of imperfections.*

ENV 583-6, *Non-destructive testing — Ultrasonic examination — Part 6: Time-of-flight diffraction technique as a method for detection and sizing of imperfections.*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Foreword to amendment 1

This document EN 583-1:1998/A1:2003 has been prepared by Technical Committee CEN/TC 138, Non-destructive testing, the Secretariat of which is held by AFNOR.

This amendment to the European standard EN 583-1:1998 shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2004, and conflicting national standards shall be withdrawn at the latest by June 2004.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

Contents

1	Scope	3
2	Normative references	3
3	Qualification and certification of personnel	3
4	Information required prior to examination	4
5	Principles of ultrasonic examination	4
6	Equipment	5
7	Settings	7
8	Preparation for examination	8
9	Examination	8
10	Characterization of imperfections	9
11	Examination procedure	9
12	Examination report	10

1 Scope

This standard defines the general principles required for the ultrasonic examination of industrial products that permit the transmission of ultrasound.

The specific conditions of application and use of ultrasonic examination, which depend on the type of product examined, are described in documents which could include:

- product standards;
- specifications;
- codes;
- contractual documents;
- written procedures.

Unless otherwise specified in the referencing documents the minimum requirements of this standard are applicable.

This standard does not define:

- extent of examination and scanning plans;
- acceptance criteria.

2 Normative references

This European Standard incorporates, by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

EN 473, *Qualification and certification of NDT personnel — General principles*.

EN 27963, *Welds in steel — Calibration block No. 2 for ultrasonic examination of welds*. (ISO 7963:1985).

prEN 583-2, *Non-destructive testing — Ultrasonic examination — Part 2: Sensitivity and range setting*¹⁾

EN 583-3, *Non-destructive testing — Ultrasonic examination — Part 3: Transmission technique*.

prEN 12223, *Non-destructive testing — Ultrasonic examination — Specification for calibration block No. 1*¹⁾.

prEN 12668-1, *Non-destructive testing — Characterization and verification of ultrasonic examination equipment — Part 1: Instruments*¹⁾.

prEN 12668-2, *Non-destructive testing — Characterization and verification of ultrasonic examination equipment — Part 2: Probes*¹⁾.

prEN 12668-3, *Non-destructive testing — Characterization and verification of ultrasonic examination equipment — Part 3: Combined equipment*¹⁾.

3 Qualification and certification of personnel

The examination shall be performed by personnel qualified in accordance with EN 473.

The requirements for qualification and certification shall be specified in the product standards and/or other applicable documents.

¹⁾ In preparation.

4 Information required prior to examination

Prior to examination the following information shall be available, as applicable:

- purpose of examination;
- qualification and certification of personnel;
- environmental conditions and state of examination object;
- requirement for a written examination procedure;
- any special requirements for preparation of scanning surface;
- examination volume;
- examination sensitivity and method of setting-up sensitivity;
- requirements for evaluation and recording level;
- acceptance criteria;
- extent of examination including scanning plan;
- requirements for a written examination report.

5 Principles of ultrasonic examination

5.1 General

An ultrasonic examination is based on propagation of ultrasonic waves through the object to be examined, and monitoring either the transmitted signal (termed the transmission technique), or the signal reflected or diffracted from any surface or discontinuity (termed the pulse echo technique).

Both techniques can employ a single probe acting as both transmitter and receiver, or double (twin) transducer probe, or separate transmitting and receiving probes. Similarly, both techniques can involve intermediate reflection from one or more surfaces of the object under examination.

The examination can be performed manually or by the use of semi-automatic or fully automatic equipment, and can use contact, gap or immersion scanning, or other coupling methods adapted to specific problems.

5.2 Vibration mode and direction of sound propagation

The most commonly used types of waves are longitudinal and transverse, and these can be propagated either perpendicularly, or at an angle, to the test surface. Other types of modes, e.g. Lamb waves or Rayleigh waves can also be used for special applications.

The choice of wave mode and direction of propagation will depend on the purpose of the examination, and should take into account the specular nature of reflection from planar reflectors. Except when using Lamb waves, the direction of sound propagation, for single probe pulse echo scanning, should be as nearly perpendicular to the plane of the reflector as possible.

5.3 Transmission technique

This technique is based on measuring the signal attenuation after the passage of an ultrasonic wave through the examination object.

The signal used for measurement can be either:

- a) a back wall echo; or
- b) any other signal transmitted either directly, or after intermediate reflection from the surfaces of the object.

Further details of this technique are contained in EN 583-3.

5.4 Pulse echo technique

This technique utilizes the reflected or diffracted signal from any interface of interest within the object under examination. This signal is characterized by its amplitude and position along the timebase; the latter related to the distance between the reflector and the probe. The location of the reflector is determined from the knowledge of its distance, the direction of sound propagation, and the position of the probe.

It is recommended that the signal amplitude be measured by comparison with either:

- a) a distance amplitude correction (DAC) curve, or a series of DAC curves, obtained by using artificial reflectors (sidedrilled holes, flat-bottomed holes or notches etc.) within one or more reference blocks;
- b) an equivalent reflector diagram (DGS system);
- c) echoes from suitable notches; or
- d) echoes from large planar reflectors perpendicular to the acoustic axis (e.g. back wall echo).

These techniques are described in prEN 583-2.

In order to obtain further information about the shape and size of reflectors, other techniques may be used. Such techniques are based, for example on variations in signal amplitude with movement of the probe, measurement of sound path or frequency analysis.

6 Equipment

6.1 Ultrasonic instrument

The ultrasonic instrument shall fulfil the requirements of prEN 12668-1.

6.2 Ultrasonic probes

The probe shall fulfil the requirements of prEN 12668-2.

6.2.1 Probe selection

The choice of the probe depends on the purpose of the examination and the requirements of the referencing standard or specification. It depends on:

- the material thickness, shape and surface condition;
- the type and metallurgical condition of the examined material;
- the type, position and orientation of imperfections to be identified.

The probe parameters listed in 6.2.2, 6.2.3 and 6.2.4 shall be considered in relation to the characteristics of the examination object stated above.

6.2.2 Frequency and dimensions of transducer

The frequency and dimensions of a transducer determine the shape of the beam (near field and beam divergence). The selection shall assure that the characteristics of the beam are the optimum for the examination by a compromise between the following:

- the near field length which shall remain, whenever possible, smaller than the thickness of the object under examination;

NOTE It is possible to detect imperfections in the near field, but their characterization is less accurate and less reproducible.

- the beam width, which shall be sufficiently small within the examination zone furthest from the probe to maintain an adequate detection level;
- the beam divergence, which shall be sufficiently large to detect planar imperfections that are unfavourably orientated.

Apart from the above considerations the selection of frequency shall take into account the sound attenuation in the material and the reflectivity of imperfections. The higher this frequency, the greater the examination resolution, but the sound waves are more attenuated (or the spurious signals due to the structure are greater). The choice of frequency thus represents a compromise between these two factors. Most examinations are performed at frequencies between 1 MHz and 10 MHz.

6.2.3 Dead zone

The choice of the probe shall take into account the dead zone in relation to the examination volume.

6.2.4 Damping

The selection of probe shall also include consideration of the damping which influences the resolution as well as the frequency spectrum.

6.2.5 Focusing probes

Focusing probes are mainly used for the detection of small defects and for sizing reflectors. Their sound fields should be described by focal zone and focal diameter. Their advantages in relation to unfocussed single crystal probes are an increased lateral resolution and a higher signal to noise ratio. Sensitivity setting has to be carried out by using reference reflectors.

6.3 Coupling media

Different coupling media can be used, but their type shall be compatible with the materials to be examined. Examples are:

- water, possibly containing an agent e.g. wetting, anti-freeze, corrosion inhibitor;
- contact paste;
- oil;
- grease;
- cellulose paste containing water, etc.

The characteristics of the coupling medium shall remain constant throughout the verification, calibration operations and the examination. It shall be suitable for the temperature range in which it will be used.

If the constancy of the characteristics cannot be guaranteed between calibration and examination, a transfer correction may be applied. One method for determining the necessary correction is described in prEN 583-2.

After the examination is completed, the coupling medium shall be removed if its presence is liable to hinder subsequent operations, inspection or use of the object.

6.4 Calibration blocks

The calibration blocks used are defined in standard prEN 12223 and EN 27963.

The stability of calibration can be verified using the blocks above.

6.5 Reference blocks

When amplitudes of echoes from the object are compared with echoes from a reference block, certain requirements relating to the material, surface condition, geometry and temperature of the block shall be observed.

Where possible, the reference block shall be made from a material with acoustic properties which are within a specified range with respect to the material to be examined, and shall have a surface condition comparable to that of the object to be examined. If these characteristics are not the same, a transfer correction shall be applied. A method for determining the necessary correction is described in prEN 583-2.

The geometrical conditions of the reference block and the object under examination shall be considered. For further details, see prEN 583-2.

The geometry of the reference block, its dimensions, and the position of any reflectors, should be indicated on a case-by-case basis in the specific standards and codes. The position and number of reflectors should relate to the scanning of the entire examination zone.

The most commonly used reflectors are:

- a) large planar reflectors, compared to the beam width, perpendicular to the acoustic axis (e.g. back wall);
- b) flat-bottomed holes;
- c) side-drilled holes;
- d) grooves or notches of various cross-sections.

When reference blocks are used for immersion examination the influence of water in the holes shall be considered or the ends of the holes shall be plugged.

The consequences of temperature differences between examination object, probes, and reference blocks, shall be considered and compared to the requirements for the accuracy of the examination. If necessary the reference blocks shall be maintained within the specified temperature range during the examination.

6.6 Specific blocks

In certain cases, specific blocks e.g. with identified natural defects can be used to finalize the examination method and to check the stability of the sensitivity.

7 Settings

7.1 General settings

In the absence of defined instructions in the standards or detailed specifications, it is essential to ensure that:

- suppression shall not be used unless specifically called for by the referencing documents;
- the amplifier is used in an appropriate frequency band;
- filtering is set to give optimum resolution;
- the impedance matching of the examination system is adjusted, if necessary, to obtain a maximum echo height while preserving resolution;
- the pulse energy setting is as low as possible taking the amplification reserve into consideration.

These settings shall be maintained throughout the examination.

The settings shall be made at the start of each examination sequence and then checked periodically at established time intervals and whenever a system parameter is changed or the operator suspects a drift (see prEN 12668-3).

A maximum drift of amplitude and range shall be established. If such maxima are exceeded new settings are required or agreed actions are necessary.

7.2 Range settings

Each range shall be selected to cover the examination zone defined in the relevant standard, procedure or detailed specification.

The time base and delay settings shall be made using a calibration block or by calculation. They shall be verified by ultrasonically checking the location of the reflectors in the reference block.

7.3 Amplification

The amplification and pulse energy settings shall be made using the echoes from artificial reflectors, or from the opposite surface of the reference block or the examination object. They shall be adequate to:

- detect all the imperfections from which the signal exceeds the recording level or other signals of interest defined in the referencing documents;
- evaluate all the imperfection indications, or other signals of interest, by one of the methods described in the relevant standard or by any other methods described in detail specifications associated with the product to be examined.

The amplification settings can be different during the examination for detection, and during evaluation.

For the detection of imperfections by manual examination, the setting shall be such that all signals above the evaluation level, up to the maximum range under examination, are displayed at a minimum of 20 % full screen height or as specified in the reference documents. Methods of setting sensitivity are described in prEN 583-2.

7.4 Pulse repetition frequency

When adjustable, the pulse repetition frequency should be sufficiently high to ensure adequate screen brightness and to detect all relevant signals, whilst being sufficiently low to avoid the production of ghost echoes when working on long path lengths particular in low attenuation materials (see also 9.2.2).

8 Preparation for examination

8.1 Surface preparation

All scanning surfaces shall be free from dirt, loose scale, weld spatter etc., and shall be of sufficiently uniform contour and smoothness that satisfactory acoustic coupling can be maintained. In addition, such features of the surface of the object that may give rise to errors of interpretation shall be removed prior to examination (see prEN 583-2).

8.2 Identification and datum points

Where the reporting of imperfections or other local features is a requirement of the referencing document(s), each object to be examined shall be uniquely identified and an agreed method of referencing shall be used to clearly locate the position of any reportable imperfection. This method can be based on the provision of suitably permanent datum points, or on the use of suitable geometrical features.

8.3 Application of transfer correction

During the evaluation of signals by means of reference blocks, these shall display an ultrasonic wave attenuation, and surface losses, equivalent to that of the examination object.

If not, a transfer correction shall be applied to compensate for differences in the surface losses and material attenuation. Simple methods are proposed in prEN 583-2.

For certain objects of complex shape, coated objects, austenitic steel objects, etc., it can be difficult, or even impossible, to develop an industrial method of equivalence verification. If so, a specific procedure shall be implemented.

For the examination of specific products of relatively low thickness, or whose attenuation is known to be negligible, transfer correction is possibly not necessary.

9 Examination

9.1 Examination coverage

Scanning shall be carried out in accordance with the requirements of the referencing document(s). These requirements shall include the area to be scanned and the scanning direction, and can include the type, size, frequency and beam angle of the probe(s) to be used.

9.2 Overlap and scanning speed

9.2.1 Overlap

For a 100 % examination, the interval between two successive scan lines shall not be greater than the –6 dB beam width at any depth within the examination volume.

9.2.2 Scanning speed

The choice of scanning speed shall take into consideration the pulse repetition frequency and the ability of the operator to recognize or of the instrument to record signals.

In semi-automatic or automatic examination, the maximum scanning speed ($V_{\max}$) is determined by the passage of a reference block beneath the probe, or is calculated from the following equation:

$$V_{\max} = \frac{d \times f_{\text{rep}}}{n} \text{ (mm/s)}$$

where

- d is the minimum beam width at –6 dB, in millimetres (mm) as applicable for the examination;
- f_{rep} is the pulse repetition frequency in hertz (Hz);
- n is the number of consecutive signals of an indication before alarm.

9.3 Evaluation and recording levels

The evaluation and recording levels are defined in relevant standards. When these levels are not defined, the values applied during the examination shall be included in the examination report.

9.3.1 *Pulse echo technique*

If the amplitude of an echo exceeds the evaluation level, the signal shall be evaluated against the acceptance criteria.

9.3.2 *Transmission technique*

If the amplitude of the transmitted signal is below the evaluation level, the signal shall be evaluated against the acceptance criteria.

10 Characterization of imperfections

10.1 Pulse echo technique

The imperfections are characterized by at least:

- their location in the object (x , y and z co-ordinates);
- their reflectivity determined by measuring the maximum amplitude of the echo by one of the methods described in prEN 583-2.

Supplementary characteristics can also be determined, such as:

- orientation;
- size determined by 6 dB drop technique, or other probe movement techniques;
- planar or non-planar characteristic.

10.2 Transmission techniques

The imperfections are characterized by at least:

- their position in the object (x and y co-ordinates);
- the maximum reduction of the transmitted signal.

Supplementary characteristics can also be determined such as the extent of the area of reduced signals.

11 Examination procedure

For any ultrasonic examination an examination procedure shall be established. In addition to the requirements stated in this general standard, at least the following details shall be included, as applicable:

- description of the products to be examined;
- reference documents;
- qualification and certification of examination personnel;
- state of examination object;
- examination zones;
- preparation of scanning surfaces;
- coupling medium;
- description of examination equipment;
- environmental conditions;
- calibration and settings;
- scanning plan;
- description and sequence of examination operations;
- evaluation and recording levels;
- characterization of imperfections;
- acceptance criteria;
- examination report.

A product standard, or a standard describing a specific technique, can serve as an examination procedure if it is self-sufficient with respect to the examination. If referencing documents require a written examination procedure, it shall include at least the above information.

12 Examination report

The examination report shall contain at least the following information:

- a) identification of the manufacturer, and/or the order;
- b) complete identification of the examined object;
- c) place of examination;
- d) state of examination object;
- e) identification of the examination equipment used;
- f) reference to contractual documents (standards etc.);
- g) reference to the examination procedure;
- h) name, qualification and signature of the examiner or any other responsible for the examination;
- i) date of examination;
- j) results of examination and evaluation;
- k) any deviation from the procedure.

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover.
Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001.
Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre.
Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration.
Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001.
Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager.
Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553.
Email: copyright@bsi-global.com.