

Welding and allied processes — Joint preparation —

Part 2: Submerged arc welding of steels

The European Standard EN ISO 9692-2:1998 has the status of a
British Standard

ICS 25.160.10

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW



National foreword

This British Standard is the English language version of EN ISO 9692-2:1998, including corrigendum July 1999. It is identical with ISO 9692-2:1998.

The UK participation in its preparation was entrusted to Technical Committee WEE/1, Definitions and symbols for welding, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

Attention is drawn to the fact that CEN and CENELEC standards normally include an annex which lists normative references to international publications with their corresponding European publications. The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled “International Standards Correspondence Index”, or by using the “Find” facility of the BSI Standards Electronic Catalogue.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN ISO title page, the EN foreword page, the ISO title page, page ii, pages 1 to 8, an inside back cover and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

This British Standard, having been prepared under the direction of the Engineering Sector Board, was published under the authority of the Standards Board and comes into effect on 15 July 1998

© BSI 04-2000

ISBN 0 580 29678 4

Amendments issued since publication

Amd. No.	Date	Comments
10293 Corrigendum No. 1	April 2000	Corrects the EN foreword

English version

Welding and allied processes — Joint preparation — Part 2: Submerged arc welding of steels

(ISO 9692-2:1998)

Soudage et techniques connexes — Préparation
de joints — Partie 2: Soudage à l'arc sous flux en
poudre des aciers
(ISO 9692-2:1998)

This European Standard was approved by CEN on 26 January 1998.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart 36, B-1050 Brussels

© 1998 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. EN ISO 9692-2:1998 E

Foreword

The text of the International Standard ISO 9692-2:1998 has been prepared by Technical Committee ISO/TC 44 “Welding and allied processes” in collaboration with Technical Committee CEN/TC 121 “Welding”, the secretariat of which is held by DS.

This European Standard supersedes EN 29692:1994.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 1998, and conflicting national standards shall be withdrawn at the latest by October 1998.

This European Standard has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association. This European Standard is considered to be a supporting standard to those application and product standards which in themselves support an essential safety requirement of a New Approach Directive and which make reference to this European Standard.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of the International Standard ISO 9692-2:1998 was approved by CEN as a European Standard without any modification.

Contents

	Page
Foreword	ii
Introduction	1
1 Scope	1
2 Normative references	1
3 Materials	1
4 Types of joint preparation	1
Table 1 — Joint preparations for butt welds, welded from one side	2
Table 2 — Joint preparations for butt welds, welded from both sides	5

INTERNATIONAL STANDARD

ISO
9692-2

First edition
1998-04-01

Welding and allied processes — Joint preparation —

Part 2: Submerged arc welding of steels

*Soudage et techniques connexes — Préparation de joints —
Partie 2: Soudage à l'arc sous flux en poudre des aciers*



Reference number
ISO 9692-2:1998(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 9692-2 was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 7, *Representation and terms*.

ISO 9692 consists of the following parts, under the general title *Welding and allied processes* — *Joint preparation*.

- *Part 1: Metal arc welding of steel with covered electrode (currently ISO 9692:1992);*
- *Part 2: Submerged arc welding of steels;*
- *Part 3: Manual welding of aluminium and its alloys.*

Descriptors: Welding, arc welding, submerged arc welding, welded joints, butt joints, specifications, preparation.

Introduction

The intention of this International Standard is to use it as an addition to ISO 9692:1992 (which is to become ISO 9692-1, see Foreword) *Metal-arc welding with covered electrode, gas-shielded metal-arc welding and gas welding — Joint preparations for steel*. It follows similar rules and the same layout. Therefore, the introduction given in ISO 9692 also applies.

1 Scope

This part of ISO 9692 applies to types of joint preparation for submerged arc welding with one wire electrode (process 121 according to ISO 4063) on steel.

This part of ISO 9692 covers only the welding positions PA and PB according to ISO 6947. In case PC is used, special preparation will be necessary.

It applies to fully penetrated welds. For partly penetrated welds, types of joint preparation, shapes and dimensions may differ from the listed proposals if they are specified in the relevant application standard or agreed by parties concerned.

If the root is welded by a different arc welding process (see ISO 4063), the joint preparation according to ISO 9692 should be taken into account.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards listed below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 2553:1992, *Welded, brazed and soldered joints — Symbolic representation on drawings*.

ISO 3834-1:1994, *Quality requirements for welding — Fusion welding of metallic materials — Part 1: Guidelines for selection and use*.

ISO 3834-2:1994, *Quality requirements for welding — Fusion welding of metallic materials — Part 2: Comprehensive quality requirements*.

ISO 3834-3:1994, *Quality requirements for welding — Fusion welding of metallic materials — Part 3: Standards quality requirements*.

ISO 3834-4:1994, *Quality requirements for welding — Fusion welding of metallic materials — Part 4: Elementary quality requirements*.

ISO 4063:—¹⁾, *Welding and allied processes — Nomenclature of processes and reference numbers*.

ISO 6947:1990, *Welds — Working positions — Definitions of angles of slope and rotation*.

ISO 9692:1992²⁾, *Metal-arc welding with covered electrode, gas-shielded metal arc welding and gas welding — Joint preparations for steel*.

ISO 9956-2:1995 and Amd.1 —³⁾, *Specification and approval of welding procedures for metallic materials — Part 2: Welding procedure specification for arc welding*.

3 Materials

Joint preparations recommended in this part of ISO 9692 are suitable for all types of weldable steel.

4 Types of joint preparation

The recommended types of joint preparation and dimensions are specified in Table 1 and Table 2.

The root gaps referred to in this part of ISO 9692 are those gaps presented after tack welding, if used.

This part of ISO 9692 gives no dimensions or type of possibly used backing materials. Root runs may also be used as backing. They may influence the quality requirements for welding (according to the relevant part of ISO 3834) and the preparation as given in Table 1 and Table 2. They shall be part of the welding procedure specification according to ISO 9956-2.

According to the application standard or agreement between contracting parties, it may be necessary to grind the slag before welding the next run.

NOTE The reference numbers have been determined in accordance with the following scheme:

The first digit corresponds to the number of the table; the second digit or numerical group corresponds to the number in ISO 2553; the third indication, expressed by a letter, takes into account the variants of joint preparations.

¹⁾ To be published. (Revision of ISO 4063:1990)

²⁾ See Foreword.

³⁾ To be published.

Table 1 — Joint preparations for butt welds, welded from one side

Dimensions in millimetres

Weld					Joint preparation					Welding position (in accordance with ISO 6947)	Remarks
Ref. No.	Workpiece thickness <i>t</i>	Designation	Symbol (in accordance with ISO 2553)	Illustration	Cross section	Angle <i>α, β</i>	Gap <i>b</i> Radius <i>R</i>	Thickness of root face <i>c</i>	Depth of preparation <i>h</i>		
1.2	$3 \leq t \leq 12$	Square butt weld				—	$b \leq 0,5 t$ max. 5	—	—	PA	With backing minimal thickness for backing: 5 mm or 0,5 <i>t</i>
1.3	$10 \leq t \leq 20$	Single-V butt weld	∇			$30^\circ \leq \alpha \leq 50^\circ$	$4 \leq b \leq 8$	$c \leq 2$	—	PA	With backing minimal thickness for backing: 5 mm or 0,5 <i>t</i>
1.14	$t > 20$	Steep-flanked single-V butt weld	∇			$4^\circ \leq \beta \leq 10^\circ$	$10 \leq b \leq 25$	—	—	PA	With backing minimal thickness for backing: 5 mm or 0,5 <i>t</i>
1.3.3	$t > 12$	Single-V butt weld with V root	≡			$60^\circ \leq \alpha \leq 70^\circ$ $4^\circ \leq \beta \leq 10^\circ$	$1 \leq b \leq 4$	$0 \leq c \leq 3$	$4 \leq h \leq 6$	PA	Root run welded with optional welding process

Table 1 — Joint preparations for butt welds, welded from one side

Weld					Joint preparation					Welding position (in accordance with ISO 6947)	Remarks
Ref. No.	Workpiece thickness t	Designation	Symbol (in accordance with ISO 2553)	Illustration	Cross section	Angle α, β	Gap b Radius R	Thickness of root face c	Depth of preparation h		
1.3.7	$t \geq 12$	Single-U butt weld with V root				$60^\circ \leq \alpha \leq 70^\circ$ $4^\circ \leq \beta \leq 10^\circ$	$1 \leq b \leq 4$ $5 \leq R \leq 10$	$0 \leq c \leq 3$	$4 \leq h \leq 6$	PA	Root run welded with optional welding process
1.7	$t \geq 30$	Single-U butt weld				$4^\circ \leq \beta \leq 10^\circ$	$1 \leq b \leq 4$ $5 \leq R \leq 10$	$2 \leq c \leq 3$	—	PA	With backing minimal thickness for backing: 5 mm or 0,5 t
1.4	$3 \leq t \leq 16$	Single-bevel butt welded				$30^\circ \leq \beta \leq 50^\circ$	$1 \leq b \leq 4$	$c \leq 2$	—	PA PB	With backing minimal thickness for backing: 5 mm or 0,5 t

Table 1 — Joint preparations for butt welds, welded from one side

Weld					Joint preparation					Dimensions in millimeters	
Ref. No.	Workpiece thickness <i>t</i>	Designation	Symbol (in accordance with ISO 2553)	Illustration	Cross section	Angle <i>α, β</i>	Gap <i>b</i> Radius <i>R</i>	Thickness of root face <i>c</i>	Depth of preparation <i>h</i>	Welding position (in accordance with ISO 6947)	Remarks
1.15	$t \geq 16$	Steep-flanked single-bevel butt weld				$8^\circ \leq \beta \leq 10^\circ$	$5 \leq b \leq 15$	—	—	PA PB	With backing minimal thickness for backing: 5 mm or 0,5 <i>t</i>
1.8	$t \geq 16$	Single-J butt weld				$4^\circ \leq \beta \leq 10^\circ$	$2 \leq b \leq 4$ $5 \leq R \leq 10$	$2 \leq c \leq 3$	—	PA PB	With backing minimal thickness for backing: 5 mm or 0,5 <i>t</i>

Table 2 — Joint preparations for butt welds, welded from both sides

Dimensions in millimetres

Weld					Joint preparation					Welding position (in accordance with ISO 6947)	Remarks
Ref. No.	Workpiece thickness t	Designation	Symbol (in accordance with ISO 2553)	Illustration	Cross section	Angle α, β	Gap Radius R	Thickness of root face c	Depth of preparation h		
2.2	$3 \leq t \leq 20$	Square butt weld				—	$b \leq 2$	—	—	PA	Width of gap shall be kept within small tolerances
2.5.9	$10 \leq t \leq 35$	Single-Y butt weld with broad root face and backing run				$30^\circ \leq \alpha \leq 60^\circ$	$b \leq 4$	$4 \leq c \leq 10$	—	PA	Root run may be welded by another fusion welding process.
2.5.2	$10 \leq t \leq 20$	Single-V butt weld with square butt weld				$60^\circ \leq \alpha \leq 80^\circ$	$b \leq 4$	$5 \leq c \leq 15$	—	PA	Root run may be welded by another fusion welding process.
2.5.5	$t \geq 16$	Double-V butt weld with broad root face				$30^\circ \leq \alpha \leq 70^\circ$	$b \leq 4$	$4 \leq c \leq 10$	$h_1 \approx h_2$	PA	—

Table 2 — Joint preparations for butt welds, welded from both sides





Dimensions in millimetres

Weld					Joint preparation					Welding position (in accordance with ISO 6947)	Remarks
Ref. No.	Workpiece thickness t	Designation	Symbol (in accordance with ISO 2553)	Illustration	Cross section	Angle α, β	Gap b Radius R	Thickness of root face c	Depth of preparation h		
2.7.9	$t \geq 30$	Single-U butt weld with backing run				$5^\circ \leq \beta \leq 10^\circ$	$b \leq 4$ $5 \leq R \leq 10$	$4 \leq c \leq 10$	—	PA	
2.7.7	$t \geq 50$	Double-U butt weld				$5^\circ \leq \beta \leq 10^\circ$	$b \leq 4$ $5 \leq R \leq 10$	$4 \leq c \leq 10$	$h = 0,5 (t - c)$	PA	This type of joint preparation can also be produced asymmetrically in a similar manner to the asymmetrical double-V butt weld.
2.6.6	$t \geq 12$	Double-bevel butt weld with broad root face				$30^\circ \leq \beta \leq 50^\circ$	$b \leq 4$	$4 \leq c \leq 10$	—	PA PB	This type of joint preparation can also be produced asymmetrically in a similar manner to the asymmetrical double-V butt weld. Root run may be necessary.

Table 2 — Joint preparations for butt welds, welded from both sides

Weld					Joint preparation					Welding position (in accordance with ISO 6947)	Remarks
Ref. No.	Workpiece thickness t	Designation	Symbol (in accordance with ISO 2553)	Illustration	Cross section	Angle α, β	Gap b Radius R	Thickness of root face c	Depth of preparation h		
2.8.9	$t \geq 20$	Single-J butt weld with backing run				$5^\circ \leq \beta \leq 10^\circ$	$b \leq 4$ $5 \leq R \leq 10$	$4 \leq c \leq 10$	—	PA PB	Root run may be necessary.
2.4.9	$t < 12$	Single bevel butt weld with backing run				$30^\circ \leq \beta \leq 50^\circ$	$b \leq 4$	$c \leq 2$	—	PA PB	Root run may be necessary.
2.8.8 A	$t \geq 30$	Double-J butt weld				$5^\circ \leq \beta \leq 10^\circ$	$b \leq 4$ $5 \leq R \leq 10$	$2 \leq c \leq 7$	—	PA PB	This type of joint preparation can also be produced asymmetrically in a similar manner to the asymmetrical double-V butt weld. Root run may be necessary.

Table 2 — Joint preparations for butt welds, welded from both sides

Weld					Joint preparation					Dimensions in millimetres	
										Welding position	Remarks
Ref. No.	Workpiece thickness <i>t</i>	Designation	Symbol (in accordance with ISO 2553)	Illustration	Cross section	Angle <i>α, β</i>	Gap <i>b</i> Radius <i>R</i>	Thickness of root face <i>c</i>	Depth of preparation <i>h</i>	(in accordance with ISO 6947)	
2.8.8 B	$t \leq 12$	Double-J butt weld for single pass welding process				—	$b \leq 2$ $5 \leq R \leq 10$	$2 \leq c \leq 3$	—	PA PB	Joint preparation for single pass welding process
2.8.8 C	$t > 12$	Double-J butt weld for multipass welding process				$5^\circ \leq \beta \leq 10^\circ$	$b \leq 4$ $5 \leq R \leq 10$	$2 \leq c \leq 7$	—	PA PB	Joint preparation for multi-pass welding process Root run may be necessary.

Blank page

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.

BSI
389 Chiswick High Road
London
W4 4AL