



Standard Test Method for Damage to Contacting Solid Surfaces under Fretting Conditions¹

This standard is issued under the fixed designation G204; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

Fretting is small amplitude oscillating motion usually in the range of 10 to 300 μm . Contacting solid surfaces subjected to this type of motion can develop significant damage in the form of mass loss, pitting, debris generation, etc. Frequently, pitting damage caused by fretting creates stress concentrations that contribute to mechanical failures. Most material couples are susceptible to fretting damage and this test method is intended to assess a tribocouple's relative susceptibility to damage under fretting conditions.

When tribocouples experience oscillating relative motion less than about 10 μm , gross slip (all points in a contact experience relative slip over a complete cycle) may not occur. The elastic behavior of the real contacts may accommodate this motion and fretting damage may not occur.

When metal couples are subjected to fretting motion, there is a potential for chemical reaction with the ambient environment to be a component of the damage. In metals rubbing in air, oxidation of freshly fractured surfaces can occur. When chemical reaction is conjoint with the mechanical damage produced by fretting, it is called fretting corrosion. When most plastic couples are damaged by fretting motion, the fractured surfaces may not react with the environment and fretting wear occurs as opposed to fretting corrosion.

1. Scope

1.1 This test method covers the studying or ranking the susceptibility of candidate materials to fretting corrosion or fretting wear for the purposes of material selection for applications where fretting corrosion or fretting wear can limit serviceability.

1.2 This test method uses a tribological bench test apparatus with a mechanism or device that will produce the necessary relative motion between a contacting hemispherical rider and a flat counterface. The rider is pressed against the flat counterface with a loading mass. The test method is intended for use in room temperature air, but future editions could include fretting in the presence of lubricants or other environments.

1.3 The purpose of this test method is to rub two solid surfaces together under controlled fretting conditions and to quantify the damage to both surfaces in units of volume loss for the test method.

1.4 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[G40 Terminology Relating to Wear and Erosion](#)

[G99 Test Method for Wear Testing with a Pin-on-Disk Apparatus](#)

[G133 Test Method for Linearly Reciprocating Ball-on-Flat Sliding Wear](#)

3. Terminology

3.1 *Definitions:*

¹ This test method is under the jurisdiction of ASTM Committee [G02](#) on Wear and Erosion and is the direct responsibility of Subcommittee [G02.40](#) on Non-Abrasive Wear.

Current edition approved April 1, 2010. Published April 2010. DOI:10.1520/G0204-10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.




FIG. 1 Schematic of a Suitable Fretting Testing Rig

- a* = loading arm pivot
- b* = counterface test specimen
- c* = rider test specimen
- d* = device to measure rider movement
- e* = device to measure counterface movement

3.1.1 *fretting*, *n*—in tribology, small amplitude oscillating motion usually tangential between two solid surfaces in contact. **G40**

3.1.2 *fretting corrosion*, *n*—form of fretting wear in which corrosion plays a significant role. **G40**

3.1.3 *fretting wear*, *n*—wear arising as a result of fretting. **G40**

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *coefficient of variation (COV)*, *n*—test standard deviation divided by the test mean.

3.2.2 *counterface*, *n*—flat surface that the rider rubs on in this test.

3.2.3 *crater*, *n*—counterface damage in a fretting test from a hemispherical or spherical rider characterized by loss of material in the form of a surface depression.

3.2.4 *fretting amplitude*, *n*—sliding distance between direction reversals (for example, if a dial indicator is used to measure stroke, the amplitude is the indicator movement on the dial).

3.2.5 *rider*, *n*—ball or hemisphere that oscillates on another surface to produce fretting damage.

3.2.6 *scar*, *n*—damage to either rider or counterface in a fretting test.

4. Summary of Test Method

4.1 This test method rubs a spherical or hemispherical solid rider on a solid flat under prescribed conditions to produce fretting damage on one or both surfaces. If damage occurs, it is quantified as a wear volume on each member and as system wear, the sum of the rider and counterface wear.

4.2 Friction forces can be measured during the fretting test, but these measurements, as well as reporting these data, is optional.

5. Significance and Use

5.1 Fretting wear and corrosion are potential serviceability factors in many machines. They have always been factors in shipping finished goods by truck or rail. Packing materials rubbing on a product in transit can make the product unsalable. Beverage cans and food cans can lose their trade dress and consumers often equate container damage to content damage.

5.2 Clamping surfaces on injection molds are damaged by fretting motions on clamping. This damage is a significant cause for mold replacement.

5.3 Machines in shipment are subject to fretting damage in the real area of contact of the bearings on the machines.

5.4 Operating vibration and movement of mechanically clamped components, like screwed assemblies, can produce damage on the clamped faces and other faces that affects machine function or use. Many times fretting damage appears in the form of pits, which are stress concentrators that can lead to mechanical fractures.

5.5 Electrical contacts in any device that is subject to vibration are susceptible to failure (open circuit) due to fretting damage at real areas of contact.

5.6 This test method is intended to be used to identify mating couples that may be less prone to fretting damage than others. This information in turn is used to select materials of construction or surface treatments that are less prone to fretting damage for applications where fretting conditions are known or perceived to exist.




FIG. 2 Fretting Test Specimens

A = counterface
B = rider (a ball may be adhered to a pin to make the rider)
Surface roughness of both specimens = $< 0.1 \mu\text{m Ra}$

6. Apparatus

6.1 Fig. 1 is a schematic of the test apparatus showing necessary features. The schematic shows the counterface moving laterally with respect to the rider. The rider could reciprocate with respect to the counterface as long as it still can move in the downward direction to accommodate wear.

6.2 The rider or counterface holder can be instrumented to sense friction force, but the device cannot interfere with achieving the required relative motion between the rider and counterface. Test rigs need instrumentation or a system to verify that the amplitude of oscillation is the test value of $50 \pm 2 \mu\text{m}$ at test frequency.

6.3 The test specimens must be affixed to the test rig in such a manner that their movement in specimen clamps is less than $1 \mu\text{m}$ during testing.

6.4 Wear in the specified test can be such that vertical motion of the rider as wear occurs can be hundreds of micrometers. Thus, the test rig should be designed such that the rider can move into the counterface at least $500 \pm 20 \mu\text{m}$.

6.5 The test specimens should be protected from environmental contamination during testing and testing should be done in an atmosphere that stays consistent in nature throughout the test. The standard test is performed in ordinary laboratory air at 20°C , 50 to 70% RH.

6.6 The test rig shall be capable of an oscillating frequency of $13 \pm 0.8 \text{ Hz}$ (see Note 1). Most test rigs have variable frequency capability, and it is not usual to design a rig for a wide frequency range. Mechanical actuators are usually adequate for frequencies in the range of 1 to 50 Hz. Higher test

frequencies usually require piezocrystals or the like as a source of oscillation. The standard test was developed using mechanical activation (electric motor driven crank).

NOTE 1—This frequency was chosen for convenience. It produces 10^6 cycles in about 21.4 h. Users can do a test a day.

7. Test Specimens

7.1 The test specimens used in this test method can vary in shape as long as the rider has a 3.17 mm radius at the point of contact and the counterface is flat within $1 \mu\text{m}$ per cm at the point of contact. The test specimens used in the development of this test method are shown in Fig. 2.

7.2 Measuring wear scars with surface analysis instruments can be very challenging. The standard test was developed with surface roughnesses on both rider and counterface of less than $0.1 \mu\text{m Ra}$. Surface finish can play a role in susceptibility to fretting damage. Polished surfaces produce the most succinct wear scars. Very rough surfaces ($> 1 \mu\text{m Ra}$) may produce hard-to-measure scars. Sometimes, only the rider wears; sometimes only the counterface wears; sometimes both members wear. Test Method G99 and G133 describe wear scar measurement in detail.

7.3 Some surfaces of interest, like thermal spray deposits, are often incapable of being ground and lapped to this roughness. They can be tested, but the users need to establish the effect of excessive roughness on repeatability. The COV may be high for these test couples.

7.4 The surface lay of the test specimens can affect results and care should be taken to produce non-directional lay in the counterface and accurate curvature (no centerline protuberance

greater than 1 μm on the rider). If test surfaces have a distinct lay, the relationship of the rubbing to the lay (parallel or perpendicular) should be kept the same for each test couple.

7.5 Grain direction can be a factor in both counterface and rider in crystalline materials. It is acceptable to ignore grain orientation in ground balls, but the grain orientation in the counterface should simulate the application. The test was developed with counterfaces produced as flat-rolled steel and testing was performed on the flat surfaces as opposed to end grain.

8. Procedure

8.1 Clean test specimens of all films and particles. Ultrasonic degreasing for 1 min in 100 mL of fresh acetone for each specimen has been determined to be adequate for metals. Clean plastics and ceramics with techniques that do not contaminate or attack the test surface.

8.2 Assemble specimens into the test rig after cleaning using procedures that do not contaminate the testing surfaces. Affix the rider to the rider arm and the counterface to the counterface holder. Gently lower the rider onto the counterface so there is no damage from this initial contact. Do not drop the rider on the flat.

8.3 Load the rider on the flat with a normal force of 10 N. Cycle the test rig in “jog mode” for up to 100 cycles or similar such that the relative movement between the rider and counterface can be measured. Adjust the machine so that this relative motion is $50 \pm 2 \mu\text{m}$.

8.4 When the required amplitude is achieved, commence testing at 13 Hz (780 cycles/minute) and continue until reciprocating 10^6 cycles are completed (21.36 h) Use ultrasonics or other processes to clean the debris from the fretting damaged surfaces (for example, inhibited acid etch).

8.5 Measure the wear volumes on both members. If a flat is worn on the spherical-shaped rider, the flat diameter can be used to calculate a wear volume using the formulas in the G99 procedure for pin-on-disk testing. Counterface wear can usually be measured by profilometer traces through the wear crater; establish the cross-section area of the crater and calculate the volume swept by revolution of this area or by suitable other calculations. It is possible that one member of the test couple will not wear. It is also possible that one member will adhere to the other such that the wear volume is really a mass increase. Most often, both members wear.

8.6 Use mass change to calculate specimen wear and converted to volume using material densities, but the mass changes are usually so small that this technique may lead to a high COV, which is the test standard deviation divided by the test mean. Volume calculation from scar dimensions is the preferred technique.

8.7 Calculate system friction coefficients for the test. They will likely vary during the test and the friction coefficient averaging technique should be stated. The total friction energy dissipated in the test (in joules) may be useful, but it is an optional test metric. This standard was developed without friction measurement, since force measurement devices usually

Test No.	
Descriptions	
1. Test Couple:	
Rider	
Counterface	
2. Surface Condition (Ra)	
Rider	
Counterface	
3. Test Force	10 N
4. Test Amplitude	50 μm
5. Test Frequency	13
6. Test Environment	20°C, 50% RH
7. Test Duration	10^6 cycles
8. Rider Wear Volume	
9. Counterface Wear Volume	
10. System Wear Volume	
11. Friction and Other Comments	

FIG. 3 Sample Test Report

deflect to in order to sense force. Thus, this deflection must be considered in its effect on fretting amplitude. Three test replicates are a minimum for each test couple.

9. Report

9.1 See Fig. 3 for a sample test report. Be sure to include the wear volume of each member and the system wear volume.

10. Precision and Bias

10.1 There is no established absolute magnitude for the fretting wear value that occurs with a specific mating couple, so it is not possible to state a bias, but the following factors could create a bias between different labs testing the same couple under the same conditions:

10.1.1 Specimens moved during testing, so the rubbing amplitude is different than planned.

10.1.2 The dynamic fretting amplitude may be different than the amplitude measured at startup in jog mode.

10.1.3 Specimens are contaminated in handling.

10.1.4 Systemic errors in calculating wear volumes.

10.1.5 Not adequately removing wear debris when measuring scar depths and dimensions.

10.2 The repeatability of one lab using one material couple is shown below:

Test	Rider Wear Volume	Counterface Wear
#8	24.27×10^{-12}	2.36×10^{-12}
#9	24.27×10^{-12}	2.11×10^{-12}
#11	24.27×10^{-12}	1.57×10^{-12}
#12	26.68×10^{-12}	1.65×10^{-12}

Rider average = 24.97×10^{-12} , s = 1.21×10^{-12} , COV = 0.048

Counterface average = 1.92×10^{-12} , s = 0.37×10^{-12} , COV = 0.19

10.3 All volume losses are in cubic metres. The test couple was Type 52100 steel rider at 60 HRC versus Type A2 tool steel at 60 HRC counterface. The normal force was 10N; the frequency was 11.66 Hz; the test amplitude was 50 μm ; the rider radius was 3.17 mm. Rider wear was measured from scar diameter; counterface wear was measured by profilometry through the center of the wear crater.

10.4 The interlaboratory reproducibility standard deviation and coefficient of variation will be determined upon completion of an interlaboratory testing program and will be available before June 29, 2011.

10.5 *Effect of Test Rig*—Fretting wear and corrosion test results can be affected by which member is moving and which is stationary, by frequency, by normal force, by environment, and by system compliance. System compliance is the nature and degree that the mating surfaces contact each other. Specimen geometry, type of material, the rig stiffness, and the dynamics of the test rig determine compliance. The wear volumes obtained on a specific couple could vary significantly for different machines even though the prescribed test parameters are used.

10.6 For example, test rigs that use a loading system driven by feedback controlled stepper motors may see different results from the results of a test rig with dead-weight loading. A rig with piezoelectric crystal driver may produce different results with a specific couple than a rig with mechanical activation.

10.7 The *repeatability* data in this standard was obtained on a test rig with the rider stationary, dead weight loaded, and with the flat moving specimen attached to a flexure that was reciprocated with an electric motor-driven cam. Machines with different designs may produce different wear results for the test couple used in interlaboratory tests: 5200 rider versus A2 tool steel, but this should not be a user concern when the test is used to compare candidate materials or treatments. The interlaboratory tests will probably be run on non-identical rigs and the rig compliance effect will be determined and included in updated versions of this standard.

11. Keywords

11.1 fretting; fretting corrosion; fretting wear

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).