

Database of Steel and Alloy (Marochnik)

splat.kharkov.com/en

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Aluminium alloy](#)

Characteristics for grade A85 (A85).

Grade :	A85 (A85)
Classification :	Primary aluminium
Equivalent grades:	Go here

Chemical composition in % for grade A85 (A85)

Fe	Si	Mn	Ti	Al	Cu	Mg	Zn	Ga	Impurity
max 0.08	max 0.06	max 0.02	max 0.008	min 99.85	max 0.01	max 0.02	max 0.02	max 0.03	other, each 0.02;

Mechanical properties under T=20°C for grade A85 (A85)

Assortment	Dimension	Direct.	σ_B	σ_T	δ_5	ψ	KCU	Heat treatment
-	mm	-	MPa	MPa	%	%	kJ / m ²	-
Pipe annealed , GOST 18475-82			60		20			
Pipe cold-worked , GOST 18475-82			80		4-5			

Physical properties for grade A85 (A85)

T	E 10 ⁻⁵	α 10 ⁶	λ	ρ	C	R 10 ⁹
Grade	MPa	1/Grade	Watt/(m·Grade)	kg/m ³	J/(kg·Grade)	Ohm·m
20				2700		

Equivalent steels for grade A85 (A85)

Warning! Indicated both exact and nearest equivalents.

USA	European
-	EN
Aluminium 1085 Aluminium 1185	ENAW-1085

Specification :

Mechanical properties :

σ_B	- Tensile strength , [MPa]
σ_T	- Yield stress , [MPa]
δ_5	- Specific elongation at fracture , [%]
ψ	- Reduction of area , [%]
KCU	- Impact strength , [kJ / m ²]
HB	- Brinell hardness , [MPa]

Physical properties :

- T** - Test temperature , [Grade]
E - Young modulus , [MPa]
 α - Coefficient of linear expansion (range 20° - T) , [1/Grade]
 λ - Thermal (heat) condition coefficient , [Watt/(m·Grade)]
 ρ - Density , [kg/m³]
C - Specific heat (range 20° - T) , [J/(kg·Grade)]
R - Electrical resistance , [Ohm·m]

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more then 2500 steels and alloys (stainless steel, alloy steel, carbone steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).
 Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)

© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

