

Database of Steel and Alloy (Marochnik)

splat.kharkov.com/en

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Aluminium alloy](#)

Characteristics for grade A98 (A98).

Grade :	A98 (A98)
Classification :	Primary aluminium
Equivalent grades:	Go here

Chemical composition in % for grade A98 (A98)

Fe	Si	Mn	Ti	Al	Cu	Mg	Zn	Ga	Impurity
max 0.006	max 0.006	max 0.002	max 0.002	min 99.98	max 0.002	max 0.002	max 0.003	max 0.003	other, each 0.001;

Equivalent steels for grade A98 (A98)

Warning! Indicated both exact and nearest equivalents.

USA	European
-	EN
1098 1198	ENAW-1098

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more then 2500 steels and alloys (stainless steel, alloy steel, carbone steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).
Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)

© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

