

Database of Steel and Alloy (Marochnik)

splav.kharkov.com/en

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Aluminium alloy](#)

Characteristics for grade AK5M2 (AK5M2).

Grade :	AK5M2 (AK5M2) (АЛ3В)
Classification :	Aluminium casting alloys
Equivalent grades:	Go here

Chemical composition in % for grade AK5M2 (AK5M2)

Fe	Si	Mn	Ni	Ti	Al	Cu	Mg	Zn	Impurity
max 1.3	4 - 6	0.2 - 0.8	max 0.5	0.05 - 0.2	85.9 - 94.05	1.5 - 3.5	0.2 - 0.8	max 1.5	all 2.8

Comment: **Al** is a basis; the percentage of **Al** is given approximately.

Mechanical properties under T=20°C for grade AK5M2 (AK5M2)

Assortment	Dimension	Direct.	σ_B	σ_T	δ_5	ψ	KCU	Heat treatment
-	mm	-	MPa	MPa	%	%	kJ / m ²	-
Casting, GOST 1583-93			118-206		0.5-2			

Brinell hardness for AK5M2 (AK5M2) , Casting GOST 1583-93	HB 10⁻¹ = 65 - 75 MPa
--	---

Equivalent steels for grade AK5M2 (AK5M2)

Warning! Indicated both exact and nearest equivalents.

USA	Japan	France	China
-	JIS	AFNOR	GB
360 A319.0	AC2B AC8B	A-S11UNG A-S5U3G	ZL104 ZL14

Specification :

Mechanical properties :

σ_B	- Tensile strength , [MPa]
σ_T	- Yield stress , [MPa]
δ_5	- Specific elongation at fracture , [%]
ψ	- Reduction of area , [%]
KCU	- Impact strength , [kJ / m ²]
HB	- Brinell hardness , [MPa]

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more then 2500 steels and alloys (stainless steel, alloy steel, carbone steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).
Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

