

# Database of Steel and Alloy (Marochnik)

[splav.kharkov.com/en](http://splav.kharkov.com/en)

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Aluminium alloy](#)

## Characteristics for grade AL6 ( АЛ6 ).

|                    |                          |
|--------------------|--------------------------|
| Grade :            | AL6 ( АЛ6 )              |
| Classification :   | Aluminium casting alloys |
| Equivalent grades: | <a href="#">Go here</a>  |

### Chemical composition in % for grade AL6 ( АЛ6 )

| Fe      | Si      | Mn      | Al          | Cu    | Mg      | Zn      | Impurity |
|---------|---------|---------|-------------|-------|---------|---------|----------|
| max 1.5 | 4.5 - 6 | max 0.3 | 91.9 - 93.5 | 2 - 3 | max 0.1 | max 0.3 | all 2.1  |

Comment: **Al** is a basis; the percentage of **Al** is given approximately.

### Mechanical properties under T=20°C for grade AL6 ( АЛ6 )

| Assortment | Dimension | Direct. | $\sigma_B$ | $\sigma_T$ | $\delta_5$ | $\psi$ | KCU                 | Heat treatment |
|------------|-----------|---------|------------|------------|------------|--------|---------------------|----------------|
| -          | mm        | -       | MPa        | MPa        | %          | %      | kJ / m <sup>2</sup> | -              |
|            |           |         | 150        |            | 1          |        |                     |                |

|                                    |                              |
|------------------------------------|------------------------------|
| Brinell hardness for AL6 ( АЛ6 ) , | HB 10 <sup>-1</sup> = 45 MPa |
|------------------------------------|------------------------------|

### Physical properties for grade AL6 ( АЛ6 )

| T     | E 10 <sup>-5</sup> | $\alpha$ 10 <sup>6</sup> | $\lambda$      | $\rho$            | C            | R 10 <sup>9</sup> |
|-------|--------------------|--------------------------|----------------|-------------------|--------------|-------------------|
| Grade | MPa                | 1/Grade                  | Watt/(m·Grade) | kg/m <sup>3</sup> | J/(kg·Grade) | Ohm·m             |
| 20    |                    |                          | 143            | 2750              |              |                   |
| 100   |                    | 21.5                     |                |                   |              |                   |

### Equivalent steels for grade AL6 ( АЛ6 )

Warning! Indicated both exact and nearest equivalents.

| USA             | Germany    | Japan | France | England    | China |
|-----------------|------------|-------|--------|------------|-------|
| -               | DIN, WNr   | JIS   | AFNOR  | BS         | GB    |
| 319.0<br>A03190 | G-AlSi6Cu4 | AC4B  | A-S5UZ | L79<br>LM4 | ZL107 |

### Specification :

#### Mechanical properties :

- $\sigma_B$  - Tensile strength , [MPa]
- $\sigma_T$  - Yield stress , [MPa]
- Specific elongation at fracture , [ % ]

$\delta_5$  $\psi$  - Reduction of area , [ % ]**KCU** - Impact strength , [ kJ / m<sup>2</sup>]**HB** - Brinell hardness , [MPa]**Physical properties :****T** - Test temperature , [Grade]**E** - Young modulus , [MPa] $\alpha$  - Coefficient of linear expansion (range 20° - T ) , [1/Grade] $\lambda$  - Thermal (heat) condition coefficient , [Watt/(m·Grade)] $\rho$  - Density , [kg/m<sup>3</sup>]**C** - Specific heat ( range 20° - T ) , [J/(kg·Grade)]**R** - Electrical resistance , [Ohm·m]

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more then 2500 steels and alloys (stainless steel, alloy steel, carbone steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).  
 Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

