

# Database of Steel and Alloy ( Marochnik )

[splat.kharkov.com/en](http://splat.kharkov.com/en)

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Aluminium alloy](#)

## Characteristics for grade AKM ( AKM ).

|                           |                          |
|---------------------------|--------------------------|
| <b>Grade :</b>            | AKM ( AKM )              |
| <b>Classification :</b>   | Aluminium wrought alloys |
| <b>Equivalent grades:</b> | Is absent                |

## Chemical composition in % for grade AKM ( AKM )

| Fe    | Si        | Mn        | Ni      | Cr      | Ti      | Al        | Cu        | Mg        | Zn    | Impurity |
|-------|-----------|-----------|---------|---------|---------|-----------|-----------|-----------|-------|----------|
| max 1 | 0.8 - 2.2 | 0.2 - 0.8 | max 0.1 | max 0.2 | max 0.2 | 90.6 - 97 | 1.2 - 2.6 | 0.8 - 1.4 | max 1 | all 0.2  |

Comment: **Al** is a basis; the percentage of **Al** is given approximately.

## Mechanical properties under T=20°C for grade AKM ( AKM )

| Assortment                      | Dimension | Direct. | $\sigma_B$ | $\sigma_T$ | $\delta_5$ | $\psi$ | KCU                 | Heat treatment       |
|---------------------------------|-----------|---------|------------|------------|------------|--------|---------------------|----------------------|
| -                               | mm        | -       | MPa        | MPa        | %          | %      | kJ / m <sup>2</sup> | -                    |
| Bar, GOST 21488-97              |           |         | 245        |            | 12         |        |                     | Annealing            |
| Bar, GOST 21488-97              |           |         | 315        |            | 12-14      |        |                     | Hardening and ageing |
| Profile annealed , GOST 8617-81 |           |         | 196        |            | 14         |        |                     |                      |
| Profile, GOST 8617-81           |           |         | 314        |            | 12         |        |                     |                      |

## Physical properties for grade AKM ( AKM )

| T     | E 10 <sup>-5</sup> | $\alpha$ 10 <sup>6</sup> | $\lambda$      | $\rho$            | C            | R 10 <sup>9</sup> |
|-------|--------------------|--------------------------|----------------|-------------------|--------------|-------------------|
| Grade | MPa                | 1/Grade                  | Watt/(m·Grade) | kg/m <sup>3</sup> | J/(kg·Grade) | Ohm·m             |
| 20    |                    |                          |                | 2765              |              |                   |

### Specification :

#### Mechanical properties :

- $\sigma_B$  - Tensile strength , [MPa]
- $\sigma_T$  - Yield stress , [MPa]
- $\delta_5$  - Specific elongation at fracture , [ % ]
- $\psi$  - Reduction of area , [ % ]
- KCU** - Impact strength , [ kJ / m<sup>2</sup> ]
- HB** - Brinell hardness , [MPa]

#### Physical properties :

- T** - Test temperature , [Grade]
- E** - Young modulus , [MPa]

$\alpha$  - Coefficient of linear expansion (range 20° - T ) , [1/Grade]

$\lambda$  - Thermal (heat) condition coefficient , [Watt/(m·Grade)]

$\rho$  - Density , [kg/m<sup>3</sup>]

**C** - Specific heat ( range 20° - T ), [J/(kg·Grade)]

**R** - Electrical resistance , [Ohm·m]

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more then 2500 steels and alloys (stainless steel, alloy steel, carbone steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).

Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)

© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

