

Database of Steel and Alloy (Marochnik)

splat.kharkov.com/en

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Latten \(copper-zinc alloy\)](#)

Characteristics for grade LO70-1 (ЛО70-1).

Grade :	LO70-1 (ЛО70-1)
Classification :	Copper-zinc alloys pressure treated
Equivalent grades:	Is absent

Chemical composition in % for grade LO70-1 (ЛО70-1)

Fe	P	Cu	Pb	Zn	Sb	Bi	Sn	Impurity
max 0.07	max 0.01	69 - 71	max 0.07	27.2 - 30	max 0.005	max 0.002	1 - 1.5	all 0.3

Comment: Zn is a basis; the percentage of Zn is given approximately.

Mechanical properties under T=20°C for grade LO70-1 (ЛО70-1)

Assortment	Dimension	Direct.	σ_B	σ_T	δ_5	ψ	KCU	Heat treatment
-	mm	-	MPa	MPa	%	%	kJ / m ²	-
Pipe, GOST 21646-2003			320	100	45			
Pipe, GOST 21646-2003			360	150	40			

Brinell hardness for LO70-1 (ЛО70-1) , soft	HB 10 ⁻¹ = 55 - 65 MPa
Brinell hardness for LO70-1 (ЛО70-1) , hard	HB 10 ⁻¹ = 145 - 155 MPa

Friction coefficient of the material LO70-1 (ЛО70-1) .

Friction coefficient with oil :	0.0082
Friction coefficient without oil :	0.3

Technological properties of the material LO70-1 (ЛО70-1) .

Melting temperature :	935 °C
Forging temperature :	650 - 750 °C
Annealing temperature :	550 - 650 °C

Physical properties for grade LO70-1 (ЛО70-1)

T	E 10 ⁻⁵	α 10 ⁶	λ	ρ	C	R 10 ⁹
Grade	MPa	1/Grade	Watt/(m·Grade)	kg/m ³	J/(kg·Grade)	Ohm·m
20	1.05		117	8600		72

Specification :
Mechanical properties :

- σ_B - Tensile strength , [MPa]
 σ_T - Yield stress , [MPa]
 δ_5 - Specific elongation at fracture , [%]
 ψ - Reduction of area , [%]
KCU - Impact strength , [kJ / m²]
HB - Brinell hardness , [MPa]

Physical properties :

- T** - Test temperature , [Grade]
E - Young modulus , [MPa]
 α - Coefficient of linear expansion (range 20° - T) , [1/Grade]
 λ - Thermal (heat) condition coefficient , [Watt/(m·Grade)]
 ρ - Density , [kg/m³]
C - Specific heat (range 20° - T) , [J/(kg·Grade)]
R - Electrical resistance , [Ohm·m]

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more then 2500 steels and alloys (stainless steel, alloy steel, carbone steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).
 Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)

© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

