

Database of Steel and Alloy (Marochnik)

splav.kharkov.com/en

[Home](#) [European steel grades](#) [Steel and Alloy](#) [Search](#) [Equivalent grades](#) [Grading](#) [GOST Standard](#) [Contacts](#)

YOU HERE: [Steel and Alloy](#) -> [Latten \(copper-zinc alloy\)](#)

Characteristics for grade LTS14K3S3 (ЛЦ14K3C3).

Grade :	LTS14K3S3 (ЛЦ14K3C3)
Classification :	Cast cooper-zinc alloys
Equivalent grades:	Is absent

Chemical composition in % for grade LTS14K3S3 (ЛЦ14K3C3)

Fe	Si	Mn	Ni	Al	Cu	Pb	Zn	Sb	Sn	Impurity
max 0.6	2.5 - 4.5	max 1	max 0.2	max 0.3	77 - 81	2 - 4	8.2 - 18.5	max 0.1	max 0.3	all 2.3

Comment: Zn is a basis; the percentage of Zn is given approximately.

Mechanical properties under T=20°C for grade LTS14K3S3 (ЛЦ14K3C3)

Assortment	Dimension	Direct.	σ_B	σ_T	δ_5	ψ	KCU	Heat treatment
-	mm	-	MPa	MPa	%	%	kJ / m ²	-
cast in a metal mould, GOST 17711-93			294		15			
sand (mould) casting, GOST 17711-93			245		7			

Brinell hardness for LTS14K3S3 (ЛЦ14K3C3) , cast in a metal mould GOST 17711-93	HB 10⁻¹ = 100 MPa
Brinell hardness for LTS14K3S3 (ЛЦ14K3C3) , sand (mould) casting GOST 17711-93	HB 10⁻¹ = 90 MPa

Friction coefficient of the material LTS14K3S3 (ЛЦ14K3C3) .

Friction coefficient with oil :	0.009
Friction coefficient without oil :	0.15

Technological properties of the material LTS14K3S3 (ЛЦ14K3C3) .

Melting temperature :	900 °C
------------------------------	---------------

Physical properties for grade LTS14K3S3 (ЛЦ14K3C3)

T	E 10 ⁻⁵	α 10 ⁶	λ	ρ	C	R 10 ⁹
Grade	MPa	1/Grade	Watt/(m·Grade)	kg/m ³	J/(kg·Grade)	Ohm·m
20		17	83.7	8600		200

Specification :

Mechanical properties :

σ_B	- Tensile strength , [MPa]
σ_T	- Yield stress , [MPa]
δ_5	- Specific elongation at fracture , [%]
ψ	- Reduction of area , [%]
KCU	- Impact strength , [kJ / m ²]
HB	- Brinell hardness , [MPa]

Physical properties :

T	- Test temperature , [Grade]
E	- Young modulus , [MPa]
α	- Coefficient of linear expansion (range 20° - T) , [1/Grade]
λ	- Thermal (heat) condition coefficient , [Watt/(m·Grade)]
ρ	- Density , [kg/m ³]
C	- Specific heat (range 20° - T) , [J/(kg·Grade)]
R	- Electrical resistance , [Ohm·m]

Database of steels and alloys (Marochnik) contains information about chemical composition and properties more then 2500 steels and alloys (stainless steel, alloy steel, carbone steel, structural steel, tool steel, cast iron, aluminum alloy, titanium alloy, copper alloy, nickel alloy, magnesium alloy and others).
Helpfull for specialists in grade technology, structural engineer, mechanical engineer, metallurgy and metal trader

[Top](#)

© 2003 - 2013 All rights reserved. [About program.](#)

The entire risk as to use of the Database of Steel and Alloy (Marochnik) content is assumed by you the user

